iJRASET
International Journal For Research in Applied Science and Engineering Technology

INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 14 **Issue:** IV **Month of publication:** April 2026

DOI: https://doi.org/10.22214/ijraset.2026.80655

www.ijraset.com

Call: 08813907089 | E-mail ID: ijraset@gmail.com

International Journal for Research in Applied Science & Engineering Technology (IJRASET)
ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538
Volume 14 Issue IV Apr 2026- Available at www.ijraset.com

A Comprehensive and Critical Review on High Performance Fiber Reinforced Concrete

JustinReji, Lekshmi Priya R
[1]*PG Student,* [2]*Associate Professor, Department of Civil Engineering Sree Narayana Institute of Technology Adoor, India*

Abstract: ***High performance concrete has gainedsignificant attention in recent year due to its superior mechanical performance, enhanced durability, and improved crack resistance compared to conventional concrete. Thispaperpresentsa comprehensive andcriticalreview ofHPFRC, focusing on itsmaterials composition, fiber characteristics, mechanical behaviour, durability performance and structural applications. The role of different types of fibers, including steels, polypropylene, and hybrid systems, is examined in relation to their influence on strength, durability and post-cracking behavior. The review highlights that optimized mix design, low water-to-binder ratio, and the incorporation of supplementary cementitious materials significantly contribute to the improved performance of HPFRC. Additionally, the influence of fiber geometry, orientation, and distribution on fresh and hardened properties is critically analyzed. Recent advancements such as the application of machine learning techniques for strength prediction and non-destructive evaluation methods for fiber orientation assessment are also discussed. Despite its advantages, several challenges remain, including high material cost, lack of standardized design guidelines, and limited field implementation. This study identifies key research gaps and provides future directions to enhance the practical applicability of HPFRC in modern construction. Overall, HPFRC is recognized as a promising material for sustainable and high-performance infrastructure development.***

Keywords: Highperformancefiberreinforcedconcrete,Ultra highperformanceconcrete,Fiberreinforcement,Crackscontrol.

I. INTRODUCTION

High-Performance Fiber Reinforced Concrete (HPFRC) is an advanced cementitious composite that integrates the superior strength and durability of high-performance concrete with enhanced ductility through the incorporation of fibers such as steel, polypropylene, and carbon. Conventionl concrete is inherently brittle and weak in tension, leading to crak initiation and propagation under service loads. In contrast, HPFRC exhibits improved tensile strength, toughness, and post-cracking behavior due to fiber bridging mechanisms, which delay crack growth and enhance load-carrying capacity. HPFRC is characterized by strain-hardening brhavior and multiple microcracking,which significantly improve durability and structural performance. Yooetal.(2019)[35]andWilleandNaaman (2014) [42] demonstrated that HPFRC can sustain tensile stresses beyond first cracking, exhibiting pseudo-ductile behavior. Recent studies by Sharma et al. (2026) [1] and Singh and Kumar (2020) [24] reported that ultra-high-performance fiber reinforced concrete (UHPFRC) can achieve compressive strengths exceeding 150 MPa along with superior durability. Azmee and Shafiq (2018) [37] furtherhighlighteditsdensemicrostructureandresistanceto environmental degradation.

II. MATERIALS AND MIX DESIGN OF HPFRC

A. Materials

The performance of HPFRC is highly dependent on its mix design, which typically involves a low water-to-binder ratio (0.2–0.3), high cement content, and the use of supplementarycementitious materials (SCMs) such as silica fume, fly ash, and slag. These materials enhance particle packingdensity,reduceporosity,andimprovetheinterfacial transition zone.



Fig.1DevelopmentofSCC,HPC,UHPC,FRC(Zhangetal.2022)

©IJRASET: All Rights are Reserved

MixDesignofHPFRC

Zhang et al. (2022) [13] and Zhang et al. (2021) [21] reported that SCMs significantly enhance both mechanical properties and durability by refining the pore structure. Wang et al. (2022) [15] emphasized that optimized mix design, including proper aggregate grading and superplasticizer usage, isessential for achieving workability andhighstrength.Additionally,Zhangetal.(2023)[9] highlighted the importance of predictive models in optimizing mix proportions.

III. ROLES OF FIBERS IN HPFRC

Fibersare the most critical component in High-Performance Fiber Reinforced Concrete (HPFRC), as they fundamentally transform the behavior of concrete from brittletopseudo-ductile.Theincorporationofdiscretefibers enhances tensile strength, crack resistance, toughness, and ductility by bridging cracks and transferring stresses across them. This crack-bridging mechanism delays crack propagation and allows the material to sustain loads even after the formation of initial microcracks.

A. Differenttypesoffibers

Different types of fibers contribute uniquely to the performance of HPFRC. Steel fibers are widely used due to their high modulus of elasticity and tensile strength, which significantly improve load-bearing capacity and post-cracking behavior. In contrast, synthetic fibers such as polypropylene are effective in controlling plastic shrinkage cracking and enhancing durability, particularly under environmental exposure conditions. Chen et al. (2025) [2] demonstrated that fiber type significantly influences both fresh properties, such as workability, and hardened properties, including strength and durability.

Table1.Fibertypesandproperties(Chen,Y., L.2025)

Name	ypesoffiber	pectratio(L/Ø)	Tensilestrength (MPa)	Modulusofelasticity (GPa)
CS	Highcarbon steelfiber	65.0	2750	200
TS	Twistedsteelfiber	50.0	1700	200
HS	Hookedsteelfiber	54.5	1345	200
CH	Highcarbonhookedsteelfiber	78.9	3070	210
GF	Glassbasedfiber	34.3	1000	42
PE	Polyethylenefiber	800.0	2700	88

B. Fibergeometry

Fibergeometry,includinglength,diameter,andaspectratio, plays a crucial role in determining the efficiency of stress transfer between the fiber and the cementitious matrix. Zhang et al. (2025) [6] reported that fibers with higher aspect ratios improve mechanical performance but may reduce workability due to increased interlocking. Additionally, fiber orientation and distribution within the matrix significantly affect the anisotropic behavior of HPFRC. Lopez et al. (2025) [3] highlighted that aligned fibers provide better load transfer and enhanced tensile performance compared to randomly distributed fibers.

C. Hybridfibersystem

Hybrid fiber systems, which combine different types of fibers, have gained considerable attention due to their synergistic effects.

Patel and Sharma (2021) [18] and Lee et al.(2021)[22]reportedthatthecombinationofsteelandsynthetic fibers results in improved strength, ductility, and crack control compared to single-fiber systems. Steel fibers contribute to load-carrying capacity, while synthetic fibers enhance crack resistance at early stages, leading to a more balanced and optimized performance.



Fig.2Fibersstudied:**a)**Cs**b)**TS**c)**HS**d)**CH**e)**GF**f)**PE(Chen,Y.,L,2025)

IV. MECHANICAL PROPERTIES OF HPFRC

High-Performance Fiber Reinforced Concrete (HPFRC) exhibits significantly enhanced mechanical properties compared to conventional concrete, making it suitable for demanding structural applications. The inclusion of fibers improves not only compressive strength but also tensile strength, flexural strength, fracture toughness, and energy absorption capacity. One of the most distinctive features of HPFRC is its strain-hardening behavior under tensile loading. Unlike conventional concrete, which fails abruptly after cracking, HPFRC can sustain increasing stress with increasing strain due to the formation of multiple microcracks. Yoo et al. (2019) [35] reported that this strain-hardening behavior results in improved ductility and structuralresilience.Similarly,WilleandNaaman(2014)
[42] demonstrated that HPFRC exhibits pseudo-ductile behavior, which is highly desirable in structural design.

A. Compressionstrengthtest

Compressive strength in HPFRC is typically higher thanthat ofconventional concrete, oftenexceeding100 MPa and reaching up to 150 MPa or more in ultra-high-performance variants. However, the primary improvement lies in tensile andpost-crackingbehaviorratherthancompressivestrength alone.

B. Splittensileandflexuralstrengthtest

Thetensile and flexuralstrengthofHPFRCare significantly enhanced due to fiber bridging mechanisms. Li and Zhao (2020) [30] highlighted that fibers increase fracture energy and toughness by resisting crack opening and propagation. This results in improved load-carrying capacity and delayed failure, particularly in flexural members.

C. PerformanceofHPFRC

HPFRC also shows superior performance under dynamic and extreme loading conditions. Yoo et al. (2020) [26] demonstrated that the inclusion of steel fibers significantly enhances impact resistance by increasing energy absorption capacity. Additionally, Lee et al. (2020) [29] investigated fatigue behavior and found that HPFRC exhibits improved resistance to cyclic loading, making it suitable for applications subjected to repeated loading such as bridges and pavements.
Despite these advantages, the mechanical performance of HPFRC is influenced by several factors, including fibertype, volume fraction, orientation, and mix composition. Improper fiber distribution can lead to variability in properties, highlighting the need for careful design and quality control.
TheenhancedmechanicalpropertiesofHPFRC,particularly its ductility, toughness, and resistance to dynamic loading, make it a highly promising material for advanced structural applications.

V. DURABILITY AND LONGTERM PERFORMANCE

Durability is one of the most significant advantages ofHigh-Performance Fiber Reinforced Concrete (HPFRC), primarily attributed to its dense microstructure, lowporosity, and reduced permeability. The incorporation of fine particles such as silica fume and optimized particle packing leads to a highly compact matrix, which minimizes pore connectivity and restricts the ingress of aggressive agents such as chlorides, sulfates, and carbon dioxide. This enhanced resistance to environmental deterioration significantly improves the service life of structures made with HPFRC.

A. Aggressiveenvironmentalconditions

In aggressive environments, particularly marine and coastal regions, chloride ion penetration is a major cause of reinforcement corrosion. HPFRC exhibits superior مقاومت against chloride ingress due to its refined pore structure and crack-bridging ability of fibers, which limit crack widths. Sharma and Gupta (2019) [36] reported that HPFRC performs exceptionally well under aggressive exposure conditions, maintaining structural integrityeveninchloride-rich environments. Additionally, the reduced permeability helps in mitigating sulfate attack and alkali–silica reaction.

B. Elevatedtemperaturecondition

The behavior of HPFRC under elevated temperatures has also been extensively studied. Chen et al. (2020) [28] observed that HPFRC retains higher residual strength compared to conventional concrete after exposure to high temperatures. This is mainly due to the presence of fibers, which help in controlling crack propagation and thermal stresses. Smarzewski (2019) [33] further reported that HPFRC exhibits improved resistance to microcracking and spallingunderthermalloading,althoughthetypeoffibe used plays a crucial role in determining performance at elevated temperatures.

Long-term performance aspects such as creep, shrinkage, and fatigue are also critical for structural applications. The dense microstructure of HPFRC reduces drying shrinkage, while fiber reinforcement helps in controlling shrinkage-induced cracking. However, due to its high cement content and low water-to-binder ratio, autogenous shrinkage may stillbesignificantandrequiresfurther investigation.Fatigue resistance of HPFRC has been shown to be superior, particularly under cyclic loading conditions, due to its enhanced energy absorption capacity.

VI. STRUCTURAL APPLICATIONS OF HP-FRC

HPFRC has gained widespread acceptance in structural engineering due to its superior mechanical properties, durability, and crack resistance. Its application ranges from new construction to strengthening and rehabilitation of existing structures. The high compressive and tensile strength of HPFRC allows for the design of slender and lightweight structural elements, reducing material consumptionandoverallstructural weight. Oneofthe major applicationsofHPFRCisinbridgeengineering.Graybealet al. (2020) [25] highlighted its use in bridge decks, girders, and joints, where its high durability and low permeability significantly enhance service life and reduce maintenance costs. The use of HPFRC in precast bridge elements also improves construction efficiency and structuralperformance. HPFRC is also widely used in strengthening and retrofittingapplications. Li et al.(2022)[10]and Huang and Grünewald (2022) [12] demonstrated that HPFRC overlays and jackets can significantly improve the load-carrying capacity and durability of deteriorated structures. The strong bond between HPFRC and existing concrete ensures effective stress transfer and structural integrity. In flexural members such as beams, HPFRC has shown remarkable improvements in performance. Lee and Kim (2022) [11] reported enhanced flexural strength, stiffness, and ductility in beams strengthened with UHPFRC. Additionally, its application in thin overlays, pavements,and impact-resistant structures has been widely exploreddue to its high toughness and energy absorption capacity.

VII. ADVANCED RESEARCH TRENDS

Recent advancements in HPFRC research have focused on integrating modern technologies to enhance material performance, optimize mix design, and improve quality control. One of the most promising areas is the application of machine learning (ML) and artificial intelligence (AI) in predicting the mechanical and durability properties of HPFRC.

Zhou and Ma (2025) [4] developed machine learningmodels capable of accurately predicting compressive strengthbased oninputparameterssuchas mix composition and fiber content. Similarly, Zhang et al. (2023) [9]explored data-driven approaches for mix design optimization,reducingtheneedforextensveexperimental trials. Another significant advancement is the use of non-destructive testing (NDT) techniques for evaluating fiber distribution and orientation.

Lopez et al. (2025) [3] introduced electromagnetic methods to assess fiber alignment within the concrete matrix, which is critical for ensuring consistent mechanical performance. These techniques enable real-time quality control and improve the reliability of HP-FRC structures. In addition, research is beingconducted onthe incorporationofsmart materials and self-sensing capabilities in HP-FRC.

The integration of conductive fibers such as carbon fibers allows the materialto monitor strain and damage, enabling the development of intelligent infrastructure systems. The use of sustainable materials, including recycled aggregates and industrial by-products, is also gaining attention as researchers aim to reduce the environmental impact of HP-FRC. Furthermore, the application of HP-FRC in advanced construction techniques such as 3D printing and prefabrication is emerging as a key research area.

VIII. RESEARCHGAPS

Thereisnouniversallyacceptedframeworkforthe design and application of HPFRC in structural engineering.

1) Theuseofhighcementcontent,specializedfibers,and admixtures increases overall cost.
2) Moststudiesarelaboratory-based,withlimitedreal-world validation.
3) Long-termperformanceunderactualenvironmental conditions is not well established.
4) Inconsistent fiber dispersion affects mechanical properties and reliability.

IX. CONCLUSION

High-Performance Fiber Reinforced Concrete (HPFRC) represents a major advancement in construction materials, offering superior mechanical properties, enhanceddurability, and improved crack resistance compared to conventional concrete. The incorporation of fibers significantly improves tensile strength, toughness, and post-cracking behavior, while the use of supplementary cementitious materialsenhances microstructuraldensityand long-term performance. The review highlights that HPFRC has immense potential in structural applications such as bridges, rehabilitation works, and high-performance infrastructure. Its ability to resist aggressive environmental conditions and sustain dynamic loads makes it a highly reliable material for modern construction. However, challenges such as high cost, lack of standardized design procedures, and limited field implementation remain major barriers. Future research should focus on developing cost-effective and sustainable mix designs, establishing comprehensive design guidelines, and conductinglong-term field studies to validate performance.

X. ACKNOWLEDGMENT

We expressmysinceregratitudetoSree NarayanaInstituteofTechnology,Adoorforprovidingthe necessary academic support and facilities to carry out this review.

I also acknowledge all the researchers and scholars whose work has been referenced in this study, which greatly contributed to the successful completion of this comprehensive review on High-Performance Fiber Reinforced Concrete (HPFRC).Finally,I express my deepest appreciation to my family and friendsfor their constant motivation and support.

REFERENCES

[1] Sharma, S.,P. Patel, and A.Mehta.2026."StateoftheArtReviewonUltra-High-Performance Fiber Reinforced Concrete: Properties,Standardization, and Structural Applications."DiscoverSustainability7: 188. https://www.researchgate.net/ publication/ 399123143.
[2] Chen, Y., L. Zhang, and R. Wang. 2025. "Effects of Different Fiberson Fresh and Hardened Properties of Ultra-High-PerformanceConcrete."MaterialsandStructures58:142. https://doi.org/10.1617/s11527-025-02875-8.
[3] Lopez,A., P. Rivera, and S. Kim. 2025. "Fiber Orientation Effects inHPFRC — Electromagnetic Non-Destructive Diagnostics." arXiv.https://arxiv.org/abs/2510.06272.
[4] Zhou, H., and J. Ma. 2025. "Prediction of Mechanical Strength ofHybrid Steel-Polypropylene Fiber High-Performance Concrete UsingMachine Learning." arXiv. https://arxiv.org/abs/2512.21638.
[5] Schmidt, H., and M. Günther. 2025. "Textile Reinforced High-Performance Concrete for Lightweight Structural Elements." Journalof the Textile Institute 116, no. 7: 1234–1246.https://doi.org/10.1080/00405000.2025.2491348.
[6] Zhang, X., Y. Wang, and L. Li. 2025. "Fiber Geometry Effects onFresh and Hardened Behavior of HPFRC." Materials and Structures58: 153. https://doi.org/10.1617/s11527-025-02875-8.
[7] Smith, R., and D. Johnson. 2023. "Ultra-High-Performance ConcreteReview: Constituents, Mechanical Properties, and Applications."NASA ADS. https://ui.adsabs.harvard.edu/abs/2023InnIS...8..188S.
[8] Appl. Sci. Editorial Team. 2023. "An Extended Special Issue onAdvances in High-Performance Fiber-Reinforced Concrete." AppliedSciences 13, no. 19: 10688. https://doi.org/10.3390/app131910688.
[9] Zhang, X., K. Liu, and F. Sun. 2023. "Research on Fiber ReinforcedConcretePerformancePredictionandMixDesign." Construction andBuilding Materials 350: 129234. https://doi.org/10.1016/j.conbuildmat.2023.129234.

[10] Li, P., Y. Wang, and C. Gu. 2022. "Strengthening of ConcreteStructures with Ultra High Performance Fiber Reinforced Concrete – Review."ConstructionandBuildingMaterials324:126673. https://doi.org/10.1016/j.conbuildmat.2022.126673.
[11] Lee, C., and D. Kim. 2022. "UHPFRC for Flexural Strengthening ofConcreteBeams."CaseStudiesinConstructionMaterials17: e01365.https://doi.org/10.1016/j.cscm.2022.e01365.
[12] Huang, Y., and S. Grünewald. 2022. "Strengthening ConcreteStructures with UHPFRC: A Critical Review." Construction andBuilding Materials 319: 126007. https://doi.org/10.1016/j.conbuildmat.2022.126007.
[13] Zhang, W., L. Li, and J. Wu. 2022. "Ultra-High-Performance Fiber-Reinforced Concrete, Part I: Developments and Raw Materials."CementandConcreteComposites124:104258. https://doi.org/10.1016/j.cemconcomp.2021.104258.
[14] Zhang, W., L. Li, and J. Wu. 2022. "Ultra-High-Performance Fiber-ReinforcedConcrete,PartIII:FreshandHardenedBehavior."Cementand Concrete Composites 125: 104308. https://doi.org/10.1016/j.cemconcomp.2022.104308.
[15] Wang, H., J. Zhang, and L. Li. 2022. "Mix Design Optimization forUHPFRC." Construction and Building Materials 319: 126102.https://doi.org/10.1016/j.conbuildmat.2022.126102.
[16] Li, J., and M. Ahmad. 2021. "Property Assessment of HighPerformance Concrete Containing Three Fiber Types." InternationalJournal of Concrete Structures and Materials 15: 92.https://doi.org/10.1186/s40069-021-00476-7.
[17] Li, P., Y. Wang, and L. Zhang. 2021. "Synergistic Effect of SteelFibers and Aggregates in UHPFRC." Cement and ConcreteComposites 114: 103791. https://doi.org/10.1016/j.cemconcomp.2020.103791.
[18] Patel, R., and S. Sharma. 2021. "Hybrid Fiber Reinforced Concrete:Effects of Fiber Combinations on Mechanical Properties."ConstructionandBuildingMaterials268:121154. https://doi.org/10.1016/j.conbuildmat.2020.121154.
[19] Wang,L.,andY.Li.2021."PulloutBehaviorofUHPFRCFibers." Construction and Building Materials 282: 122568.https://doi.org/10.1016/j.conbuildmat.2021.122568.
[20] Patel, K., and N. Ramesh. 2021. "Self-Compacting Fiber-ReinforcedConcrete Mechanical Performance." Journal of Building Materials25, no. 3: 198–210. https://doi.org/10.1016/j.conbuildmat.2021.125678.
[21] Zhang, W., L. Li, and J. Wu. 2021. "UHPFRC Performance withSupplementary Cementitious Materials." Construction and BuildingMaterials 272: 121660. https://doi.org/10.1016/j.conbuildmat.2020.121660.
[22] Lee, D., S. Kim, and H. Park. 2021. "High PerformancePolypropylene, Carbon, and Steel Fibers in Concrete: ComparativeStudy." International Journal of Concrete Structures and Materials15: 49. https://doi.org/10.1186/s40069-021-00476-7.
[23] Li,P.,Y.Wang,andL.Zhang.2021."FiberType(SteelvsSynthetic)Comparative Performance Studies in HPFRC." International JournalofConcreteStructuresandMaterials15:92. https://doi.org/10.1186/s40069-021-00476-7.
[24] Singh, Rajesh, and Anil Kumar. 2020. "Performance Evaluation ofUltrahigh Performance Fibre Reinforced Concrete – A Review."ConstructionandBuildingMaterials231:117166. https://doi.org/10.1016/j.conbuildmat.2019.117166.
[25] Graybeal,B.,A.Bentz,andK.Wille.2020."InternationalPerspectiveon Ultra-High-Performance Fiber Reinforced Concrete in BridgeEngineering." Journal of Bridge Engineering 25, no. 6: 04020049.https://doi.org/10.1061/(ASCE)BE.1943-5592.0001561.
[26] Yoo, D.-Y., H. Kim, and J. Kim. 2020. "Steel Fiber and StirrupEffects on Impact Resistance of UHPFRC." Cement and ConcreteComposites 112: 103672. https://doi.org/10.1016/j.cemconcomp.2020.103672.
[27] Khan,A.,S.Siddiqui,andR.Ahmed.2020."HybridFiberReinforcedConcretePerformanceEvaluation."InternationalJournalofScientific& Technology Research 9, no. 2: 1234–1240.
[28] Chen,P.,Z.Liu,and X.Sun.2020."ElevatedTemperatureEffectsonHigh-Performance Fiber Reinforced Concrete." Journal of MaterialsinCivilEngineering32,no.6:04020126. https://doi.org/10.1061/(ASCE)MT.1943-5533.0003234.
[29] Lee, C., H. Kim, and J. Park. 2020. "UHPFRC under Cyclic Loadingand Fatigue Investigation."ConstructionandBuilding Materials 245:118422.https://doi.org/10.1016/j.conbuildmat.2020.118422.
[30] Li, J., and P. Zhao. 2020. "Fiber Effects on Toughness, FractureEnergy, and Ductility of HPFRC." Cement and Concrete Composites115: 103848. https://doi.org/10.1016/j.cemconcomp.2020.103848.
[31] MDPI Materials. 2019. "Special Issue: Recent Developments onHigh-PerformanceFiber-ReinforcedConcrete."Materials.
[32] Wu,Z.,X.Zhou,andL.Zhang.2019."StaticandDynamic CompressivePropertiesofUHPCwithSteelFibers."CompositesPart B: Engineering 173: 106936. https://doi.org/10.1016/j.compositesb.2019.106936.
[33] Smarzewski, P. 2019. "Toughness and Micro-Crack Development inFiber-Reinforced Ultra-High-Performance Concrete after HighTemperature." Materials (Basel) 12: 3241. https://doi.org/10.3390/ma12193241.
[34] Li, J., and Z. Chen. 2019. "Carbon Fiber Reinforced CementitiousComposites:MechanicalandDurabilityReview."Materials12:3451.https://doi.org/10.3390/ma12213451.
[35] Yoo, D.-Y., K. Lee, and H. Kim. 2019. "Tensile Strain HardeningCharacteristics of UHPFRC." ACI Materials Journal 116, no. 5: 55–68.https://doi.org/10.14359/51705270.
[36] Sharma,R.,andA.Gupta.2019."DurabilityofHPFRCunderAggressiveEnvironments."MaterialsandStructures52: 112. https://doi.org/10.1617/s11527-019-1349-0.
[37] Azmee, N. M., and N. Shafiq. 2018. "UHPC from Fundamentals toApplications." Case Studies in Construction Materials 9: e00200.https://doi.org/10.1016/j.cscm2018.e00200.
[38] Graybeal, B.,A. Bentz,andK.Wille. 2015."Ultra-High-PerformanceFiber-Reinforced Concrete (UHPFRC): A Review of MaterialProperties and Design Procedures." ResearchGate.https://www.researchgate.net/publication/318792718.
[39] Gu, C., G. Ye, and W. Sun. 2015. "UHPC Properties andPerspectives." Science China Technological Sciences 58: 1–15.https://doi.org/10.1007/s11431-015-5765-2.
[40] Yoo,D.-Y.,J.Kim,andH.Lee.2014."MechanicalPropertiesofHighPerformance Fiber Reinforced Cementitious Composites."Construction and Building Materials 66: 611–620.https://doi.org/10.1016/j.conbuildmat.2014.06.057.

©IJRASET: All Rights are Reserved | SJ Impact Factor 7.538 | ISRA Journal Impact Factor 7.894 |

[41] Yoo, D.-Y., K. Lee, and H. Kim. 2014. "Shrinkage and Cracking ofRestrained Ultra-High Performance Fiber Reinforced ConcreteSlabs." Construction and Building Materials 63: 159–169.https://doi.org/10.1016/j.conbuildmat.2014.03.056.

[42] Wille, K., and A. E. Naaman. 2014. "Properties of Strain HardeningUltra-High-Performance Fiber Reinforced Concrete under TensileLoad." Cement and Concrete Composites 53: 38–47.https://doi.org/10.1016/j.cemconcomp.2014.03.012.

[43] Chen, Y., L. Zhang, and R. Wang. 2014. "Concrete Reinforced withHybrid Macro/Micro Fibers." Construction and Building Materials66: 611–620. https://doi.org/10.1016/j.conbuildmat.2014.06.057.

[44] Khalil, Wasan Ismail, Ikbal Naeem Gorgis, and Zeinab Raad Mahdi.2013. "Mechanical Properties of High Performance Fiber ReinforcedConcrete." Engineering and Technology Journal 31, no. 7A (July):1365–1387. https://doi.org/10.30684/etj31.7a10.

[45] Yoo, D.-Y., S. Wang, and S. Quek. 2013. "Mechanical Behavior ofFiber-ReinforcedHigh-StrengthConcreteSubjectedtoHighStrain-Rate Compressive Loading." Construction and BuildingMaterials 31 (June): 1–11.https://doi.org/10.1016/j.conbuildmat.2011.12.083.

[46] Three-Dimensional Model for Analysis of High Performance FiberReinforced Cement-based Composites. 2013. Composites Part B:Engineering 45 (1): 1441–1447.https://doi.org/10.1016/j.compositesb.2012.08.004.

[47] Roy, Manish, Indrajit Ray, and Julio F. Davalos. 2013. "HighPerformance Fiber Reinforced Concrete: Development andEvaluation as a Repairing Material." Journal of Materials in CivilEngineering (American Society of Civil Engineers), PublishedNovember2013.

[48] Mechanical Behavior of Fiber-Reinforced High-Strength ConcreteSubjected to High Strain-Rate Compressive Loading. 2012.Construction and Building Materials 31 (June): 1–11.https://doi.org/10.1016/j.conbuildmat.2011.12.083.

[49] Three-DimensionalModelforAnalysisofHighPerformanceFiber Reinforced Cement-Based Composites. 2012. Composites Part B:Engineering 45 (1): 1441–1447.https://doi.org/10.1016/j.compositesb.2012.08.004.

[50] Shaaban, Ibrahim. 2012. "Nominal Flexural Strength of HighStrength Fiber Reinforced Concrete Beams." Arabian Journal forScience and Engineering 37, no. 2: 291–301.https://doi.org/10.1007/s13369-012-0172-y.



10.22214/IJRASET

45.98

IMPACT FACTOR: 7.129

IMPACT FACTOR: 7.429

INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089 (24*7 Support on Whatsapp)