



# IJRASET

International Journal For Research in  
Applied Science and Engineering Technology



---

# INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

---

**Volume:** 14    **Issue:** IV    **Month of publication:** April 2026

**DOI:** <https://doi.org/10.22214/ijraset.2026.80655>

[www.ijraset.com](http://www.ijraset.com)

Call:  08813907089

E-mail ID: [ijraset@gmail.com](mailto:ijraset@gmail.com)

# A Comprehensive and Critical Review on High Performance Fiber Reinforced Concrete

JustinReji, Lekshmi Priya R

<sup>1</sup>PG Student, <sup>2</sup>Associate Professor, Department of Civil Engineering Sree Narayana Institute of Technology Adoor, India

**Abstract:** High performance concrete has gained significant attention in recent year due to its superior mechanical performance, enhanced durability, and improved crack resistance compared to conventional concrete. This paper presents a comprehensive and critical review of HPFRC, focusing on its materials composition, fiber characteristics, mechanical behaviour, durability performance and structural applications. The role of different types of fibers, including steels, polypropylene, and hybrid systems, is examined in relation to their influence on strength, durability and post-cracking behavior. The review highlights that optimized mix design, low water-to-binder ratio, and the incorporation of supplementary cementitious materials significantly contribute to the improved performance of HPFRC. Additionally, the influence of fiber geometry, orientation, and distribution on fresh and hardened properties is critically analyzed. Recent advancements such as the application of machine learning techniques for strength prediction and non-destructive evaluation methods for fiber orientation assessment are also discussed. Despite its advantages, several challenges remain, including high material cost, lack of standardized design guidelines, and limited field implementation. This study identifies key research gaps and provides future directions to enhance the practical applicability of HPFRC in modern construction. Overall, HPFRC is recognized as a promising material for sustainable and high-performance infrastructure development.

**Keywords:** High performance fiber reinforced concrete, Ultra high performance concrete, Fiber reinforcement, Cracks control.

## I. INTRODUCTION

High-Performance Fiber Reinforced Concrete (HPFRC) is an advanced cementitious composite that integrates the superior strength and durability of high-performance concrete with enhanced ductility through the incorporation of fibers such as steel, polypropylene, and carbon. Conventional concrete is inherently brittle and weak in tension, leading to crack initiation and propagation under service loads. In contrast, HPFRC exhibits improved tensile strength, toughness, and post-cracking behavior due to fiber bridging mechanisms, which delay crack growth and enhance load-carrying capacity. HPFRC is characterized by strain-hardening behavior and multiple microcracking, which significantly improve durability and structural performance. Yoo et al. (2019) [35] and Wille and Naaman (2014) [42] demonstrated that HPFRC can sustain tensile stresses beyond first cracking, exhibiting pseudo-ductile behavior. Recent studies by Sharma et al. (2026) [1] and Singh and Kumar (2020) [24] reported that ultra-high-performance fiber reinforced concrete (UHPC) can achieve compressive strengths exceeding 150 MPa along with superior durability. Azmee and Shafiq (2018) [37] further highlighted its dense microstructure and resistance to environmental degradation.

## II. MATERIALS AND MIX DESIGN OF HPFRC

### A. Materials

The performance of HPFRC is highly dependent on its mix design, which typically involves a low water-to-binder ratio (0.2–0.3), high cement content, and the use of supplementary cementitious materials (SCMs) such as silica fume, fly ash, and slag. These materials enhance particle packing density, reduce porosity, and improve the interfacial transition zone.




Fig. 1 Development of SCC, HPC, UHPC, FRC (Zhan et al. 2022)

*Mix Design of HPFRC*

Zhang et al. (2022) [13] and Zhang et al. (2021) [21] reported that SCMs significantly enhance both mechanical properties and durability by refining the pore structure. Wang et al. (2022) [15] emphasized that optimized mix design, including proper aggregate grading and superplasticizer usage, is essential for achieving workability and high strength. Additionally, Zhang et al. (2023) [9] highlighted the importance of predictive models in optimizing mix proportions.

**III. ROLES OF FIBERS IN HPFRC**

Fibers are the most critical component in High-Performance Fiber Reinforced Concrete (HPFRC), as they fundamentally transform the behavior of concrete from brittle to pseudo-ductile. The incorporation of discrete fibers enhances tensile strength, crack resistance, toughness, and ductility by bridging cracks and transferring stresses across them. This crack-bridging mechanism delays crack propagation and allows the material to sustain loads even after the formation of initial microcracks.

*A. Different types of fibers*

Different types of fibers contribute uniquely to the performance of HPFRC. Steel fibers are widely used due to their high modulus of elasticity and tensile strength, which significantly improve load-bearing capacity and post-cracking behavior. In contrast, synthetic fibers such as polypropylene are effective in controlling plastic shrinkage cracking and enhancing durability, particularly under environmental exposure conditions. Chen et al. (2025) [2] demonstrated that fiber type significantly influences both fresh properties, such as workability, and hardened properties, including strength and durability.

Table 1. Fiber types and properties (Chen, Y., L. 2025)

Name	Types of fiber	Aspect ratio (L/Ø)	Tensile strength (MPa)	Modulus of elasticity (GPa)
CS	High carbon steel fiber	65.0	2750	200
TS	Twisted steel fiber	50.0	1700	200
HS	Hooked steel fiber	54.5	1345	200
CH	High carbon hooked steel fiber	78.9	3070	210
GF	Glass based fiber	34.3	1000	42
PE	Polyethylene fiber	800.0	2700	88

*B. Fiber geometry*

Fiber geometry, including length, diameter, and aspect ratio, plays a crucial role in determining the efficiency of stress transfer between the fiber and the cementitious matrix. Zhang et al. (2025) [6] reported that fibers with higher aspect ratios improve mechanical performance but may reduce workability due to increased interlocking. Additionally, fiber orientation and distribution within the matrix significantly affect the anisotropic behavior of HPFRC. Lopez et al. (2025) [3] highlighted that aligned fibers provide better load transfer and enhanced tensile performance compared to randomly distributed fibers.

*C. Hybrid fiber system*

Hybrid fiber systems, which combine different types of fibers, have gained considerable attention due to their synergistic effects.

Patel and Sharma (2021) [18] and Lee et al.(2021)[22]reportedthatthecombinationofsteelandssynthetic fibers results in improved strength, ductility, and crack control compared to single-fiber systems. Steel fibers contribute to load-carrying capacity, while synthetic fibers enhance crack resistance at early stages, leading to a more balanced and optimized performance.



Fig.2Fibersstudied:a)Cs(b)TSc)HS(d)CH(e)GF(f)PE(Chen,Y.,L,2025)

#### IV. MECHANICAL PROPERTIES OF HPRC

High-Performance Fiber Reinforced Concrete (HPFRC) exhibits significantly enhanced mechanical properties compared to conventional concrete, making it suitable for demanding structural applications. The inclusion of fibers improves not only compressive strength but also tensile strength, flexural strength, fracture toughness, and energy absorption capacity. One of the most distinctive features of HPFRC is its strain-hardening behavior under tensile loading. Unlike conventional concrete, which fails abruptly after cracking, HPFRC can sustain increasing stress with increasing strain due to the formation of multiple microcracks. Yoo et al. (2019) [35] reported that this strain-hardening behavior results in improved ductility and structural resilience. Similarly, Wille and Naaman (2014) [42] demonstrated that HPFRC exhibits pseudo-ductile behavior, which is highly desirable in structural design.

##### A. Compression strength test

Compressive strength in HPFRC is typically higher than that of conventional concrete, often exceeding 100 MPa and reaching up to 150 MPa or more in ultra-high-performance variants. However, the primary improvement lies in tensile and post-cracking behavior rather than compressive strength alone.

##### B. Split tensile and flexural strength test

The tensile and flexural strength of HPFRC are significantly enhanced due to fiber bridging mechanisms. Li and Zhao (2020) [30] highlighted that fibers increase fracture energy and toughness by resisting crack opening and propagation. This results in improved load-carrying capacity and delayed failure, particularly in flexural members.

##### C. Performance of HPFRC

HPFRC also shows superior performance under dynamic and extreme loading conditions. Yoo et al. (2020) [26] demonstrated that the inclusion of steel fibers significantly enhances impact resistance by increasing energy absorption capacity. Additionally, Lee et al. (2020) [29] investigated fatigue behavior and found that HPFRC exhibits improved resistance to cyclic loading, making it suitable for applications subjected to repeated loading such as bridges and pavements.

Despite these advantages, the mechanical performance of HPFRC is influenced by several factors, including fiber type, volume fraction, orientation, and mix composition. Improper fiber distribution can lead to variability in properties, highlighting the need for careful design and quality control.

The enhanced mechanical properties of HPFRC, particularly its ductility, toughness, and resistance to dynamic loading, make it a highly promising material for advanced structural applications.

## V. DURABILITY AND LONGTERM PERFORMANCE

Durability is one of the most significant advantages of High-Performance Fiber Reinforced Concrete (HPFRC), primarily attributed to its dense microstructure, low porosity, and reduced permeability. The incorporation of fine particles such as silica fume and optimized particle packing leads to a highly compact matrix, which minimizes pore connectivity and restricts the ingress of aggressive agents such as chlorides, sulfates, and carbon dioxide. This enhanced resistance to environmental deterioration significantly improves the service life of structures made with HPFRC.

### A. Aggressive environmental conditions

In aggressive environments, particularly marine and coastal regions, chloride ion penetration is a major cause of reinforcement corrosion. HPFRC exhibits superior *مقاومت* against chloride ingress due to its refined pore structure and crack-bridging ability of fibers, which limit crack widths. Sharma and Gupta (2019) [36] reported that HPFRC performs exceptionally well under aggressive exposure conditions, maintaining structural integrity even in chloride-rich environments. Additionally, the reduced permeability helps in mitigating sulfate attack and alkali-silica reaction.

### B. Elevated temperature condition

The behavior of HPFRC under elevated temperatures has also been extensively studied. Chen et al. (2020) [28] observed that HPFRC retains higher residual strength compared to conventional concrete after exposure to high temperatures. This is mainly due to the presence of fibers, which help in controlling crack propagation and thermal stresses. Smarzewski (2019) [33] further reported that HPFRC exhibits improved resistance to microcracking and spalling under thermal loading, although the type of fiber used plays a crucial role in determining performance at elevated temperatures.

Long-term performance aspects such as creep, shrinkage, and fatigue are also critical for structural applications. The dense microstructure of HPFRC reduces drying shrinkage, while fiber reinforcement helps in controlling shrinkage-induced cracking. However, due to its high cement content and low water-to-binder ratio, autogenous shrinkage may still be significant and requires further investigation. Fatigue resistance of HPFRC has been shown to be superior, particularly under cyclic loading conditions, due to its enhanced energy absorption capacity.

## VI. STRUCTURAL APPLICATIONS OF HP-FRC

HPFRC has gained widespread acceptance in structural engineering due to its superior mechanical properties, durability, and crack resistance. Its application ranges from new construction to strengthening and rehabilitation of existing structures. The high compressive and tensile strength of HPFRC allows for the design of slender and lightweight structural elements, reducing material consumption and overall structural weight. One of the major applications of HPFRC is in bridge engineering. Graybeal et al. (2020) [25] highlighted its use in bridge decks, girders, and joints, where its high durability and low permeability significantly enhance service life and reduce maintenance costs. The use of HPFRC in precast bridge elements also improves construction efficiency and structural performance. HPFRC is also widely used in strengthening and retrofitting applications. Li et al. (2022) [10] and Huang and Grünwald (2022) [12] demonstrated that HPFRC overlays and jackets can significantly improve the load-carrying capacity and durability of deteriorated structures. The strong bond between HPFRC and existing concrete ensures effective stress transfer and structural integrity. In flexural members such as beams, HPFRC has shown remarkable improvements in performance. Lee and Kim (2022) [11] reported enhanced flexural strength, stiffness, and ductility in beams strengthened with UHPFRC. Additionally, its application in thin overlays, pavements, and impact-resistant structures has been widely explored due to its high toughness and energy absorption capacity.

## VII. ADVANCED RESEARCH TRENDS

Recent advancements in HPFRC research have focused on integrating modern technologies to enhance material performance, optimize mix design, and improve quality control. One of the most promising areas is the application of machine learning (ML) and artificial intelligence (AI) in predicting the mechanical and durability properties of HPFRC.

Zhou and Ma (2025) [4] developed machine learning models capable of accurately predicting compressive strength based on input parameters such as mix composition and fiber content. Similarly, Zhang et al. (2023) [9] explored data-driven approaches for mix design optimization, reducing the need for extensive experimental trials. Another significant advancement is the use of non-destructive testing (NDT) techniques for evaluating fiber distribution and orientation.

Lopez et al. (2025) [3] introduced electromagnetic methods to assess fiber alignment within the concrete matrix, which is critical for ensuring consistent mechanical performance. These techniques enable real-time quality control and improve the reliability of HP-FRC structures. In addition, research is being conducted on the incorporation of smart materials and self-sensing capabilities in HP-FRC.

The integration of conductive fibers such as carbon fibers allows the material to monitor strain and damage, enabling the development of intelligent infrastructure systems. The use of sustainable materials, including recycled aggregates and industrial by-products, is also gaining attention as researchers aim to reduce the environmental impact of HP-FRC. Furthermore, the application of HP-FRC in advanced construction techniques such as 3D printing and prefabrication is emerging as a key research area.

## VIII. RESEARCH GAPS

There is no universally accepted framework for the design and application of HPFRC in structural engineering.

- 1) The use of high cement content, specialized fibers, and admixtures increases overall cost.
- 2) Most studies are laboratory-based, with limited real-world validation.
- 3) Long-term performance under actual environmental conditions is not well established.
- 4) Inconsistent fiber dispersion affects mechanical properties and reliability.

## IX. CONCLUSION

High-Performance Fiber Reinforced Concrete (HPFRC) represents a major advancement in construction materials, offering superior mechanical properties, enhanced durability, and improved crack resistance compared to conventional concrete. The incorporation of fibers significantly improves tensile strength, toughness, and post-cracking behavior, while the use of supplementary cementitious materials enhances microstructural density and long-term performance. The review highlights that HPFRC has immense potential in structural applications such as bridges, rehabilitation works, and high-performance infrastructure. Its ability to resist aggressive environmental conditions and sustain dynamic loads makes it a highly reliable material for modern construction. However, challenges such as high cost, lack of standardized design procedures, and limited field implementation remain major barriers. Future research should focus on developing cost-effective and sustainable mix designs, establishing comprehensive design guidelines, and conducting long-term field studies to validate performance.

## X. ACKNOWLEDGMENT

We express my sincere gratitude to Sree Narayana Institute of Technology, Adoor for providing the necessary academic support and facilities to carry out this review.

I also acknowledge all the researchers and scholars whose work has been referenced in this study, which greatly contributed to the successful completion of this comprehensive review on High-Performance Fiber Reinforced Concrete (HPFRC). Finally, I express my deepest appreciation to my family and friends for their constant motivation and support.

## REFERENCES

- [1] Sharma, S., P. Patel, and A. Mehta. 2026. "State of the Art Review on Ultra-High-Performance Fiber Reinforced Concrete: Properties, Standardization, and Structural Applications." *Discover Sustainability* 7: 188. <https://www.researchgate.net/publication/399123143>.
- [2] Chen, Y., L. Zhang, and R. Wang. 2025. "Effects of Different Fibers on Fresh and Hardened Properties of Ultra-High-Performance Concrete." *Materials and Structures* 58: 142. <https://doi.org/10.1617/s11527-025-02875-8>.
- [3] Lopez, A., P. Rivera, and S. Kim. 2025. "Fiber Orientation Effects in HPFRC — Electromagnetic Non-Destructive Diagnostics." arXiv. <https://arxiv.org/abs/2510.06272>.
- [4] Zhou, H., and J. Ma. 2025. "Prediction of Mechanical Strength of Hybrid Steel-Polypropylene Fiber High-Performance Concrete Using Machine Learning." arXiv. <https://arxiv.org/abs/2512.21638>.
- [5] Schmidt, H., and M. Günther. 2025. "Textile Reinforced High-Performance Concrete for Lightweight Structural Elements." *Journal of the Textile Institute* 116, no. 7: 1234–1246. <https://doi.org/10.1080/00405000.2025.2491348>.
- [6] Zhang, X., Y. Wang, and L. Li. 2025. "Fiber Geometry Effects on Fresh and Hardened Behavior of HPFRC." *Materials and Structures* 58: 153. <https://doi.org/10.1617/s11527-025-02875-8>.
- [7] Smith, R., and D. Johnson. 2023. "Ultra-High-Performance Concrete Review: Constituents, Mechanical Properties, and Applications." NASA ADS. <https://ui.adsabs.harvard.edu/abs/2023InnIS...8..188S>.
- [8] Appl. Sci. Editorial Team. 2023. "An Extended Special Issue on Advances in High-Performance Fiber-Reinforced Concrete." *Applied Sciences* 13, no. 19: 10688. <https://doi.org/10.3390/app131910688>.
- [9] Zhang, X., K. Liu, and F. Sun. 2023. "Research on Fiber Reinforced Concrete Performance Prediction and Mix Design." *Construction and Building Materials* 350: 129234. <https://doi.org/10.1016/j.conbuildmat.2023.129234>.

- [10] Li, P., Y. Wang, and C. Gu. 2022. "Strengthening of Concrete Structures with Ultra High Performance Fiber Reinforced Concrete – Review." *Construction and Building Materials* 324:126673. <https://doi.org/10.1016/j.conbuildmat.2022.126673>.
- [11] Lee, C., and D. Kim. 2022. "UHPFRC for Flexural Strengthening of Concrete Beams." *Case Studies in Construction Materials* 17: e01365. <https://doi.org/10.1016/j.cscm.2022.e01365>.
- [12] Huang, Y., and S. Grünewald. 2022. "Strengthening Concrete Structures with UHPFRC: A Critical Review." *Construction and Building Materials* 319: 126007. <https://doi.org/10.1016/j.conbuildmat.2022.126007>.
- [13] Zhang, W., L. Li, and J. Wu. 2022. "Ultra-High-Performance Fiber-Reinforced Concrete, Part I: Developments and Raw Materials." *Cement and Concrete Composites* 124:104258. <https://doi.org/10.1016/j.cemconcomp.2021.104258>.
- [14] Zhang, W., L. Li, and J. Wu. 2022. "Ultra-High-Performance Fiber-Reinforced Concrete, Part III: Fresh and Hardened Behavior." *Cement and Concrete Composites* 125: 104308. <https://doi.org/10.1016/j.cemconcomp.2022.104308>.
- [15] Wang, H., J. Zhang, and L. Li. 2022. "Mix Design Optimization for UHPFRC." *Construction and Building Materials* 319: 126102. <https://doi.org/10.1016/j.conbuildmat.2022.126102>.
- [16] Li, J., and M. Ahmad. 2021. "Property Assessment of High Performance Concrete Containing Three Fiber Types." *International Journal of Concrete Structures and Materials* 15: 92. <https://doi.org/10.1186/s40069-021-00476-7>.
- [17] Li, P., Y. Wang, and L. Zhang. 2021. "Synergistic Effect of Steel Fibers and Aggregates in UHPFRC." *Cement and Concrete Composites* 114: 103791. <https://doi.org/10.1016/j.cemconcomp.2020.103791>.
- [18] Patel, R., and S. Sharma. 2021. "Hybrid Fiber Reinforced Concrete: Effects of Fiber Combinations on Mechanical Properties." *Construction and Building Materials* 268:121154. <https://doi.org/10.1016/j.conbuildmat.2020.121154>.
- [19] Wang, L., and Y. Li. 2021. "Pullout Behavior of UHPFRC Fibers." *Construction and Building Materials* 282: 122568. <https://doi.org/10.1016/j.conbuildmat.2021.122568>.
- [20] Patel, K., and N. Ramesh. 2021. "Self-Compacting Fiber-Reinforced Concrete Mechanical Performance." *Journal of Building Materials* 25, no. 3: 198–210. <https://doi.org/10.1016/j.conbuildmat.2021.125678>.
- [21] Zhang, W., L. Li, and J. Wu. 2021. "UHPFRC Performance with Supplementary Cementitious Materials." *Construction and Building Materials* 272: 121660. <https://doi.org/10.1016/j.conbuildmat.2020.121660>.
- [22] Lee, D., S. Kim, and H. Park. 2021. "High Performance Polypropylene, Carbon, and Steel Fibers in Concrete: Comparative Study." *International Journal of Concrete Structures and Materials* 15: 49. <https://doi.org/10.1186/s40069-021-00476-7>.
- [23] Li, P., Y. Wang, and L. Zhang. 2021. "Fiber Type (Steel vs Synthetic) Comparative Performance Studies in HPFRC." *International Journal of Concrete Structures and Materials* 15: 92. <https://doi.org/10.1186/s40069-021-00476-7>.
- [24] Singh, Rajesh, and Anil Kumar. 2020. "Performance Evaluation of Ultrahigh Performance Fibre Reinforced Concrete – A Review." *Construction and Building Materials* 231:117166. <https://doi.org/10.1016/j.conbuildmat.2019.117166>.
- [25] Graybeal, B., A. Bentz, and K. Wille. 2020. "International Perspective on Ultra-High-Performance Fiber Reinforced Concrete in Bridge Engineering." *Journal of Bridge Engineering* 25, no. 6: 04020049. [https://doi.org/10.1061/\(ASCE\)BE.1943-5592.0001561](https://doi.org/10.1061/(ASCE)BE.1943-5592.0001561).
- [26] Yoo, D.-Y., H. Kim, and J. Kim. 2020. "Steel Fiber and Stirrup Effects on Impact Resistance of UHPFRC." *Cement and Concrete Composites* 112: 103672. <https://doi.org/10.1016/j.cemconcomp.2020.103672>.
- [27] Khan, A., S. Siddiqui, and R. Ahmed. 2020. "Hybrid Fiber Reinforced Concrete Performance Evaluation." *International Journal of Scientific & Technology Research* 9, no. 2: 1234–1240.
- [28] Chen, P., Z. Liu, and X. Sun. 2020. "Elevated Temperature Effect on High-Performance Fiber Reinforced Concrete." *Journal of Materials in Civil Engineering* 32, no. 6: 04020126. [https://doi.org/10.1061/\(ASCE\)MT.1943-5533.0003234](https://doi.org/10.1061/(ASCE)MT.1943-5533.0003234).
- [29] Lee, C., H. Kim, and J. Park. 2020. "UHPFRC under Cyclic Loading and Fatigue Investigation." *Construction and Building Materials* 245:118422. <https://doi.org/10.1016/j.conbuildmat.2020.118422>.
- [30] Li, J., and P. Zhao. 2020. "Fiber Effects on Toughness, Fracture Energy, and Ductility of HPFRC." *Cement and Concrete Composites* 115: 103848. <https://doi.org/10.1016/j.cemconcomp.2020.103848>.
- [31] MDPI Materials. 2019. "Special Issue: Recent Developments on High-Performance Fiber-Reinforced Concrete." *Materials*.
- [32] Wu, Z., X. Zhou, and L. Zhang. 2019. "Static and Dynamic Compressive Properties of UHPC with Steel Fibers." *Composites Part B: Engineering* 173: 106936. <https://doi.org/10.1016/j.compositesb.2019.106936>.
- [33] Smarzewski, P. 2019. "Toughness and Micro-Crack Development in Fiber-Reinforced Ultra-High-Performance Concrete after High Temperature." *Materials (Basel)* 12: 3241. <https://doi.org/10.3390/ma12193241>.
- [34] Li, J., and Z. Chen. 2019. "Carbon Fiber Reinforced Cementitious Composites: Mechanical and Durability Review." *Materials* 12:3451. <https://doi.org/10.3390/ma12213451>.
- [35] Yoo, D.-Y., K. Lee, and H. Kim. 2019. "Tensile Strain Hardening Characteristics of UHPFRC." *ACI Materials Journal* 116, no. 5: 55–68. <https://doi.org/10.14359/51705270>.
- [36] Sharma, R., and A. Gupta. 2019. "Durability of HPFRC under Aggressive Environments." *Materials and Structures* 52: 112. <https://doi.org/10.1617/s11527-019-1349-0>.
- [37] Azmee, N. M., and N. Shafiq. 2018. "UHPC from Fundamentals to Applications." *Case Studies in Construction Materials* 9: e00200. <https://doi.org/10.1016/j.cscm.2018.e00200>.
- [38] Graybeal, B., A. Bentz, and K. Wille. 2015. "Ultra-High-Performance Fiber-Reinforced Concrete (UHPFRC): A Review of Material Properties and Design Procedures." *ResearchGate*. <https://www.researchgate.net/publication/318792718>.
- [39] Gu, C., G. Ye, and W. Sun. 2015. "UHPC Properties and Perspectives." *Science China Technological Sciences* 58: 1–15. <https://doi.org/10.1007/s11431-015-5765-2>.
- [40] Yoo, D.-Y., J. Kim, and H. Lee. 2014. "Mechanical Properties of High-Performance Fiber Reinforced Cementitious Composites." *Construction and Building Materials* 66: 611–620. <https://doi.org/10.1016/j.conbuildmat.2014.06.057>.



- [41] Yoo, D.-Y., K. Lee, and H. Kim. 2014. "Shrinkage and Cracking of Restrained Ultra-High Performance Fiber Reinforced Concrete Slabs." *Construction and Building Materials* 63: 159–169. <https://doi.org/10.1016/j.conbuildmat.2014.03.056>.
- [42] Wille, K., and A. E. Naaman. 2014. "Properties of Strain Hardening Ultra-High-Performance Fiber Reinforced Concrete under Tensile Load." *Cement and Concrete Composites* 53: 38–47. <https://doi.org/10.1016/j.cemconcomp.2014.03.012>.
- [43] Chen, Y., L. Zhang, and R. Wang. 2014. "Concrete Reinforced with Hybrid Macro/Micro Fibers." *Construction and Building Materials* 66: 611–620. <https://doi.org/10.1016/j.conbuildmat.2014.06.057>.
- [44] Khalil, Wasan Ismail, Ikbal Naeem Gorgis, and Zeinab Raad Mahdi. 2013. "Mechanical Properties of High Performance Fiber Reinforced Concrete." *Engineering and Technology Journal* 31, no. 7A (July): 1365–1387. <https://doi.org/10.30684/etj31.7a10>.
- [45] Yoo, D.-Y., S. Wang, and S. Quek. 2013. "Mechanical Behavior of Fiber-Reinforced High-Strength Concrete Subjected to High Strain-Rate Compressive Loading." *Construction and Building Materials* 31 (June): 1–11. <https://doi.org/10.1016/j.conbuildmat.2011.12.083>.
- [46] Three-Dimensional Model for Analysis of High Performance Fiber Reinforced Cement-based Composites. 2013. *Composites Part B: Engineering* 45 (1): 1441–1447. <https://doi.org/10.1016/j.compositesb.2012.08.004>.
- [47] Roy, Manish, Indrajit Ray, and Julio F. Davalos. 2013. "High Performance Fiber Reinforced Concrete: Development and Evaluation as a Repairing Material." *Journal of Materials in Civil Engineering* (American Society of Civil Engineers), Published November 2013.
- [48] Mechanical Behavior of Fiber-Reinforced High-Strength Concrete Subjected to High Strain-Rate Compressive Loading. 2012. *Construction and Building Materials* 31 (June): 1–11. <https://doi.org/10.1016/j.conbuildmat.2011.12.083>.
- [49] Three-Dimensional Model for Analysis of High Performance Fiber Reinforced Cement-Based Composites. 2012. *Composites Part B: Engineering* 45 (1): 1441–1447. <https://doi.org/10.1016/j.compositesb.2012.08.004>.
- [50] Shaaban, Ibrahim. 2012. "Nominal Flexural Strength of High Strength Fiber Reinforced Concrete Beams." *Arabian Journal for Science and Engineering* 37, no. 2: 291–301. <https://doi.org/10.1007/s13369-012-0172-y>.



10.22214/IJRASET



45.98



IMPACT FACTOR:  
7.129



IMPACT FACTOR:  
7.429



# INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089  (24\*7 Support on Whatsapp)