



IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 10 Issue: V Month of publication: May 2022

DOI: https://doi.org/10.22214/ijraset.2022.43409

www.ijraset.com

Call: 🕥 08813907089 🔰 E-mail ID: ijraset@gmail.com



# Agriculture Waste Used as Partial Replacement in Green Concrete Manufacturing

Tejashree Mohan Kanjawane<sup>1</sup>, Manoj P. Wagh<sup>2</sup>

<sup>1</sup>Student, Department of Civil Engineering, Dr. Vithalrao Vikhe Patil College of Engineering, <sup>2</sup>Professor and Dean Academics, Department of Civil, Dr. Vithalrao Vikhe Patil College of Engineering, Ahmednagar, Maharashtra, India -414111

Abstract: Nowadays the total requirement of concrete increased in the whole world. This paper is about green concrete based on agricultural waste, research is using agricultural waste as a substitute for cement. Concrete mix proportion used is 1:1:2 (concrete of grade M25), from that quantities of different materials find out for Rice Husk Ash and Coconut Shell as a partial replacement of cement and coarse aggregates respectively. Like this three mix design done, one mix for Rice husk, one for coconut shell and one for combination of both.

Agricultural waste contains chemical compounds which have pozzolanic properties. The rice husk ash is finely ground material which can give the pozzolanic reaction. The silica contents in the agricultural waste material reacted with calcium oxide to produce calcium silicate gel helps in binding the concrete. Some researches has been done for the use of agricultural waste in concrete.

Collection of materials, mix design and quantities required to produce concrete blocks is find out then actual preparation of concrete blocks and different test on concrete done in this experiment. From the experimentation result is that 9% utilization of these materials in the replacement of cement gives rise to 15% increase in strength of concrete. Rice husk ash powder has a large amount of silica with which gives pozzolanic action and increases the strength. Use of coconut shell pieces of proper size (i.e. 20 mm nominal size) as a partial substitute of coarse aggregates in different percentage ranging from 0% to 50%. From the experiment results, if coconut shells used greater than 12.5% by weight of coarse fraction gives lightweight concrete without much reduction in strength. Use of both Rice husk ash and coconut shell improves test results than concrete with only coconut shell replacement. Its use reduces the environmental burden of decomposition of organic waste and also reduces pollution generated by it.

Keywords: Pozzolanic, Rice Husk Ash, Coconut Shell, Partial replacement, Agro-waste.

### I. INTRODUCTION

Concrete is the second largest used material on the earth while water came first. We were harming the nature with the use of conventional concrete. It enormous areas that results in some environmental impact like it kills the Habitat and it requires natural resources in production. Also produces ground water pollution, air pollution due to emission of CO2, soil pollution, etc.

Civil engineers especially structural engineer play a vital role in the betterment and environmental conservation that we live in. That is why, as future structural engineer, aims to produce eco-friendly green Concrete by using agricultural waste, specifically coconut shells, as a partial alternative to fine aggregates and be able to utilize plenty of available agro-waste materials that can be used in the design mix of the Green concrete. Two of the materials find out which can be used in concrete these are coconut shell and rice husk ash, wherein coconut shells would be used to partial substitute coarse aggregate and rice husk ash for partial substitution to cement. Coconuts are abundantly available in tropical countries like the India, but it also means excessive waste, such as coconut shells. Hence, the aim is to connect the environmental problems caused by the use of conventional concrete and agro-waste problem. It also aims to achieve several Sustainable Development Goals such as creating resilient infrastructure, building sustainable cities and communities, and climate change mitigation. Furthermore, its purpose is to elevate the economy and bring green development in the construction industry, whether locally or globally, resulting in productive employment and further boosting the economy.

This project studies that use of agriculture waste in concrete and its effectiveness. Impact of using agriculture waste in concrete by partial substitution give some difference in properties than the normal concrete. From that some effects are beneficial some are not. Use of ash and coconut shell in concrete gives lightweight concrete. Use of agriculture waste reduces emission of carbon dioxide during production of cement and transportation of natural aggregate. Conservation of natural aggregates can be done by the use of coconut shell as a partial replacement of coarse aggregate.



International Journal for Research in Applied Science & Engineering Technology (IJRASET) ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538

Volume 10 Issue V May 2022- Available at www.ijraset.com

On the other hand the strength of concrete may affect with large amount of replacement. Small amount of replacement lead to same strength as that of normal concrete. Both coconut shell as partial replacement of coarse aggregate and rice husk as partial replacement of cement used at a time leads to greater strength than used separately. This is the first time that coconut shell and rice husk ash used in concrete. This concrete can be used in small scale construction like one story to two story house, footpaths, compound walls, small cow shades, etc. Less harm to the nature also conservation of nature can be done with the use of this agriculture waste based type green concrete. With the use of agriculture waste in concrete we will take small steps towards conservation of natural resources, less energy use and sustainable development.

This paper summarizes feasibility of use of agro-waste products in concrete, to improve the environmental friendliness of concrete, to make it "Sustainable Green Building Material". It is the most economical and environment friendly partial replacement for ordinary Portland cement (OPC) and coarse aggregates with Rice Husk Ash and Coconut Shell respectively.

- A. Objective of this project work is as follows
- 1) To find the agricultural waste things that can be used to replace concrete component to make green concrete.
- 2) To find percentage by which it can replace concrete components.
- 3) To determine the concrete mix design for green concrete.
- 4) To find workability of concrete,
- 5) By comparing with normal mix, find out optimum percentage by which concrete component can be replace to get require strength.

### **II. LITERATURE REVIEW**

r					
Sr.	Title of paper	Journal	Author	Finding	Remark
no.		name and	detail		
		Issue			
1.	Experimental	Internationa	Dileep	This paper is about rises cash and coconut shell used	Total 25%
	Investigation on	l Research	Kumar B	as partial replacement in concrete with 10% RHA and	replacement of
	Partial Replacement	Journal of	M, S	5%, 10%, 15%, 20% and 25% CS. Study was done for	coarse aggregate
	of Rice Husk Ash as	Engineering	Suresh	mechanical and durability property of RHA and CS	by coconut shell
	Cement and Coconut	and		concrete. 25% replacement gives 10 to 13% less dense	and ordinary
	Shell as Coarse	Technology		than concrete. Compressive strength and split tensile	portland cement
	Aggregate for the	(IRJET)		strength increases by 13 and 23% for 10 % RHA and	by rice husk ash
	Production of Light	Volume: 05		decreases with addition of CS. Chloride permeability	gives light
	Weight Concrete.	Issue: 08,		also increase by 24% for 25% replacement then	weight and
	-	Aug 2018		normal concrete.	nearly same
		C			strength concrete
					as normal mix.
2.	Rice husk ash as a	Innovative	Ganta	The study based on the extensive review highlights the	RHA can be used
	potential	Infrastructu	Mounika,	possibility for utilizing the RHA as a conventional	up to 30% in
	supplementary	re Solutions	Ramesh	binder in concrete. RHA increases for smaller	concrete with
	cementitious	(2021)	Baskar,	replacement up to 30% in concrete shows better bond	good strength
	material in concrete		Jyosyula	strength when compared to conventional mix and it	
	solution towards		Sri	also reduces chloride diffusion, efflorescence and	
	sustainable		Kalyana	increases resistance to sulphate and chemical attacks.	
	construction.		Rama		

TABLE I LITERATURE REVIEW



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 10 Issue V May 2022- Available at www.ijraset.com

3.	Coconut Shell as Partial Replacement of Coarse Aggregate in Concrete.	05 (02) 2018 Internationa l Research Journal of Engineering and Technology	Anand Ramesh, Anandhu K J	Results showed a rise in compressive strength at 7 days curing time for 5%, 10% replacement of coarse aggregate with coconut shell. There was a rise in compressive strength at 28 days curing time for 5% but strength lowered for 15% replacement of coarse aggregate with coconut shell. Splitting tensile strength decreased for 5% replacement of coarse aggregate with coconut shell.	Coconut shell has more power to resist crushing, and impact compared to traditional aggregate.
4.	Use of Coconut Shell as Partly Substitution of Coarse Aggregate - An Experimental Analysis.	AIP Conference Proceedings 2158, 020021 (2019)	Sanjay Kumar Vermaand SagarShriv astava	On 10% partial replacement of natural coarse aggregate with waste Coconut shell, compressive strength of coconut shell concrete has obtained 20.10 N/mm2 at 28 days. Coconut shell can be grouped under lightweight aggregate because 28 day air dry densities of coconut shell aggregate concrete are less than 2000 kg/m3.	This research on coconut shell confirm that the coconut shell has potential as lightweight aggregate in concrete.
5.	Experimental study on partial replacement of coarse aggregate by coconut shell and ordinary portland cement by rice husk ash.	Internationa l Journal of Scientific & Engineering Research Volume 9, Issue 4, April-2018	R Gopinath, T Ajithkuma r, M Nithin, V Sanjay Srikanth and P Sivakumar.	The percentage of replacement are 0%, 18%, 20%, 22%, 24% with coconut shell and 0%, 5%, 8%, 10%, 12% with rice husk ash. The characteristic properties of concrete such as compressive strength, split tensile strength using the mix made by partial replacement of coarse aggregate with crushed coconut shell aggregate and OPC with RHA. The results show that high strength is attained at replacement of 18% with CS and 8% with RHA.	With the replacement of 18% with CS and 8% with RHA strength of concrete increases.

### **III.MATERIALS AND METHODOLOGY**

A. Materials Required to Produce Green Concrete

Agricultural waste as a partial replacement used in concrete-

- 1) Rice Husk Ash as a partial replacement of ordinary Portland cement.
- 2) Coconut Shell as a partial replacement of coarse aggregate

	MATERIALS AND FLACE FROM WHERE IT GOT					
Sr.	Materials required to produce	Place from where it got				
no.	concrete					
1	Rice Husk Ash	Industry named: Sainath Murmura				
		Industry				
2	Coconut Shell	From the tree which is in nearer farms				
3	Ordinary Portland Cement (43	Local shop				
	Grade)					
4	Coarse aggregate	Local crusher				
5	Fine aggregate (Sand)	Local crusher				
6	Water	Tap water				

### TABLE II MATERIALS AND PLACE FROM WHERE IT COT



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 10 Issue V May 2022- Available at www.ijraset.com

*B. Concert Mix Design* As per IS 10262: 2019 Mix Design for-

- Control Mix
- Mix type 1. Partial replacement of cement by Rice husk ash,
- Mix type 2. Partial replacement of coarse aggregates by Coconut shell and
- Mix type 3. For both partial replacement of cement by Rice husk ash and partial replacement of coarse aggregates by Coconut shell.
- 1) Requirement For Proportioning
- a) Mix proportion: 1:1:2 (M 25)
- b) Type of cement: OPC 43 grade
- c) Type of partial replacement: Rice husk ash and Coconut shell
- d) Maximum nominal size of aggregate: 20mm
- e) Minimum cement content: 300 kg/m<sup>3</sup> as per Table 5 of IS 456-200.
- f) Maximum water-cement ratio: 0.50
- g) Workability: 100 mm (slump)
- h) Exposure condition: Moderate (for reinforced concrete)
- j) Type of aggregate: Crushed angular aggregate
- 2) Test Data For Materials
- a) Cement used: OPC 43 grade
- b) Specific gravity of cement: 3.15
- c) Specific gravity of Rice husk ash: 2.14
- e) Specific gravity of
- 1) Coarse aggregate: 2.74 2) Fine aggregate: 2.74 3) Coconut shell: 1.33
- f) Water absorption:
- 1) Coarse aggregate: 0.5 percent. 2) Fine aggregate: 1.0 percent
- g) Free (surface) moisture:
- 1) Coarse aggregate: Nil (absorbed moisture also nil) 2) Fine aggregate: Nil
- h) Sieve analysis:
- 1) Coarse aggregate

TABLE III

			SIEVE	ANALYSIS		
IS sieve size	co	arse	oth	Remark		
(mm)	agg fra	regate ction	I 60 %	II 40 %	Combined 100 %	
	Ι	II				
20	100	100	60	40	100	Conforming to
10	0	72.50	0	27.5	27.5	Table 7 of IS
4.75		8.10		3.8	3.8	383

### C. Fine Aggregate

Confirming to Zone I of table 9 of IS 383.

1) Target Strength For Mix Proportioning

$$f_{ck}$$
' =  $f_{ck}$  + 1.65 s or  $f_{ck}$ ' =  $f_{ck}$  + X



Volume 10 Issue V May 2022- Available at www.ijraset.com

Where,

 $f_{ck}$ ' = target average compressive strength at 28 days,  $f_{ck}$  = characteristics compressive strength at 28 days, and s = standard deviation as per Table 2 of IS 10262 – 2019. X = factor based on grade of concrete as per Table 1 of IS 10262-2019. From Table I, Standard Deviation,  $s = 4 \text{ N/mm}^2$ . Therefore, target strength  $f_{ck}$ ' = 25 + 1.65 × 4 = 31.6 N/mm<sup>2</sup> or  $f_{ck}$ ' = 25 + 5.5 = 30.5 N/mm<sup>2</sup> Whichever is greater, so target strength is 31.6 N/mm<sup>2</sup>

2) Selection Of Water-Cement Ratio

From Fig 1 of IS 10262-2019, maximum water-cement ratio from curve 2 (for 43 grade of cement) is 0.484 for target strength of  $31.6 \text{ N/mm}^2$ . So, adopt w/c ratio = 0.45

3) Selection Of Water Content
From IS 10262: 2019 Table 4, maximum
Water content for 20 mm aggregate = 186 liter (for 50 mm slump)
Estimated water content for 100 mm slump= 186+ (6/100) × 186 = 197 liter

4) Calculation Of Cement And Agricultural Waste Content

Water-cement ratio = 0.45

Cementations material (for mix type 1, 3 = cement + Rice husk ash and for mix type 2 = cement only) content = (197/0.45) = 437.77 kg/m<sup>3</sup>

From Table 5 of IS 456, minimum cement content for 'moderate' exposure conditions  $437.77 \text{ kg/m}^3 > 300 \text{ kg/m}^3$ , hence. O.K.

5) Proportion Of Volume Of Coarse Aggregate And Fine Aggregate Content

From Table 3, IS 10262 : 2019, volume of coarse aggregate corresponding to 20 mm size aggregate and fine aggregate (Zone I) for water-cement ratio of 0.50 = 0.60.

For pump able concrete these values should be reduced by 10 percent.

Therefore, volume of coarse aggregate  $=0.60 \times 0.9 =0.54$ .

Volume of fine aggregate content = 1 - 0.54 = 0.46.

6) Mix Calculations

The mix calculations per unit volume of concrete shall be as follows:

a) Volume of concrete =  $1 \text{ m}^3$ 

b) Volume of cement = (Mass of cement/Specific gravity of cement) x (1/1000)

c) Volume of Rice husk ash

= (Mass of rice husk ash/Specific gravity of rice husk ash) x (1/1000)

d) Volume of water = (Mass of water/Specific gravity of water) x (1/1000)

 $= (197/1) \text{ x} (1/1000) = 0.197 \text{ m}^3$ 

e) Volume of all aggregates = [a - (b + c + d)]

f) Mass of fine aggregate = Volume of all aggregates x volume of fine aggregate x Specific gravity of fine aggregate x 1000

g) Mass of coarse aggregate = Volume of all aggregates x volume of coarse aggregate x Specific gravity of coarse aggregate x 1000
h) Volume of Coconut shell = (Mass of coarse aggregates/ Specific gravity of Coconut shell) x (Percentage of coconut shell to be used/100)

I) Entrapped air volume

Entrapped Air, as Percentage of Volume of Concrete is 1% for 20 mm coarse aggregate. So for 1m<sup>3</sup> of concrete = 0.01 m<sup>3</sup> entrap air



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538

Volume 10 Issue V May 2022- Available at www.ijraset.com

For Control Mix i.e. for no replacements-

	TABL	± IV	
WEIGH	HT OF QUANTITIES PER M <sup>3</sup>	FOR CONTROL MIX FOR M	125
of cement	Weight of fine	Weight of coarse	Weigh

. . . . . . .

Weight of cement	Weight of fine	Weight of coarse	Weight of water
(kg)	aggregate (kg)	aggregate (kg)	(lit.)
437.77 (0.139 m <sup>3</sup> )	824.74	967.22	197

For Mix type 1 -•

TABLE V WEIGHT OF RICE HUSK ASH, CEMENT, COARSE AND FINE AGGREGATES PER M<sup>3</sup> FOR MIX TYPE 1 RHA as % by Cement (OPC) Weight of fine Weight of Water content RHA percentage  $(Kg/m^3) = 437.77$ weight of aggregate (kg) coarse aggregate (lit.) cement (kg) RHA weight (kg) (kg) 3% 13.13 424.64 967.22 197 824.74 967.22 197 6% 26.26 411.51 824.74 9% 39.40 398.37 824.74 967.22 197 12% 52.53 385.24 824.74 967.22 197 15% 65.66 372.11 824.74 967.22 197

### For Mix type 2 -٠

Value of mass and Weight of cement, water and total aggregates per m<sup>3</sup> is same as control mix.

TABLE VI					
Weight of Coconut shell, cement, coarse and fine aggregates per $\mathrm{m}^3$ for Mix type 2					
Coconut	Weight of	Weight of	Weight of coarse	Weight of	Actual weight of
shell	cement	fine	aggregate	coconut	coarse aggregates
percentage	(kg)	aggregate	Required (kg)	shell (kg)	(kg) = 967.22 -
		(kg)			weight of CS (kg)
12.5%	437.77	824.74	967.22	120.90	846.32
25%	437.77	824.74	967.22	241.81	752.41
37.5%	437.77	824.74	967.22	362.71	604.51
			•		

967.22

### For Mix type 3-٠

50%

Value of mass and volume of cement, water and total aggregates is same as control mix.

824.74

437.77

Calculation for volume of cement, Rice husk ash, total aggregates, and fine aggregates is same as that of Mix type 1, and calculation of volume of coarse aggregates and coconut shell is same as Mix type 2.

483.61

483.61

TABLE VII

```
VOLUME OF RICE HUSK ASH, COCONUT SHELL, CEMENT, COARSE AND FINE AGGREGATES PER M<sup>3</sup> FOR MIX TYPE 3
```

Rice husk	Coconut	Weight of	Weight of	Weight of fine	Weight of	weight of coarse
ash	shell	Rice husk ash	cement =	aggregate	coconut shell	aggregate = 995.77 -
percentage	percentage	$(kg/m^3)$	437.77 –	$(kg/m^3)$	(kg)	$CS (kg/m^3)$
			RHA (kg)			
9%	12.5%	39.40	398.37	824.74	120.90	846.32
9%	25%	39.40	398.37	824.74	241.81	752.41
9%	37.5%	39.40	398.37	824.74	362.71	604.51



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 10 Issue V May 2022- Available at www.ijraset.com

7) Volume of materials required for 1 block of each type of Mix Size of block to be prepare is  $0.15m \ge 0.15m \ge 0.15m$ Volume of one block =  $0.003375 \text{ m}^3$ 

All calculation done for  $1 \text{ m}^3$  volume of concrete. Require volume can be found out by dividing it by 0.003375. Photos showing Fresh Blocks prepared in mold and hard blocks after 28 days of curing.

With the use of mix design the concrete is prepared and cubes where form. Experimentation done on fresh and hard concrete. On the fresh concrete slum cone test, Compaction factor test where perform to find out workability and self-compaction property of concrete. Then blocks where prepared, after 24 hours of setting blocks were removed from mold. Curing of blocks were done for 7days and 28 days then different test where perform to find out strength. Water absorption test and Compression test had performed. Compressive test done for 7 days and 28 days of curing. Graphs of each test were drown from that an idea of for which percentage we get better result. Along with conventional tests one advance test is also performed, called Scanning Electron Microscope (SEM) for concrete mix with the use of both RHA and CS



Fig. 1 Agro-Waste used in concrete (a) RHA and (b) CS



(a)

(b)

Fig. 2 Blocks preparation (a) Dry quantities of material for 12.5% CS, 9% RHA in concrete (b) Sample Photos of blocks

### D. Concrete Tests Carried Out

In stage II Concrete tests carried out are as follows-

Different test that are conducted on fresh concrete and hard concrete

- 1) Slump cone test
- 2) Water absorption and weight comparison with normal mix.
- 3) Compressive strength test at 7 days and 28 days of curing
- 4) Scanning Electronic microscopy test (SEM)



### International Journal for Research in Applied Science & Engineering Technology (IJRASET) ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538

Volume 10 Issue V May 2022- Available at www.ijraset.com

### a) Slump cone test

<u>Use-</u> To find out workability and consistency of concrete. To find out how easily it can handle and placed.

<u>Performance and value findings-</u> Slump cone test done on the plane plate and frustum of cone on it. This cone is firstly greased from inside. Then concrete were poured 1/3 portion of cone and it tamp for 25 number of times. Again second 1/3 portion filed and typing done for 25 times and lastly one more time done this process. After that cone were removed and it allow to flow under gravity. Measure the height of settlement that is the slump value. Slump value variation noted in the following results. Higher the value of slump more is the workability of concrete.



Fig. 3 Slump cone test

### b) Compaction factor test

<u>Use-</u> To find out self-compacting properties of concrete.

<u>Performance and value findings-</u> By using the hand scoop, place the concrete sample gently in the upper hopper to its brim and level it and then cover the cylinder. At the bottom of the upper hopper, open the trapdoor so that concrete falls into the lower hopper and with the rod, push the concrete sticking on its sides gently. To fall into the cylinder below, open the trapdoor of the lower hopper and allow the concrete to fall. By using trowels, cut off the excess of concrete above the top level of the cylinder and level it, then clean the outside of the cylinder. To the nearest 10g weight the cylinder with concrete mix in layers approximately 5 cm deep refill it and to obtain full compaction, each layer has to be heavily rammed. Level the top surface and then weight of the cylinder with fully compacted which is known as the weight of fully compacted concrete as W2. Then as W, find the weight of the empty cylinder



Fig. 4 Compaction factor apparatus





ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 10 Issue V May 2022- Available at www.ijraset.com

 $\label{eq:Weight of Empty Cylinder} = W_1 \\ \mbox{Weight of Empty Cylinder} + \mbox{Free Fall Concrete} = W_2 \\ \mbox{Weight of Empty Cylinder} + \mbox{Hand Compacted Concrete} = W_2 \\ \mbox{Weight of Partially Compacted Concrete} = W_P = W_2 \\ \mbox{Weight of Fully Compacted Concrete} = W_F = W_3 \\ \mbox{Weight of Fully Compacted Concrete} = W_F = W_3 \\ \mbox{Weight of Fully Compacted Concrete} = W_F \\ \mbox{Weight of Fully Compacted Concrete} \\ \mbox{Weight of Fully Compacted C$ 

### c) Water absorption and weight comparison with normal mix.

<u>Use-</u> Water absorption test is required to get an idea of how much water required for curing. This test is important due to lack of water in most of the aired region of India.

This test is also give superficial idea about strength of concrete, as water absorption increase there is decrease in strength.

<u>Performance and value findings-</u> First, specimens of size 0.15m x 0.15m x 0.15m were taken out from curing tank after 28 days of curing. Blocks keep for surface drying for 10 min. Then they were placed in an oven and maintained at 100 °C–110 °C for 24 h. After this period, specimens were allowed to cool at room temperature for 24 h and then the weights were measured frequently until the weights became constant. This value was considered as mass of the specimen and noted as A. The specimens were then immersed in water for 24 h and surface dried properly. The weights were taken in the surface dried condition and noted as B. Water absorption (%) = [(B - A)/A] \* 100

A=Dry weight of specimen after oven drying

B = Wet weight of specimen after 24 hr. curing after drying.

### d) Compressive strength test at 7 days and 28 days of curing

Use- Competition test use to find out load carrying capacity of concrete block.

<u>Performance and value findings-</u> In the compression test direction of loading is towards the specimen. Compression tests results in mechanical properties that include the compressive yield strength, compressive ultimate strength, and compressive modulus of elasticity in compression, % reduction in length etc.

The compressive loading tests on concretes were conducted on a compression testing machine of capacity 2000 kN. For the compressive strength test, a loading rate of 2.5 kN/s was applied as per IS: 516–1959. The test was conducted on 150mm cube specimens at 7 and 28 days. Each sample was weighed before putting into the crushing machine to ascertain it density. The compression strength of each sample was determined as follows-

Compressive strength = Crushing Load (kN) /Effective Area (mm<sup>2</sup>)



Fig. 5 Compression test



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 10 Issue V May 2022- Available at www.ijraset.com

### e) Scanning Electronic microscopy test (SEM)

<u>Use-</u> Composition i.e. compounds form after hardening of concrete can be find out. Effect on chemical bonding can be find out by Scanning Electronic microscopy test (SEM) test



Fig. 6 SEM Test specimen

<u>Performance-</u> Permeation of collage is taken before carried out the test. Test were performed in Central instrumentation facility, Savitribai Phule Pune University, Pune. 10 to 15 Test Blocks size 5mm x 5mm x 3mm were prepared to get an exact sized and sharp block. After 7days of curing blocks were sent to lab along with permeation letter and test fees. Blocks where scan under focused electron beam. Detector detects reflected electrons, and send signals to the computer to get a clear 3D image.

### IV. RESULT AND DISCUSSION

TABLE VIII

A. Workability of concrete

Workability of concrete cane find out by slump cone test

1) Slump cone test values for concrete made with RHA

SLUMP CONE TEST FOR MIX-1				
RHA replacement	Slump value			
as cement (%)	(mm)			
0	75			
3	68			
6	63			
9	56			
12	49			
15	39			

# $\begin{bmatrix} 80 \\ 60 \\ 40 \\ 20 \\ 0 \\ 0 \\ 0 \\ 3 \\ 6 \\ 9 \\ 12 \\ 15 \\ \% \text{ of RHA} \\ = \text{Slump (mm)}$

Fig. 7 Slump cone value chart for mix-1



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 10 Issue V May 2022- Available at www.ijraset.com

2) Slump cone test values for concrete made with coconut shell

TABLE IX					
SLUMP CC	DNE TEST FOR MIX-2				
CS replacement as	Slump value (mm)				
coarse aggregate (%)					
0	75				
12.5	42				
25	48				
37.5	58				
50	64				



Fig. 8 Slump cone value chart for mix-2

3) Slump cone test values for concrete made with Rice husk ash and coconut shell TABLE X

SLUN	SLUMP CONE TEST FOR MIX-3				
RHA	CS replacement as	Slump			
replacement as	coarse aggregate (%)	value			
cement (%)		(mm)			
0	0	75			
9	12.5	68			
9	25	63			
9	37.5	56			



Fig. 9 Slump cone value chart for mix-3



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 10 Issue V May 2022- Available at www.ijraset.com

- B. Compaction factor test.
- 1) Compaction factor values for concrete made with RHA

 TABLE XI

 COMPACTION FACTOR FOR RHA USED IN CONCRETE

 RHA as partial
 Compactio

 replacement of
 n factor

 cement (%)
 Used

0	0.872
3	0.868
6	0.865
9	0.862
12	0.855
15	0.851



Fig. 10 Compaction factor for concrete Mix type 1

2) Compaction factor test values for concrete made with CS

TABLE XII
COMPACTION FACTOR FOR CS USED IN CONCRETE

CS as	partial	Compaction
replacement of		factor
coa	arse	
aggreg	ate (%)	
0		0.872
12.5		0.859
25		0.847
37.5	0.838	
50	0.824	





Fig. 11 Compaction factor for Mix type 2

*3)* Compaction factor test values for concrete made with RHA and CS.

TABLE XIII
COMPACTION FACTOR FOR BOTH RHA AND CS USED IN CONCRETE

RHA	CS	Compacti
replacemen	replacement as	on factor
t as cement	coarse	
(%)	aggregate (%)	
0	0	0.872
9	12.5	0.864
9	25	0.853
9	37.5	0.842









ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 10 Issue V May 2022- Available at www.ijraset.com

- C. Water absorption
- 1) Water absorption (%) for concrete made with RHA

TABLE XIV				
WATER ABSORPTION FOR RHA USED IN CONCRETE				
RHA as	Dry weight	Water		
partial	of block in	absorption		
replacement	kg	(%) after 28		
of cement (%)		days of		
		curing		
0	8.53	1.09		
3	8.48	1.18		
6	8.44	1.21		
9	8.39	1.38		
12	8.35	1.51		
15	8.31	1.60		



2) Water absorption (%) for concrete made with CS

 TABLE XV

 WATER ABSORPTION FOR CS USED IN CONCRETE

CS as partial	Dry weight of block in	Water absorption (%)
replacement of coarse	kg	after 28 days of curing
aggregate (%)		
0	8.53	1.09
12.5	7.58	2.62
25	7.77	4.96
37.5	7.58	6.43
50	7.42	8.10





*3)* Water absorption (%) for concrete made with RHA and CS

TABLE XVI WATER ABSORPTION FOR BOTH RHA AND CS USED IN CONCRETE

RHA replacement of	CS replacement of	Dry weight of block	Water absorption (%)
cement (%)	coarse aggregate (%)	in kg	after 28 days of
			curing
0	0	8.53	1.09
9	12.5	7.96	3.07
9	25	7.57	5.08
9	37.5	7.31	7.58







Volume 10 Issue V May 2022- Available at www.ijraset.com

- D. Compressive strength test at 7 days and 28 days of curing.
- 1) Compression strength for mix type 1-

COMPRESSION TEST RESULTS FOR RHA IN CONCRETE.				
RHA replacement as	Compressive strength (N/mm <sup>2</sup> )			
coarse aggregate (%)				
	After 7 days of curing After 28 days of curing			
0	21.60	30.54		
3	22.01	31.26		
6	23.21	33.93		
9	25.08	35.10		
12	19.09	28.44		
15	17.84	26.04		

TABLE XVII



2) Compression strength for mix type 2-

CS replacement as coarse	Compressive strength (N/mm <sup>2</sup> )			
aggregate (%)	After 7 days of curing	After 28 days of curing		
0	21.60	30.54		
12.5	18.80	28.35		
25	16.68	26.97		
37.5	13.50	19.02		
50	12.00	17.45		

 TABLE XVIII

 COMPRESSION TEST RESULTS FOR COCONUT SHELL IN CONCRETE





Fig. 17 Chart showing compressive strength of concrete for Mix type 2

*3)* Compression strength for mix type 3-

TABLE XIX

RHA as	CS as replacement of	Compressive strength (N/mm <sup>2</sup> )	
replacement of	coarse aggregate (%)	After 7 days of	After 28 days of
cement (%)		curing	curing
0	0	21.36	29.98
9	12.5	22.07	28.58
9	25	14.12	23.02
9	37.5	7.90	11.83





*E. Scanning Electronic microscopy SEM) Test Results* SEM test for mix type 3-





(b)



(e)

Fig. 19 (a), (b), (c), (d), and (e) Photos under Scanning electron microscope



International Journal for Research in Applied Science & Engineering Technology (IJRASET) ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538

Volume 10 Issue V May 2022- Available at www.ijraset.com

Above pictures shows that there is good bonding between components of concrete in 3D view. Void spaces and cracking of concrete can be seen under Scanning electron microscope. Some nanosized cracks and void spaces formed which can be neglected. Lighter area of picture shows bump or convexity for that area, and dark portion shows flat surface. Therefore uniformity in 85% of portion which shows consistent hard solid concrete.

From all test results shows that M25 concrete can be used in light reinforcement structures but due to the use of 9% RHA as a partial replacement of cement compressive strength increase by 10% so RHA can be used in some high-rise construction with higher mix proportions. By using CS in concrete strength decrease, but concrete made with 12.5% CS gives 7% less strength, so that it can be used in light reinforced to no reinforced structures. Example- parapet walls, compound walls, partition walls, dividers in road, etc. But the concrete which uses both RHA and CS gives somewhat greater strength than concrete uses only CS. Therefore it can be used for the construction of less reinforced to no reinforced structures which carries very less load.

### V. CONCLUSIONS

Conclusion drown from the experimental test are as follows:-From the experimental result shows that-

- A. RHA as partial replacement of cement
- 1) 9% utilization of RHA in the replacement of cement gives near about 15% increasing the compressive strength.
- Increase in percentage of RHA as a cementitious material gives rise to decrease in absorption of concrete i.e. up to 12% decrease for 9% RHA mix at 28<sup>th</sup> day.
- 3) Workability of this type of concrete decreases with increase in percentage of RHA.
- 4) SCM test shows RHA powder has a large amount of silica with which will give pozzolanic action and increases the strength.

### B. CS as partial replacement of coarse aggregates

- 25% CS as a replacement of coarse aggregate gives optimum results more than that affects the strength. Up to 25% CS in concrete gives less decrease in strength i.e. up to 13% to 15% than control mix, but more percentage decreases compressive strength vigorously.
- 2) Use of CS pieces of proper size (i.e. 20 mm nominal size) as a partial substitute of coarse aggregates result is that, if CS used equal to or greater than 25% by weight of coarse fraction produces lightweight concrete.
- 3) Water absorption of concrete increases with increase in coconut shell percentage. For 25% CS used in concrete 20% increase in water absorption.
- 4) Workability increases with increase in coconut shell percentage.

### C. Both RHA as partial replacement of cement and CS as partial replacement of coarse aggregates in concrete

- 9% utilization of RHA in the replacement of cement along with 25% CS as a replacement of coarse aggregates gives 8% to 10% decrease in compressive strength.
- 2) Workability increases with increase in coconut shell percentage with same RHA percentage.
- 3) Water absorption also increases with increase in percentage of RHA and CS. Which may reduce strength. But we can use 9% RHA and 12.5% CS with 3% of water absorption for construction in less rainy area and away from water source.
- 4) SCM test shows that RHA and coconut shell produces bond with each other as one is water repellent and other one is water absorbent which leads to increases compressive strength than that of only CS in concrete.

### D. General Conclusions

- 1) Use of coconut shell and Rice husk ash reduces the environmental burden of decomposition of organic waste and also reduces pollution generated by it.
- 2) With the use of Rice husk ash and Coconut shell in concrete deducts the use of cement and aggregates respectively. Which helps in conservation of natural resources.
- 3) Cost of construction will get reduced without compromising with strength.
- 4) Weight of concrete also get reduced and it leads to light weight concrete.
- 5) Aim of reduction of pollution and conservation of nature get fulfilled so that this project helps in green and sustainable development



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 10 Issue V May 2022- Available at www.ijraset.com

- E. Future Scope
- 1) From the study as the percentage replacement of CS is increased water absorption increases and workability decreases to increase the workability and reduce water cement ratio, plasticizers and any other material can be used.
- 2) As the partial replacement of coconut shell in concrete is rising then the strength of concrete is falling. So in order to overcome this we can add 10 % of other ingredients like fly ash, rock powder, etc. to CS concrete and the trials should be done.
- 3) Experiments can be done on split tensile strength and flexural strength also.
- 4) Other than mentioned different percentage of RHA and CS can be used in concrete for further experimentation.

### VI.ACKNOWLEDGMENT

The first author would like to express sincere thanks to guiding Dr. Manoj Wagh, Dean Academics, and Principal Dr. Uday Naik, Dr. Vithalrao Vikhe Patil College of Engineering, Ahmednagar, Maharashtra, India.

### REFERENCES

- [1] Kartini K, "Rice Husk Ash Pozzolanic Material for Sustainability", International Journal of Applied Science and Technology, Vol. 01, Issue 01, 2011.
- [2] Karim M R, Hossain M M, Khan M N N, Zain M F M, Jamil M and Lai F C, "Utilization of Pozzolanic Wastes as an Alternative Resource of Cement", Materials Vol. 7, Issue 12, 2014.
- [3] Gupta N, Kumar P, Mishra A and Srivastava R P, "Characterization and Application of Rice Husk Ash as Pozzolanic Material in Concrete", IOSR Journal of Mechanical and Civil Engineering (IOSR-JMCE), Vol. 12, Issue 3, 2015, PP 28-32
- [4] N. Mohamad A. A. A. Samad, Muhammad Tahir, "Effects of Incorporating Banana Skin Powder (BSP) and Palm Oil Fuel Ash (POFA) on Mechanical Properties of Lightweight Foamed Concrete", International Journal of Integrated Engineering, Vol. 9, Issue 10, 2018
- [5] Roshankumar. "Green concrete", International Conference on Emerging Trends in Engineering Technology, Science and Management
- [6] Anand Ramesh, Anandhu K J, "Coconut Shell as Partial Replacement of Coarse Aggregate in Concrete", International Research Journal of Engineering and Technology, Vol. 05, Issue 02) 2018.
- [7] Tasnim S, Rahman M E and Ahmad R, "Mechanical Performance of Modified Cement Paste Made with Micro fine POFA in Ammonium Nitrate Environment", Construction and Building Materials, 162: pp. 534-542, 2018
- [8] Shubham Srivastava, Kamal Kumar, Puneet Kumar Shukla, Piyush Kumar, "Studies on Partial Replacement of Cement by Bagasse Ash in Concrete." IJIRST International Journal for Innovative Research in Science & Technology, Vol. 2, Issue 03, 2015
- [9] Dhengare S W, Raut S P, BandwalN V and Anand K, "Investigation into Utilization of Sugarcane Bagasse Ash as Supplementary Cementitious Material in Concrete." International Journal of Emerging Engineering Research and Technology, Vol. 3, Issue 4, 2015
- [10] Anantha Lekshmi M L, "Green Concrete a Stepping Stone for Future", International Journal of Engineering Research& Management, Vol. 3, Issue 1, 2016
- [11] Shrikant M Harl, "Partial replacement of coarse aggregate with coconut shell in the concrete", Journal of Research in Engineering and Applied Sciences, Vol. 2, Issue 01, 2017
- [12] Anantha Lekshmi M L, "Green concrete for the Future A review", International Journal of Engineering Research & Technology (IJERT), 2278-0181, 2016
- [13] Mahmoud Khazaleh, Baskar Gopalan, "Eco-friendly green concrete: A review", IAPE 19, Oxford, United Kingdom, 2019.
- [14] Gritsada Sua-iam, Natt Makul, "Utilization of limestone powder to improve the properties of self-compacting concrete incorporating high volumes of untreated rice husk ash as fine aggregate.", Construction and Building Materials 38 (455-464) 2013.
- [15] Sanjay Kumar Verma and Sagar Shrivastava, "Use of Coconut Shell as Partly Substitution of Coarse Aggregate An Experimenta Analysis", AIP Conference Proceedings, 2158 (020021) 2019.
- [16] Dileep Kumar B M, S Suresh, "Experimental Investigation on Partial Replacement of Rice Husk Ash as Cement and Coconut Shell as Coarse Aggregate for the Production of Light Weight Concrete", International Research Journal of Engineering and Technology (IRJET), 05 (08) 2018.
- [17] R Gopinath, T Ajithkumar, M Nithin, V Sanjay Srikanth and P Sivakumar, "Experimental study on partial replacement of coarse aggregate by coconut shell and ordinary portland cement by rice husk ash", International Journal of Scientific & Engineering Research, 9 (4) 2018.
- [18] Rice husk ash as a potential supplementary cementitious material in concrete solution towards sustainable construction. By Ganta Mounika, Ramesh Baskar, Jyosyula Sri Kalyana Rama, Innovative Infrastructure Solutions, 2021.
- [19] Godwin A., Akekea Udeme U, Udokpoh B, "Improvement in the Properties of Concrete Containing Rice Husk Ash as A Partial Replacement for Portland Limestone Cement", International Journal of Engineering Research & Technology (IJERT), 11 (02) 2022
- [20] Study on the effect of rice husk ash in coconut shell concrete. International Journal of Civil Engineering and Technology (IJCIET), 9 (5) 2018.











45.98



IMPACT FACTOR: 7.129







INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089 🕓 (24\*7 Support on Whatsapp)