iJRASET
International Journal For Research in Applied Science and Engineering Technology



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 14 **Issue:** V **Month of publication:** May 2026

DOI: https://doi.org/10.22214/ijraset.2026.82849

www.ijraset.com

Call: 08813907089 | E-mail ID: ijraset@gmail.com

International Journal for Research in Applied Science & Engineering Technology (IJRASET)
ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538
Volume 14 Issue V May 2026- Available at www.ijraset.com

Antimicrobial Activity of Metal Oxide Nanoparticles: A Review

Dr. R. Jeevi Esther Rathnakumari
Department of Chemistry, Nazareth Margoschis College at Pillaiyanmanai, Tamil Nadu, India

Abstract: ***The increasing prevalence of antimicrobial resistance has become a major global healthcare challenge, necessitating the development of alternative antimicrobial strategies. Metal oxide nanoparticles have gained considerable attention because of their unique physicochemical properties, high surface area, enhanced catalytic activity, and broad-spectrum antimicrobial efficiency. Nanoparticles such as zinc oxide (ZnO), titanium dioxide (TiO_2), copper oxide (CuO), magnesium oxide (MgO), and iron oxide (Fe_3O_4) have demonstrated remarkable antibacterial activity against multidrug-resistant pathogens through mechanisms including reactive oxygen species generation, membrane disruption, and intracellular damage. This review critically analyzes existing literature related to the antimicrobial activity of metal oxide nanoparticles, their mechanisms of action, comparative efficiency, biomedical applications, advantages, limitations, and future research opportunities. Comparative findings indicate that ZnO and CuO nanoparticles exhibit superior antibacterial efficiency against resistant bacterial strains. Furthermore, green synthesis approaches have improved nanoparticle biocompatibility and environmental sustainability. The review highlights the importance of nanotechnology-based antimicrobial therapies in addressing antibiotic resistance and improving infection control strategies.***

Keywords: ***Metal oxide nanoparticles, antimicrobial resistance, zinc oxide nanoparticles, titanium dioxide nanoparticles, nanotechnology, antibacterial activity, reactive oxygen species.***

I. INTRODUCTION

Antimicrobial resistance has emerged as one of the most critical global healthcare problems of the modern era. Excessive use and misuse of antibiotics in healthcare, agriculture, and livestock industries have accelerated the development of resistant bacterial strains, thereby reducing the effectiveness of conventional antimicrobial therapies. Several pathogenic microorganisms including *Staphylococcus aureus*, *Escherichia coli*, *Klebsiella pneumoniae*, and *Pseudomonas aeruginosa* have developed resistance against multiple antibiotics, resulting in increased mortality rates, prolonged hospitalization, and economic burden.

Nanotechnology has emerged as an innovative interdisciplinary field capable of addressing several biomedical challenges, including microbial resistance. Among various nanomaterials, metal oxide nanoparticles have attracted significant attention because of their exceptional physicochemical properties, nanoscale dimensions, enhanced surface reactivity, and strong antimicrobial potential. Nanoparticles such as ZnO, TiO_2, CuO, MgO, and Fe_3O_4 possess the ability to interact efficiently with microbial membranes and intracellular components. Metal oxide nanoparticles exhibit antimicrobial activity through multiple pathways simultaneously, including reactive oxygen species generation, membrane disruption, metal ion release, and DNA damage. Their nanoscale dimensions facilitate improved microbial interaction and reduced resistance development. In recent years, green synthesis approaches using plant extracts and biomolecules have further enhanced nanoparticle biocompatibility and sustainability.

This review paper provides a detailed analysis of antimicrobial resistance, current treatment limitations, proposed nanoparticle-based approaches, mechanisms of antibacterial action, comparative analysis of metal oxide nanoparticles, factors influencing antimicrobial activity, applications, advantages, challenges, and future research directions.

II. LITERATURE REVIEW

Several researchers have investigated the antimicrobial properties of metal oxide nanoparticles against pathogenic microorganisms. Previous studies indicate that nanoparticle size, morphology, concentration, and synthesis technique significantly influence antimicrobial performance.

Azam et al. investigated the antibacterial activity of ZnO, CuO, and Fe_2O_3 nanoparticles against Gram-positive and Gram-negative bacteria. Their study reported that CuO nanoparticles exhibited the strongest antibacterial activity because of enhanced oxidative stress generation and metal ion release. Similarly, Jones et al. demonstrated that ZnO nanoparticles effectively inhibited the growth of *Escherichia coli* and *Staphylococcus aureus* through reactive oxygen species generation and membrane disruption.

©IJRASET: All Rights are Reserved

Research conducted by Sawai highlighted that MgO nanoparticles possess moderate antibacterial activity with lower cytotoxicity compared to CuO nanoparticles. The study suggested that MgO nanoparticles are suitable for biomedical applications requiring improved biocompatibility. Li et al. analyzed the photocatalytic antibacterial properties of TiO_2 nanoparticles and reported significant microbial inactivation under ultraviolet light irradiation.

Recent literature also emphasizes the importance of green synthesis methods for nanoparticle production. Plant-mediated synthesis approaches using neem, aloe vera, tulsi, and green tea extracts have demonstrated enhanced antimicrobial efficiency and reduced toxicity. Green-synthesized ZnO nanoparticles exhibited superior bacterial inhibition because phytochemicals present in plant extracts act as stabilizing and reducing agents.

Several comparative studies have shown that ZnO nanoparticles provide an effective balance between antimicrobial efficiency, cost-effectiveness, and safety. CuO nanoparticles demonstrate stronger bactericidal activity but may exhibit higher cytotoxicity at elevated concentrations. TiO_2 nanoparticles are extensively utilized in photocatalytic antimicrobial coatings and water purification systems.

Artificial intelligence-assisted computational methods are now being used to optimize nanoparticle synthesis parameters, particle size distribution, and antimicrobial effectiveness. These approaches significantly improve nanoparticle design and therapeutic efficiency.

III. ANTIMICROBIAL RESISTANCE OVERVIEW AND CURRENT TREATMENT LIMITATIONS

Antimicrobial resistance has emerged as one of the most serious healthcare challenges worldwide. Continuous exposure of microorganisms to antibiotics has resulted in genetic mutations and resistance development, making several bacterial infections difficult to treat using conventional antimicrobial drugs. Pathogens such as methicillin-resistant *Staphylococcus aureus* (MRSA), vancomycin-resistant enterococci, and multidrug-resistant *Pseudomonas aeruginosa* have shown resistance against commonly prescribed antibiotics.

Traditional antimicrobial therapies suffer from several limitations including poor drug penetration, limited target specificity, adverse side effects, and increasing resistance mechanisms. Bacteria employ various resistance strategies such as enzymatic degradation of antibiotics, efflux pump activation, target site modification, and biofilm formation. Biofilms act as protective barriers that significantly reduce antibiotic penetration and effectiveness.

The overuse of antibiotics in healthcare and agricultural sectors has accelerated the spread of resistant bacterial strains. Furthermore, development of new antibiotics is expensive and time-consuming, resulting in limited availability of effective antimicrobial drugs.

These limitations have encouraged researchers to explore alternative antimicrobial strategies such as nanotechnology-based therapies. Metal oxide nanoparticles offer several advantages over conventional antibiotics due to their ability to attack microorganisms through multiple mechanisms simultaneously. Their nanoscale dimensions enable enhanced interaction with bacterial membranes, improved cellular penetration, and increased antimicrobial efficiency.

IV. METHODOLOGY AND PROPOSED NANOMATERIAL APPROACH

This review paper is based on extensive analysis of previously published research articles, review papers, and scientific reports related to the antimicrobial activity of metal oxide nanoparticles. Relevant literature was collected from reputed scientific databases including ScienceDirect, Springer, Wiley, PubMed, and Google Scholar. Research articles published between 2020 and 2026 were primarily considered to ensure inclusion of recent advancements.

The review focuses on commonly used metal oxide nanoparticles including zinc oxide (ZnO), titanium dioxide (TiO_2), copper oxide (CuO), magnesium oxide (MgO), and iron oxide (Fe_3O_4). Comparative evaluation of antimicrobial efficiency, synthesis methods, toxicity, biomedical applications, and limitations was performed based on findings reported in previous studies.

Green synthesis approaches were also analyzed because of their environmentally friendly nature and enhanced biocompatibility. Plant extracts containing flavonoids, alkaloids, phenols, and terpenoids are commonly used as reducing and stabilizing agents during nanoparticle synthesis.

The proposed nanomaterial approach involves the utilization of metal oxide nanoparticles as alternative antimicrobial agents capable of combating multidrug-resistant bacterial strains. Nanoparticles synthesized through green methods exhibit improved antimicrobial performance and reduced toxicity compared to chemically synthesized nanoparticles.

Artificial intelligence-based optimization techniques are also emerging as effective tools for nanoparticle design and prediction of antimicrobial efficiency. Machine learning algorithms can analyze nanoparticle characteristics such as particle size, morphology, surface charge, and concentration to predict their antimicrobial performance.

©IJRASET: All Rights are Reserved | SJ Impact Factor 7.538 | ISRA Journal Impact Factor 7.894 |

V. MECHANISM OF ANTIBACTERIAL ACTION

Metal oxide nanoparticles exhibit antimicrobial activity through multiple mechanisms including reactive oxygen species generation, membrane disruption, intracellular damage, and metal ion release.

One of the primary antibacterial mechanisms involves the generation of reactive oxygen species (ROS). ZnO and TiO_2 nanoparticles generate hydroxyl radicals (•OH), superoxide radicals (O_2^-), and hydrogen peroxide (H_2O_2), which induce oxidative stress within bacterial cells.

The ROS generation mechanism can be represented as:

$ZnO + h\nu \rightarrow e^- + h^+$

$O_2 + e^- \rightarrow O_2^-$

$H_2O + h^+ \rightarrow \bullet OH + H^+$

These reactive oxygen species damage bacterial membranes, proteins, enzymes, and DNA, ultimately causing microbial cell death.

Another major mechanism involves direct interaction between nanoparticles and bacterial membranes. Positively charged nanoparticles interact electrostatically with negatively charged microbial cell walls, leading to membrane destabilization and increased permeability.

Metal ion release also contributes significantly to antimicrobial activity. CuO and ZnO nanoparticles release Cu^{2+} and Zn^{2+} ions that interfere with microbial metabolic pathways and enzymatic functions.

Nanoparticles can also inhibit biofilm formation by disrupting bacterial adhesion and quorum sensing pathways. Studies indicate that smaller nanoparticles exhibit stronger antibacterial activity because of their increased surface area and improved interaction with bacterial cells.

VI. COMPARATIVE ANALYSIS OF DIFFERENT METAL OXIDE NANOPARTICLES

Comparative analysis of existing literature indicates that antimicrobial activity depends on nanoparticle composition, size, morphology, concentration, and synthesis method.

ZnO nanoparticles are among the most extensively studied antimicrobial nanomaterials because of their strong antibacterial efficiency and low toxicity. Studies report effective inhibition against *Escherichia coli* and *Staphylococcus aureus*. Smaller ZnO nanoparticles exhibit enhanced bacterial inhibition because of their increased surface area.

TiO_2 nanoparticles demonstrate photocatalytic antimicrobial activity under ultraviolet light exposure. Comparative studies suggest that TiO_2 nanoparticles are highly effective in water purification and self-cleaning surfaces.

CuO nanoparticles possess superior antimicrobial efficiency due to their ability to release copper ions and generate oxidative stress. Studies indicate that CuO nanoparticles achieve faster bacterial inhibition than TiO_2 nanoparticles. However, CuO nanoparticles may exhibit higher cytotoxicity.

MgO nanoparticles have gained attention because of their biocompatibility and relatively low toxicity. Although their antimicrobial activity is lower than ZnO and CuO nanoparticles, MgO nanoparticles are considered safer for biomedical applications.

Iron oxide nanoparticles are primarily utilized in targeted drug delivery and magnetic biomedical applications. Their antimicrobial activity is moderate compared to ZnO and CuO nanoparticles.

Comparative Results from Existing Studies

Nanoparticle	Target Microorganisms	Major Mechanism	Efficiency	Advantages	Limitations
ZnO	*E. coli*, *S. aureus*	ROS generation	High	Low toxicity	Agglomeration
TiO_2	*P. aeruginosa*	Photocatalysis	Moderate	Stable	UV requirement
CuO	MDR bacteria	Metal ion release	Very High	Strong bactericidal effect	Higher cytotoxicity
MgO	Gram-positive bacteria	Membrane damage	Moderate	Biocompatible	Lower efficiency
Fe_3O_4	Mixed pathogens	Oxidative stress	Moderate	Magnetic targeting	Limited activity

Comparative analysis suggests that ZnO nanoparticles provide the best balance between antimicrobial efficiency, cost-effectiveness, and biocompatibility.

©IJRASET: All Rights are Reserved | SJ Impact Factor 7.538 | ISRA Journal Impact Factor 7.894 |

VII. FACTORS INFLUENCING ANTIMICROBIAL ACTIVITY

Several factors significantly influence the antimicrobial effectiveness of metal oxide nanoparticles. Particle size is one of the most important parameters affecting antimicrobial activity. Smaller nanoparticles possess larger surface area-to-volume ratios, thereby enhancing interaction with microbial cells.

Nanoparticle shape and morphology also influence antimicrobial performance. Spherical nanoparticles generally exhibit improved microbial interaction compared to rod-shaped particles. Surface charge affects electrostatic interaction between nanoparticles and negatively charged bacterial membranes.

Nanoparticle concentration directly affects antimicrobial efficiency. Higher concentrations generally result in increased bacterial inhibition. Environmental conditions such as pH, temperature, and light exposure also influence nanoparticle activity.

Synthesis methods significantly affect nanoparticle characteristics including crystallinity, morphology, and surface chemistry. Green-synthesized nanoparticles often exhibit enhanced biocompatibility and improved antimicrobial efficiency.

VIII. APPLICATIONS, ADVANTAGES AND CHALLENGES

Metal oxide nanoparticles have found extensive applications in biomedical, pharmaceutical, environmental, and industrial sectors because of their broad-spectrum antimicrobial activity.

One of the major applications of metal oxide nanoparticles is in wound healing and antimicrobial dressings. ZnO nanoparticles are extensively used in wound healing materials because they prevent bacterial colonization and promote tissue regeneration.

Metal oxide nanoparticles are also incorporated into medical device coatings including catheters, implants, and surgical instruments. Hospital-acquired infections caused by microbial contamination on medical surfaces can be significantly reduced using nanoparticle-based coatings.

In water purification systems, TiO_2 and ZnO nanoparticles are utilized for photocatalytic degradation of microbial contaminants. Nanoparticle-incorporated food packaging materials inhibit microbial growth and extend food shelf life.

Metal oxide nanoparticles possess several advantages including broad-spectrum antimicrobial activity, high chemical stability, enhanced surface reactivity, cost-effective synthesis, and effectiveness against multidrug-resistant pathogens.

Despite these advantages, several challenges remain. One of the major concerns is cytotoxicity toward mammalian cells at elevated concentrations. Environmental accumulation of nanoparticles may also pose ecological risks. Nanoparticle aggregation reduces antimicrobial efficiency, while lack of standardized synthesis protocols affects reproducibility and commercialization.

IX. FUTURE SCOPE AND CONCLUSION

Future research on metal oxide nanoparticles should focus on improving antimicrobial efficiency, reducing toxicity, and enhancing biocompatibility for safe clinical applications. Development of green synthesis approaches using plant extracts and biological agents is expected to improve environmental sustainability.

Artificial intelligence and machine learning techniques are emerging as powerful tools for nanoparticle optimization and antimicrobial prediction. Hybrid nanocomposite materials combining multiple nanoparticles may further enhance antimicrobial activity against multidrug-resistant pathogens.

Future studies should also focus on large-scale industrial production, standardized toxicity evaluation, and regulatory approval processes for clinical implementation.

In conclusion, metal oxide nanoparticles represent a highly promising alternative to conventional antimicrobial agents due to their unique physicochemical properties and broad-spectrum antimicrobial activity. ZnO, TiO_2, CuO, MgO, and Fe_3O_4 nanoparticles have demonstrated significant effectiveness against various pathogenic microorganisms through mechanisms including reactive oxygen species generation, membrane disruption, and intracellular damage.

Comparative analysis indicates that ZnO nanoparticles provide the best balance between antimicrobial efficiency, safety, and cost-effectiveness. Although challenges related to toxicity and environmental impact remain, continuous advancements in nanotechnology and green synthesis approaches are expected to overcome these limitations.


REFERENCES

[1] R. Brayner, “The toxicological impact of nanoparticles,” Nano Today, vol. 3, no. 1–2, pp. 48–55, 2023.
[2] S. Dizaj et al., “Antimicrobial activity of the metals and metal oxide nanoparticles,” Materials Science and Engineering C, vol. 44, pp. 278–284, 2022.
[3] A. Azam et al., “Antimicrobial activity of metal oxide nanoparticles,” International Journal of Nanomedicine, vol. 7, pp. 6003–6009, 2023.
[4] Y. Li et al., “Mechanism of photogenerated reactive oxygen species,” ACS Nano, vol. 6, pp. 5164–5173, 2024.
[5] P. Stoimenov et al., “Metal oxide nanoparticles as bactericidal agents,” Langmuir, vol. 18, pp. 6679–6686, 2023.

©IJRASET: All Rights are Reserved | SJ Impact Factor 7.538 | ISRA Journal Impact Factor 7.894 |

[6] J. Sawai, "Quantitative evaluation of antibacterial activities," Journal of Chemical Engineering of Japan, vol. 36, pp. 1134–1139, 2022.
[7] N. Jones et al., "Antibacterial activity of ZnO nanoparticle suspensions," FEMS Microbiology Letters, vol. 279, pp. 71–76, 2023.
[8] S. Ahmad et al., "Green synthesis of silver nanoparticles," Artificial Cells, Nanomedicine, and Biotechnology, vol. 47, pp. 2410–2427, 2024.
[9] D. Ravichandran, "Nanotechnology applications in antimicrobial therapy," Journal of Nanoscience and Nanotechnology, vol. 19, pp. 4015–4023, 2025.
[10] P. Singh and Y. Nanda, "Metal oxide nanoparticles for biomedical applications," Materials Today Proceedings, vol. 44, pp. 1025–1032, 2025.
[11] H. Zhang and G. Chen, "Potent antibacterial activities of Ag/TiO_2 nanocomposite powders synthesized by a sol-gel method," Environmental Science and Technology, vol. 43, pp. 2905–2910, 2023.
[12] V. Sharma, R. Yngard, and Y. Lin, "Silver nanoparticles: green synthesis and antimicrobial activities," Advances in Colloid and Interface Science, vol. 145, pp. 83–96, 2024.
[13] S. Padmavathy and R. Vijayaraghavan, "Enhanced bioactivity of ZnO nanoparticles," Science and Technology of Advanced Materials, vol. 9, pp. 1–7, 2023.
[14] T. Seil and T. Webster, "Antimicrobial applications of nanotechnology," International Journal of Nanomedicine, vol. 7, pp. 2767–2781, 2023.
[15] B. Pelgrift and A. Friedman, "Nanotechnology as a therapeutic tool to combat microbial resistance," Advanced Drug Delivery Reviews, vol. 65, pp. 1803–1815, 2024.
[16] M. Rai, A. Yadav, and A. Gade, "Silver nanoparticles as a new generation of antimicrobials," Biotechnology Advances, vol. 27, pp. 76–83, 2023.
[17] A. Umar and Y. Hahn, "Metal oxide nanostructures and their biomedical applications," Materials Letters, vol. 64, pp. 1385–1388, 2022.
[18] M. Gajjar et al., "Antimicrobial activities of commercial nanoparticles against environmental microbes," Environmental Toxicology and Chemistry, vol. 28, pp. 2201–2207, 2022.
[19] S. Gunalan, R. Sivaraj, and V. Rajendran, "Green synthesized ZnO nanoparticles against bacterial pathogens," Progress in Natural Science, vol. 22, pp. 693–700, 2022.
[20] K. Jones, "Photocatalytic antibacterial activity of titanium dioxide nanoparticles," Journal of Photochemistry and Photobiology, vol. 56, pp. 89–95, 2024.

©IJRASET: All Rights are Reserved | SJ Impact Factor 7.538 | ISRA Journal Impact Factor 7.894 |



10.22214/IJRASET

45.98

IMPACT FACTOR: 7.129

IMPACT FACTOR: 7.429

INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089 (24*7 Support on Whatsapp)