iJRASET
International Journal For Research in Applied Science and Engineering Technology



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 13 **Issue:** V **Month of publication:** May 2025

DOI: https://doi.org/10.22214/ijraset.2025.70575

www.ijraset.com

Call: 08813907089 | E-mail ID: ijraset@gmail.com

International Journal for Research in Applied Science & Engineering Technology (IJRASET)
ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538
Volume 13 Issue V May 2025- Available at www.ijraset.com

Biological Properties of *Actaea Racemose* Using Silver Nanoparticles

Druva Chowdary Nagandla, Sreemoy Kanti Das, K. Suresh Babu
Faculty of Pharmacy, Lincoln university College, Malaysia

Abstract: ***Using silver nanoparticles (AgNPs) as a vehicle, this thesis explores the biological characteristics of Actaea racemosa, more commonly known as black cohosh, a medicinal herb with promising therapeutic uses, especially in women's health. Inflammation, menstruation abnormalities, and menopausal symptoms are just a few of the many traditional uses for Actaea racemosa. Despite the plant's well-documented pharmacological properties, individual applications of its bioactive components often result in subpar bioavailability, stability, and therapeutic effectiveness. In response of these difficulties, this thesis investigates a new green chemistry strategy for improving Actaea racemosa's biological activities via the manufacture and use of silver nanoparticles (AgNPs).***

A variety of state-of-the-art methods were used to ascertain the size, shape, surface charge, and stability of the silver nanoparticles, which were manufactured utilizing plant extracts. These methods included transmission electron microscopy (TEM), dynamic light scattering (DLS), and ultraviolet-visible spectroscopy (UV-Vis). Biologically relevant AgNPs with well-controlled sizes and a limited distribution were successfully synthesized, according to the findings. In addition, the phytochemical profile of the plant extract was examined using chromatography and spectroscopic techniques to determine which active chemicals were responsible for the therapeutic benefits.

The antibacterial, anti-inflammatory, antioxidant, and cytotoxic effects of the AgNP-functionalized extract and the Actaea racemosa extract were among the many biological characteristics that were evaluated using biological assays. Various harmful bacterial and fungus strains were used to test the antimicrobial activity, and important biomarkers were used to evaluate the antioxidant and anti-inflammatory characteristics in vitro. To ensure a safe and effective treatment profile, cytotoxicity experiments were conducted to assess the possible therapeutic dosage for human cell lines using a combination of AgNPs and Actaea racemosa extract.

The findings showed that Actaea racemosa's biological activities were improved by synthesizing AgNPs, leading to a significant increase in the antibacterial and anti-inflammatory effects when compared to only using the plant extract. The combinations enhanced antioxidant capabilities also suggest it may be useful in warding off illnesses caused by oxidative stress. The specific cytotoxicity shown by the AgNPs further supports their use as a cancer treatment adjuvant. The hypothesised role of the nanoparticles as carriers for enhanced absorption and targeted administration is further investigated in the thesis as a means by which AgNPs enhance the bioavailability and activity of the plant's bioactive components.

The combination therapeutic system of Actaea racemosa and silver nanoparticles is thoroughly examined in this study. The results show how natural products may have their pharmacological qualities improved by the use of nanotechnology, which provides important insights into the area of nanomedicine. This study offers a potential strategy for the improvement of herbal treatments by increasing the bioavailability and effectiveness of Actaea racemosa. This approach could be applied to women's health issues and other conditions involving inflammation, infection, and oxidative stress.

Keywords: Actaea racemosa, silver nanoparticles, green synthesis, antioxidant activity, antimicrobial properties.

I. INTRODUCTION

Recent years have seen exciting developments in biomedical research as nanotechnology and plant-based medicine have come together, posing new questions about the management of diseases, the delivery of drugs, and potential therapeutic uses. One of the many ways to synthesize nanomaterials is by green synthesis, which uses plant extracts. This process is more sustainable, less harmful to the environment, and cheaper than traditional chemical and physical procedures. By incorporating the inherent therapeutic qualities of plants, this strategy not only improves the biological efficiency of nanoparticles but also lessens the environmental load linked with harmful chemicals. Black cohosh, or *Actaea racemosa*, has a lot of promise in this regard because of its potential as a natural reducing and stabilizing agent in nanoparticle production and its well-documented medicinal properties.

©IJRASET: All Rights are Reserved

A perennial herbaceous plant indigenous to North America, *Actaea racemosa* has a long history of herbal medicine usage, most notably in the relief of menopausal symptoms, premenstrual pain, and rheumatic pain. With its abundance of triterpene glycosides, flavonoids, and phenolic chemicals, this plant has a wide range of pharmacological actions, including those that reduce inflammation, alleviate pain, and prevent spasms. *A. racemosa* has a long history of use in conventional medicine, but there is growing interest in incorporating it into nanotechnology-based applications to increase its therapeutic potential by synthesizing silver nanoparticles (AgNPs).

Many industries, including healthcare, food processing, farming, and environmental safeguarding, are interested in silver nanoparticles due to their unusual physicochemical and biological characteristics. They are very useful in creating cutting-edge materials for antimicrobial coatings, drug delivery systems, and wound healing because to their antibacterial, antioxidant, and anti-inflammatory properties. Chemical production of AgNPs, on the other hand, often makes use of toxic compounds, endangering both humans and the environment. Plant extracts, such as *A. racemosa*, provide an alternative that is environmentally friendly, safe, and scalable when it comes to biosynthesising AgNPs. This method also adds biological usefulness by using the plant's own bioactive chemicals.

Not only do the phytochemicals in *Actaea racemosa* help reduce silver ions to nanoparticles, but they also stabilize the nanoparticles, which makes them more biologically active. Research has shown that AgNPs produced using plant-mediated processes are more biocompatible and bioactive than their conventionally manufactured counterparts. An intriguing new direction for the development of more effective and safer medicinal medicines has emerged thanks to the synergistic interaction between bioactive chemicals found in plants and the intrinsic characteristics of silver nanoparticles.

Examining the biological characteristics of silver nanoparticles produced using *Actaea racemosa* extracts is the primary aim of this research. Research into these biogenic nanoparticles will center on their potential antibacterial, antioxidant, and cytotoxic effects. This research seeks to provide a thorough knowledge of how plant-mediated synthesis might improve the biological usefulness of nanoparticles by studying the size, shape, and structural properties of the generated AgNPs and their interactions with different biological systems.

Furthermore, the possible biological and pharmacological uses of AgNPs produced by *A. racemosa* are another focus of this investigation. Innovative nanocomposites combining plant-based bioactivity with nanotechnology may provide useful answers to the rising problems of antibiotic resistance and the need for safer, more efficient medicinal treatments. To further comprehend these nanoparticles' therapeutic potential and to open the way for future research in this multidisciplinary field, the study delves into the processes behind their biological interactions.

Ultimately, the use of *Actaea racemosa* in the production of silver nanoparticles is an exciting new frontier in the fields of nanotechnology, medicine, and pharmacology. In order to provide the groundwork for these nanoparticles' potential use in clinical and industrial contexts, this thesis will give a comprehensive analysis of their production, characterisation methods, and biological assessments. The goal of this study is to help create new, long-lasting treatments by combining modern nanotechnology with age-old plant-based medicine.

II. BACKGROUND OF THE STUDY

Thanks to recent breakthroughs in science and technology, conventional medical practices may now work in tandem with state-of-the-art technologies like nanotechnology. The pharmacological characteristics, low risk of side effects, and relative affordability of medicinal plants have made them a promising new source of bioactive chemicals for use in medicine. Black cohosh, scientifically known as *Actaea racemosa*, is a North American perennial plant. Its long history of usage in traditional medicine includes the treatment of a wide range of illnesses, including rheumatism, premenstrual syndrome, menopausal symptoms, and more, especially among Native American cultures.

A. racemosa's bioactive components, which include secondary metabolites, phenolic acids, flavonoids, triterpene glycosides (such as actein and cimicifugoside), and other substances, provide it a broad range of medicinal uses. Among their many beneficial effects, these chemicals are known to reduce inflammation, kill germs, alleviate pain, and even fight cancer. Although *A. racemosa* has a diverse array of phytochemicals, it has not yet been fully investigated for its potential, even when coupled with cutting-edge technologies such as nanotechnology.

Medicine, agriculture, and the environmental sciences are just a few of the many areas that have benefited from nanotechnology's revolutionary solutions. The unique physicochemical characteristics and shown promise in biological applications of silver nanoparticles (AgNPs) have made them stand out among the many kinds of produced nanoparticles.

©IJRASET: All Rights are Reserved | SJ Impact Factor 7.538 | ISRA Journal Impact Factor 7.894 |

The enhanced antibacterial, antioxidant, and anti-inflammatory properties of AgNPs are attributed to their high surface-area-to-volume ratio, which also increases their bioavailability and reactivity. Furthermore, the cytotoxic effects of silver nanoparticles on cancer cells have been extensively researched, making them an attractive tool for the development of novel cancer treatments.

An increasingly popular and less expensive alternative to traditional physical and chemical procedures is the synthesis of AgNPs using plant extracts; this process is also known as green synthesis or biological synthesis. This method makes the procedure more eco-friendly and safer for the environment by doing away with the use of harmful chemicals. During the creation of nanoparticles, the bioactive chemicals included in plant extracts serve as agents that reduce and stabilize. Additionally, this approach improves the biological characteristics of the plant extracts and the nanoparticles, resulting in a multiplicative impact.

There has been a lot of study on silver nanoparticles and *Actaea racemosa* individually, but not much on how these two fields interact. Synthesizing AgNPs using *A. racemosa* extracts might be a game-changer for the development of new, safer, more effective medicines. The size, form, and stability of the produced AgNPs may be impacted by the bioactive chemicals found in *A. racemosa*, which in turn affects their biological activity. This innovative method has the potential to provide two benefits: first, the long-established medicinal uses of the plant; and second, the cutting-edge biomedical uses of nanotechnology.

We want to learn more about the biological effects of *Actaea racemosa* and silver nanoparticles in this work. The produced nanoparticles' antibacterial, antioxidant, and cytotoxic actions will be the primary focus of the study. This research will examine the bio-synthesized AgNPs for their cytotoxic effects on certain cancer cell lines, their capacity to neutralize free radicals, and their effectiveness against bacterial and fungal infections. This work has the potential to revolutionize pharmaceutical research by revealing new approaches to treating cancer, oxidative stress-related illnesses, and infections.

In addition, our understanding of green nanotechnology and plant-based therapies will be expanded by the results of this study. Research into the potential synergy between *A. racemosa* and AgNPs has the potential to pave the way for the creation of greener, safer, and more effective medicinal agents. Antibiotic resistance, chronic inflammation, and cancer treatment are just a few of the present healthcare issues that may be greatly improved by combining conventional medicine with contemporary nanotechnology.

To sum up, the hope is that this research will help bring together conventional plant-based therapy with cutting-edge nanotechnology. Future study on medicinal plant nanoparticle production and their potential biological uses may build on this basis. Improving world health and wellbeing may be as simple as creating new medicinal agents that are both long-lasting and highly effective.

III. LITERATURE REVIEW

A. Introduction to Actaea racemosa

The forests of North America are home to the perennial herbaceous plant *Actaea racemosa*, most often known as black cohosh. For many years, it was a go-to remedy for menstruation issues, rheumatic pain, and other menopausal symptoms among both Native American and early European immigrants. Triterpene glycosides (actein and cimicifugoside), phenolic compounds, flavonoids, alkaloids, and other phytochemicals have piqued the curiosity of scientists in this plant throughout the years. The many medicinal properties, including anti-inflammatory, antioxidant, antibacterial, and analgesic actions, are due to these components (Blumenthal et al., 2018).

Because of its estrogen-like effect without directly influencing estrogen receptors, the plant has recently gained attention as a promising candidate for use in contemporary pharmacology. *A. racemosa* is a vital natural resource for studying alternative treatments for hormone-related diseases and other long-term health issues because of these characteristics.

B. Silver Nanoparticles (AgNPs): Synthesis and Properties

The size of silver nanoparticles (AgNPs) may vary from one nanometer to one hundred nanometers, and they are metallic nanostructures. A high surface area-to-volume ratio, quantum effects, and exceptional catalytic activity are some of their well-known physical, chemical, and biological characteristics. Because of these characteristics, AgNPs are useful in many scientific and industrial domains, including biomedicine, agriculture, and environmental sciences, due to their significant antibacterial, antioxidant, and anti-inflammatory effects (Iravani et al., 2014).

It is common practice to use energy-intensive techniques and potentially harmful substances when producing AgNPs using traditional methods. An option that is sustainable, inexpensive, and good for the environment is green synthesis, which uses plant extracts. In order to create biocompatible nanoparticles with little effect on the environment, these methods use phytochemicals derived from plant extracts as organic reducing and stabilizing agents.

©IJRASET: All Rights are Reserved | SJ Impact Factor 7.538 | ISRA Journal Impact Factor 7.894 |

ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538
Volume 13 Issue V May 2025- Available at www.ijraset.com

C. Phytochemical-Mediated Synthesis of AgNPs

The process of creating AgNPs using plant extracts entails using natural phytochemicals to reduce silver ions (Ag+) to elemental silver (Ag0). The reduction and stabilization processes are greatly aided by secondary metabolites such phenolics, flavonoids, terpenoids, alkaloids, and tannins. Nanoparticles produced by plants are more homogeneous and stable, and they show better biological activity, according to many studies (Mittal et al., 2013).

Extracts from *A. racemosa* may be able to help with the environmentally friendly production of AgNPs due to its extensive phytochemical profile. As a more environmentally friendly alternative to traditional chemical synthesis techniques, these nanoparticles that were bio-synthesized not only have improved biological characteristics but also show synergistic effects between the silver and chemicals obtained from plants.

D. Biological Properties of Actaea racemosa-Mediated AgNPs

1) Antimicrobial Activity

There is substantial evidence that silver nanoparticles have strong antibacterial effects against a variety of microbes, including viruses, fungi, bacteria (both Gram-positive and Gram-negative), and bacterial strains. Interactions between silver ions and microbial cell membranes cause structural changes, protein malfunction, and cell death, which is the primary cause of the antibacterial effect. The antibacterial action is likely amplified when *A. racemosa* preparations are used in conjunction with them, thanks to the bioactive chemicals found in the plant (Shahverdi et al., 2007).

Evidence suggests that bioactive *A. racemosa* and AgNPs may work synergistically to increase the effectiveness of inhibitory zones against a range of diseases. This might have great potential in the pharmaceutical, personal care, and food preservation industries as a means of creating natural antibacterial agents.

2) Antioxidant Potential

Numerous long-term health problems, including as cancer, neurological disorders, and cardiovascular illnesses, are associated with oxidative stress, which results from an excess of free radicals relative to antioxidants in the body. Because of its high polyphenolic content, which may inhibit oxidative damage and neutralize free radicals, *A. racemosa* is considered an antioxidant.

These antioxidant properties could be increased when added to silver nanoparticles. Research conducted by Kumar et al. (2017) found that when AgNPs are combined with plant extracts, they demonstrate more potent free radical scavenging capabilities than when each component is used alone. Nanoparticles' larger surface area enables them to interact with reactive oxygen species (ROS) in biological systems more effectively, which is why they are so effective.

3) Cytotoxic and Anticancer Activities

Because of its ability to induce apoptosis (programmed cell death), block angiogenesis, and limit cancer cell growth, silver nanoparticles have attracted a lot of interest as a possible anticancer agent. When AgNPs are made from plant extracts that are abundant in bioactive chemicals, these effects tend to be amplified.

Ghosh et al. (2012) found that nanoparticles mediated by *A. racemosa* may selectively kill cancer cells while leaving normal cells alone, however there has been little direct investigation on this topic. New cancer treatments may be possible as a result of the synergistic combination of the plant's natural chemicals with silver's cytotoxic effects.

E. Applications and Future Perspectives

A green synthesis of AgNPs including *A. racemosa* extracts is an intriguing prospect for the creation of new medicinal compounds with improved biological characteristics. These nanoparticles have a wide range of possible uses in several industries:

Biomedical Uses: Possible incorporation into wound dressings, targeted medication delivery systems, and antibacterial coatings for medical equipment.

Research and development of nanoformulations for the treatment of infectious diseases, malignancies, and illnesses associated with oxidative stress in the pharmaceutical industry.

Cosmetics & Personal Care: Their antibacterial and antioxidant qualities make them ideal for use in skincare products.

Use in water treatment systems to avoid microbiological contamination is one example of an environmental use.

©IJRASET: All Rights are Reserved | SJ Impact Factor 7.538 | ISRA Journal Impact Factor 7.894 |

ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538
Volume 13 Issue V May 2025- Available at www.ijraset.com

Optimisation of synthesis parameters for application-specific control of nanoparticle size, shape, and stability should be the focus of future study. For these nanoparticles to be used safely in biomedical and industrial settings, thorough toxicity evaluations are also required.


F. Conclusion

An intriguing prospect for the development of long-term, environmentally safe medicinal medicines is the combination of *Actaea racemosa* with silver nanoparticles. The antibacterial, antioxidant, and maybe anticancer capabilities of the produced nanoparticles are amplified by the combined action of silver ions and bioactive chemicals generated from plants. To improve synthesis procedures, assess their safety for clinical and commercial uses, and completely understand the mechanisms behind these effects, more research is required.

IV. SYNTHESIS OF SILVER NANOPARTICLES

The broth solution was prepared in a 300 mL Erlenmeyer flask by combining 100 mL of double-distilled sterile water with 10 g of freshly washed, finely chopped A. racemosa leaves. Five minutes after the water came to a boil, the leaves were delicately removed. Use the extract within a week after treating it with Whatman filters no. 1 or storing it at -15 °C. Following straining, the material was transferred to an Erlenmeyer flask where it was incubated at a temperature higher than room temperature with a 1 mM aqueous AgNO3 solution. A brownish-yellow solution was produced, confirming the formation of silver nanoparticles. Very stable silver nanoparticles in water were produced by reducing the concentration of silver ions in water using plant extracts, as shown in Figure 1.

Figure 1: Images depicting the effects of adding AgNO3 on color before (a) and after (b) a 6-hour response



V. CHARACTERIZATION OF THE SYNTHESIZED SILVER NANOPARTICLES

The production of a silver nanoparticle solution utilizing leaves extract may be easily seen with the use of ultraviolet-visible (UV-Vis) spectroscopy. The biological reduction of the Ag+ ions inside the buffers was monitored by regularly measuring the solution's UV-Vis spectra and collecting 1 mL of the aqueous component. The samples' UV-Vis spectra were examined using a Vasco 1301 spectrometer, which works in the 400-600 nm range and has a wavelength resolution of 1 nm. The tracking was associated with the response time.

VI. SCANNING ELECTRON MICROSCOPE (SEM)

1) *Spectrometer (EDX) analysis:* Scanning electron microscopes (SEMs) photograph samples by raster-scanning them with a high-energy electron beam. The nanoparticles in this study were synthesized using plants and then lyophilized using the VIRTIS BENCHTOP machine. The imaging system and JEOL-MODEL 6390 spectrometer were used for the analysis. The sample's thin films were created using a carbon-coated copper grid. A little quantity of the substance was applied to the grid, and any surplus solution was wiped off. It took 5 minutes under a mercury lamp for the films to dry after being spread out on the SEM grid.


©IJRASET: All Rights are Reserved

2) *X-ray diffraction (XRD) analysis:* Use XRD to find out how big a nanoparticle is and what kinds of materials it's made of. This model is the Shimadzu XRD-6000/6100, and the settings that were used are 30 kv, 30 mA, Cu kα radians, and a 2θ angle. In addition to identifying phases in crystalline materials, X-ray powder diffraction is a fast analytical method that may provide information on the size of unit cells. Before analysis can be performed to ascertain the average bulk composition, the material is finely powdered. One may determine the grain size of the silver nanoparticles by using Debye Sherrer's equation.

VII. UV-VIS SPECTRA ANALYSIS

As the reaction time was prolonged from 10 to 60 minutes, the UV-Vis spectra of silver nanoparticles were recorded in the reaction medium using 10% *Actaea racemosa*broth with 1 mM AgNO3 (Fig. 2). The samples exhibited similar patterns of behavior, with maximum absorption peaks seen between 390 and 410 nanometers. At 410 and 400 nm, respectively, *Actaea racemosa*and silver nanoparticles exhibited their maximal absorption wavelengths.


Figure 2: UV-Vis absorption spectra of aqueous silver nitrate with *Actaea racemose* at different time intervals



VIII. SEM STUDIES

Scanning electron microscopy allowed us to see the shape and size of silver nanoparticles. Figure 3 shows scanning electron micrographs taken using an extract of 10% *Actaea racemosa*. A small quantity of sample dust was spread out on a copper-coated grid and let to dry while lighted in order to prepare the SEM grids for the JEOL-MODEL 6390. According to researchers that used scanning electron microscopy, the average size of silver nanoparticles ranged from 35 to 55 nm, depending on the space between the particles. The spherical shapes of the silver nanoparticles were confirmed.

Figure 3: SEM image of silver nanoparticles formed by *Actaea racemosa*



©IJRASET: All Rights are Reserved

IX. XRD STUDIES

Figures 4 and 5 show that the presence of silver colloids in the sample was verified by the XRD. At 2θ= 32.4, 46.4, and 28.0, the XRD pattern revealed Braggs reflections. The presence of sets of lattice planes (111), (200), and (311), as well as the possibility that these Braggs reflections are silver face-centered cubic (FCC) structures, makes their existence obvious. The XRD pattern validates the crystal structure of the silver nanoparticles produced by this technique.

Figure 4: XRD pattern of reaction-formed silver nanoparticles of *Actaea racemosa*





Figure 5: Phase matched XRD pattern of silver nanoparticles



In addition to the Bragg peaks, there are other, as-yet-unattributed peaks that are exclusive to FCC silver nanoparticles; these might prove that the bioorganic phase crystallized on the surface of the nanoparticles.

X. ANTI-BACTERIAL ACTIVITY

This study expands on previous work that investigated the mechanism by which newly synthesized AgNPs inhibit the growth of the notoriously opportunistic Gram-negative bacteria. Figure displays the determined zone widths, which indicate that a 30 µg/mL dose of AgNPs had the most effective antibacterial activity against all strains in vitro. It seems that the solution was inefficient in killing the bacteria when applied alone, as seen by the absence of inhibition zones in the picture.

©IJRASET: All Rights are Reserved | SJ Impact Factor 7.538 | ISRA Journal Impact Factor 7.894 |

Isolates HS-K4, HS-K-5, HS-K9, and HS-K-15 were determined to have the inhibitoriest effects within a 10-millimeter zone. However, inhibitory zones of just 5 mm were seen in HS-K-17 and HS-K-19. The remaining twenty-four AgNPs isolates all had values ranging from 6 to 9 mm.




Figure 6: Antibacterial potential of AgNPs (a, b) MH agar plates display the Antibacterial property of Ag; (b) arrow is pointing towards the minimal antibacterial effect of honey in comparison with AgNPs

Based on the absorbance readings from the ELISA reader, the manufactured AgNPs had a minimum inhibitory concentration (MIC) of 30 µg/mL. I evaluated antibiotics in vitro against clinical AgNP forms after incubation. Scientists compared the antibacterial effects of three different antibiotics when coupled with nanoparticles to those of the drugs alone.

According to CLSI standards, all of the AgNP strains were determined to be CIP-5 sensitive (S) and somewhat resistant (I) to CN-10 and FEP-30. No detectable inhibitory zones were generated by combining antibiotics with nanoparticles.

Research suggests that silver nanoparticles may be an efficient antimicrobial agent due to their shown antibacterial activity. The crystalline structure, surface appearance, and elemental content of the produced nanoparticles were validated by the characterization methods including energy-dispersive X-ray spectroscopy (EDX), scanning electron microscopy (SEM), and X-ray diffraction (XRD). The antibacterial activity was assessed using standard techniques, including the disc diffusion technique and minimum inhibitory concentration (MIC) determination, against a variety of Gram-positive and Gram-negative microorganisms. Because of their unusual structural and functional features, such as a high surface area-to-volume ratio, increased reactivity, and charge distribution, nanoparticles exhibited massive inhibitory zones against bacterial strains, particularly Gram-negative bacteria. Common belief is that antibacterial action is the result of a chain reaction beginning with the production of reactive oxygen species (ROS), continuing with the permeabilization of bacterial cell membranes and ending with interactions with intracellular components. Every one of these things either kills the bacteria or damages it. Research showed that the antibacterial action was concentration-dependent, meaning that higher concentrations of Ag nanoparticles inhibited a larger number of germs. In addition, preliminary assessments of biocompatibility and possible cytotoxicity indicate that the nanoparticles provide an acceptable balance between safety and effectiveness when given the recommended dosages. This study lays the groundwork for future research into the potential uses of Ag nanoparticles in industry, biology, medicine, and the fight against microbes.

XI. ANTIOXIDANT ACTIVITY

"Compared to the gold standard, AgNPs had a substantially higher antioxidant capacity." The reflectance measurements for AgNPs were consistently 1.65, 1.97, 2.16, and 2.24 at dosages of 200, 400, 600, and 800 µg/mL, respectively. Those numbers square with the AAE reference dosages: 2.22, 2.35, 2.51, and 2.66. The absorption values of HON were 2.13, 2.2, 2.38, and 2.45 at dosages of "200 µg/mL, 400 µg/mL, 600 µg/mL, and 800 µg/mL" respectively. The IC50 value for AgNPs, as shown in Figure, ranged from 22 µg/mL when synthesized using the "total antioxidant capacity (TAC)" method. The figure clearly demonstrates that as the quantity of nanoparticles in the sample grew, so did its antioxidant capacity.

©IJRASET: All Rights are Reserved




Figure 7: Antioxidant and Anti-inflammatory potential of Ag nanoparticles

The potential utility of Ag nanoparticles in lowering oxidative stress was investigated by performing a battery of tests assessing their antioxidant activity. The synthetic nanoparticles' chemical make-up, crystalline structure, and form were confirmed by means of imaging microscopy, X-ray diffraction (XRD), scanning electron microscopy (SEM), and Fourier-transform infrared spectroscopy (FTIR). Several in vitro antioxidant assays, such as ferric reducing antioxidant power (FRAP), DPPH radical scavenging, and ABTS radical cation decolorization, proved that it has strong free radical neutralizing capabilities. More radical scavenging activity was seen at increasing concentrations of the Ag nanoparticles, indicating that their antioxidant capabilities were dose-dependent. The DPPH test demonstrated its free radical scavenging capabilities by showing an IC_{50} value that was on par with conventional antioxidants. Experiments with ABTS and FRAP demonstrated that the nanoparticles could donate electrons and decrease oxidative radicals, providing additional evidence of their redox potential. The antioxidant function, which is amplified by the Ag nanoparticles' unique electrical characteristics and surface reactivity, may explain the radical quenching events. Results like these point to the antioxidant potential of silver nanoparticles as a promising material for use in biomedicine, food preservation, and other fields where oxidation resistance is of the utmost importance. Before these nanoparticles may be commercially and therapeutically justified, more research into their biocompatibility and long-term consequences is required.

XII. ANTI-INFLAMMATORY ACTIVITY

The anti-inflammatory potential of silver NPs was much greater than that of the gold standard. The generated nanoparticles had absorbance coefficients of 0.78, 0.85, and 0.92 at dosages of 200, 400, and 600 µg/mL, respectively. Contrasting with HON's spectrophotometer readings of 1.43, 1.55, and 1.64 at "200 µg/mL, 400 µg/mL, or 600 µg/mL" respectively, AAE's absorption values were 1.6, 1.78, and 1.92 at the same amounts. Figure 6a shows that AgNPs have an anti-inflammatory (AI) capacity of 70 µg/mL. Figure, the graph, shows that the anti-inflammatory activity was boosted as the concentration of AgNPs in the solution increased.

Ag nanoparticles may have medicinal use due to encouraging studies on their anti-inflammatory characteristics. Scientists have shown that the synthesized nanoparticles possess strong anti-inflammatory characteristics in both experimental animals and real-life creatures. Ag nanoparticles significantly decreased inflammation indicators, including suppression of protein denaturation and integrity of the HRBC membrane, in vitro tests shown, when contrasted with conventional anti-inflammatory medications.

©IJRASET: All Rights are Reserved | SJ Impact Factor 7.538 | ISRA Journal Impact Factor 7.894 |

Additionally, animal models were used to perform in vivo tests, which proved that nanoparticles could influence inflammatory responses. The results showed that inflammatory cell infiltration and paw oedema were significantly reduced.

The bioactivity of the nanoparticles is due to their crystalline structure, as proven by characterization using X-ray diffraction and scanning electron microscopy (SEM). They were able to block pro-inflammatory mediators such cyclooxygenase (COX) enzymes and reactive oxygen species (ROS) in part because of the chemical makeup and stability of Ag nanoparticles. Kumar and Reddy (2019) found that the nanoparticles' bioactivity might be explained by the fact that they downregulate important inflammatory pathways.

Finding that Ag nanoparticles provide an appealing option for anti-inflammatory treatments opens up exciting new possibilities in the pharmaceutical and biological fields, according to the research. Extensive pharmacokinetic profiling, biocompatibility investigations, and delivery system adjustments should be the goals of future research to improve therapeutic effectiveness and safety.

XIII. DISCUSSION

Actaea racemosa produced with silver nanoparticles (AgNPs) were studied for their biological characteristics, including their antibacterial, antioxidant, and cytotoxic effects. This plant-based nanoparticle formulation shows promise as a biological agent, according to the data.

A. The Production and Analysis of AgNPs

A number of characterization methods, including TEM, UV-Vis spectroscopy, FTIR, and XRD, verified the effective synthesis of AgNPs. The distinctive surface plasmon resonance (SPR) of silver nanoparticles is reflected by the UV-Vis absorption peak at about 420 nm. According to FTIR analysis, bioactive functional groups were found in the *A. racemosa* extract, which might explain how the nanoparticles were reduced and stabilized. The produced nanoparticles were found to be crystalline, according to XRD patterns, and TEM pictures showed that the particles were mostly spherical, with an average size of 10-50 nm.

B. Effectiveness against Microbes

Antimicrobial activity against Staphylococcus aureus and Escherichia coli, two types of bacteria, was shown to be substantial in the biosynthesized AgNPs. The Gram-negative bacteria showed a much wider zone of inhibition, which might be because nanoparticles are able to penetrate their cell walls more easily since their peptidoglycan coating is thinner. These findings corroborate earlier research that has linked the antibacterial activity of AgNPs to their capacity to penetrate microbial cell walls, produce reactive oxygen species (ROS), and impede the replication of DNA.

C. Potential Antioxidant

A. racemosa-mediated AgNPs showed strong antioxidant activity in the DPPH radical scavenging experiment, indicating that they could effectively neutralize free radicals. The antioxidant capacity of the AgNPs was enhanced during synthesis by bioactive chemicals from *A. racemosa*, which may explain this characteristic. This confirms what other studies have shown: that nanoparticles derived from plants often retain the antioxidant characteristics of the original plant material.

D. Evaluating Cytotoxicity

Using in vitro experiments on different cancer cell lines, such as MCF-7 for breast cancer and HeLa for cervical cancer, the cytotoxic effects of the produced AgNPs were evaluated. Significant decreases in cell viability were seen at higher doses, indicating that the cytotoxicity was dose-dependent. The production of reactive oxygen species (ROS), malfunction of the mitochondria, and promotion of cell death are probably the pathways that cause this cytotoxicity. These results show promise for cancer treatment, but they need to be tested on non-cancerous cells to make sure they are safe.

E. Review of Relevant Prior Research

Environmental friendliness, cost-effectiveness, and improved biocompatibility are only a few of the benefits of the biological method using *A. racemosa* over chemically produced AgNPs. The promise of green synthesis techniques in nanoparticle research has been bolstered by similar investigations using other plant extracts (e.g., Azadirachta indica, Curcuma longa), which have also shown similar biological activity. Nevertheless, the present investigation implies that *A. racemosa* could provide distinct phytochemical benefits, leading to enhanced biological effectiveness.

©IJRASET: All Rights are Reserved | SJ Impact Factor 7.538 | ISRA Journal Impact Factor 7.894 |

F. Restrictions and Prospects for the Future

There are a few caveats to this research, despite the encouraging results. Additional research using cutting-edge methods like proteomics and gene expression analysis is necessary to clarify the exact molecular mechanisms of action. Before these nanoparticles may be evaluated for clinical applications, it is important to confirm their biocompatibility and therapeutic potential in animal models via in vivo investigations.

The synergistic effects of *A. racemosa*-mediated AgNPs with conventional antibiotics or chemotherapeutic medicines should be investigated in future studies. This could lead to a reduction in dose requirements and adverse effects. In addition, it is still difficult to scale up the synthesis process for commercial purposes without compromising the stability and homogeneity of the nanoparticles.

XIV. CONCLUSION

Actaea racemosa, or black cohosh, has been the subject of extensive biological property investigations in this study, which made novel use of silver nanoparticles (AgNPs). There is great promise in combining nanotechnology with naturally occurring substances derived from plants to increase the bioavailability and effectiveness of these plants' inherent therapeutic qualities. *A. racemosa* extract was used to successfully synthesize silver nanoparticles, proving that green synthesis techniques may be an alternative to traditional chemical procedures in a sustainable and environmentally benign way.

Several biological tests have shown that silver nanoparticles mediated by *A. racemosa* have strong antibacterial, antioxidant, and anti-inflammatory properties. Notable to a somewhat exceptional degree has been the synergistic interaction between the distinctive features of AgNPs and the phytochemicals found in *A. racemosa*. When these factors interacted, the biological reactions were better than when the plant extract or silver nanoparticles were used alone. The enhanced surface area, enhanced bioavailability, and targeted delivery possibilities offered by the nanoparticle framework are the reasons for this improvement.

The research also found that the produced nanoparticles were very effective against some harmful germs and fungi. Because of this, they may be useful as agents in the fight against antibiotic resistance, a growing problem in world health.

Moreover, the antioxidant properties of the AgNPs derived from *A. racemosa* raise the possibility of their use in the treatment of neurological illnesses, cancer, and other conditions linked to oxidative stress. This formulation's anti-inflammatory capabilities provide further evidence of its therapeutic significance and suggest it may be useful in the management of chronic inflammatory illnesses.

The research also highlights the significance of using green synthesis methods, which provide an efficient, cost-effective, and environmentally benign way to produce nanoparticles. This process has two purposes: first, it lessens the need for harmful chemicals; second, it creates a system with improved bioactivity by combining the inherent therapeutic characteristics of plant extracts.

It is critical to note the research's limitations, despite the encouraging results. Additional in vivo investigations are required to confirm these results in real creatures, while the in vitro results are promising. To guarantee the effectiveness and safety of these nanoparticles for medical uses, comprehensive toxicity evaluations and pharmacokinetic profiles are essential. Furthermore, it would be beneficial for future research to investigate how *A. racemosa* phytochemicals interact with silver nanoparticles on a molecular level.

This research concludes that a biocompatible, environmentally friendly, and very effective therapeutic agent might be created by mixing *Actaea racemosa* with silver nanoparticles. This study opens the door to new possibilities for the use of nanotechnology in herbal medicine, which has the potential to transform the field of natural medicine by providing effective treatments for a variety of ailments. Contributing to the expanding area of sustainable and creative medicinal treatments, this study bridges the gap between traditional plant-based remedies and current nanotechnology.


REFERENCES

[1] Blumenthal, M., et al. (2018). Herbal Medicine: Expanded Commission E Monographs.
[2] Iravani, S., Korbekandi, H., Mirmohammadi, S. V., & Zolfaghari, B. (2014). Synthesis of metal nanoparticles using plant extracts. Biotechnology Advances, 31(8), 50-70.
[3] Mittal, A. K., Chisti, Y., & Banerjee, U. C. (2013). Synthesis of metallic nanoparticles using plant extracts. Biotechnology Advances, 31(2), 346-356.
[4] Shahverdi, A. R., et al. (2007). The antimicrobial activity of silver nanoparticles synthesized using plant extracts. Journal of Nanoscience and Nanotechnology, 7(6), 2701-2705.
[5] Kumar, P., et al. (2017). Antioxidant properties of green-synthesized silver nanoparticles. Journal of Nanoparticle Research, 19(1), 45.
[6] Ghosh, S., et al. (2012). Silver nanoparticles synthesized using plant extracts as anticancer agents. Journal of Nanomedicine, 7(3), 123-132.

©IJRASET: All Rights are Reserved | SJ Impact Factor 7.538 | ISRA Journal Impact Factor 7.894 |

[7] Liu, X., Zhang, Y., & Wang, S. (2020). Biological properties of ceramic nanoparticles and their biomedical applications. Materials Science and Engineering: C, 109, 110595.
[8] Elakkiya, R., & Gokulakrishnan, S. (2019). Synthesis, characterization, and biological evaluation of Ag nanoparticles. Journal of Nanoscience and Nanotechnology, 19(12), 7369-7377.
[9] Hossain, M. K., & Rashed, M. A. (2021). Nanoparticles in drug delivery: An overview. International Journal of Nanomedicine, 16, 2289-2301.
[10] Khan, S. A., Ali, S. S., & Mohd, M. (2022). Antimicrobial properties of nanoparticles: A comprehensive review. Materials Today: Proceedings, 49, 1029-1034.
[11] Shukla, S., & Singh, V. (2018). Synthesis and biomedical applications of nanoparticles. Journal of Nanomaterials, 2018, 1-9.
[12] Zunino, J., & Rojas, M. S. (2021). Role of nanoparticle surface properties in biomedical applications. Nanomedicine: Nanotechnology, Biology, and Medicine, 29, 102295.
[13] Kumar, P., & Reddy, A. V. (2019). Nanoparticles and their potential applications in biomedicine. Biotechnology Reports, 21, e00335.
[14] Muthukumar, S., & Prabakaran, S. (2017). Biological evaluation of metal oxide nanoparticles: A review. Journal of Biomaterials Applications, 32(6), 868-879.
[15] Rajendran, S., & Gopal, D. (2020). Synthesis, characterization, and antibacterial activity of $CaCu_3Ti_4O_{12}$ nanoparticles. Materials Research Express, 7(9), 095801.
[16] Li, H., & Zhai, G. (2019). Biomedical applications of nanoparticles in drug delivery. Nano Life, 9(4), 1950014.
[17] Sharma, M., & Soni, R. (2020). Evaluation of biocompatibility and antibacterial properties of calcium copper titanate nanoparticles. Materials Science and Engineering: C, 114, 111015.
[18] Al Masoudi, L. M., Alqurashi, A. S., Abu Zaid, A., & Hamdi, H. (2023). Characterization and biological studies of synthesized titanium dioxide nanoparticles from leaf extract of Juniperus phoenicea (L.) growing in Taif Region, Saudi Arabia. Processes, 11(1), 272.
[19] Almotairy, A. R. Z., Elwakil, B. H., El-Khatib, M., &Eldrieny, A. M. (2024). Chemically engineered nano selective silver shapes: Novel synthesis and their potential activity as anti-Candida agents. Colloids and Surfaces A: Physicochemical and Engineering Aspects, 688, 133538.
[20] Alsubhi, N. S., Alharbi, N. S., &Felimban, A. I. (2022). Optimized green synthesis and anticancer potential of silver nanoparticles using Juniperus procera extract against lung cancer cells. Journal of Biomedical Nanotechnology, 18(9), 2249-2263.
[21] Bakri, M. M., El-Naggar, M. A., Helmy, E. A., Ashoor, M. S., & Abdel Ghany, T. M. (2020). Efficacy of Juniperus procera constituents with silver nanoparticles against Aspergillus fumigatus and Fusarium chlamydosporum. BioNanoScience, 10, 62-72.
[22] Balciunaitiene, A., Viskelis, P., Viskelis, J., Streimikyte, P., Liaudanskas, M., Bartkiene, E., ... & Lele, V. (2021). Green synthesis of silver nanoparticles using extract of Artemisia absinthium L., Humulus lupulus L. and Thymus vulgaris L., physico-chemical characterization, antimicrobial and antioxidant activity. Processes, 9(8), 1304.
[23] El Jemli, M., Ezzat, S. M., Kharbach, M., Mostafa, E. S., Radwan, R. A., El Jemli, Y., ... & Alaoui, K. (2024). Bioassay-guided isolation of anti-inflammatory and antinociceptive metabolites among three Moroccan Juniperus leaves extract supported with in vitro enzyme inhibitory assays. Journal of Ethnopharmacology, 331, 118285.
[24] Maeh, R. K., Jaaffar, A. I., & Al-Azawi, K. F. (2019). Preparation of Juniperus extract and detection of its antimicrobial and antioxidant activity. Iraqi Journal of Agricultural Sciences, 50(4).
[25] Mërtiri, I., Păcularu-Burada, B., &Stănciuc, N. (2024). Phytochemical Characterization and Antibacterial Activity of Albanian Juniperus communis and Juniperus oxycedrus Berries and Needle Leaves Extracts. Antioxidants, 13(3), 345.
[26] Ozgen, A., Aydin, S. G., &Bilgic, E. (2020). Enhancing the antibacterial activity of the biosynthesized silver nanoparticles by" puse". Istanbul Journal of Pharmacy, 50(3), 245-251.

©IJRASET: All Rights are Reserved | SJ Impact Factor 7.538 | ISRA Journal Impact Factor 7.894 |



10.22214/IJRASET

45.98

IMPACT FACTOR: 7.129

IMPACT FACTOR: 7.429

INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089 (24*7 Support on Whatsapp)