



# **iJRASET**

International Journal For Research in  
Applied Science and Engineering Technology



---

# **INTERNATIONAL JOURNAL FOR RESEARCH**

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

---

**Volume:** 12    **Issue:** II    **Month of publication:** February 2024

**DOI:** <https://doi.org/10.22214/ijraset.2024.58297>

**[www.ijraset.com](http://www.ijraset.com)**

**Call:** ☎ 08813907089

**E-mail ID:** [ijraset@gmail.com](mailto:ijraset@gmail.com)

# Combined Effect of Banana Fibre and Nano Silica on the Strength Properties of Concrete

Ankita Prasad<sup>1</sup>, Siddhartha Deb<sup>2</sup>, Satyendra Dubey<sup>3</sup>, Anubhav Rai<sup>4</sup>

Gyan Ganga Institute of Technology and Science

**Abstract:** This study investigates the combined effect of nano silica and banana fibres on mechanical properties of concrete of grade M-25. Nano silica has been used as a partial replacement of cement by weight. Nano silica has been kept constant at 3% as maximum strength was achieved at this percentage according to past studies. Banana fibre has been added by weight of cement in proportions of 0.5%, 1%, 2%, 3%, 4% and 5%. Length of banana fibres kept at 40mm. Compressive strength was determined by using different combinations of nano silica and banana fibre. Nano concrete provides good strength as compared to conventional concrete. The addition of banana fibres in nano concrete improved the strength properties of nano concrete as well as improvement in crack resistance of concrete. On the other hand, the addition of banana fibres resulted in reduction workability as well as permeability of concrete.

**Keywords:** Nano silica, banana fibre, compressive strength, workability, cement, concrete.

## I. INTRODUCTION

Concrete is the most widely used material in the construction industry because of its high load bearing capacity. It is an artificial composite material, comprising of cementitious material (typically Portland cement), filler material [aggregate](#) (typically a rocky material, loose stones, and sand) and water. Now-a-days many [types of concrete](#) are available, determined by the type and formulations of binders and the other types of materials used to suit the application of the engineered material. In the recent years, researchers have targeted on the use of different materials like fly ash, nano silica, micro silica, steel fibres, banana fibres etc.

A lot of researchers have found a remarkable result in enhancing the strength and other properties of conventional concrete by using nano silica and banana fibre. Nano-silica or silicon dioxide (SiO<sub>2</sub>) has an amazing cementitious property which can be used to partially replace cement. The addition of nano silica in a required amount within a concrete mixture modifies the material properties and performance by reducing the void space between the cement and aggregate in the cured concrete. This improves the strength, durability, shrinkage and bonding to steel reinforcing bars. In most studies, it was found that nano silica gives highest strength on partially replacing cement by 3% nano silica content. Banana fibres are eco-friendly and have valuable qualities like low density, light weight, low cost, excellent strength properties, fire and water resistance. This type of waste has a higher likelihood of finding use in various construction and building material applications. Adding banana fibres in concrete also resulted in increase in strength, prevents shrinkage cracks, reduces permeability and lessens water bleeding. In this investigation, cement is partially replaced by nano silica and different combinations of banana fibre and nano silica are used together in concrete by varying banana fibre content and keeping nano silica constant at 3%.

## II. OBJECTIVES

- 1) To determine the compressive strength of nano concrete by using banana fibre (*Musa acuminata*) in different proportions.
- 2) The comparison is made between conventional concrete and the concrete using nano silica and banana fibre in different percentages.
- 3) To determine the optimum content of banana fibre.

## III. EXPERIMENTAL DETAILS

### A. Materials

- Ordinary Portland cement of 53 grade
- Coarse aggregate
- Fine aggregate
- Nano silica
- Banana fiber
- Water

- 1) **Cement:** For making of M-25 concrete, OPC 53 grade (Emami double bull cement) was used having specific gravity of 3.14.
- 2) **Coarse Aggregate:** Machine crushed stone angular in shape was used as coarse aggregate. Two fractions of coarse aggregates were used, of size 20mm and 12.5mm in proportions of 60% and 40% respectively. Specific gravity of aggregates is 2.94 and water absorption is 0.8%.
- 3) **Fine Aggregate:** Locally available Narmada river sand is used for experiment passing through 4.75mm sieve having specific gravity of 2.67 and water absorption of 1.8%.
- 4) **Nano Silica:** Nano silica, also called quartz dust or silica dust is one of the most widely used nano materials to improve the mechanical properties of concrete. It comes in white powdered form and the size is below 100nm. It is known to increase the strength and durability of concrete as well as workability. It can significantly improve the carbonation resistance, chloride resistance, and sulphate resistance of concrete.



**Fig. 3.1 Nano silica**

- 5) **Banana Fibre:** Banana fibres are widely available as agricultural waste and are eco-friendly. Its chemical composition has cellulose, hemicelluloses and lignin content. It is highly strong and lightweight fibre which has smaller elongation. Banana fibre offers the resistance to suddenly applied loads, limits the shrinkage and cracks, increases the compressive and flexural strength, decreases the permeability and hence ultimately decreases the bleeding of water as its water absorption capacity is good. Length of fibres used is 40mm.




**Fig. 3.2 Banana fiber**

- 6) **Water:** Portable water from the laboratory was used for mixing and curing of concrete.

#### **B. Methodology**

- 1) **Test Specimen Preparation:** All the materials were tested in the laboratory as per the guidelines. Mix design of M-25 concrete was done conforming to IS- 10262: 2019. Target strength was 31.6 KN/mm<sup>2</sup>. Variations were done in the standard mix according to the percentage replacement of cement by nano silica at 3% and addition of banana fibre in variations of 0.5%, 1%, 2%, 3%, 4% and 5% by weight of cement. Water cement ratio used was 0.5. Mix design ratio of materials used was 1: 1.89: 3.41 for cement, fine aggregates and coarse aggregates respectively. Cube moulds of size 150mm\*150mm\*150mm were used. Cube specimens were casted for compressive strength test and cured for 28 days. Testing was done using UTM machine after 28 days of curing.



#### IV. RESULTS

##### A. Compressive Strength Test

Cube samples were tested in the UTM machine after 28 days of curing.

Sample No.	Nano silica %	Banana fiber %	Average compressive strength at 28 days (N/mm <sup>2</sup> )
Conventional concrete	0%	0%	31.8
Nano concrete	3%	0%	40.3
Sample 1	3%	0.5%	44.6
Sample 2	<u>3%</u>	1%	48.1
Sample 3	<u>3%</u>	1.5%	41.2
Sample 4	<u>3%</u>	2%	36.7
Sample 5	<u>3%</u>	2.5%	30.33
Sample 6	<u>3%</u>	3%	25.5

#### V. CONCLUSION

- 1) Workability was improved by using nano silica but decreases on adding banana fibre.
- 2) Compressive strength of concrete was maximum at 1% banana fibre content and after that it gradually decreases on increasing banana fibre content.
- 3) Compressive strength increased by 51.25% as compared to conventional concrete and by 19.35% as compared to nano concrete.

#### REFERENCES

- [1] Ahsan Afraz and Majid Ali (2021). Effect of Banana Fiber on Flexural Properties of Fiber Reinforced Concrete for Sustainable Construction. Engineering Proceedings.
- [2] Akash Kumar, Gurpreet Singh (2018). Effect of Nano Silica on the Fresh and Hardened Properties of Cement Mortar. International Journal of Applied Engineering Research.
- [3] Amgad Elbehiry, Omar Elnawawy, Magdy Kassem, Amr Zaher, Nasim Uddin, Marwan Mostafa (2020). Performance of concrete beams reinforced using banana fiber bars. Elsevier.
- [4] A Paktiawal and M Alam (2020). Nano- Silica and its Role on Performance of Cement Concrete- A Review of Experimental Investigation. IOP Conf. Series: Earth and Environmental Science, ICECAE.



- [5] Arun Nischal Guleria, Sandeep Salhotra (2016). EFFECTS OF SILICA FUME 9MICRO SILICA OR NANO SILICA ON MECHANICAL PROPERTIES OF CONCRETE: A REVIEW. International Journal of Civil Engineering and Technology (IJCIET).
- [6] Bangaru Sai Srinivas, K.V.V. Rama Raju (2022). Strength Evaluation and Durability on Addition of Nanosilica in M30 Grade Concrete. International Journal for Research in Applied Science & Engineering Technology (IJRASET).
- [7] Chandra Mouli K, Pannirselvam N, Vijaya Kumar D, Anitha V, M.Chaitanya Nava Kumar (2019). Strength Studies on Pine Apple Fibre Concrete with Nano Silica. International Journal of Innovative Technology and Exploring Engineering (IJITEE).
- [8] Changjiang Liu, Xin Su, Yuyou Wu, Zhoulian Zheng, Bo Yang, Yuanbing Luo, Jingwei Yang and Jiangying Yang (2021). Effect of nano- silica as cementitious materials – reducing admixtures on the workability, mechanical properties and durability of concrete. De Gruyter.
- [9] Dr. K. Chandra Mouli, Dr. N. pannirselvam, V. Anitha, Dr. D. Vijaya Kumar, S. Valeswara Rao (2019). STRENGTH STUDIES ON BANANA FIBRE CONCRETE WITH METAKAOLINE. International journal of civil engineering and technology(IJCIET).
- [10] Dr. K. Chandramouli, J. Sree Naga Chaitanya, Mohammad Abdullah (2013). An Experimental Investigation on Banana Fiber Concrete with Nano Silica. International Journal For Research in Applied Science and Engineering Technology (IJRASET).
- [11] Dr. K. CHANDRA MOULI, V. ANITHA AND SHREE NAGA CHAITANYA (2018). Comparative Study of Banana Fiber Reinforced Concrete with Normal Concrete. SSRG International journal of civil engineering.
- [12] Dr. Pannirselvam N, Dr. Chandra Mouli K, Anitha V, Dr. Vijaya KumarD (2018). PULSE VELOCITY TEST ON BANANA FIBRE CONCRETE WITH NANO SILICA. International journal of civil engineering and technology (IJCIET).
- [13] D S V S M R K Chekravarty, A Mallika, P Srinivasa Rao (2021). Impact of nano silica on mechanical properties of concrete using optimized dosage of nanosilica as a partial replacement of cement. SSRG International journal of civil engineering.
- [14] Er. Sahul Kumar, Er. Suhail Ashaq (2020). Partial Replacement of Cement with Flyash and Addition of Banana Fibre in Concrete. International Journal for Scientific Research & Development\ Vol.8, Issue 8, 2020.
- [15] G. VAISHNAVI, J. SUNIL, B. NIKHITHA, ARKAPALLY MAHESH, AMGOTH SHIVAJI (2022). ENHANCING PROPERTIES OF CONCRETE BY USING NANO SILICA AS A PARTIAL REPLACEMENT IN CEMENT. Journal of Engineering Sciences.
- [16] G. Vinod Kumar, Dr. B Narendra Kumar (2020). Influence of Nano- Alumina on Properties of Concrete. International Journal of Engineering Research in Current Trends (IJERCT).
- [17] Jyoti Panchore, Sushma Mahajan, Sh. Yunus Manihar, Manish Gandhi (2018). Effect of Banana Fiber on Concrete Strength. International Journal of Research in Advent Technology (IJRAT).
- [18] K. Chandramouli, N. Pannirselvam, D. V. V. NagaSaiPardhu, V. Anitha (2019). Banana Fibre Reinforced Concrete with Conventional Concrete. Blue Eyes Intelligence & Science Publication.
- [19] M. Chaitanya Nava Kumar, J. Sree Naga Chaitanya, Dr. N. Pannirselvam, Dr. K.Chandramouli, N. Sada Siva (2022). PERFORMANCE ON BANANA FIBRE CONCRETE BY PARTIAL REPLACEMENT OF CEMENT WITH MARBLE DUST POWDER BY USING M30 GRADE. INTERNATIONAL JOURNAL OF CREATIVE RESEARCH THOUGHTS (IJCRT).
- [20] Neha Tirkey, G. B Ramesh (2018). Experimental Study on the Banana Fiber Reinforced Concrete. International Journal of Pure and Applied Mathematics.
- [21] S. Kesvraman (2017). STUDIES ON METAKAOLIN BASED BANANA FIBRE REINFORCED CONCRETE. International Journal of Civil Engineering and Technology (IJCIET).
- [22] Rodgers B. Mugume, Adolph Karubanga, and Michael Kyakula (2021). Impact of Addition of Banana Fibres at Varying Length and Content on Mechanical and Microstructural Properties of Concrete. Advances in civil engineering.
- [23] Syed Nooruddin, Syed Shah Maqdoom Hussaini, Syed Umair, Akshay Belgar, Prof. Sujeet Patil (2019). Strength of Nano Concrete using Nano Silica. International Journal of Engineering Research & Technology (IJERT).
- [24] Tabbassum A. Pathan, Rashida A. Jhumarwala (2022). Evaluation of Mechanical Properties of High Strength Banana Fibre Concrete (HSBFC) incorporating Fly ash and Silica Fume. International Journal For Research in Applied Science and Engineering Technology.
- [25] Vidya Bharathi.S, Vinodhkumar. S, Saravanan.M.M (2021). Strength characteristics of banana and sisal fiber reinforced composites. IOP Conf. Series: Materials Science and Engineering, IVC RAISE 2020.



10.22214/IJRASET



45.98



IMPACT FACTOR:  
7.129



IMPACT FACTOR:  
7.429



# INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089  (24\*7 Support on Whatsapp)