



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 10 Issue: IV Month of publication: April 2022

DOI: https://doi.org/10.22214/ijraset.2022.41163

www.ijraset.com

Call: © 08813907089 E-mail ID: ijraset@gmail.com

Volume 10 Issue IV Apr 2022- Available at www.ijraset.com

Effect on Compression Strength of Masonary Mortar by Replacing Fine Aggregates with Waste Glass

Prem Pramod¹, Ramoo Ram²

¹Department of Civil Engg., Vivekananda Global University, Jaipur 303012 ²Assistant Professor, Department of Civil Engg., VivekanandaGlobal University, Jaipur 303012

Abstract: Eco- friendly, low-carbon, and energy-intensive materials are required for a accountable approach to sustainable development. Glass debris can be used to substitute fine natural aggregate in a constructive way. The effects of adding glass cullet to the mechanical characteristics of mortar were investigated for this purpose.

The glass aggregate was created from recycled post-consumer waste glass (mainly bottles) from the food, medical, and cosmetics industries. Four different contents of fine glass cullet were used in this experiment (5, 10, 15, and 20 wt. percent of fine aggregate). Compressive, flexural, and split tensile strengths were all assessed. The modulus of elasticity and the Poisson coefficient were also calculated.

The inclusion of glass sand aggregate to mortar improves its mechanical qualities. The acquired improvement in split tensile strength was the least influenced when comparing the strengths. Rarely has the found effect for the increased examined attributes of the glass sandaggregate content been documented. Furthermore, it was discovered that increasing the recycled glass sand aggregate content in mortar reduced the density. The links between the properties of mortar containing glass sand aggregate were also investigated.

Keywords: Portland Pozzolana Cement (ultra-Tech), Drinking Water, natural sand, and waste glass replacement were used in the current experiment.

I. INTRODUCTION

The most often used construction materials are cement, masonry mortar, and concrete. According to current state-of-the-art masonry mortar, it is not just a three-component system of cement, water, and fine aggregates; many other materials, such as fly ash, silica fumes, waste glass, and stone dust, are successfully utilised in masonry mortar to improve its qualities. The natural resources of conventional material (Fine Aggregates) are decreasing at a faster rate as a result of increased usage. Any effort to conserve natural resources by utilising alternative materials, particularly readily available local waste (waste glass) from diverse industries, is greatly admired. The goal of this project is to see if there is a way to use locally available waste materials. claimed that one of the best solutions is to use waste materials instead of natural resources, and investigated the potential of using waste glass as a partial replacement for fine aggregates.

Many researches are being done on strength on masonry mortar stated that in any reinforced structural construction, the strength of mortar is a special anxiety to the engineer because mortar is responsible to give defense in the outer part of the structure as well as to the brick joint masonry wall system.

The present study aimed at utilizing waste glass as partial substitution of fine aggregates by weight.

Glass is a non-crystalline formless solid and is often transparent. It has widespread practical, technological and ornamental use. Scientifically glass can be defined in a broader sense, as every solid that possesses a non-crystalline (amorphous) structure in the atomic scale and that exhibits a glass transition when heated towards the liquid state. The most familiar and the oldest types of glass are "silicate glasses". Glass is used in day to day life and when they break. They are put in the rubbish and dumped on the ground. The most frequent method for disposing of waste glass and solid wastes is land filling. It is damaging to the environment because it affects soil quality and reduces fertility.

In this study, we replaced fine aggregates (FA) with waste glass by weight and investigated its physical qualities. Cubical specimens are cast after varied proportions are prepared, and their compressive strength is compared to control masonry mortar.



International Journal for Research in Applied Science & Engineering Technology (IJRASET)

ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 10 Issue IV Apr 2022- Available at www.ijraset.com

II. MATERIALS USED

Portland Pozzolana Cement (ultra-Tech), Drinking Water, natural sand, and waste glass replacement were used in the current experiment.

A. Cement

Fly ash-based Portland Pozzolana cement (ultra-Tech) complying to IS: 1489-1991 (Part 1). Thephysical qualities of cement were determined through a series of tests.

B. Sand

Naturally sand is used which is passes through 4.75mm sieves.

C. Waste Glass

The broken window glass was used as waste which has supplied from glass market. The fine waste glass is used.

III. RESULT AND DI SCUSSION

The tests were carried out on cubes of hardened brick mortar. Destructive experiments on masonry mortar cubes were performed on 45 cubes of masonry mortar.

This chapter covers the presenting of test results as well as a discussion of how the compressive strength of control masonry mortar develops over time. For each proportion, tests were conduction fresh masonry mortarand hardened masonry mortar.

The compressive strength of the sample masonry mortar was compared to that of a 1:3 grade Controlmasonry mortar.

A. Compressive Strength as per IS: 2250-1981

Compressive strength is the most important criterion for structural design. Compressive strength tests were performed at the ages of 7, 14, and 28 days to compare the strength development of masonry mortar to that of Control masonry mortar. The outcomes of the tests are as follows: Most concrete structures are built on the assumption that concrete has sufficient compressive strength, as shown in the table for masonry mortar management.


B. Compressive Strength at 7 days

Three cubes of each sample were cast and compared to standard masonry mortar to determine compressive strength after seven days. <u>Table 4.1 shows the outco</u>me values, while graph no. 4 shows the graphical depiction.

Table 4.1:- Compressive strength test result at 7 days

| FA replaced | CTM reading(in KN) | Average load (KN) | Compressive strength |
|-------------|--------------------|-------------------|----------------------|
| | | | (N-mm2) |
| 0% | 80 | | |
| | 70 | 73.34 | 14.98 |
| | 70 | | |
| 10% | 72 | | |
| | 75 | 77.67 | 15.14 |
| | 86 | | |
| 15% | 85 | | |
| | 90 | 88.34 | 18.04 |
| | 90 | | |
| 20% | 70 | | |
| | 75 | 73.34 | 14.97 |
| | 75 | | |
| 25% | 70 | 68.34 | 13.96 |
| | 65 | | |
| | 70 | | |


Volume 10 Issue IV Apr 2022- Available at www.ijraset.com



C. Compressive Strength at 14 Days

Table 4.2:- compressive strength test result at 14 days

| FA replaced | CTM reading (in KN) | Average load (KN) | Compressive |
|-------------|---------------------|-------------------|-------------------------------|
| | | | strength (N-mm ²) |
| 0% | 82 | | |
| | 100 | 94 | 19.23 |
| | 100 | | |
| 10% | 92 | | |
| | 110 | 104 | 21.30 |
| | 110 | | |
| 15% | 112 | | |
| | 112 | 111.34 | 22.86 |
| | 110 | | |
| 20% | 90 | | |
| | 110 | 103.34 | 21.02 |
| | 110 | | |
| 25% | 100 | | |
| | 110 | 106.67 | 21.80 |
| | 110 | | |



Graph No. 5:-Compressive strength test result at 14 days




Volume 10 Issue IV Apr 2022- Available at www.ijraset.com

D. Compressive Strength at 28 days

Table 4.3:- Compressive strength at 28 days

| FA replaced | CTM reading (in KN) | Average load(KN) | Compressive strength (N-mm ²) |
|-------------|---------------------|------------------|---|
| 0% | 100 | | |
| | 100 | 96.67 | 19.72 |
| | 90 | | |
| 10% | 110 | | |
| | 108 | 111.34 | 22.71 |
| | 116 | | |
| 15% | 120 | | |
| | 120 | 120 | 24.48 |
| | 120 | | |
| 20% | 110 | | |
| | 110 | 113.34 | 23.12 |
| | 120 | | |
| 25% | 105 | | |
| | 105 | 110 | 22.08 |
| | 120 | | |
| | | | |



Graph No. 6:- Compressive Strength test result at 28 days


Volume 10 Issue IV Apr 2022- Available at www.ijraset.com

E. Compressive Strength Analysis

Combined compressive strength at 7days, 14 days and 28 days are shown in table below and graphical representation of the same in graph no 7

| rable 4.4:- Compressive strength result | | | | | |
|---|------------------------------|------------------------------|------------------------------|--|--|
| FA replaced | 7 days average | 14 days average | 28 days average | | |
| | Compressive | compressive | compressive | | |
| | strength(N/mm ²) | strength(N/mm ²) | strength(N/mm ²) | | |
| 0% | 14.98 | 19.23 | 19.72 | | |
| 10% | 15.14 | 21.30 | 22.71 | | |
| 15% | 18.04 | 22.86 | 24.48 | | |
| 20% | 14.97 | 21.02 | 23.12 | | |
| 25% | 13.96 | 21.80 | 22.08 | | |

Table 4.4:- Compressive strength result



Graph No. 7 Compressive strength analysis

IV. CONCLUSION

Following conclusion were made based on result obtained from the result

- 1) Based on the results of the entire study comparing control masonry mortar versus modified masonrymortar.
- 2) When trash is added as fine aggregates, the rate of strength gain is slow at first, but by 28 days, it has reached virtually the needed design strength.
- 3) At 7 days, 14 days, and 28 days, 15 percent WG is added to obtain the maximum compressive strength.
- 4) When compared to control mortar, the compressive strength of masonry mortar containing 15% WG rose by
- 5) 20.42 percent after 7 days.
- 6) When compared to control mortar, the compressive strength of masonry mortar containing 15% WG rose by (18.87 percent) after 14 days.
- 7) The 28 days compressive strength of concrete containing 15% WG was increased by (24.13%) from controlmortar.
- 8) Waste glass with a size of less than 1.18 mm can be utilised as a partial replacement for fine particles inmasonry mortar.
- 9) The addition of WG to masonry mortar produces acceptable results.
- 10) Why Because glass is non-biodegradable and its decomposition is a challenge for the environment, using WG will assist in resolving environmental issues associated with waste glass.



International Journal for Research in Applied Science & Engineering Technology (IJRASET)

ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 10 Issue IV Apr 2022- Available at www.ijraset.com

V. FUTURE SCOPE AND SIGNIFICANCE

Environmental pollution caused by the increased output of home and industrial waste is a serious issue in developing countries like India. Waste disposal has become a serious issue in India's urban centres, particularly the disposal of waste glass generated by the country's home and industrial sectors. Due to increased industrialization and a rapid development in the standard of living, the amount of waste glass has increased in recent years. As a result, it is vital and critical to find some environmentally acceptable alternatives.

One of the alternatives is to use waste glass. Other materials are being employed in the production of concrete to address the environmental issues generated by industrial waste. When waste glass is utilised in the creation of masonry mortar, it not only benefits the environment, but it also improves the performance of the mortar when used in the right amounts. Masonry mortar is a concrete matrix-based masonry compound. Binder and fine aggregates make up this mixture. It is a necessary component of every reinforced structural structure.

REFERENCES

- [1] Nwaubani Sunny O. and Konstataninos I, Poutos. (2013). "The effect of waste glass powder fineness on cement masonry mortar properties" ISSN: 2319 4847, vol. 2, pages. 110 116, International journals of application or innovation in engineering and management.
- [2] Bhandari P. S., Dhale S. A., and Pathan V. G. (2014). "Fine aggregates' effect on cement masonry mortar." Journal of chemical and pharmaceutical science, ISSN: 0974 2115, vol. 8, pp 906 910. International journals of engineering and computer science, ISSN: 2319 7242, vol. 3, replacement of cement with glass powder" Journal of chemical and pharmaceutical science, ISSN: 0974 2115, vol. 8, pp 906 910.
- [3] Sharma. Ashutosh (2015) "Glass powder a partial substitute for cement" ISSN: 2348–9510, vol. 1, pp. 86–93, international journal of core engineering and management.
- [4] Hoque. Tasnia, Harunur Rashid, RokanHasan. MD and FprhadMondol.Ebna. (2013), "The effect of stone dust as a partial replacement for cement and sand on various mechanical parameters of masonry mortar." ISSN 2319-5347, vol. 2, pp. 54–57.
- [5] Mahzuz . H. M. A., Ahmed. A. A. and Yusuf. M. A. (2011) "Use of stone powder as an alternative to sand in concrete and masonry mortar", Journal of environmental science and technology, Vol. 5.Pp 381–388.
- [6] Andrew. Smith., Frederik. Verhelst., Christophe. Denayer and Richard. Givens. (2014) 'Estimating the advantages of lime in cement-based building mortars." Guimaraes, Portugal, 9th International Masonry Conference, pp. 1–9.
- [7] B. Muhit. Imrose., T. Raihan. Muhammad and Nuruzzaman. MD. (2014) "Determination of masonry mortar strength utilising stone dust as a partially replaced material for cement and sand," vol. 2, pp. 249–259.
- [8] Raihan. M. T. and Muhit. I. B. (2014) "Assessing the strength of masonry mortar by using stone dust as a cement and substituting materials" 2nd International Conference on Civil Engineering Advances. Chittagong University of Engineering and Technology (CUET), Bangladesh
- [9] A . Jadhav .priyanka and K. Kulkarni. Dilip (2013). "The effect of using synthetic sand instead of natural sand on the characteristics of cement masonry mortar." (2013). Civil and structural engineering is an international journal. Vol. 3, pp. 621–628. ISSN: 0976–4399.
- [10] Bashar Taha, GhassanNonnu "Utilizing waste recycled glass as a sand/cement replacement in concrete," ASCE Journal of Materials in Civil Engineering, vol. 21, No. 12 (December 2009), pp. 709-721.
- [11] FarshadRajabipour, HamedMaraghechi and Gregor Fischer "Investigating the Alkali- "Silica Reaction of Recycled Glass Aggregates in Concrete Materials," ASCE Journal of Materials in Civil Engineering, Vol. 22, No. 12, December 2010, pp. 1201-1208.
- [12] A.Bahurudeen, KaisarWani, Mirza Abdul Basit, and Manu Santhanam "Assessment of the pozzolanic performance of sugarcane bagasse ash," ASCE Journal of Materials in Civil Engineering, December 2015, pp 04015095. (11).
- [13] Maria Harja, MarinelaBarbuta and Irina Baran "Comparison of mechanical properties for polymer concrete with various types of filler," ASCE Journal of Materials in Civil Engineering, Vol. 22, No. 7, July 1, 2010, pp. 696-701.
- [14] Caijun Shi Journal of Materials in Civil Engineering, ASCE, Vol. 21, No. 10, October 1, 2009, pp 529-534, "Corrosion of glasses and expansion mechanism of concrete incorporating waste glasses as aggregates."
- [15] MohammadrezaMirzahosseini, Kyle A. Riding "The effect of combined particles on hydration in cementitious systems," ASCE Journal of Materials in Civil Engineering, August 18, 2014, pp 04014190. (13).
- [16] P.S Mane Deshmukh and R.Y. Mane Deshmukh International journal of science and research (IJSR), Vol. 3, December 12, 2014, pp 1457-1458, "Comparative study of waste glass powder utilised in concrete."
- [17] Dr. G. Vijayakumar, Ms H Vishaliny, Dr D. Govindarajulu "Studies on the use of glass powder as a partial replacement for cement in the making of concrete" Vol. 3, no. 2, February 2, 2013, pp. 153-157 in International Journal of Emerging Technology and Advanced Engineering.
- [18] Omoniyi T.E., Akinyemi B.A and Fowowe A.O. Scholars Journal of Engineering and Technology (SJET), 2014, pp 517-522, "Effects of Waste Glass Powder as PozzolanicMaterial in Saw Dust Cement Brick."
- [19] IS 1489-1981 (Part 1), Portland Pozzolana Cement Standard Specification in India.









45.98



IMPACT FACTOR: 7.129



IMPACT FACTOR: 7.429



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call: 08813907089 🕓 (24*7 Support on Whatsapp)