iJRASET
International Journal For Research in Applied Science and Engineering Technology



# INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

**Volume:** 10 **Issue:** III **Month of publication:** March 2022

**DOI:** https://doi.org/10.22214/ijraset.2022.40621

www.ijraset.com

Call: 08813907089 | E-mail ID: ijraset@gmail.com

International Journal for Research in Applied Science & Engineering Technology (IJRASET)
*ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538*
*Volume 10 Issue III Mar 2022- Available at www.ijraset.com*

# Dielectric Properties of $Pb(Fe_{0.5}Nb_{0.5})O_3$ (PFN) Material Synthesized by B-site Precursor Method

V. Rathod
*Government College Autonomous Kalaburagi*

***Abstract:*** ***B-site precursor method was employed for the synthesis of $Pb(Fe_{0.5}Nb_{0.5})O_3$ (PFN) Ceramic material. Formation of Perovskite was confirmed by XRD. Study of electrical and dielectric properties were carried out. The increase in dielectric loss and decrease in ac resistivity was observed at higher temperature.***
***Keywords: Perovskite, XRD, B-site precursor, AC conductivity, Dielectric constant.***

## I. INTRODUCTION

Relaxor ferroelectrics are a class of ferroelectrics that have a diffuse permittivity maximum, which is frequency- dependent [1,2]. For many practical applications, a very broad permittivity maximum is desirable. Lead iron niobate [Pb ($Fe_{1/2}$ $Nb_{1/2}$)$O_3$: PFN] is one of the family of lead-based complex perovskites which is of interest as a component in commercial electro ceramic materials. High relative permittivities and low sintering temperatures typically characterize it. Work by Lejeune and Boilot [3] has indicated that PFN is formed indirectly via a sequence of intermediates, some of these being lead niobium oxide pyrochlores. It was also proposed that formation of a perovskite PFN phase requires a high reactivity of ferric oxide, $Fe_2O_3$, with other phases in the PbO-$NbO_3$ system.

Alkaline-earth titanates such as $BaTiO_3$, $SrTiO_3$, and $CaTiO_3$ are traditionally used for electronic devices [4]. Because the temperatures required to sinter these materials are generally higher than 1300°C in air [5], expensive noble metals such as palladium, platinum, or their alloys are needed as internal electrode materials. Extensive research has been carried out on dielectric materials that can be sintered at temperatures around 1000°C such that inexpensive electrodes (e.g., silver or silver-palladium) can be utilized [6]. It was reported that perovskite solid solutions based on lead ferroniobate $Pb(Fe_{1/2}Nb_{1/2})O_3$ are ideal candidates for fabricating multiplayer ceramic capacitors with inexpensive electrodes, since they have relatively low sintering temperatures around 900° to 950°C [7]. In addition, these compositions show very high dielectric constants > 20000 providing the possibility for further miniaturization of the multilayer capacitors [8].

## II. MEASUREMENT TECHNIQUE

### *A. Sample Preparation*

The B-site precusor method [9] was employed for the preparation of the Lead Iron Niobate (PFN) ceramic studied here. The detailed procedureemployed for the synthesis of PFN ceramic is described elsewhere [10]. The samples of PFN ceramics were previously characterized in detail by X-ray diffraction, TG-DTA and SEM[10]. The measured XRD patterns are presented in Fig 1.PFN perovskite formation was confirmed from the XRD pattern.





Fig 1. XRD for PFN Perovskite.

©IJRASET: All Rights are Reserved | SJ Impact Factor 7.538 | ISRA Journal Impact Factor 7.894 |

### *B. Dielectric Measurements*

For dielectric measurements, the sintered pellets were polished with $Al_2O_3$ powder (particle size: 1µm) and cleaned using ultrasonic cleaner. The samples were electroded by sputtering gold and then applying air-drying silver paste on the top. By studying their I-V characteristics we could check the ohmic nature of the contacts.

Capacitance and dielectric loss (tan δ) were measured using HP 4194A, impedance/ gain phase analyzer in the frequency range of 100 Hz- 1 MHz. The temperature of the sample was varied from 27°C to 600°C using variable sample holder. The dielectric constant was then calculated from the capacitance and the physical dimensions (area of the electroded portion and the thickness) of the sample. The data was collected during the heating and cooling cycle; however, data collected during heating and cooling cycles were found to match.

## III. RESULT AND DISCUSSION

### *A. Dielectric Properties*

The temperature dependence of dielectric constant for PFN at various frequencies are plotted in Fig 2. At low frequency (100Hz), a broad peak can be found at about $T_c$ =118°C. This is in agreement with the literature value. PFN exhibit typical characteristics of diffuse phase transition, which is in agreement with Sun-Gon Jun [11] and N.S. Almodovar et.al,.[12]. The temperature dependence of dielectric loss for PFN at various frequencies is plotted in Fig 3. The dielectric loss increases at higher temperatures.

### *B. AC Resistivity*

The temperature dependence of AC resistivity at various frequencies are plotted in Fig 4. It is clear that, at low frequency a broad peak at 60°C was observed. AC resistivity decreases at higher temperatures and is almost constant. Decrease in AC resistivity indicates the increase in AC conductivity at higher temperatures. This increase in conductivity at higher temperature causes the increase in dielectric loss as confirmed from Fig 4. The values of dielectric constant and dielectric loss for PFN at various frequencies at $T_c$ are summarized in Table 1.

Table No 1. Dielectric constant and dielectric loss for PFN

| Frequency | Dielectric constant | Dielectric loss |
|---|---|---|
| 100 Hz | 56063 | 0.89 |
| 1 KHz | 35483 | 0.40 |
| 10 KHz | 28984 | 0.10 |
| 100 KHz | 27088 | 0.01 |





Fig 2.Plot for temperature dependence of dielectric constant at various frequencies for PFN.





Fig 3. Plot for temperature dependence of dielectric loss at various frequencies for PFN.





Fig 4. Plot for temperature dependence of AC-Resistivity at various frequencies for PFN.

## IV. CONCLUSION

The temperature dependence of dielectric constant showed that the paraelectric to ferroelectric transition in PFN at 118°C is diffusive in character, which is caused by the redistribution of $Fe^{3+}$ and $Nb^{5+}$ ions in B-site of $ABO_3$ compound. The dielectric loss is observed to increase at higher temperatures. AC resistivity decreases with temperature indicative of an increase in AC conductivity at higher temperatures and is confirmed by high values of dielectric losses at such high temperatures. The possibility of sintering PFN at low temperatures allows the usage of gold and silver paste as electroding material. PFN ceramics are potential materials for ferroelectric memory and high dielectric constant applications.

## REFERENCES

[1] M.E.Lines and A.M.Glass, “Principles and Applications of Ferroelectrics and Related Materials”, Oxferd Press, 1977.
[2] G.A.Smolenskii, V.A.Bokov, V.A.Isopov, N.N.Krainik, R.E.Pasynkov, and A.I.Sokolov., Ferroelectrics and Related Materials. Gordon and Breach, New York, 1984.
[3] M.Lejeune, and J.P.Boilot, Ceram.Inter, **8** 99-103, 1982.
[4] Y.Shimada, K.Utsumi, M.Yonezawa, and H.Takamizawa, Jpn.J.Appl.Phys. Suppl., **20** 143,1981.
[5] W.Heywang, J.Am.Ceram.Soc. **47** 484, 1964.
[6] W.R.Bussem and T.I.Prokopowicz, Ferroelectrics, **10** 225, 1976.
[7] M.Halmi, G.Desgardin, and B.Raveav, Mater.Lett. **5** 103, 1987.
[8] S.A.Mabud, Phase Transitions, **4** 183, 1984.
[9] Bong-Ho Lee, Nam-Kyoung Kim, Je0ng-Joo Kim and Sang-Hee Cho, Ferroelectrics, 211, 233-247, 1998.
[10] V. Rathod, “Synthesis and the Study of Mechanism of Perovskite Formation of $Pb(Fe_{1/2}Nb_{1/2})O_3$ Ceramics, IJRASET, 10, 432-437, 2022.
[11] S-G Jun, N-K Kim, J-J Kim and S-H Cho, Mater. Lett., 34, 1998.
[12] N.S. Almoodovar, R. Font, J, Portelles, O, Raymond, E. Martinez, J.M. Siqueiros, “Preparation and characterization of 0.5PMN-0.5PFN ceramics using $[Fe_{0.6}, Mg_{0.4}]O_4$ as precursor, J. of Mat. Sci., 38, 2003.

*ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538*
*Volume 10 Issue III Mar 2022- Available at www.ijraset.com*


**ABOUT THE AUTHOR**

Dr. VinodkumarRathod is currently working as Assistant Professor of Physics at Government College (Autonomous) Kalaburagi. He has about 20 years of teaching experience including Undergraduate and Post graduate. He served as Chairman Department of Physics in GFGC Shahapur and Government College Kalaburagi. He Served as Chaiman and Member of BOS and BOE (UG&PG) at Government College (Autonomous) Kalaburagi and BOE member at Gulbarga University Kalaburagi. He has published many Research articles in National and International Journals and presented Research papers in Regional, National Seminars. Completed one UGC Research Project.



Dr. Vinodkumar Rathod
E-mail: vinodkumarsrathod@gmail.com
Cell: +91 9448586111

©IJRASET: All Rights are Reserved 



10.22214/IJRASET

45.98

IMPACT FACTOR: 7.129

IMPACT FACTOR: 7.429

# INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089 (24*7 Support on Whatsapp)