



IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 10 Issue: IV Month of publication: April 2022

DOI: https://doi.org/10.22214/ijraset.2022.41436

www.ijraset.com

Call: 🕥 08813907089 🔰 E-mail ID: ijraset@gmail.com



Nitin Gotkhindikar¹, Parshwa Mehta², Shrutika Londhe³, Anushka Kulkarni⁴, Maithili Rekhe⁵ ^{1, 2, 3,} 4, 5All India Shri Shivaji Memorial Society College of Engineering Pune

Abstract: Fused Deposit modeling (FDM) is an additive manufacturing (AM) process that's frequently used to fabricate geometrically complex shaped prototypes and complex parts. It's gaining market as it reduces cycle time for product development without the need for high priced tools. Still, the commercialization of FDM technology in other artificial operations is presently limited due to several failings, alike as inadequate mechanical properties, poor surface quality, and low dimensional accuracy. The rates of FDM- produced products are affected by other process parameters, for illustration, layer thickness, build angle, raster width, or print speed. The process parameters and their range depends on the section of FDM machines. Filament materials, nozzle dimensions, and the type of machine determine the range of other parameters. The optimum setting of parameters is supposed to ameliorate the rates of three-dimensional (3D) printed specimens and may reducepost-production work. This paper intensely reviews state-of-the- art literature on the influence of parameters on part qualities and the being work on process parameter optimization. Also, the failings of being workshop are linked, challenges and openings to work in this field are suggested

Keywords: Fused deposition modelling; process parameters; part characteristics; optimization.

I. INTRODUCTION

The commercialization of FDM technology in various industrial applications is currently limited due to several shortcomings, like insufficient mechanical properties, poor surface quality, and low dimensional accuracy. The qualities of FDM-produced products are stricken by various process parameters, for example, layer thickness, build orientation, raster width, or print speed. The process parameters and their range depends on the section of FDM machines [4]. Filament materials, nozzle dimensions, and so the factors of the machine determine the range of varied parameters. The optimum setting of parameters is deemed to reinforce the qualities of three-dimensional (3D) printed parts and will reduce post-production work. Due to the unique advancement, the AM framework has grown widely in many real-time applications. So, the function of the AM process FDM was often used, considering the other approaches FDM has a low price and is straightforward to use. But in several strategies, this method suffered a lot because of its complex design and fewer prediction measure [2]. So, to bolster the AM mechanism an optimized deep neural model is planned to implement to maximize the defeat detection rate and designed object behaviour.

II. EXPERIMENTAL PROCEDURE

.Polylactic acid also known as (PLA) is a thermoplastic monomer derived from renewable, organic sources such as starch and sugarcane Formula : $(C_3H_4O_2)_n$ The basic properties of PLA are given below in comparison with ABS material

PLA is used shrink-wrap material as it constricts under heat. It is green material, uses 65% less energy than ABS and it is in toxic.PLA is popular for 3D printing as it can easily be sanded, painted, post-processed. A user-friendly material, this plastic works with low extrusion temperatures and there is no need for a heated bed, printer chamber, or a reinforced nozzle. Reason for selecting PLA over ABS is mentioned below in the form of comparison.<u>Fig1. [1]</u>

Property	PLA	ABS	
Printing temperature (°C)	180-230	210-250	
Build platform temperature (°C)	20-60	80-110	
Raft	Optional	Mandatory	
Strength	High	Medium	
Flexibility	Brittle	Moderately flexible	
Heat resistance	Low	Moderate	
Biodegradability	Yes	No	
Moisture absorption	Yes	Yes	

Fi	g1.	Com	oarison	of I	PLA	and	ABS	materia	ıl
	ω								



International Journal for Research in Applied Science & Engineering Technology (IJRASET) ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 10 Issue IV Apr 2022- Available at www.ijraset.com

A. Methodology

The Taguchi approach is used for experimental design. Solidworks 2020 is used for developing CAD model and conversion to .STL format. After that Cura ultimaker 2020 is used as a stimulator of sample fabrication process [3-9]. The extrusion based additive manufacturing technology utilizes and produces test specimens. The compressive and tensile tests are performed on universal testing machine (UTM). The acquired data is further used for statistical analysis and model development. Based on Taguchi approach array has been created. The parameters used are print speed (mm/sec), distance from each point (mm), layer thickness (mm), and nozzle diameter (mm). Some authors studied the effect of layer thickness on elastic properties of PLA material.

B. Procedure

The basic steps procedure is given below in the form of flow chart. Fig2. [7]



Fig2. Procedure for sample fabrication

The modelling part has been carried out by using Solidworks 2020 and then converted into .STL format. After this, .STL format is sliced in Cura ultimaker software using parameters such as speed (mm/sec), distance from each point (mm), layer thickness (mm), and nozzle diameter (mm).The dimension of testing specimen is set according to American Society for Testing and Measurements (ASTM). Four infill parameters with three levels are been selected for analysis. These parameters are selected as they produce lightweight and strong parts. In this study the four variable parameters are speed (mm/sec), distance from each point (mm), layer thickness (mm), and nozzle diameter (mm) and their variable levels are as follows. Table1. [10-15]

Factor	Level 1	Level 2	Level 3		
Print speed(mm/s)	40	60	80		
Distance from each print line(mm)	0.3	0.5	0.7		
Layer thicknss(mm)	0.1	0.2	0.3		
Nozzle diameter(mm)	0.4	0.4	0.4		

Table1. Parameters of	fabrication.
-----------------------	--------------

1) Manufacturing

There are five steps in manufacturing in Cura Ultimate 2020





International Journal for Research in Applied Science & Engineering Technology (IJRASET)

ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 10 Issue IV Apr 2022- Available at www.ijraset.com



Fig4. FDM machine D 300

The specimen is fabricated using the above steps and then subjected to physical measurement and mechanical testing. The machine used for fabrication is: D 300 3DeoMetry Make: Build 300 X 300 and testing machine is UNITEK 94100, Tensile testing Machine: ASTM 638 (type IV), Universal Testing Machine: Zwick Type (1474): ASTM D695



Fig5. FDM G codes



Fig6. FDM G codes



Fig7. Fabricated parts and CAD Model



2) Experimental Results

Sr No	Print	Distance from each	Laver	Nozzle	Tensile	Compressive
51110	speed(mm/s)	print line (mm)	thickness	diameter	strength	strength
	1		(mm)	(mm)	(MPa)	(MPa)
1	40	0.3	0.1	0.4	34.871	29.980
2	40	0.3	0.2	0.4	34.871	29.700
3	40	0.3	0.3	0.4	38.153	31.000
4	40	0.5	0.1	0.4	34.051	28.578
5	40	0.5	0.2	0.4	34.871	29.652
6	40	0.5	0.3	0.4	34.871	29.789
7	40	0.7	0.1	0.4	33.641	28.231
8	40	0.7	0.2	0.4	32.821	27.976
9	40	0.7	0.3	0.4	37.333	30.855
10	60	0.3	0.1	0.4	33.230	28.000
11	60	0.3	0.2	0.4	32.820	27.435
12	60	0.3	0.3	0.4	32.820	26.899
13	60	0.5	0.1	0.4	33.641	27.200
14	60	0.5	0.2	0.4	34.051	28.999
15	60	0.5	0.3	0.4	30.769	23.800
16	60	0.7	0.1	0.4	34.871	28.999
17	60	0.7	0.2	0.4	35.692	30.528
18	60	0.7	0.3	0.4	30.769	23.750
19	80	0.3	0.1	0.4	35.282	29.989
20	80	0.3	0.2	0.4	34.461	29.654
21	80	0.3	0.3	0.4	30.769	23.981
22	80	0.5	0.1	0.4	34.051	28.888
23	80	0.5	0.2	0.4	32.000	26.333
24	80	0.5	0.3	0.4	33.230	26.752
25	80	0.7	0.1	0.4	31.589	25.632
26	80	0.7	0.2	0.4	30.769	24.000
27	80	0.7	0.3	0.4	30.358	23.600

Table2. Experiment results



International Journal for Research in Applied Science & Engineering Technology (IJRASET) ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538

Volume 10 Issue IV Apr 2022- Available at www.ijraset.com

C. Statistical Model and Multi Objective Optimization

The experimental results developed are further considered for optimization of process parameters. The generated model of material strength and material consumption helps to decide the process parameters.

The algorithm is obtained from Matlab software 2019. This study focuses on simultaneous maximization of mechanical strength and minimization of material consumption. The outline of the basic algorithm for optimization used in Matlab is given below

```
Algorithm.1 proposed SMbDBNS
           Input: Nozzle design parameters
Start
           Initialization
           {
                 Int P_{s_1}, P_1, L_1, L_d, \pi^* \Rightarrow I_v
                 // here, I_v is the input variable
           }
           Neural layers training
                 T' = I_{v}
           Layer thickness
              \pi^* = nL
              // here, nL is the number of layers
           Lateral displacement
              q(a,b) = each \ layers \ of the \ nozzle
           Evaluate start and end point printing line
              Find starting point printing line
                    SM_{starting} = line \Rightarrow Nozzle layers
                                                                    // local leader fitness
              Find ending pint printing line
                    SM_{ending} line \Rightarrow Nozzle layers
                                                                   // global leader fitness
              3D printing process
                       Fault detection based on SM starting _ line , SM ending _ line
              Continuously monitor the connection status
Stop
           Output: finest solution
```

Fig8. Proposed Algorithm

International Journal for Research in Applied Science & Engineering Technology (IJRASET)



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 10 Issue IV Apr 2022- Available at www.ijraset.com

III. RESULT AND DISCUSSION

The results have been represented in Table2, which shows tensile and compressive strengths for different parameters.

A. Prediction Accuracy and Overflow Rate

A correctly predicted printing line is defined as prediction accuracy. Moreover, accuracy is calculated in the ratio of accurate prediction printing lines to the overall printing lines. In the nozzle design primarily find the starting and ending point of the printing line then only easily predict the mismatch printing line.



a) Prediction accuracy of proposed b) Overflow rate of proposed SMbDBNS SMbDBNS



The accuracy of the proposed method is represented in <u>Fig9</u>. The representation demonstrates that the projected method has attained 95% accuracy for 250 epochs. The flow rate of nozzle is defined as the measure of nozzle diameter and differential pressure at the closed pipe. Moreover, the calculation of overflow rate is mentioned.

Moreover, the overflow rate of proposed SMBDBNS is demonstrated in <u>Fig9</u>. During the printing process, the overflow rate is increased based on the samples.







B. Tensile and Compressive strength

Tensile strength is the capacity of a material, for example, pressure to oppose disappointment under bowing pressure which can be assessed by coordinating to three- or four-points twisting elasticity test. We have found out the Tensile strength of various parameters and plotted the graph against strain value.



Fig11. Graph of tensile strength v/s strain.

IV. CONCLUSIONS

- A. The present study depicts the potentials of optimum process conditions inspired by natural configuration. The experiment and multi-objective optimization approach implemented to investigate the influence of process parameters.
- *B.* Print speed of 40mm/s and layer thickness of 0.3mm provides highest tensile and compressive strength among all selected combinations of parameters.
- *C.* The relationship between two selected objectives with respect to their parameters also established through SMBDBNS. The SMBDBNS can help to get maximum mechanical strength with optimized parameters. The present work can be extended to analyze mechanical properties other than analyzed with similar process conditions

V. ACKNOWLEDGEMENTS

I would like to thanks to AISSMS College of Engineering Pune for constantly encouragement and guidance to perform this research work, and also 3-Deometry solutions Pune for fabrication work and Matlabs India.ltd Pune for their contribution in testing the specimens.

REFERENCES

- [2] D. Popescu, A. Zapciu, C. Amza, F. Baciu, R. Marinescu, FDM process parameters influence over the mechanical properties of polymer specimens: a review, Polym. Test. 69 (2018) 157–166.
- [3] O. Ahmed, S. Hasan, J. Lal, Optimization of fused deposition modeling process parameters for dimensional accuracy using I-optimality criterion, Measurement 81 (2016) 174–196.
- [4] Z. Luo, F. Yang, Orientation optimization in layer-based additive manufacturing process, in: Proceedings of the ASME 2016 International Design Engineering Technical Conferences and Computers and Information in Engineering Conference IDETC/CIE, Charlotte, North Carolina, 2016, pp. 1– 10.
- [5] B. Ezair, F. Massarwi, G. Elber, Orientation analysis of 3D objects toward minimal support volume in 3D-printing, Comput. Graph 51 (2015) 117–124.
- [6] H.S. Byun, K.H. Lee, Determination of the optimal part orientation in layered manufacturing using a genetic algorithm, Int. J. Prod. Res. 43 (2005) 2709–2724.
- [7] S. Magar, N.K. Khedkar, S. Kumar, Review of the effect of built orientation on mechanical properties of metal-plastic composite parts fabricated by additive manufacturing technique, Mater. Today Proc. 5 (2018) 3926–3935.
- [8] P. Alexander, S. Allen, D. Dutta, Part orientation and build cost determination in layered manufacturing, CAD Comput. Aided Des. 30 (1998) 343–356.
- [9] R. Hernandez, D. Slaughter, D. Whaley, J. Tate, B. Asiabanpour, Analyzing the tensile, compressive, and flexural properties of 3D printed ABS P430 plastic based on printing orientation using fused deposition modeling, (2016) 939–950.
- [10] M. Taufik, P.K. Jain, Role of build orientation in layered manufacturing: a review Mohammad Taufik* and Prashant K. Jain, Int. J. Manuf. Technol. Manag. 27 (2013) 47–73.
- [11] K. Thrimurthulu, P.M. Pandey, N.V. Reddy, Optimum part deposition orientation in fused deposition modeling, Int. J. Mach. Tools Manuf. 44 (2004) 585–594.
- [12] O.A. Mohamed, S.H. Masood, J.L. Bhowmik, Optimization of fused deposition modeling process parameters: a review of current research and future prospects, Adv. Manuf. 3 (2015) 42–53.
 - ©IJRASET: All Rights are Reserved | SJ Impact Factor 7.538 | ISRA Journal Impact Factor 7.894 |

International Journal for Research in Applied Science & Engineering Technology (IJRASET)



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538

Volume 10 Issue IV Apr 2022- Available at www.ijraset.com

- [13] B.H. Lee, J. Abdullah, Z.A. Khan, Optimization of rapid prototyping parameters for production of flexible ABS object, J. Mater. Process. Technol. 169 (2005) 54–61.
- [14] S. Ziemian, M. Okwara, C.W. Ziemian, S. Ziemian, M. Okwara, C.W. Ziemian, Tensile and fatigue behavior of layered acrylonitrile butadiene styrene, Rapid Prototyp. J. 21 (2015) 270–278.
- [15] C.M. González-henríquez, M.A. Sarabia-vallejos, J. Rodriguez-hernandez, Progress in polymer science polymers for additive manufacturing and 4Dprinting: materials, methodologies, and biomedical applications, Prog. Polym. Sci. 94 (2019) 57–116.
- [16] R. Lippert, Bastian, Lachmayer, A design method for restriction oriented lightweight design by using selective laser melting, in: 21st International Conference on Engineering Design, ICED17, The University of British Columbia, Vancouver, Canada, 5, 2017, pp. 1–10.
- [17] P.J. Baikerikar, C.J. Turner, Comparison of as-built FEA simulations and experimental results for additively manufactured dogbone geometries, Int. Design Eng. Tech. Conf. Comput. Information Eng. Conf. IDETC/CIE 2017 (2017) 1–14.
- [18] D. Farbman, C. Mccoy, Materials Testing of 3D Printed ABS and PLA Samples to Guide Mechanical MSEC2016-8668, 2017.
- [19] C. Emmelmann, M. Petersen, J. Kranz, Bionic lightweight design by laser additive manufacturing (LAM) for aircraft industry, in: SPIE Eco-Photonics, Strasbourg, France, 2019.
- [20] S. Rathee, M. Srivastava, S. Maheshwari, A. Noor, Effect of varying spatial orientations on build time requirements for FDM process: a case study, Def. Technol. 13 (2017) 92–100.
- [21] M. Vishwas, C.K. Basavaraj, M. Vinyas, Experimental investigation using taguchi method to optimize process parameters of fused deposition modeling for ABS and nylon materials, Mater. Today Proc. 5 (2018) 7106–7114.
- [22] F. Ma, H. Zhang, K.K.B. Hon, Q. Gong, An optimization approach of selective laser sintering considering energy consumption and material cost, J. Clean. Prod. (2018).











45.98



IMPACT FACTOR: 7.129







INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089 🕓 (24*7 Support on Whatsapp)