



iJRASET

International Journal For Research in
Applied Science and Engineering Technology



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 10 Issue: VII Month of publication: July 2022

DOI: <https://doi.org/10.22214/ijraset.2022.45786>

www.ijraset.com

Call:  08813907089

E-mail ID: ijraset@gmail.com

Fiber Reinforced Concrete Using Coconut Shell

Lohit Kumar Mahanta¹, Abhijit Mangaraj², Surajit Pattnaik³

¹Affiliated to Biju Patnaik University of Technology

²Affiliated to Biju Patnaik University of Technology

³Affiliated to Biju Patnaik University of Technology

Abstract: Coconut shell as aggregate in concrete production not only solves the problem of disposing this solid waste but also helps conserve natural resources. In this paper, the physical properties of crushed coconut shell aggregate were presented. The fresh concrete properties such as density and 28-days compressive strength of a lightweight concrete made with coconut shell as coarse aggregate also presented. The findings indicated that water absorption of the coconut shell aggregate was high about 24 % but the crushing value and impact value was comparable to that of other lightweight aggregates. The average fresh concrete density and 28-day cube compressive strength of the concrete using coconut shell aggregate were 1975 kg/m³ and 19.1 N/mm² respectively. It is concluded that crushed coconut shells are suitable when it is used as substitute for conventional aggregates in lightweight concrete production.

Keywords: Lightweight aggregate, Agriculture waste, Coconut shell, Physical properties, Compressive strength.

I. INTRODUCTION

Normal concrete contains four components, cement, crushed stone, river sand and water. The crushed stone and sand are the components that are usually replaced with lightweight aggregates. Lightweight concrete is typically made by incorporating natural or synthetic light weight aggregates or by entraining air into a concrete mixture. Some of the lightweight aggregates used for lightweight concrete productions are pumice, perlite, expanded clay or vermiculite, coal slag, sintered fly ash, rice husk, straw, sawdust, cork granules, wheat husk, oil palm shell, and coconut shell. Following a rapid growth in population, the amount and type of waste materials have increased accordingly creating environmental problems. Different alternative waste materials and industrial by products such as fly ash, bottom ash, recycled aggregates, foundry sand, china clay sand, crumb rubber etc were replaced with natural aggregates.

A. Problem Statement

- 1) Large scale cultivation of coconut in coastal regions of India including Kerala, Andhra Pradesh, Goa, Tamil Nadu, Odisha etc.
- 2) After the kernel is consumed, the shell is thrown away here and there causing environmental pollution.
- 3) Due to its tough made tissue, the shell is not decomposed easily and remains as solid waste for years. Hence utilizing it in a proper manner reduces environmental problems.

II. LITERATURE REVIEW

Kulkarni P. Vishwas and Gaikwad Sanjay kumar B. (2013) have made a comparative study on coconut shell aggregate with conventional concrete and concluded that coconut shell aggregate concrete has a low modulus of elasticity.

Shelke et al; (2014) have reviewed coconut shell as partial replacement for coarse aggregate and they made the following inference that the increase in percentage of coconut shell decreased with density of concrete. With the increase in the percentage of coconut shell, the strength of 7 days curing increased with the corresponding 28 days curing strength. Coconut shell is most suitable and compatible with the cement. The 28 days air dry density of coconut shell aggregates is less than 2000 kg/m³ and this is within the structural light weight concrete. Coconut shell aggregates satisfies the requirements of ASTM C 330.

Kambli Parag S. and Mathapati Sandhya R. (2014) have studied the application of coconut shell in concrete and arrived at the following conclusions i.e. coconut shell has potential as light weight aggregate in concrete. It can be used where conventional aggregates are costly.

Rao et al; (2015) have studied the strength properties of coconut shell concrete and arrived at the following conclusions that addition of coconut shell aggregate alone decreases the workability of concrete. Increase in coconut shell percentage decreased densities of concrete.

Presently in India, about 960 million tones of solid wastes are being generated annually as by-products during industrial, mining, municipal, agricultural and other processes. Of this 350 million tonnes are organic wastes from agricultural sources; 290 million tones are inorganic waste of industrial and mining sectors. However, it is reported that about 600 MT of wastes have been generated in India from agricultural sources alone.

III. SCOPE OF WORK

The scope of this work is limited to the following:

- 1) To determine the optimum percentage replacement of the coconut shell in concrete without compromising the strength.
- 2) The mechanical properties of coconut shell.
- 3) Test of the compressive strength of coconut shell concrete.
- 4) The engineering properties of other aggregates used in the concrete (stone and fine aggregate)
- 5) The chemical properties of the binder used (ordinary Portland Test of compressive strength of cubes with partial replacement of normal
- 6) Stone aggregate with coconut shell.

IV. AIM AND OBJECTIVE OF THE STUDY

The aim of this research is to investigate the use of coconut shell as coarse aggregate in concrete, through:

- 1) Characterization of the materials used for the works.
- 2) Experimental determination of the mechanical properties of the concrete.

V. MATERIALS USED

A. Coconut Shell

Coconut shell is one of the by-products from the processing of coconut, it is organic in nature and similar to hard woods in chemical composition though lign in content is higher and cellulose content is lower

Table 5.1 . COCONUT SHELL COMPOUND

| COCONUT SHELL COMPOUND | |
|------------------------|-------------|
| COMPOUND | PERCENT (%) |
| CELLULOSE | 33.61 |
| LIGNIN | 36.51 |
| PENTOSANS | 29.27 |
| ASH | 0.61 |

VI. EXPERIMENTS AND RESULTS

A. Soundness of Cement Test

The soundness test for the brand of ordinary Portland cement used was conducted using the „Le Chatelier“ method of measuring expansion in accordance to NIS 447(2003) and BS 4550 (1978). The results of the soundness tests are presented in table.

Table 3.1: Soundness test results of ordinary Portland cement used.

| OPC samples | Average Expansion (mm) | Total average Expansion |
|-------------|------------------------|-------------------------|
| Specimen A | 4.80 | 4.78 |
| Specimen B | 4.75 | |
| Specimen C | 4.80 | |

B. Fineness Test of the OPC used

The test was carried out in accordance with BS 12 (1991) and NIS 448, (2003). The test results are presented in table

Table 6.2. The test was performed using the Blaine air permeability

| OPC Samples | Specific surface area | Average Specific surface |
|-------------|-----------------------|--------------------------|
| Sample A | 658 | 658 |
| Sample B | 659 | |
| Sample C | 657 | |

C. Initial and Final setting time for the OPC used

| Samples Of OPC | Average initial setting time | Overall average initial setting time (mins) | Average final setting time | Overall average initial setting time (mins) |
|----------------|------------------------------|---|----------------------------|---|
| Sample | 1hr. 42mins | 1hr.45mins | 3hrs. 02mins | 3hrs.05mins |
| Sample | 1hr. 45mins | | 3hrs. 08mins | |
| Sample | 1hr. 48 mins | | 3hrs.05mins | |

D. Chemical Composition test of the OPC used.

Table 6.4. Composition of cement

| Sl/no | Oxide composition | Percentage of oxide composition |
|-------|--------------------------------|---------------------------------|
| 1. | CaO | 65.22 |
| 2. | SiO ₂ | 21.55 |
| 3. | Al ₂ O ₃ | 5.28 |
| 4. | Fe ₂ O ₃ | 3.95 |
| 5. | MgO | 1.85 |
| 6. | SO ₃ | 1.50 |
| 7. | Loss of Ignition | 1.44 |
| 8. | Insoluble residue | 0.65 |
| | TOTAL | 100.00 |



Fig 6. Machine crushed Coconut shell aggregate.

E. Coconut shell Aggregate Impact Value

Table 6.5. impact value test

| Samples | Aggregate impact value % | Average aggregate impact value % |
|---------|--------------------------|----------------------------------|
| A1 | 1.32 | 1.33 |
| A2 | 1.31 | |
| A3 | 1.33 | |
| B1 | 1.29 | 1.29 |
| B2 | 1.30 | |
| B3 | 1.29 | |
| C1 | 1.31 | 1.30 |
| C2 | 1.30 | |
| C3 | 1.29 | |

Table 6.6: Coconut shell aggregate crushing value

| Samples | Single aggregate size (mm) | Aggregate crushing value | Average aggregate crushing value % |
|---------|----------------------------|--------------------------|------------------------------------|
| A1 | 10mm | 1.159 | 1.156 |
| A2 | 10mm | 1.158 | |
| A3 | 10mm | 1.153 | |
| B1 | 10mm | 1.169 | 1.162 |
| B2 | 10mm | 1.158 | |
| B3 | 10mm | 1.160 | |
| C1 | 10mm | 1.158 | 1.157 |
| C2 | 10mm | 1.154 | |
| C3 | 10mm | 1.159 | |

VII. MATERIAL PROPORTIONING AND PREPARATION OF MIX

Table 7.1. Material proportion for the various mix ratios (coconut shell concrete)

| sl/no | mix ratio | w/c ratio | agg/c ratio | Cement kg/m ³ | Fine Agg kg/m ³ | Coconut Shell aggregate kg/m ³ |
|-------|-----------|-----------|-------------|-----------------------------|-------------------------------|--|
| 1. | 1:1:1 | 0.5 | 2.0 | 425 | 425 | 425 |
| 2. | 1:2:2 | 0.5 | 2.0 | 424 | 849 | 849 |

A. Compressive Strength Result

Table 7.1. Compressive strength of specimens

| Replacement % | Average compressive strength N/mm ² at the different age of test | | | | |
|---------------|---|-------|--------|--------|--------|
| | 3 day | 7 day | 14 day | 21 day | 28 day |
| 0% | 8.10 | 17.00 | 21.00 | 24.00 | 27.00 |
| 25% | 6.90 | 14.00 | 18.00 | 20.00 | 23.00 |
| 50% | 6.00 | 12.00 | 14.00 | 16.00 | 20.00 |
| 75% | 5.10 | 11.00 | 12.00 | 15.00 | 17.00 |
| 100% | 4.50 | 10.00 | 11.00 | 14.00 | 15.00 |

VIII. RESULTS AND DISCUSSION

- 1) The average moisture content and water absorption of the crushed coconut shell was found to be 4.20 % and 24.00 % respectively.
- 2) The slump obtained for the trial mix was 55 mm, which has showed that CS concrete has a medium degree of workability. The fresh concrete density and 28-day hardened concrete density (under SSD condition) using coconut shell were found to be in the range between 1975 - 2110 kg/m³ and 1880 - 1930 kg/m³ respectively.
- 3) The 28-day compressive strength of the concrete using coconut shell aggregate was found to be 19.1 N/mm² under full water curing. The compressive strength of concrete using coconut shell coarse aggregate was more than 17.2 N/mm², which is a requirement for structural lightweight concrete.

REFERENCES

- [1] Basri H.B. et al (1999), "Concrete using waste oil palm shells as aggregate", International Journal of Cement and Concrete research, pp 619-622.
- [2] Joseph Khedari et al (2001), "New lightweight composite construction materials with low thermal conductivity" International Journal of Cement & Concrete Composites, 65-70.
- [3] Mannan.M.A. and Ganapathy.C (2002), "Engineering properties of concrete with oil palm shell as coarse aggregate", International Journal of Construction and Building Materials, pp 29-34.
- [4] Loehr RC (1984), "Pollution Control of agriculture", 2 nd edition, Orlando, FL: Academic Press: 1984.
- [5] Asokan Pappu (2007), "Solid wastes generation in India and their recycling potential in building materials", International Journal of Building and Environment 42 (2007), pp 2311-2320.
- [6] Martirena J.F. (1998), "Use of Wastes of the Sugar Industry as Pozzolana In Lime-Pozzolana Binders: Study of The Reaction", International Journal of Cement and Concrete Research, Vol. 28, No. 11, pp. 1525-1536, 1998.
- [7] Medjo Eko, R. and G. Riskowski.(1999), "A Procedure for Processing Mixtures of Soil, Cement, and Sugar Cane Bagasse". Agricultural Engineering International: the CIGR Journal of Scientific Research and Development. Manuscript BC 99 001. Vol. III
- [8] Turgut Ozturk and Muzaffer bayrakl (2005), "The possibilities of using Tobacco waste in producing Light Weight Concrete", Agricultural Engineering International: the CIGR Ejournal, Vol. VII. Manuscript BC 05 006. August, 2005.
- [9] Alabadian B.A. (2006), et al "The potentials of Groundnut shell ash as concrete admixtures", Agricultural Engineering International: the CIGR Ejournal, Vol. VIII. Manuscript BC 05 012. February, 2006.
- [10] Demirbas.A. and Aslan.A.(1998), "Effects of Ground Hazelnut Shell, Wood, and Tea Waste On the Mechanical Properties of Cement", International Journal of Cement and Concrete Research, Vol. 28, No. 8, pp. 1101-1104O



- [11] Ianipekun E.A.(2006) et al, "A comparative study of concrete properties using coconut shell and palm kernel shell as coarse aggregates", International Journal of Building and Environment 41 (2006) 297–301.
- [12] Mindess.S. and Young.J.F. (1981), "Concrete", Prentice-Hall, Englewood Cliffs, NJ, 981.
- [13] Mannan M.A. and C. Ganapathy (2001), "Mix design for oil palm shell concrete", International Journal of Cement and Concrete Research 31 (2001) 1323–1325.
- [14] Paramasivam. P. and Loke. Y. O. (1980), "Study of saw dust concrete", The International Journal of Lightweight Concrete. Vol 2, No 1, pp 57-61, 1980 .-
- [15] Neville A.M (2005)., "Properties of concrete", Fourth and final edition, Pearson Education Limited, London, 2005.
- [16] Mannan M.A. and Ganapathy.C (2004), "Concrete from an agricultural waste - oil palm shell (OPS)", International Journal of Building and Environment 39 (2004), pp 441-448.
- [17] M. Surya, R. Kanta and P. Lakshmy, Recycled Aggregate Concrete for Transportation Infrastructure, Procedia - Social and Behavioral Sciences, 104 (2013), 1158-1167.
- [18] S. Yehia, K. Helal, A. Abusharkh, A. Zaher and H. Istaitiyeh, Strength and Durability Evaluation of Recycled Aggregate Concrete, International Journal of Concrete Structures and Materials, 9 (2015), 219-239.



10.22214/IJRASET



45.98



IMPACT FACTOR:
7.129



IMPACT FACTOR:
7.429



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089  (24*7 Support on Whatsapp)