



IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 10 Issue: X Month of publication: October 2022

DOI: https://doi.org/10.22214/ijraset.2022.47088

www.ijraset.com

Call: 🕥 08813907089 🔰 E-mail ID: ijraset@gmail.com

Influence of Superplasticizers (Conplast Conplast SP 430) on Fresh Properties of Self-Compacting Concrete: An Experimental Investigation

Chandrashekhar Khulhare¹, Dr. P. K. Singhai², Abhay Kumar Jha³, Barun Kumar⁴, Rajesh Misra⁵ ^{1, 2, 3, 4, 5}Department of Civil Engineering, Lakshmi Narain College of Technology, Bhopal (M.P)

Abstract: Super plasticizer has played a significant part in the recent issues of stability, particle suspension, particle segregation, flow properties, and cohesiveness in concrete. This study looked at how self-compacting concrete's characteristics and workability were affected by super plasticizer (SCC). Super plasticizers Conplast Conplast SP 430 is employed in the current investigation with concrete grades M30 and M40. Fresh concrete was used for the workability slump, compressive strength, and flexural strength test. On the hardened concrete, a test for compressive strength was performed. While every mix was acceptable, the one containing Conplast SP 430 had the best workability, compressive strength, and flexural strength. In the present investigation, it is show, how the cement content decreased by 23% and increasing compressive strength, flexural strength and reduced water –cement ratio also.

Keywords: Super plasticizer, suspension, workability, compressive strength, flexural strength.

I. INTRODUCTION

Concrete is a material that may be utilised for many various kinds of constructions and in construction. World Business Council for Sustainable Development (2015) reported that "Concrete is utilized in construction around the world twice as much as the sum of all other building materials, including wood, steel, plastic, and aluminum." Concrete does have some disadvantages, namely the potential for deterioration or damage over time. Therefore, concrete needs to be repaired. Therefore, to repair concrete, fresh concrete must be bonded to old concrete. When two or more materials are joined together so tightly that they function as a single monolithic unit, composite construction is possible. Damaged structural members frequently require composite fabrication to be repaired. Because monolithic behavior boosts a structure's or an element within a structure's strength and efficiency, which often results in a more practical design, it is desirable. The bonded interface must be successful at transferring forces like compression, tension, and shear for a composite unit to function monolithically. When two or more materials are joined together so tightly that they function as a single monolithic unit, composite construction is possible. Damaged structural members frequently require composite fabrication to be repaired. Because monolithic behavior boosts a structure's or an element within a structure's strength and efficiency, which often results in a more practical design, it is desirable. The bonded interface must be successful at transferring forces like compression, tension, and shear for a composite unit to function monolithically. To assess the compressive and tensile strengths of bonds, simple and basic standard tests are available, but few shear procedures have been formalized into standard tests (Helmick et al. 2016). In order to carry out repairs or apply overlays, engineers require a reliable method for experimentally determining the strength in shear at the interface bonded between old and new concrete.Direct, flexural, and tensional shear are the three forms of shear. A force per unit area is the definition of stress. The most fundamental and simple type of shear stress is direct or general shear stress, which is calculated by dividing the applied force by the cross-sectional area of the material. When it comes to plain concrete, the strength in shear at a bonded interface in roadways is mostly caused by adhesion and mechanical interlocking in the aggregate in the midst of base or bottom layer, which is referred to as the substrate, and top layer, which is referred to as the overlay. So,As a result, we can infer that the surface's shear capacity increases with surface roughness. The International Concrete Repair Institute, Inc. has acknowledged this as a factor (ICRI). There are

II. LITERATURE REVIEW

Bravoaj et al. (2017) Instead of actual construction and demolition trash, the majority of research on recycled aggregates for concrete focuses on aggregates created from waste concrete.



International Journal for Research in Applied Science & Engineering Technology (IJRASET)

ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 10 Issue X Oct 2022- Available at www.ijraset.com

Sulfonated-based superplastizers are less effective in recycled aggregate concrete than they are in concrete with natural aggregates, according to various studies, but there hasn't been any discernible decline in the effectiveness of polycarboxylic-based superplastizers. Due of the larger porosity, greater roughness, and lower mechanical qualities of aggregates made from actual building and demolition waste, this may not be true when using those aggregates. This study examines the mechanical characteristics of superplasticized concrete combined with demolition and construction debris. Without screening or further treatment, recycled aggregates made from building and demolition trash were taken directly from the plants and used as aggregates, simulating what would occur in

Bem et al. (2018) This study aims to demonstrate how superplasticizers and air entrainment admixtures (AEs) affect concrete's electrical resistivity. There have been studies on ten distinct kinds of concrete. Superplasticizers and air AEs have been utilised on three levels (0.20, 0.35 and 0.50 per cent). At 28, 63, and 91 days after the concrete samples were cast, the electrical resistivity was measured. Tests for density and compressive strength have also been conducted. The ideal concentration of the superplasticizer admixture was 0.35 percent, which greatly increased electrical resistance.

The electrical resistance was significantly reduced by the air AEs at the same dosage.

The highest resistivity/MPa ratio was found in the concrete containing air AEs. The results for different materials and admixtures should be carefully extrapolated.

Malaeb et al. (2019) The construction sector benefits from the revolutionary construction technique of 3D concrete printing since it decreases project time, cost, and flaws while increasing design flexibility and ecologically favourable features. This technique allows for the production of a 3D object by stacking 2D layers of a predesigned building element on top of one another. This chapter makes a scientific contribution by providing a framework for tackling the numerous design and operational limitations of 3D concrete printing, which will help this building technique be developed further. The two primary topics covered in this chapter are the design of a 3D printing machine and nozzle, on the one hand, and the design of the concrete mix that will be utilised, on the other.

Xun et al. (2020) The current study examines the fluidity of cement paste and mortar, as well as the pace at which it loses flow over time. It also looks at the pore structure and compressive strength of concrete and mortar when high-performance polycarboxylic acid water-reducing agents are present. By using a mercury intrusion test, scanning electron microscopy (SEM), and X-ray diffraction, the hydration rate, hydration products, and pore structure of concrete containing various functional polycarboxylic acid superplasticizers were examined (XRD). The findings demonstrate that the water-reducing compound Z considerably enhances the pore structure of concrete and mortar, increasing concrete's compressive strength. Additionally, the water-reducing agent H's slower reaction rate can be attributed to its shorter side chains and ester functional groups.

Ozuzun and Uzal (2021) Superplasticizers (SPs) play a significant role in the sustainable growth of the concrete industry due to the combinations' decreased water and Portland cement content. It is necessary to develop eco-efficient alternative types of SPs. In comparison to lignosulfonate- (LS) and naphthalene-based admixture, the plasticizing performance of a humic-acid based superplasticizer generated from leonardite (LHA) as a natural organic matter and its influence on hydration as well as characteristics of Portland cement (PC) were studied (NA). Through the use of isothermal calorimetry and thermo-gravimetric measurement of hardened pastes, the effect of LHA on the hydration of Portland

III. BONDING AGENT

For epoxy based bonding agent ASTM C881 provide resin system best suited for a particular application. According to viscosity and sag resistance there are three grade of epoxy, they are grade 1, grade 2 and grade 3. Also according to the type of material to be bonded together there are seven types are presented from Type 1 to Type 7. Also epoxy system are further characterized by class according to temperature ranges, they are class A, class B, class C.

According to the above categories we decided the type of bonding agent epoxy based used for bonding in our project and also thickness of bonding agent is given with the type of bond used.

Once bonding agent epoxy based is open use it within 24hrs because once it opens it starts to set in presence of air. Some bonding agent start to set within 30 min and some bonding agent take up to a time of 24 hrs to set. After applying bonding agent on the surface allow to rest the sample for 14 days before testing of samples.

International Journal for Research in Applied Science & Engineering Technology (IJRASET)



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 10 Issue X Oct 2022- Available at www.ijraset.com

IV. FLEXURAL STRENGTH TEST

Flexural power additionally called as modulus of rapture. In concrete flexure is the bowing minute caused by the applied load, in which a concrete beam has pressure at top and tensile worry at the base side.

Shafts on testing will bomb in strain because of its property and shear will show up on concrete. In this test works absolutely beams of size $700 \times 100 \times 100$ are casted of M30 and M40 grades concrete. At that point analyze the estimations of both plan blends. The flexural estimations of various blends. The load shall be increased until the specimen fails, and the maximum load applied shall be recorded to the nearest N.

Where, the flexural strength of the specimen shall be calculated as

Fb = 3PL/2bd2

Where, Fb = flexural strength, in N/mm2;

P = maximum load, in N;

L = distance between central lines of supporting rollers, in mm;

b = average width of block, measured from both Faces of the specimen, in mm;

d = average thickness, measured from both ends of the fracture line, in mm. The maximum load P shall be reported

as-the breaking load, nearest to 1 N.



Figure 1. Flexural Strength of beam

Tabla1	Doculto	of flowurg	atron ath	arada M40
rabler.	Results	or nexure	SUCHPUL	Place M40
				0

Ratio C:CA:FA	Age	Mean strength
	(days)	(N/mm2)
1:1.81:2.39	28	6.65
1:1.91:2.7	28	6.26
1:1.78:2.64	28	7.19



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 10 Issue X Oct 2022- Available at www.ijraset.com



Figure 1.Results of Flexural strength grade M40

V. CONCLUSIONS

Super plasticizers admixtures improve the workability without increasing water demand, for the two grades of concrete no decreasing in compressive strength was observed. Super plasticizers admixtures provide an increasing in ultimate strength gain by significantly reducing water demand in a concrete mix for the two grades, without affecting workability.

VI. ACKNOWLEDGMENT

This work was completed with the grants and facilities of Lakshmi Narain College of Technology, Bhopal (M.P.). Authors are thankful to this institute and faculties for extending this cooperation.

REFERENCES

- [1] American Society for Testing and Material. (2004). ASTM C128 Test Method for Density, Relative Density (Specific Gravity), and Absorption of Fine Aggregate. Philadelphia, Pennsylvania: American Society for Testing and Material.
- [2] American Society for Testing and Material. (2004). ASTM C187 Test Method for Normal Consistency of Hydraulic Cement. Philadelphia, Pennsylvania: American Society for Testing and Material.
- [3] American Society for Testing and Material. (2004). ASTM C191 Test Methods for Time of Setting of Hydraulic Cement by Vicat Needle. Philadelphia, Pennsylvania: American Society for Testing and Material.
- [4] American Society for Testing and Material. (2004). ASTM C39 Test Method for Compressive Strength of Cylindrical Concrete Specimens. Philadelphia, Pennsylvania: American Society for Testing and Material.
- [5] American Society for Testing and Material. (2005). ASTM C0136 Test Method for Sieve Analysis of Fine and Coarse Aggregates. Philadelphia, Pennsylvania.: American Society for Testing and Material.
- [6] American Society for Testing and Material. (2005). ASTM C0143 Test Method for Slump of Hydraulic-Cement Concrete. Philadelphia, Pennsylvania: American Society for Testing and Material.
- [7] American Society for Testing and Materials. (1994). ASTM C293, Standard Test Method for Flexural Strength of Concrete (Using Simple Beam with center-Point Loading), American Society for Testing and Materials. Philadelphia, Pennsylvania.: American Society for Testing and Materials.
- [8] BASF . (2008). Mode of Action Of Superplasticizer For Cement Based Construction Material.
- [9] Bem, at.al. (2018), "Effect of chemical admixtures on concrete's electrical resistivity", International Journal of Building











45.98



IMPACT FACTOR: 7.129







INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089 🕓 (24*7 Support on Whatsapp)