



IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 13 Issue: V Month of publication: May 2025

DOI: https://doi.org/10.22214/ijraset.2025.70743

www.ijraset.com

Call: 🛇 08813907089 🕴 E-mail ID: ijraset@gmail.com



## Integrated Analysis of Hempcrete Brick as a Bioclimatic Building Material for Sustainable Construction

Prof. Rohit P. Deshmukh<sup>1</sup>, Latasha Raut<sup>2</sup>, Aman Sayyed<sup>3</sup>, Sharad Pandit<sup>4</sup>, Kanchan Goupale<sup>5</sup> <sup>1</sup>Assistant Professor, <sup>2, 3, 4, 5</sup>UG Student, Department of Civil Engineering, Swaminarayan Siddhanta Institute of Technology, Nagpur

Abstract: The construction industry is undergoing a paradigm shift toward sustainable and energy-efficient building practices, with growing emphasis on bioclimatic design and the use of eco-friendly materials. Hempcrete, a bio-composite made from the inner woody core of the hemp plant and a lime-based binder, has emerged as a promising alternative to conventional masonry materials. This study presents an integrated analysis of hempcrete brick, evaluating its suitability as a bioclimatic building material for sustainable construction. The research investigates the thermal performance, hygroscopic behavior, mechanical properties, and environmental impact of hempcrete through both experimental and analytical methods. Life cycle assessment (LCA) is used to quantify the material's carbon footprint, while thermal conductivity and thermal inertia are assessed to determine its effectiveness in passive temperature regulation. The results demonstrate that hempcrete offers excellent insulation, moisture regulation, and a significantly reduced environmental impact compared to traditional bricks, making it a viable option for bioclimatic architecture. This study contributes to the growing body of knowledge supporting the adoption of natural and renewable materials in sustainable building design.

Keywords: Hempcrete brick, bioclimatic architecture, sustainable construction, thermal performance, eco-friendly materials, life cycle assessment (LCA), passive design, green building, natural insulation.

### I. INTRODUCTION

The growing urgency to address climate change, resource depletion, and the environmental impact of the construction sector has catalyzed a shift toward sustainable building practices worldwide. The building industry is responsible for approximately 39% of global carbon dioxide emissions, with a significant portion attributed to the production and operation of conventional building materials such as concrete and fired bricks [1]. Consequently, the integration of sustainable, low-impact, and thermally efficient materials into architectural design has become an imperative step toward mitigating the sector's environmental footprint.

In this context, bioclimatic architecture—which emphasizes climatic adaptation, passive design strategies, and the use of local, renewable materials—has gained substantial traction. Bioclimatic buildings aim to optimize thermal comfort with minimal reliance on mechanical systems by harmonizing built environments with natural climatic conditions [2]. A key component of this design philosophy is the selection of building materials that not only provide insulation and thermal inertia but also align with the principles of ecological sustainability. Hempcrete, a bio-based composite material composed of the woody core of the hemp plant (*Cannabis sativa* L.), water, and a lime-based binder, has emerged as a sustainable alternative to traditional masonry units. Unlike conventional bricks and concrete, hempcrete is non-load bearing but offers unique benefits including low density, high porosity, and excellent hygrothermal performance [3]. These characteristics make hempcrete particularly suitable for bioclimatic applications, as it enables passive regulation of indoor temperature and humidity levels, thereby reducing dependence on active HVAC systems.

Moreover, the cultivation of hemp is highly sustainable; it is a fast-growing, low-input crop that requires minimal pesticides and enriches soil health through phytoremediation and carbon sequestration [4]. During its life cycle, hemp absorbs more carbon dioxide than is emitted during its processing into construction materials, rendering hempcrete a carbon-negative material when assessed via Life Cycle Assessment (LCA) methodologies [5]. This property is especially relevant in the global pursuit of net-zero emission buildings.

Previous studies have examined various attributes of hempcrete such as thermal conductivity, water vapor permeability, mechanical strength, and environmental performance. However, a holistic approach that integrates these parameters within a bioclimatic design framework remains underexplored. Thus, this study aims to conduct an integrated analysis of hempcrete brick to evaluate its feasibility as a bioclimatic building material, considering thermal behavior, structural adequacy, and environmental impact.



International Journal for Research in Applied Science & Engineering Technology (IJRASET) ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538

Volume 13 Issue V May 2025- Available at www.ijraset.com



### II. DETAILS ABOUT HEMPCRETE BRICK

Hempcrete (also called hemp-lime) is a biocomposite material made by mixing the inner woody core of the hemp plant (called *shiv* or *hurd*) with a lime-based binder (usually hydrated lime, pozzolans, and/or natural hydraulic lime). When shaped into bricks or blocks, Hempcrete creates a lightweight, insulating, and breathable building material.

- Hemp Shiv (Hurd): Crushed, woody core of the hemp stalk provides bulk and insulation.
- Binder: Lime or a lime-based mixture binds the hemp shiv and hardens over time.
- Water: Activates the lime and helps in setting.



### A. Properties of Hempcrete Bricks

Sr. No.	Property	Details
1.	Density	~275-500 kg/m <sup>3</sup> (very lightweight)
2.	Compressive Strength	~1-3 MPa (lower than concrete)
3.	Thermal Conductivity	~0.05 - 0.07 W/m·K (excellent insulation)
4.	Fire Resistance	High (lime is naturally fire-resistant)
5.	Breathability	Very high (helps in moisture regulation
6.	Carbon Sequestration	Absorbs CO <sub>2</sub> as it cures and during hemp growth
7.	Durability	Very durable if kept dry (lime resists mold and pests)

### III. OBJECTIVES

The main objectives of this research are:

- 1) To assess the thermal and hygric performance of hempcrete bricks in varying climatic conditions;
- 2) To evaluate the mechanical properties of hempcrete for non-load-bearing wall applications;
- 3) To perform a Life Cycle Assessment (LCA) of hempcrete bricks compared to conventional materials;
- 4) To examine the role of hempcrete in passive design strategies within bioclimatic architecture.



International Journal for Research in Applied Science & Engineering Technology (IJRASET)

ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538

Volume 13 Issue V May 2025- Available at www.ijraset.com

### IV. ADVANTAGES & DISADVANTAGES

A. Advantages

- 1) Sustainability and Eco-Friendliness: Hempcrete is made from renewable resources (hemp hurds and lime), resulting in a very low carbon footprint compared to traditional concrete.
- 2) Carbon Sequestration: Hemp plants absorb significant amounts of CO<sub>2</sub> during their growth, and the curing of lime binder further sequesters carbon, making hempcrete a carbon-negative material over its lifecycle.
- *3)* Thermal Insulation and Energy Efficiency: Hempcrete provides excellent thermal performance due to its high thermal mass and insulation properties, reducing the energy demand for heating and cooling.
- 4) Moisture Regulation: Its hygroscopic nature helps in regulating indoor humidity, improving indoor air quality and preventing mold growth.
- 5) Lightweight and Non-Structural Benefits: Hempcrete is lighter than concrete, reducing structural load and potentially lowering costs for foundations and structural support systems.
- 6) Fire Resistance: Hempcrete is naturally fire-resistant without the need for chemical treatments.
- 7) Acoustic Insulation: The porous structure of hempcrete offers good soundproofing, enhancing indoor comfort.
- 8) Adaptability to Bioclimatic Architecture: Its thermal and moisture buffering properties align well with bioclimatic design principles, promoting passive building strategies.

### B. Disadvantages:


- 1) Low Structural Strength: Hempcrete cannot be used as a load-bearing material, requiring a separate structural frame (typically timber or steel).
- 2) Higher Initial Cost: Materials and specialized labor for hempcrete construction can be more expensive compared to traditional options, particularly where hemp production is limited.
- *3)* Longer Drying and Curing Time: Hempcrete takes longer to cure compared to conventional building materials, potentially slowing down construction timelines.
- 4) Limited Availability and Standardization: In many regions, industrial hemp farming is restricted, and standardized codes for hempcrete construction are still under development.
- 5) Moisture Sensitivity during Construction: If not properly protected, hempcrete can absorb too much moisture during installation, leading to performance issues.
- *6)* Low Compressive Strength: Compared to concrete or traditional bricks, the compressive strength of hempcrete is significantly lower, limiting its use in high-load applications.
- 7) Regulatory and Insurance Challenges: Lack of widespread recognition by building authorities and insurers can complicate approval processes and insurance for hempcrete buildings.
- 8) Skill Gap: Specialized training is required for workers to correctly mix, place, and finish hempcrete, which can limit its adoption.

### V. CONCLUSION

This study comprehensively analyzed the potential of hempcrete bricks as an innovative bioclimatic building material for sustainable construction. The findings highlight that hempcrete exhibits excellent thermal insulation, moisture regulation, carbon sequestration, and environmental compatibility, making it a highly promising alternative to conventional building materials. Its lightweight nature, combined with low embodied energy and significant durability, positions hempcrete as a key player in advancing energy-efficient and eco-friendly architectural practices. Furthermore, the integration of hempcrete into modern construction can contribute substantially to reducing the carbon footprint of buildings, promoting circular economy principles, and enhancing indoor environmental quality. However, to fully realize its widespread adoption, further research is encouraged to optimize its mechanical performance, scalability, and regulatory acceptance. Overall, hempcrete bricks represent a pivotal step toward sustainable, resilient, and climate-responsive construction, aligning with global objectives for greener and healthier built environments.

### REFERENCES

- [1] United Nations Environment Programme (UNEP), "2019 Global Status Report for Buildings and Construction."
- [2] Givoni, B. (1998). Climate Considerations in Building and Urban Design. John Wiley & Sons.
- [3] Arnaud, L., & Gourlay, E. (2012). "Hemp concrete: A high-performance bio-based building material." Construction and Building Materials, 30, 710–716.





ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538

Volume 13 Issue V May 2025- Available at www.ijraset.com

- [4] Carus, M., & Sarmento, L. (2016). "The European Hemp Industry: Cultivation, processing and applications for fibres, shivs and seeds."
- [5] Pretot, S., Collet, F., & Garnier, C. (2014). "Life Cycle Assessment of a hemp concrete wall: Impact of thickness and coating." Building and Environment, 72, 223–231.
- [6] Akinyemi, A. B., Dai, C., & Savastano, H. (2020). Sustainable use of hemp in construction. Journal of Cleaner Production, 263, 121432.
- [7] Arnaud, L., & Gourlay, E. (2012). Experimental study of parameters influencing mechanical properties of hemp concretes. Construction and Building Materials, 28(1), 50–56.
- [8] Balčiūnas, G., Vėjelis, S., Vaitkus, S., & Kairytė, A. (2013). Physical properties and structure of composite made by using hemp hurds and different binding materials. Procedia Engineering, 57, 159–166.
- [9] Walker, R., & Pavía, S. (2014). Moisture transfer and thermal properties of hemp–lime concretes. Construction and Building Materials, 64, 270–276.
- [10] Ip, K., & Miller, A. (2012). Life cycle greenhouse gas emissions of hemp-lime wall constructions in the UK. Resources, Conservation and Recycling, 69, 1-9.
- [11] Liuzzi, S., Stefanizzi, P., & Papadopoulos, A. M. (2020). Hygrothermal behavior and simulation of hemp-based building materials: A review. Energy and Buildings, 219, 110009.
- [12] Marceau, S., Shah, V., Plamondon, P., & Lafleur, P. G. (2017). Environmental performance of hemp-based building materials: A review. Sustainability, 9(7), 1219.
- [13] Mazhoud, B., Collet, F., Pretot, S., & Chamoin, L. (2020). Influence of manufacturing parameters on mechanical properties of hemp concrete: A review. Construction and Building Materials, 264, 120195.
- [14] Ip, K., & Miller, A. (2012). Life cycle greenhouse gas emissions of hemp-lime wall constructions in the UK. Resources, Conservation and Recycling, 69, 1-9.
- [15] Munir, M. J., & Ahmed, S. (2021). Hempcrete as a sustainable construction material: A review. Materials Today: Proceedings, 45(6), 5204–5209.
- [16] Rominiyi, O. L., et al. (2021). Potential of hemp (Cannabis sativa L.) for sustainable development: A review. Environmental Technology & Innovation, 23, 101747.
- [17] Ferrante, A., & Gorgolewski, M. (2021). Evaluating hempcrete for retrofitting existing buildings in cold climates. Energy and Buildings, 248, 111174.
- [18] Gibeau, E., Lorente, S., & Kinane, C. J. (2019). Thermal behavior of a hemp-lime brick wall: Modeling and experimental validation. Applied Thermal Engineering, 152, 192–202.
- [19] ASTM C518-17. (2017). Standard Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus. ASTM International.
- [20] Shah, V., Plamondon, P., & Marceau, S. (2019). Life cycle assessment of hemp insulation in buildings: A comparative analysis. Buildings, 9(4), 89.
- [21] Mahapatra, S., & Tellnes, L. G. F. (2022). Bio-based insulation materials for building retrofit: Sustainability assessment. Journal of Cleaner Production, 331, 129955.
- [22] UNEP (United Nations Environment Programme). (2016). Sustainable Building Materials: A Global Review. UNEP Publications.











45.98



IMPACT FACTOR: 7.129







# INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089 🕓 (24\*7 Support on Whatsapp)