



# **iJRASET**

International Journal For Research in  
Applied Science and Engineering Technology



# **INTERNATIONAL JOURNAL FOR RESEARCH**

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

**Volume: 13    Issue: V    Month of publication: May 2025**

**DOI: <https://doi.org/10.22214/ijraset.2025.70006>**

**[www.ijraset.com](http://www.ijraset.com)**

**Call:  08813907089**

**E-mail ID: [ijraset@gmail.com](mailto:ijraset@gmail.com)**

# Literature Review on Self-Healing Concrete by Using Bacteria

Pallavi Khemraj Jambhulkar<sup>1</sup>, Dr. Tushar Shende<sup>2</sup>, Dr. Alok Rai<sup>3</sup>

<sup>1</sup>Research Scholar, <sup>2,3</sup>Assistant Professor, Structural Engineering, Department of Civil Engineering, G. H. Raison College of Engineering and Management, Nagpur, Maharashtra, India

**Abstract:** *The purpose of this literature paper is to determine the use of bacteria is one of the most rising as well as bright approaches. The primary component of a concrete construction is cement. In concrete structure crack development is a typical phenomenon, it reduces durability & strength. Also analyse the impact of oxygen and water on the crack portion. In this study use of bacteria because the bacteria are having repair ability. This paper focuses on the mechanical properties of Bacillus family self-healing concrete. The mix proportion of material are taken while performing on bacterial based concrete. In the process of research and development of self-healing concrete, it is observed that there are main component of healing agent is bacteria which can produce or make the Calcite as a by-product of their activity. When these bacteria are incorporated into concrete, they can fill the cracks and voids with calcite, reducing permeability. Also improve concrete's mechanical properties and Enhance durability and resistances to degradation. In this study there are some kind of test and bacteria were used for performance in concrete mixture and to highlight the crack process also to point on the crack width how bacterial as well as bacteria concrete can heal the crack in minimum time period of crack developed on it. Current study used the bacteria in capsules formed to prevent the bacteria in other chemical reaction used capsule they can work on projection membrane of bacteria.*

**Keywords:** Self-healing, Crack closing, Bacteria, Strength, Durability etc.

## I. INTRODUCTION

Microbial technology-based self-healing concrete has become a viable option for improving the workability and sustainability of concrete structures throughout the past 20 years. Since the introduction of Portland cement in the early 19th century, concrete has been the most widely used construction material globally. Concrete is a construction material because it is inexpensive and has several desirable features such as workability, great compressive strength, and durability. Concrete's durability is threatened by a variety of chemical, mechanical, and biological phenomena [1]. Crack opening and expansion have a significant impact on the characteristics of concrete. In 2019, the British government pledged to spending 500.000 million pounds between 2020 and 2021 to restore the country's infrastructure, which is primarily composed of concrete [2]. In the Bhaskar work et al. [3]. The amount of cement produced increases with the demand for concrete, and this process emits a large amount of carbon dioxide (CO<sub>2</sub>) into the environment. This specific CO<sub>2</sub> emission accounts for approximately 8% of all CO<sub>2</sub> emissions induced by human activities [3]. One method for achieving such capacity recovery is to improve the material's ability to mend its own cracks as they occur. The healing ability of micro-cracks, cracks and discontinuous cracks in the concrete without any external influence is called self-healing [4]. Non-reacted stone and calcium-based nutrients undergo a biological reaction with the aid of bacteria like as bacillus to heal the cracks appeared in the structure. The cracks in the structure can be healed by the bacteria. Formation of Calcium Carbonate (CaCO<sub>3</sub>) as Calcium ion present in concrete reacts with CO<sub>2</sub> with the exposure of oxygen and water, this results in the formation of Calcium Carbonate layer which further heal the cracks [5][Assessing the potential application]. To extend the useful life of structures and reduce the high maintenance costs [6]. Adonay et al. [7] state that 20% of these repairs exhibit flaws after five years, and the majority are only functional for ten to fifteen years [7]. Microcapsules [8], Vascular technologies, Bacteria used in the cementitious composites should be able to survive in a high alkali environment [9] [Wei Zhang et al 2020]. The bacterial germs have likewise been enclosed in this consideration. Making use of porous materials (like expanded clays) [10]. Consider factors like as load-bearing capacity, surface crack pattern, crack propagation between layers, and healing effectiveness. The beams' maximum crack width surpassed 0.3 mm. According to a recent study, bacteria-based self-healing concrete has an 85% higher environmental effect per cubic meter than ordinary concrete because bacteria require nutrients and calcium precursors [11]. [Shan He, Masi Nuri et al., 2024]. To explore a variety of papers, they describe the bacterial concrete mixture was prepared by replacing 20% of the coarse aggregate by volume with bacteria-encapsulated.

The main cause of structural failure is the creation of microcracks in concrete as its ability to withstand rivet stresses declines [12]. Alkali-resistant bacteria spores packed in porous solid or gel microcapsules were directly injected into concrete to mend fissures [13]. The study indicated that the fracture openings were  $< 300 \mu\text{m}$ , and the healing duration was 42 days. Concrete has an innate healing potential, known as autogenous healing [14] [M. Roig-Flores, S. Moscato et al., 2015]. According to the materials used for the concrete's self-healing, self-healing in this context is divided into two categories: autonomous or independent healing [15, 16]. In concrete, autonomous self-healing outperforms autogenous self-healing due to its greater healing capabilities. Specifically, autonomous self-healing can repair fissures that are more than twice the breadth of those fixed by autogenous self-healing [17].

After studying so many papers it concluded, that how well bacterial concrete can repair itself and withstand pressure also, many research work aimed to analyze the self-healing capabilities and compressive strength of bacterial concrete. It also compares different ways of adding bacteria to concrete to see which method works best [18] [Sachindra Pratap et al., 2023]. Such result show that the different cracking methods, were as the manual crack injection, grouting, and sealing. The primary process of bacterial self-healing in concrete is accomplished through calcium carbonate ( $\text{CaCO}_3$ ) precipitation, which fills the cracks and promotes their recovery. Moreover, this  $\text{CaCO}_3$  precipitation has the potential to permeate internal voids within undamaged concrete, thereby enhancing its density and overall strength. However, this might not always hold true due to various influencing factors pertaining to the bacteria and the mixture, which can impact this process and, consequently, the concrete's strength [16] bacterial concentration [19] [Zaerkabeh et al., 2024], bacteria carriers [20] [Huynh et al., 2017], concrete mix sign and additives [21] [Mirshahmohammad et al., 2022; Justo-Reinoso et al., 2022]. For the same regard [22]. After 100 days, it was shown that *Bacillus alkalinitrilicus* type could seal a 0.4 mm crack, whereas autogenous self-healing caused 0.18 mm-wide cracks in the bacterial-free control concrete specimen to repair. [23] [Jianyun et al., 2014]. A crack width of 0.79 mm was fully healed using *B. cohnii*, species [24]. The current literature also contains information on other bacterial species that are utilized. Each bacterium was isolated from the others using the streak plate technique. [25], [26], [27]. Recent research has solved this issue by developing self-healing concrete that can recover its own durability [28]. Overloading, structural ageing, forced deformations, shrinkage from drying, volume changes caused by temperature stresses, differential settlement, freezing and thawing processes, geological variables, climate changes, and human involvement all contribute to crack formation [29]. [Sankara et al., 2024]. Cracks are divided as structural and non-structural cracks [30]. [B. A. Mir et al., 2023]. Cracks on structural elements such as beams, columns, and slabs are caused by flexure, shear, torsion, tension, bond, slide, corrosion, and shrinkage. Cracks can occur in vertical, horizontal, or diagonal directions [31].

## II. ADOPTED METHODOLOGY

Precipitation of various calcium carbonate by bacteria is considered a general phenomenon if the improper growth of crack in structures [32]. The most studied species for the method is MICP i.e. (microbially induced calcium carbonate precipitation) is *Sporosarcina pasteurii* also, the Bacteria were used is the *Bacillus* family fungi, [33]. In experimental studies focused on concrete self-healing, bacteria are often embedded within carriers to maintain their vitality within the concrete matrix. These carriers serve as shelters, shielding the bacteria from the concrete's alkaline environment and moisture fluctuations. Various materials have been tested as encapsulation agents, including [34]: ceramsite, silica [35], hydrogels [36], and expanded clay particles [37]. The use of *bacillus* bacteria they can increase the strength as well as the age, life of the structure. To address varying types of damage, further research is necessary to explore and identify effective autonomous self-healing strategies [38] [Yasmina et al., 2024].

## III. TEST SPECIMENS AND TESTING PROCEDURE

Researchers studied, the phenomenon about the sample and cubes were used, firstly the blocks without bacteria and the second one is the block with bacteria. Taking the cube of (150x150x150mm) add-mixture of cement, sand and aggregate ratio is grade M25. Mix properly and second sample of cube with bacteria added in capsules forms. There are 5-8 blocks are moulded at a time of casting it depends on capacity of work type. After the concrete block were made then the various test are performed on the blocks i.e. Compressive test, Slump test, Split tensile strength test, tensile strength test. Also read different literature paper they explain about the cracking process that is the minimum crack can heal is  $0.3 \mu\text{m}$  some cubes were pre cracked and were used to Use water permeability and fracture closure to assess self-healing capacity. The self-healing properties of bacterial concrete were investigated using a controlled cracking and healing protocol. The methodology involved: 1. Preparation of cubic specimens with induced cracks. 2. Monitoring of crack healing progression over time. 3. Evaluation of healing effectiveness and crack width decrease. 4. Quantification of healing efficiency through image analysis and microscopy.



5. Statistical analysis of healing time and crack size. 6. Examination of the impacts of environmental factors, nutrient availability, and bacterial strain [38]. The crack healing process were start in minimum 3 week of crack developed, they take 21-24 days for complete the healing process.

Author	Bacteria	Test	Result/findings
1. Manpreet Bagga. et, al.	Bacillus cohnii, Bacillus subtilis, Bacillus Sphaericus, Bacillus mucilaginous, Sporosarcina ureae.	Microbially induced calcium carbonate precipitation.	Overall, the aim of these models was to give directions for the manufacturing of self-healing materials with embedded capuseles containing the healing agents,but they give little or no consideration cement chemistry or the biological components.
2. Hesam Doostkami. et, al.	Bacillus Subtilis, II) SerpoBiotec Solution	1)Slump Test, 2)Water permeability test, 3)Compressive test	The slump for different mixes containing bacteria liquid solution were 7.5 and 2cm, resp. less their respective reference mixes, which measured 20 & 8cm.
3. Adonnay Pinto. et, al.	Yeast extract 0.75%	1) Flow test, 2)Vicat Apparatus test,	Combination of XRD techniques, it was possible to determine the chemical composition arising during the hydration process.The add. of Lactate caused notable changes in the reaction of the aluminate.
4. Linzhen Tan. et, al.	Bacillus Cohnii	1)Hydration kinetics, 2)crack Creation, 3)Healing regimes,	Compared with calcium nitrate basd specimenise calcium acetrate based specimen shown greatest healing performance.
5. Jae-InLee, Se-jin Choi	Cementitious material capsules.	1)Chloride-ion permeability test, 2)Spilting test, 3)silicon Sheet attachment test, 4)Clamp fastening test, 5)Measurement of water passing through the crack.	The 56-D Compressive recovery rate of the control sample was approximately 110%, an no increase in the recovery rate was observed after 28 days.
6. Krishna kumar Maurya. et, al.	Bacillius cohnii bacteria, Bacillius subtills bacteria	1)EMI technique, 2)CVC sensor preparation	The EMI technique strongly refelected the crack healing by the bacteria over a time. The developed concept can be implemented for the damage and crack healing performanance assessment of real-life concrete infrastructure.
7. Muhammad Basit Ehsan Khan. et, al.	Sporosarcina pasteurii, bacillius Subtills	X-ray diffraction (XRD) analysis and scanning electron microscopy (SEM). XL Scanning Electron Microscope.	In this study the specimens are taken is to be specimens containing only nutrients (NU), and bacteria-based mortar specimens with Group 2 EPAs, i.e. specimens containing both bacterial spores and nutrients (BA).

#### IV. RESEARCH GAP

Concrete is a fundamental construction material, is prone to cracking and degradation, leading to structural damage and costly repairs. Conventional repair techniques are frequently labor-intensive and impermanent. Recently, self-healing concrete using bacteria has emerged solution.

- 1) Optimal bacterial strain selection for self-healing efficiency.
- 2) Understanding the role of bacteria in improving concrete's tensile strength.
- 3) Effects of self-healing on concrete's stiffness and ductility.
- 4) Effects of bacterial activity on concrete's microstructure and durability.
- 5) Development of predictive models for self-healing concrete's mechanical behaviour.
- 6) Optimization of Bacterial Strains: Limited understanding of the most effective bacterial strains and their optimal concentrations.
- 7) Mechanical Properties: Insufficient data on self-healing concrete's mechanical properties, such as tensile strength and durability.
- 8) Environmental Factors: Lack of understanding of how environmental conditions like, humidity, pH. Impact self-healing efficiency.
- 9) Standardization and Regulation: Absence of standardized testing protocols and regulatory frameworks.

#### V. CONCLUSION

The concept we've developed can be used to evaluate how well real-life concrete structures can heal cracks and damages. This is important for making sure these structures last longer and stay safe. Autogenous healing is the term for concrete's inherent capacity to mend itself. However, this process has limitations: - It only works for small cracks. It's affected by the surrounding environment (temperature, humidity, etc.) Benefits of self-healing concrete is Improved durability, Increased lifespan, Reduced maintenance costs, Enhanced sustainability. Water helps concrete heal faster But, sealing cracks completely is still the best way to prevent water leaks. Compared to other conditions, water immersion showed higher healing rates. Self-healing concrete using bacteria has the potential to revolutionize the construction industry, providing a sustainable and resilient solution for infrastructure development.

#### REFERENCES

- [1] Manpreet Bagga, Charlotte Hamley-Bennett, Aleena Alex, Advancements in bacteria based self-healing concrete and the promise of modeling. Construction and Building Materials, volume 358, page129 sci 2023,
- [2] Abir Al-Tabbaa, Chrysoula Litina, Application and performance of microcapsule-based self-healing concrete. volume 208, Pages 669-685, sci30 may 2019.
- [3] Bhaskar Bashaveni, Rama Mohan Rao Pannem, Development of self-healing property in self compacting concrete. Case Studies in Construction Materials Volume 20, sci July 2024.
- [4] Hesam Doostkami a, Javier de Jesús Estacio Cumberbatch, Self-healing capability of conventional, high-performance, and Ultra High-Performance Concrete with commercial bacteria characterized by means of water and chloride penetration. Construction and building Materials, volume 401 , page 13, sci 2023.
- [5] Manpreet Bagga, Ismael Justo-Reinoso, Assessing the potential application of bacteria-based self-healing cementitious materials for enhancing durability of wastewater treatment infrastructure. Cement and Concrete Composites, volume 143, Page 105, sci October 2023.
- [6] Muhammad Khubaib Akhtar a, Maria Kanwal, Assessment of mechanical attributes and microstructural densification of self-healing recycled coarse aggregate concrete using various bacterial immobilizers. Journal of Building Engineering, volume 69, Page 89, 15 June 2023.
- [7] Construction and building Materials, volume 404, Page 201, sci, 5 Sept,2023.
- [8] Jirapa Intarasoontron, Wiboonluk Punggrasmi, Evaluation of Microencapsulation Techniques for MICP Bacterial Spores Applied in Self-Healing Concrete. Construction and Building Materials, volume 302, sci, 4 October 2023.
- [9] Wei Zhang, Qiaofeng Zheng, Ashraf Ashour c, Baoguo Han, Self-healing cement concrete composites for resilient infrastructures: A review. Composites Part B: Engineering, volume 189, Page 107, 15 May 2020,
- [10] Rubaiya Rumman, Ahmed Bediwy, M. Shahria Alam Development of self-healing system for concrete with selective heating around crack. Case Studies in construction materials, volume 20, july 2024.
- [11] Shan He, Masi Nuri, Henk M. Jonkers, Mladena Luković, Erik Schlangen, Structural behaviour of reinforced concrete beams with self-healing cover zone as lost formwork. Developments in the Built Environment, volume 18, page 100, April 2024
- [12] S. Shivanshi, Gourab Chakraborti, K. Sandesh Upadhyaya, N. Kannan, A study on bacterial self-healing concrete encapsulated in lightweight expanded clay aggregates. Materialstoday; Proceedings, 3 april 2023.
- [13] Sailong Hou, Kai Li, Zemei Wu, Fumin Li, Caijun Shi, Quantitative evaluation on self-healing capacity of cracked concrete by water permeability test – A review, Cement and Concrete Composites, volume 127, page 104, march 2022.
- [14] Vanessa Giaretton Cappellesso, Tim Van Mullem, Elke Gruyaert, Kim Van Tittelboom, Nele De Belie, Self-healing concrete with a bacteria-based or crystalline admixture as healing agent to prevent chloride ingress and corrosion in a marine environment. Developments in the Built Environment, volume 19, October 2024.
- [15] Elke Gruyaert, Kim Van Tittelboom, Nele De Belie, Self-healing capability of concrete with crystalline admixtures in different environments. Oct. 2024.
- [16] Iman Abavisani, Omid Rezaifar, Ali Kheyroddin, Efficient approaches to autogenous and autonomous self-healing concrete: a review. Magazine of Concrete Research, volume 75, page 1051-1079, 4 july 2023.

- [17] Self-healing concrete-what is it good for?
- [18] Sachindra Pratap Singh Rajawat, Balram Singh Rajput, Manoj Sharma, Gaurav Jain, Exploring the potential of bacterial concrete: An analysis of self-healing capabilities and compressive strength. *Materialstoday:Proceedings*, 9 august 2023.
- [19] M. Omar Osta, Faisal Mukhta, Effect of bacteria on uncracked concrete mechanical properties correlated with damage self-healing efficiency – A critical review. *Developments in the Built Environment*, volume 17, march 2024.
- [20] M. Omar Osta, Faisal Mukhtar, Effect of bacteria on uncracked concrete mechanical properties correlated with damage self-healing efficiency – A critical review. *Developments in the Built Environment*, volume 17, March 2024.
- [21] Guoqing Wang, Liang Zhang, Chenjia Xu, Shujia Zhang, Analysis of factor affecting the stavility of large-span cable-braced timber gridshells. *Devolpments in the Built Environment*, volume 17, March 2024
- [22] Effects of pre-cracked width and seawater erosion on the cracking bahaviur of SFRC beams with BFRP bars subjected to cyclic loading.
- [23] Virginie Wiktor, Henk M. Jonkers, Quantification of crack-healing in novel bacteria-based self-healing concrete. *Cement and Concrete Composites*, volume 33, pages 763-770, 7 August 2011.
- [24] Jianyun Wang, Jan Dewanckele, Veerle Cnudde, X-ray computed tomography proof of bacterial-based self-healing in concrete. *Cement and Concrete Composites*, volume 53, pages 289-304, Octoober 2014.
- [25] Jianguang Zhang, Yuanzhen Liu , Tao Feng , Mengjun Zhou, Immobilizing bacteria in expanded perlite for the crack self-healing in concrete. *Construction and Building Materials*, volume 148, pages 610-617, 1 September 2017.
- [26] Sini Bhaskar, Khandaker M. Anwar Hossain, Mohamed Lachemi a, Gideon Wolfaardt, Effect of self-healing on strength and durability of zeolite-immobilized bacterial cementitious mortar composites. *Cement and Concrete Composites*, volume 82, pages 23-33, September 2017.
- [27] Pui Yan Wong, Joyabrata Mal, Anna Sandak, Self healing concrete based on different bacteria: a review. *Science of The Total Environment*, volume 947, 15 October 2024.
- [28] Jae-In Lee, Se-Jin Choi, Compressive strength, chloride-ion-penetration resistance, and crack-recovery properties of self-healing cement composites containing cementitious material capsules and blast-furnace-slag aggregates. *Journal of CO2 Utilization*, volume 86, August 2024.
- [29] Sankaran Deeba, Arun Kumar Ammasi, Self healing of high strength concrete after deterioration by freeze/thaw, Self-healing characterization of engineered cementitious composite materials, *Ceramic Processing Research Review on the self-healing concrete-approach and evaluation technique. Case Studies in Construction Materials*, volume 20, July 2024.
- [30] B.A. Mir, T. Sasaki, K. Nakao, K. Nagae, Causes and evaluation of cracks in concrete structures. *Precision Engineering*, volume 76, pages
- [31] Study on Causes of Cracks & its Preventive Measures in Concrete Structures, Research on different types of cracks in plain and reinforced concrete.
- [32] Production of calcite (calcium carbonate) crystals by soil bacteria is a general phenomenon
- [33] Sudha Uthaman, Vinita Vishwakarma, Remediation of concrete using microorganisms. *Journal of Building Engineering*, volume 79, 15 November 2023
- [34] Linzhen Tan, Bianca Reeksting, Veronica Ferrandiz-Mas, Effect of carbonation on bacteria-based self-healing of cementitious composites. *Construction and Building Materials*, volume 257, page 105-119, 10 October 2020.
- [35] J.Y. Wang, D. Snoeck, W. Verstraete, Application of hydrogel encapsulated carbonate precipitating bacteria for approaching a realistic self-healing in concrete. *Construction and Building Materials*, volume 68, pages 110-119, 15 October 2024.
- [36] E. Tziviloglou, V. Wiktor, H.M. Jonkers, E. Schlangen, Bacteria-based self-healing concrete to increase liquid tightness of cracks. *Construction and Building Materials*, volume 122, pages 118-125, 20 September 2016.
- [37] Yasmina Shields, Davide di,Summa, Nicolas Ospitia, Gontran Herrier, Erik Schlangen, Tony Jefferson, Kim Van Tittelbom, First large scale application with self-healing concrete in Belgium: analysis of the laboratory control tests. *Journal of Building Engineering*, volume 95, page 110, 15 October 2024.
- [38] Hesam Doostkami, Sidiclei Formagini, Pedro Serna, Marta Roig-Flores, Self-healing capability of conventional, high-performance, and Ultra High-Performance Concrete with commercial bacteria characterized by means of water and chloride penetration. *Construction and Building Materials*, volume 401, page 132, 19 October 2023.
- [39] Rahul Roy, Emanuele Rossib, Johan Silfwerbranda, Henk Jonkers, Self-healing capacity of mortars with added-in bio-plastic bacteria-based agents: Characterization and quantification through micro-scale techniques. *Construction and Building Materials*, volume 297, 23 August 2021.





10.22214/IJRASET



45.98



IMPACT FACTOR:  
7.129



IMPACT FACTOR:  
7.429



# INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089  (24\*7 Support on Whatsapp)