iJRASET
International Journal For Research in Applied Science and Engineering Technology



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 10 **Issue:** V **Month of publication:** May 2022

DOI: https://doi.org/10.22214/ijraset.2022.43168

www.ijraset.com

Call: 08813907089 | E-mail ID: ijraset@gmail.com

International Journal for Research in Applied Science & Engineering Technology (IJRASET)
ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538
Volume 10 Issue V May 2022- Available at www.ijraset.com

Mechanical Properties of Light Weight Concrete using Lightweight Expanded Clay Aggregate

Abhishek Kumar Singh[1], R. Niveda[2], Ashish Anand[3], Ajay Yadav[4], Diwakar Kumar[5], Gaurav Verma[6]
[1, 2, 3, 4, 5, 6]*Dept.of Civil Engineering, Galgotias College of Engg. & Technology, Greater Noida, India*

Abstract: ***This research investigates the impact of partially substituting coarse aggregate with light weight coarse material (LECA). In numerous aspects, LECA mirrors the properties of coarse aggregate. Because self-weight accounts for a major amount of the total load applied to the structure, LECA is utilized in concrete to lower the need for coarse aggregate and in the design of concrete buildings. This is crucial in circumstances like poor soils and tall constructions. It also offers significant advantages in terms of lowering concrete density, which improves labour efficiency. Lightweight concrete has a lower density than standard concrete and provides better thermal insulation. The main purpose of this study is to examine the weight and strength characteristics of concrete, such as cube compressive strength, split tensile strength cylinders, and flexural strength of light weight concrete versus conventional concrete by substituting LECA for natural aggregates by 25%, 50%, 75%, and 100%, respectively. For far over two millennia, lightweight aggregate has been used successfully.***
Keywords: Lightweight Expanded Clay Aggregate (LECA), Light-weight concrete, Flyash, Compressive Strength, Density.

I. INTRODUCTION

Concrete is the most widely utilised building material in the world's construction sector. The large self-weight of concrete is one of the downsides of traditional concrete [1]. The density of ordinary concrete ranges from 2200 to 2600 kg/m3. Because of its high self-weight, it requires greater load bearing parts and foundations, making it an non-economical material. Experiments have been made in the past to lower the self-weight of concrete in order to improve its structural adaptability [2]. As a result, light-weight concrete with densities ranging from 300 kg/m3 to 1850 kg/m3 emerged [3].

There are three basic methods for generating low weight Concrete. By substituting light weight aggregate for the traditional mineral aggregate. Adding gas or air bubbles to the mortar. This is referred to as "aerated concrete." By not including the sand fraction in the aggregate [4]. This type of concrete is known as 'no-fines' concrete. As a result, they are rarely employed in the production of light-weight concrete [5]. Pumice, diatomite, scoria, volcanic cinders, saw dust, and rice husk are some of the natural light weight aggregates, with pumice being the only one that is commonly employed [6].

The properties of expanded perlite aggregate (EPA) include extremely low bulk density, high brightness, high absorption, low thermal and acoustic conductivity, and non-flammability [7]. The test results for steel fibrous revealed a linear relationship between compressive strength and splitting-tensile strength [8]. The mechanical characteristics of light weight Geopolymer concrete generated by substituting regular coarse aggregate with light weight expanded clay aggregates are investigated in this research (LECA) [9]. However, structural application of LECA with a density of 1700kg/m3 was restricted to 60% replacement of coarse aggregate. Both split tensile strength and flexural strength reduced by roughly 35 percent when coarse aggregate was replaced with LECA by 40 percent, although they were still well within structural limitations [10].

Experimental inquiry on concrete mix M20 is done by replacing cement with fly ash, fine aggregate with bottom ash, and coarse aggregate with Light Expanded Clay Aggregate (LECA) at the rates of 5%, 10%, 15%, 20%, 25%, 30%, and 35 percent [11]. The results reveal that replacing 5% of the cement with fly ash, fine aggregate with bottom ash, and coarse aggregate with Light Expanded Clay Aggregate (LECA) yielded satisfactory compressive strength results [13]. To investigate the qualities of lightweight concrete, such as compressive and tensile strengths, EPS beads are utilised as a partial substitute for coarse aggregates in the amounts of 5, 10, 15, 20, 25, and 30% [13]. The compressive and tensile strength of concrete is reduced as the amount of EPS beads in the mix is increased. Non-structural uses include wall panels, partition walls, and the like [14].

Light Expanded Clay Aggregate (LECA) was employed as a fine aggregate for enhancing the mechanical characteristics of porous asphalt [15]. Three distinct combinations of stone material and LECA (0, 10 and 20% LECA) were employed to conduct the experiment in this study. The findings of moisture susceptibility tests showed that adding LECA to a porous asphalt mixture can improve the combination's resistance to moisture damage [16].

Lightweight concrete has grown in popularity in recent years as the result of the many advantages it provides over traditional concrete [17]. Lightweight concrete has a number of advantages, including reducing dead load, increasing construction pace, and lowering handling costs [18]. The comparatively low heat conductivity and strong sound insulation are two more key characteristics of light weight concrete [19]. With these considerations, this study is aimed on using LECA, investigate the mechanical characteristics of light weight concrete

©IJRASET: All Rights are Reserved

II. LITERATURE SURVEY

Thomas Tamu and colleagues [9], To investigate the qualities of lightweight concrete, such as compressive and tensile strengths. EPS beads are utilised as a partial substitute for coarse aggregates in the amounts of 5, 10, 15, 20, 25, and 30%. The compressive and tensile strength of concrete is reduced as the amount of EPS beads in the mix is increased. Non-structural uses include wall panels, partition walls, and the like.

V.Khonsari, E.Eslami, and Ah.Anvari[4], The properties of expanded perlite aggregate (EPA) include extremely low bulk density, high brightness, high absorption, low thermal and acoustic conductivity, and non-flammability. The test results for steel fibrous revealed a linear relationship between compressive strength and splitting-tensile strength.

Mahyar Arabani et al [10], Light Expanded Clay Aggregate (LECA) was employed as a fine aggregate for enhancing the mechanical characteristics of porous asphalt. Three distinct combinations of stone material and LECA (0, 10 and 20% LECA) were employed to conduct the experiment in this study. The findings of moisture susceptibility tests showed that adding LECA to a porous asphalt mixture can improve the combination's resistance to moisture damage.

Sivakumar and B.Kameshwari [8], Experimental inquiry on concrete mix M20 is done by replacing cement with fly ash, fine aggregate with bottom ash, and coarse aggregate with Light Expanded Clay Aggregate (LECA) at the rates of 5%, 10%, 15%, 20%, 25%, 30%, and 35 percent. The results reveal that replacing 5% of the cement with fly ash, fine aggregate with bottom ash, and coarse aggregate with Light Expanded Clay Aggregate (LECA) yielded satisfactory compressive strength results.

Paul, Sachin Ganesh Babu[7], The mechanical characteristics of light weight Geopolymer concrete generated by substituting regular coarse aggregate with light weight expanded clay aggregates are investigated in this research (LECA). However, structural application of LECA with a density of 1700kg/m3 was restricted to 60% replacement of coarse aggregate. Both split tensile strength and flexural strength reduced by roughly 35 percent when coarse aggregate was replaced with LECA by 40 percent, although they were still well within structural limitations.

III. MATERIAL AND METHODOLOGY

A. Cement

"Ordinary Portland Cement" (OPC) (43 Grade) was employed, which had a 34 percent normal consistency and complied with IS: 8112-1989. Cement has a specific gravity (SG) of 3.14 and a fineness modulus of 4% respectively.

B. Coarse Aggregate

A coarse material used was 'crushed stone' that complied with IS 383 – 1987. Physical parameters were determined as well as the free and compacted bulk density values of coarse aggregates, which were 4.417kg and 4.905kg, respectively were also determined. The specific gravity is found to be 2.74

C. Fine Aggregate

Throughout the experiment, 'normal river sand was used as the fine aggregate', which conformed to grading 'zone III'. By conducting tests in accordance with IS 2386(part -1)-1963, the qualities of sand can be determined. The value of specific gravity is 2.65.

D. Lightweight Expanded Clay Aggregate (LECA)

'LECA' of size 10-20 mm were utilised. The bulk density of the light weight expanded clay aggregate utilised ranges from 300 to 750 kg/m3, with water absorption ranging from 18 to 20% of the size. The specific gravity of leca is 0.60.



E. Water

Because it actively participates in chemical reactions with cement, water is asignificant component of concrete. The concrete mixture was made using clean potable water that met IS 456 – 2000 standards.

F. Fly ash

Fly ash is a finely split residue produced by the burning of pulverised coal that is carried away by exhaust gases from the combustion chamber. Low-Calcium Fly Ash (ASTM Class F) was procured from a Thermal Power Plant for this investigation. Fly

ash has a specific gravity of 2.36 and a fineness of 4 percent.

G. Design of Concrete Mix

'M25' grade with design mix as per 'IS 456-2000' was used in this study. For a 1m3 concrete mix, use a weight-based proportion and a 'water-to-cement' ratio of '0.45'. Mix proportion obtained for M25 Grade of conventional concrete and 100 percent, light weight concrete mix ratio was 1:1.37:2.6 and 1:1.37:0.49 respectively. The percentage 25%, 50%, 75 and 100%, The fly ash percentage of 20% was utilised as a partial substitute for cement concrete and was used as a partial replacement for natural coarse aggregate.

H. Casting and Testing

In this, LECA was replaced with natural aggregate in 25, 50 ,75 and 100 percent . To determine the hardened properties of concrete, cubes and cylinders were formed for each percent of LECA replacement as coarse aggregate. For each proportion of fresh concrete, a slump test is performed. The cube and cylinder's final strength is measured after, 7 and 28 days of cure. The average compressive and tensile strengths for each mix fraction are then calculated and explained in the final result. Furthermore, the to quantify the amount of strength increased over conventional concrete, the strength of light weight aggregate concrete is compared to that of conventional grade concrete.



IV. RESULTS

A. Compressive Strength

The bar graph depicts the compressive strength of conventional concrete and light weight aggregate concrete using LECA for various grades . Compressive strength results of 24.64N/mm2 , 22.04N/mm2 and strength reduction of 14.44% and 23.47% where for LECA25 & LECA50 respectively these percentages of replacement are attributable to light weight concrete with densities ranging from 1100- 2100kg/m3. This mixture may also be used to build structures. It is observed that the concrete made with LECA aggregates is marginal to that of conventional concrete.

B. Split Tensile Strength

Split tensile strength results of 2.20 N/mm2 , 1.90 N/mm2 . The split tensile strength was reduced by 22.26 percent and 32.86 percent when 25% and 50% of LECA were replaced, respectively.

C. Density


Table 1 shows the densities of normal concrete and light weight aggregate concrete using LECA. The difference in density was estimated to be roughly 1250 kg/m3.


D. Workability

The workability of Light weight aggregate concrete with LECA was measured using conventional slump cone test apparatus. The details of the results are presented in Table 2.



Fig. Compression testing





CONCRETE	WEIGHT (Kg)	DENSITY
NORMAL	8.21	2432.5
25%	7.22	2139.2
50%	5.87	1739.2
75%	4.98	1475.5
100%	4.03	1194.07

Table 1: Weight and density

S.no.	Percentage of leca	Slump value (mm)
1	0	76
2	25	73.5
3	50	74
4	75	72
5	100	71

Table 2 : Slump value

V. CONCLUSION

LECAs (lightweight expanded clay aggregates) are a type of fabricated lightweight aggregate that has a wide range of applications and has become a well-known material in civil engineering projects. LECA has unique properties that make it an excellent structural and geotechnical material. LECA has been used to construct lightweight concrete buildings, lightweight fill, drainage, and insulating materials in embankments for roads, railroads, and other traffic zones, and lightweight backfill for retaining walls and as foundation for structures and agricultures. According to the findings, incrementing the percentage of lightweight aggregate reduces the weight of the cubes from 8.21 to 4.03 kilograms.

1) The results of the investigation show that as the amount of leca increases, the compressive strength of the cube decreases.
2) With an increase in the amount of leca, the split tensile strength gradually decreases.
3) With a above percentage of regular aggregate replaced with leca, the density of concrete is shown to decrease.

4) When 50% of the leca is replaced with regular aggregate, the compressive strength, tensile strength and density are improved, as compared with other mix proportions.

5) As a result, we infer that concrete manufactured with these aggregates can be used in the construction sector to reduce the concrete's dead weight in multi-story buildings.

6) From the above result we can also conclude that It can be used as :

a) Screeds and thickening for general use, particularly when such screeds or thickening are used to support the weight of floors, roofs, and other structural parts.

b) Screeds and walls where wood must be nailed in place.

c) Using structural steel as a covering for architectural purposes or to protect it from fire and corrosion.

d) Roof and wall insulation for heat .

e) Insulating water pipes .

f) In frame structures, build partition walls and panel walls.


g) Surface rendered for small house outside walls,

VI. ACKNOWLEDGEMENT

We are highly thankful to Department of Civil Engineering, Galgotias College of Engineering and Technology for providing the help for this work.

REFERENCES

[1]. Lightweight Concrete with Aggregates Made by Using Industrial Waste Diana Bajare, Janis Kazjonovs*, Aleksandrs Korjakins Riga Technical University, Faculty of Civil Engineering, Kalku st. 1, LV-1658, Riga, Latvia
[2]. Jihad Hamad Mohammed, Ali Jihad Hamad, 2014, A Classification of Lightweight Concrete: Materials, Properties and Application Review, International Journal of Advanced Engineering Applications, Vol.7, Iss.1, 2014, 52-57
[3]. R.Garg and R.Garg, "Performance evaluation of polypropylene fiber waste reinforced concrete in presence of silica fume," *Mater. Today Proc.*, vol. 43, no. xxxx, pp. 809–816, 2020, doi: 10.1016/j.matpr.2020.06.482.
[4]. Raymond T, Hemmings, Bruce J, Cornelius, 2009, Comparative Study of Light Weight Aggregates, World of Coal Ash Conference, May 2009
[5]. R. Garg, R. Garg, B. Chaudhary, and S. Mohd. Arif, "Strength and microstructural analysis of nano-silica based cement composites in presence of silica fume," *Mater. Today Proc.*, vol. 46, no. xxxx, pp. 6753–6756, 2020, doi: 10.1016/j.matpr.2021.04.291.
[6]. R. Garg, R. Garg, and N. O. Eddy, "Microbial induced calcite precipitation for self-healing of concrete: a review," *J. Sustain. Cem. Mater.*, vol. 0, no. 0, pp. 1–14, 2022, doi: 10.1080/21650373.2022.2054477.
[7]. Arioz O, Kilinc K, Karasu B, Kaya G, Arslan G, Tuncan M, Tuncan A, Korkut M and Kivrak S A preliminary research on the properties of lightweight expanded clay aggregate Journal of the Australian Ceramic Society 44 23–40, (2008).
[8]. S.Sivakumar1 and B.Kameshwari2 , Influence of Fly Ash, Bottom Ash and Light Expanded Clay Aggregate in Concrete
[9]. Thomas Tamu et al., Partial Replacement of Coarse Aggregates By Expanded Polystyrene Beads In Concrete. Construction and Building Materials, Vol-3, 2014
[10]. Mahyar Arabani*1 , Gholam Hossein Hamedi2 , Hasan Jaefari3 , Evaluating the Effects of Light Expanded Clay Aggregate on Mechanical Properties of Porous Asphalt. Current Advance in Civil Engineering.
[11]. S. Dhiman, R. Garg, R. Garg, and S. Singla, "Experimental investigation on the strength of chipped rubber-based concrete," *IOP Conf. Ser. Mater. Sci. Eng.*, vol. 961, no. 1, 2020, doi: 10.1088/1757-899X/961/1/012002.
[12]. Rishav Garg, Manjeet Bansal, and Yogesh Aggarwal, "Split Tensile Strength of Cement Mortar Incorporating Micro and Nano Silica at Early Ages," *Int. J. Eng. Res.*, vol. V5, no. 04, pp. 16–19, 2016, doi: 10.17577/ijertv5is040078.
[13]. M. N. Khan, S. Singla, R. Garg, and R. Garg, "Effect of Microsilica on Strength and Microstructure of the GGBS-based Cement composites," *IOP Conf. Ser. Mater. Sci. Eng.*, vol. 961, no. 1, 2020, doi: 10.1088/1757-899X/961/1/012007.
[14]. R. Garg, P. Rani, R. Garg, and N. O. Eddy, "Study on potential applications and toxicity analysis of green synthesized nanoparticles," *Turkish J. Chem.*, vol. 45, no. 6, pp. 1690–1706, 2021, doi: 10.3906/kim-2106-59.
[15]. M. Kumar, M. Bansal, and R. Garg, "An overview of beneficiary aspects of zinc oxide nanoparticles on performance of cement composites," *Mater. Today Proc.*, vol. 43, part 2, pp. 892–898, 2020, doi: 10.1016/j.matpr.2020.07.215.
[16]. C. M. Kansal, S. Singla, and R. Garg, "Effect of Silica Fume & Steel Slag on Nano-silica based High-Performance Concrete," *IOP Conf. Ser. Mater. Sci. Eng.*, vol. 961, no. 1, 2020, doi: 10.1088/1757-899X/961/1/012012.
[17]. V. Kumar, S. Singla, and R. Garg, "Strength and microstructure correlation of binary cement blends in presence of waste marble powder," *Mater. Today Proc.*, vol. 43, Part 2, pp. 857–862, 2020, doi: 10.1016/j.matpr.2020.07.073.
[18]. R. Garg, M. Kumari, M. Kumar, S. Dhiman, and R. Garg, "Green synthesis of calcium carbonate nanoparticles using waste fruit peel extract," *Mater. Today Proc.*, vol. 46, part 15, pp. 6665–6668, 2020, doi: 10.1016/j.matpr.2021.04.124.
[19]. N. O. Eddy, R. Garg, R. Garg, A. O. Aikoye, and B. I. Ita, "Waste to resource recovery: mesoporous adsorbent from orange peel for the removal of trypan blue dye from aqueous solution," *Biomass Convers. Biorefinery*, 2022, doi: 10.1007/s13399-022-02571-5.
[20]. R. Garg, R. Garg, A. Thakur, and S. M. Arif, "Water remediation using biosorbent obtained from agricultural and fruit waste," *Mater. Today Proc.*, vol. 46, no. xxxx, pp. 6669–6672, 2020, doi: 10.1016/j.matpr.2021.04.132.
[21]. D. Prasad Bhatta, S. Singla, and R. Garg, "Microstructural and strength parameters of Nano-SiO2based cement composites," *Mater. Today Proc.*, vol. 46, no. xxxx, pp. 6743–6747, 2020, doi: 10.1016/j.matpr.2021.04.276.
[22]. R. Garg, R. Garg, and S. Singla, "Experimental Investigation of Electrochemical Corrosion and Chloride Penetration of Concrete Incorporating Colloidal Nanosilica and Silica Fume," *J. Electrochem. Sci. Technol.*, vol. 12, no. 4, pp. 440–452, 2021, doi: 10.33961/JECST.2020.01788.
[23]. Mohd Roji Samidi,(1997). First report research project on lightweight concrete, Universiti Teknologi Malaysia, Skudai, Johor Bahru.
[24]. Siamak Boudaghpour, and Shervin Hashemi, A Study on Light Expended Clay Aggregate (LECA) in a Geotechnical View and it Application on Greenhouse and Green roof Cultivation. International Journal of Geology, Volume 2, 2008
[25]. O. Arioz1 *, K.Kilinc1 , et al, A Preliminary Research On The Properties of Lightweight Expanded Clay Aggregate, J. Aust. Ceram. Soc. 44 [1] (2008) 23-30.



10.22214/IJRASET

45.98

IMPACT FACTOR: 7.129

IMPACT FACTOR: 7.429

INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089 (24*7 Support on Whatsapp)