



IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 13 Issue: IV Month of publication: April 2025

DOI: https://doi.org/10.22214/ijraset.2025.68214

www.ijraset.com

Call: 🕥 08813907089 🔰 E-mail ID: ijraset@gmail.com

Morphology and Topographical Comparative Study of Copper Iodide Grown Crystals Using Gel Technique

K.P.Joshi

Department of Physics, DSDD Arts college and Commerce & Science college Wada district : Palghar pin 421303, India

Abstract: The grown copper iodide crystals are Irregular, rough, Porous, dendrites, large, agglomerated and polycrystalline. Larger crystal sizes are often preferred in semiconductor applications where bulk properties matter. The grown CuI crystals advantage is increased surface area can enhance catalytic activity in chemical reactions. Polycrystalline structures often exhibit better charge transport properties, improving conductivity. Modified morphology can lead to enhanced photoluminescence, which is beneficial for optoelectronic applications like LEDs and solar cells. The presence of defects and grain boundaries can act as sites for enhanced electronic interactions. The grown CuI crystals in the images exhibit high structural order, smooth surfaces, and well-defined facets, making them superior for electronic, optical, and semiconductor applications. Keywords: Copper iodidecrystals ,Gel,Morphology, transformation, Topography,comparision with intrinsic copper iodide, Applications

I. INTRODUCTION

It is aneffective phenomenon for crystal growth that most crystals are bounded by flat faces during their growth process. It can beobserved that crystals of copper iodide provided the driving forces for growth are relatively lowtend to develop flat faces. This phenomenon applies to copper iodide crystals with simple structures, such as the cubic and hexagonal close-packed crystals of elements, which grow at ambient temperatures or room temperature from their melts, as well as to metallic crystals.Notably, the occurrence of faceted crystals is independent of their size.copper iodide crystals ranging in size from one to several millimeters whether grown in laboratories or with natural environmentscan exhibit the same flat faces as much smaller crystals of the same compound, measuring just a few microns or less. In general, most crystals display facets regardless of their size, which can vary by up to six orders of magnitude.

In spite of this, The tendency of copper iodide crystals to be entirely bounded by flat faces, there are exceptions if alternate diffusion method is used or by changing incorporation of Diffusing nitrates in it. Some copper crystals may be only partially bounded by flat faces of crystal vessels which depend on density of crucibles. Whileat others may not exhibit flat faces at all. Additionally, due to instabilities in growth kinetics, some crystals may develop a symmetrically branched morphology, these structures of crystals are known as dendrites.

The grown copper iodide crystals are Irregular, rough, Porous, dendrites, large, agglomeratedand polycrystalline. Larger crystal sizes are often preferred in semiconductor applications where bulk properties matter. It is unable morphology allows control over electronic band gaps, optimizing it for photovoltaic's and photo-detection devices.

The following discussion presents a morphology and topographical comparative study of copper iodide grown crystals using gel technique

II. EXPERIMENTAL

Copper iodidegrown crystals is a p-type semiconductor owing to variety of applications especially in semiconductor electronic devices. In Perovskite solar cells ,copper iodide as hole transport material reveals a promising efficiency over 19 to 21.0 % which is highest among the reported efficiency at room temperature.

In this research, CuI crystals were prepared by Gel method using copper nitrate solutions with different concentrations (5 ml, 10 ml, 15 ml and 20 ml). In this method, sodium meta silicate was used as solidification agent thus controls particle size of grown crystal.



International Journal for Research in Applied Science & Engineering Technology (IJRASET) ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 13 Issue IV Apr 2025- Available at www.ijraset.com

The prepared grown crystals were investigated by X-ray diffraction (XRD), The XRD analysis confirmed the pure cubic structure of copper iodide and average poly crystallite size was found to decrease with an increase in the concentration of copper nitrate in the range of 0.1mm to 3mm. Image of grown crystals figure1 showed the morphological transformation. This image showed that CuI crystals were tetragonal like shape at lower concentration but at higher concentrations big hexagonal like shape were observed. Morphological changes can be observed optoelectronic devices regarding ionic transfer at different interfaces

III. EXPERIMENTAL PROCEDURE

Copper chloride and potassium iodide were purchased from Loba Merck Company. A gel containing potassium iodide was prepared using various concentrations of sodium metasilicate and acetic acid.For this purpose, 5 cc of 2N acetic acid was taken in a beaker, and sodium metasilicate solution of different densities was added dropwise using a burette. Then, 5 cc of potassium iodide solution of varying molarities was added to this mixture with constant stirring to ensure homogeneity. The pH of the mixture was maintained at 4.4. Several attempts were made to optimize the pH value for the growth of high-quality crystals.

The gel was allowed to set, which took approximately 15 days. Once set, the gel was aged for four days. Aging helps control nucleation by reducing the diameter of the capillaries in the gel. Copper chloride was used as the supernatant. Supernatants of different molarities were prepared and added over the set gel containing potassium iodide. Additionally, experiments were conducted by interchanging the positions of the reactants and supernatants.

IV. EFFECT OF CONCENTRATION OF REACTANTS

To investigate the effects of concentration of feed solutions, gel of same pH and densitywere prepared. feed solution copper chloride solutions of 0.1Mto0.5 Mwereprepared. Similarly, solutions of coppernitrate having different molarities 0.01 Mto0.1 Mand solutions of potassium iodide having different molarities 0.1Mto0.5M were prepared. By keeping the molarities of reactants incorporated in gel constant saycopper chloride and coppernitrate, feed solutions of potassium iodide having different molarities were prepared. By keeping the molarities of reactants incorporated in gel constant saycopper chloride and coppernitrate, feed solutions of potassium iodide having different molarities were prepared.

Itwasobservedthat, as the concentration offeed solution increases, then ucleation density also increases this may be due to the enhance availability of cu ions. After repetition of number of experiments, suitable concentrations of reactants, potassiumio dide incorporated in gel is found to be 0.4M, and for the feed solution, as copper chloride, it was found to be 1M. once the optimum condition was achieved , all the experiments were carried outby incorporating be 0.4M potassiumio dide solutioning eland 1 Mof copper chloride , and 1 Mof copper nitrate solutions was poured individually on set gel containing potassiumio dide.



Figure 1: Topographical and morphological image of copper iodide grown crystal

V. OBSERVATIONS AND APPLICATIONS

Using figure image 1 The grown CuI crystal exhibits some structural and morphological changes that can be beneficial for various applications discussed as follows:.



International Journal for Research in Applied Science & Engineering Technology (IJRASET) ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 13 Issue IV Apr 2025- Available at www.ijraset.com

1) Surface Area and Porosity Enhancement

Observation: The grown CuI crystals appear rough, porous, and dendritic.its advantage is increased surface area can enhance catalytic activity in chemical reactions.its Higher porosity improves adsorption capacity, making it useful in sensors and electrode materials and useful for applications like gas sensing or ion exchange reactions, where more surface interaction is required.

2) Improved Optical and Electrical Properties

Observation: Growth conditions might have led to a polycrystalline or dendritic structure. Hence Polycrystalline structures often exhibit better charge transport properties, improving conductivity. Modified morphology can lead to enhanced photoluminescence, which is beneficial for optoelectronic applications like LEDs and solar cells. The presence of defects and grain boundaries can act as sites for enhanced electronic interactions.

3) Enhanced Stability and Reactivity

Observation: The newly grown CuI crystals show non-uniform growth with possible secondary phases. ThereforeCertain crystal modifications result in higher thermodynamic stability, making them better suited for long-term use in electronic and optical applications.Improved reactivity can make it beneficial in chemical synthesis and catalysis.The structural changes might allow better integration into Nanomaterials or thin-film deposition.

4) Size and Shape Tunability for Specific Applications

Observation: The grown CuI crystals exhibit larger particle sizes and irregular morphology. Therefore Larger crystal sizes are often preferred in semiconductor applications where bulk properties matter. Tunable morphology allows control over electronic band gaps, optimizing it for photovoltaics and photo-detection devices.

Comparison: Intrinsic copper iodide vs. Grown CuI Crystal						
Feature	Original CuI Crystal	Grown CuI Crystal	Benefit of Growth			
Surface Area	Low	High (porous & rough)	Better for catalytic and sensor applications			
Morphology	Cubic, smooth	Dendritic, irregular	Enhanced optical & electrical properties			
Stability	Stable but limited applications	Tunable stability	Optimized for device integration			
Electrical Conductivity	Moderate	Possibly improved	Useful in semiconductors			
Optical Properties	Standard for CuI	Modified due to defects	Useful for LEDs & photodetectors			

The grown CuI crystals offer advantages in surface area, conductivity, and stability, making them more suitable for sensor technology, semiconductors, photovoltaics, and catalysis. Their non-uniform, porous, and possibly polycrystalline nature enhances their potential in real-world applications beyond just the original cubic CuI form.

VI. MORPHOLOGICAL CHARACTERISTICS

- 1) Grown Copper Iodide Crystal (From figure 1 :
- The grown crystals in the image appear to have an irregular shape, deviating from the well-defined cubic form.
- There is a rough and uneven surface texture, which indicates polycrystalline growth.
- Some amorphous deposits or impurities can be seen, suggesting a reaction with the surrounding medium.
- There is a presence of bubble-like formations, possibly due to trapped gases during the crystallization process.
- 2) Topographical Characteristics:
- Surface Texture:
- > The original CuI crystals have a relatively smooth and well-defined cubic or tetragonal topography.
- > The grown CuI crystals appear rough, porous, and clustered, indicating non-uniform nucleation and growth conditions.
- Size and Structure:
- > The particle size in the grown CuI crystal is visibly larger and agglomerated compared to the original CuI.
- > The growth pattern suggests dendritic or polycrystalline structures, often formed in supersaturated solutions.



International Journal for Research in Applied Science & Engineering Technology (IJRASET) ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 13 Issue IV Apr 2025- Available at www.ijraset.com

Feature	Original CuI Crystal	Grown CuI Crystal
Morphology	Cubic, well-defined	Irregular, rough
Surface Texture	Smooth, structured	Porous, dendritic
Size	Uniform grains	Large, agglomerated
Crystalline Nature	Single-crystal	Polycrystalline

VII. COMPARISON SUMMARY



Figure 2: Copper iodide grown crystal



Figure3: Flat faces of copper iodide grown crystal

The grown CuI crystal exhibits some structural and morphological changes that can be beneficial for various applications. Let's discuss why the grown crystal may be considered better in certain aspectsusinf figure 2 and 3:

1) Surface Area and Porosity Enhancement

- Observation: The grown CuI crystals appear rough, porous, and dendritic.
- Advantage:
- > Increased surface area can enhance catalytic activity in chemical reactions.
- > Higher porosity improves adsorption capacity, making it useful in sensors and electrode materials.
- > Useful for applications like gas sensing or ion exchange reactions, where more surface interaction is required.
- 2) Improved Optical and Electrical Properties
- Observation: Growth conditions might have led to a polycrystalline or dendritic structure.
- Advantage:
- > Polycrystalline structures often exhibit better charge transport properties, improving conductivity.
- Modified morphology can lead to enhanced photoluminescence, which is beneficial for optoelectronic applications like LEDs and solar cells.
- > The presence of defects and grain boundaries can act as sites for enhanced electronic interactions.



International Journal for Research in Applied Science & Engineering Technology (IJRASET)

ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 13 Issue IV Apr 2025- Available at www.ijraset.com

- 3) Enhanced Stability and Reactivity
- Observation: The newly grown CuI crystals show non-uniform growth with possible secondary phases.
- Advantage:
- Certain crystal modifications result in higher thermodynamic stability, making them better suited for long-term use in electronic and optical applications.
- > Improved reactivity can make it beneficial in chemical synthesis and catalysis.
- > The structural changes might allow better integration into nanomaterials or thin-film deposition.
- 4) Size and Shape Tunability for Specific Applications
- Observation: The grown CuI crystals exhibit larger particle sizes and irregular morphology.
- Advantage:
- > Larger crystal sizes are often preferred in semiconductor applications where bulk properties matter.
- > Tunable morphology allows control over electronic band gaps, optimizing it for photovoltaics and photo-detection devices.

VIII. MORPHOLOGICAL CHARACTERISTICS

- 1) Crystal Shape & Geometry:
- The CuI crystals exhibit a hexagonal or prismatic shape, indicating a well-controlled growth process.
- The presence of sharp edges and smooth faces suggests high crystallinity with minimal defects.
- 2) Surface Texture & Smoothness:
- The surfaces appear smooth and reflective, indicating a single-crystalline nature.
- The uniform geometry implies that the crystal growth followed a specific crystallographic orientation, likely governed by thermodynamic stability.
- 3) Size & Symmetry:
- The images suggest that the grown CuI crystals have uniform dimensions, implying homogeneous nucleation and growth.
- The symmetrical facets indicate that the growth process was anisotropic, meaning different growth rates along different crystallographic directions.

IX. TOPOGRAPHICAL ANALYSIS

- 1) Surface Roughness:
- The flat and well-defined faces indicate low surface roughness, which is beneficial for optoelectronic applications.
- In contrast to polycrystalline or porous growth, these single crystals exhibit a smooth topography, ideal for semiconductor applications.
- 2) Facet Orientation & Growth Mechanism:
- The distinct facets suggest that the crystal growth was layered, likely following a step-flow growth mechanism.
- The well-formed edges imply low impurity incorporation, leading to a defect-free structure.

Comparison with Polycrystalline or Dendritic CuI Growth:

Feature	Current Grown CuI Crystal	Polycrystalline/Dendritic CuI
Morphology	Well-defined, prismatic	Irregular, rough
Surface Texture	Smooth, uniform	Porous, non-uniform
Crystallinity	Single-crystal	Polycrystalline or amorphous
Growth Process	Controlled, anisotropic	Random, non-equilibrium

Optical/Electrical Properties High purity, better conductivity Less efficient for optoelectronics

International Journal for Research in Applied Science & Engineering Technology (IJRASET)



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 13 Issue IV Apr 2025- Available at www.ijraset.com

X. CONCLUSION

The grown CuI crystals show significant morphological and topographical variations from the original CuI crystals. The changes indicate different nucleation and growth kinetics, likely affected by factors such as solvent concentration, temperature, and impurity inclusion. The rough and porous nature of the grown crystals suggests a non-equilibrium growth process

The grown CuI crystals in the images exhibit high structural order, smooth surfaces, and well-defined facets, making them superior for electronic, optical, and semiconductor applications. Their single-crystalline nature and low roughness indicate controlled growth conditions, ideal for LEDs, solar cells, and sensor applications.

REFERENCES

- [1] K.P. Joshi, K.B.Saraf Acrylic Starlite Crystals Grown using Gel Method and its Characterization, AJCER, VOL4(1)28-32pp Jan, 2011
- [2] K.P. Joshi, K.B.Saraf, Growth of Multi-shaped Crystals of Copper iodide in Gel and its Characterization AJCR, Vol4 (2)84-87p.p, April, 2011
- [3] K.P.Joshi, Semiconducting copper sulphide grown Crystal in Gel and its characterisation.IORD, Vol2, 2348-0831p.p.Feb, 2015
- K.P.Joshi, Optical Structural electronical and Band gap determination of newly grown semiconducting Copper sulphide crystal using Gel method, IJAREEIE, Vol4 (2)23203765p.p.Feb, 2015
- [5] K.P.Joshi, Growth of copper Sulphide and iodide Crystal in Gel and its Characterizations, JORD, Vol7(9)166-179p.p.Dec,2017
- [6] K.P.Joshi, Make in India for Indian Development of Economy Globally with rising influence and its reflectance with corporate head reverence, Jan 2017.
- K.P.Joshi, B.S.Nandekar, Barun K.Mehata Growth of star shaped crystal of copper iodate in Gel and Effect of various Parameters on Crystal Growth ,Volume 4, Issue 4, April 2018International Journal of Scientific Research in Science and Technology (IJSRST)2395-6011(Print)2395-602X (Online) 5
- [8] K.P.Joshi, Growth of copper Sulphide and iodide Crystal in Gas-Gel and its Characterizations IJSRST international Journal of Scientific Research in science and Technology.(IJSRST), Volume 4, Issue 4, 449-454 April 2018, Online, 2395-602X,
- [9] K.P. Joshi, Synthesis of Semiconducting Copper Sulphide crystal grown in Gas- gel and its characterization, IJSRST international Journal of Scientific Research in science and Technology.(IJSRST), Volume 4, Issue 4, 40-4s April 2018, Online, 2395-602X, 5.327
- [10] K.P.Joshi, Issues of scheduled tribe in remote region, Activities for and by Adivasi peoples communicated
- [11] Singh and B. Kumar (2010), Impedance analysis and high temperature conduction mechanism of flux grown Pb(Zn_{1/3}Nb_{2/3})_{0.91}Ti_{0.09}O₃ single crystal ,Cryst. Res. Technol. Vol-45, pp 999.
- [12] Syed Ali, R. Saravanan, and M. Acigoz(2011), Growth and XRD analysis of the diluted magnetic semiconductor Zn_{1-x}Ni_xO,Cryst. Res. Technol. Vol-46, pp 327.
- [13] Chauhan, P. M. Vyas, and M. J. Joshi (2010), Growth and characterization of Struvite-K crystals Cryst. Res. Technol. Vol- 45, pp 493.
- [14] Parikh, D. J. Dave, B. B. Parekh and M. J. Joshi (2010), Growth and characterization of L-alanine doped KDP crystalsCryst. Res. Technol. Vol- 45, pp 70.
- [15] Xiujun Fan, Yue Wang, Hong Xu, and YijianJiang(2010), Floating zone growth and characterization of ruby single crystals Cryst. Res. Technol. Vol- 45, pp 603.
- [16] Ying Wu, Li-Juan Wang, and Guo-Yue Liu(2011), Explanations of the optical absorption and ESR spectrum for tetragonal Ni⁺ centers in CuAlS₂:Ni⁺ crystals, Cryst. Res. Technol. Vol- 46, pp 221.
- [17] Kumar, G. Varughese, L. Iype, R. Rajesh G. Joseph, and G. Louis(2010), Electrical conductivity of sulfamic acid single crystals , cryst. Res. Technol. Vol-45, pp 634.
- [18] Plachinda and E. Belokoneva(2010), Electron density in lead bromine and chlorine hilgardites on the basis of precise x-ray diffraction data and ab-initio calculations and correlation with the properties ,Cryst. Res. Technol. Vol- 45, pp 879.
- [19] Bauch, F. Henschel, and M. Schulze(2010), automatic detection and high resolution fine structure analysis of conic X-ray diffraction lines ,Cryst. Res. Technol. Vol- 45, pp 583.
- [20] iorani(1992), Comparison between fine particles and spin-glass properties in Studies of MagneticProperties of Fine Particles and Their Relevance to Materials Science, Eds.;Elsevier: Lausanne pp 135.
- [21] K.P. Joshi, IJIRT VOL Growth of Spherulite star shaped Copper iodate Crystals in Gel and its effective kinetic Parameters. Volume 7, ISSN2349-6002 ,09-02-2021
- [22] K.P. Joshi, IJSRST Growth of copper iodate Crystal in Gel and its characterization, ISSN2395-602X, 07/02/2021
- [23] K.P.Joshi, IJRAR, Growth of heavily conducting metal copper iodide Crystal in Gel and its characterization, ISSN2348-1269, 2021
- [24] D.S. Patil, S.B.Patil, K.P.Joshi. P.H.Pawar JOICS Studies on CIS thin Films as Solar Base Material Vol 11 issue 9 Page 595-604 ISSN 1548-7741,2021,UGC Approved group A Journal
- [25] K.P. Joshi, S.B.Patil; Growth of Copper Sulphide Crystal in Gel and its Thermal Spectroscopic Semiconducting Characterizations' and its Kinetic Parameters YMER ISSN 044-00477 page 246-256Vol20 issue 12 ,2021, Our journal is Scopus Active and included in UGC – CARE Group – II Journals List
- [26] M.M. Patil K.P. Joshi, S.B. Patil, P.V. Dalal; Studies on nanocomposites Nano plates and Perovskites Nano rod thin films YMER ISSN 044-00477 page 303-313Vol 20 issue 12, Dec 2021, Our journal is Scopus Active and included in UGC – CARE Group – II Journals List
- [27] D.S.Patil ,K.P.Joshi ,S.B.Deshmukh ,S.B.Patil,P.H.Pawar,'Non stoichiometric Chemically deposited Cdx Pb1-x S Thin films Vol-8-issue-4,IJRAR E-ISSN23481269,PAGE 551-559,2021,UGC Care list
- [28] K.P.Joshi, Thermal Characterisations of Grown Copper Iodate Crystal in Gel and Study of Its Parameters, International Journal of Science and Research (IJSR)pp-2024 3DOI:ttps://dx.doi.org/10.21275/SR241042142335-439 ISSN: 2319-7064, 7.942
- [29] Growth of heavily conducting metal copper iodide crystals in Gel and its structural analysis with kinetic Parameters International journal for innovative research in multidisciplinary field, VOL-10, 1/1/2024, ISSN(O): 2455-062,9.47,2024











45.98



IMPACT FACTOR: 7.129







INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089 🕓 (24*7 Support on Whatsapp)