iJRASET
International Journal For Research in Applied Science and Engineering Technology



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 14 **Issue:** VII **Month of publication:** July 2026

DOI: https://doi.org/10.22214/ijraset.2026.84275

www.ijraset.com

Call: 08813907089 | E-mail ID: ijraset@gmail.com

International Journal for Research in Applied Science & Engineering Technology (IJRASET)
ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538
Volume 14 Issue VII July 2026- Available at www.ijraset.com

Next Generation Nanomaterials for Energy, Environment and Healthcare

Pramod Kumar[1], Anil Kumar[2]
[1]*Department of Botany &* [2]*Department of Physics, Brahmanand College, Kanpur, UP, India, 208004*
[2]*anil66972@gmail.com*

Abstract: ***Nanomaterials are redefining technological boundaries across energy, environment and healthcare due to their unique size-dependent physical, chemical and optical properties. Next-generation nanomaterials including 2D materials, quantum dots, metal-organic frameworks, perovskites and bio-nanocomposites offer unprecedented efficiency and multifunctionality. In energy, nanostructured electrodes and perovskite solar cells have pushed efficiencies beyond 26%. In environment, MOFs and nano-adsorbents enable selective removal of CO_2, heavy metals and microplastics. In healthcare, theranostic nanoparticles and nano-biosensors provide targeted drug delivery and early disease diagnosis. This review synthesizes recent advances from 2020-2025, compares performance metrics, and outlines challenges in scalability, toxicity and regulation. We also present a roadmap for 2026-2035 for commercial translation. Integrating AI-driven materials discovery with green synthesis will accelerate next-generation nanomaterials from lab to market. These materials are key to achieving net-zero energy goals and SDG-3 and SDG-6 targets.***

Keywords: Next-generation nanomaterials; Energy storage; Environmental remediation; Nanomedicine; 2D materials; Perovskites; MOFs

I. INTRODUCTION

The 21st century faces a triad of global challenges: sustainable energy, environmental pollution, and healthcare accessibility. Conventional bulk materials are reaching performance limits. Nanomaterials, with at least one dimension <100 nm, exhibit quantum confinement, high surface area, and tunable bandgaps that enable breakthrough performance.[1][2]

The "next generation" refers to materials beyond simple nanoparticles. These include:

- 2D materials: Graphene, MXenes, TMDs for conductivity and catalysis
- Quantum Dots: Size-tunable optical properties for imaging and PV
- Metal-Organic Frameworks: Ultra-porous structures for gas capture
- Perovskite Nanocrystals: High-efficiency optoelectronics
- Bio-nanocomposites: Biocompatible, biodegradable materials for medicine. [3][4][5][6][7]

Market projection: Global nanomaterials market will reach $125.2 Billion by 2030, CAGR 13.8%. However, challenges of toxicity, cost and scale-up remain. [8] This review covers: 1) Energy applications, 2) Environmental remediation, 3) Healthcare. We compare performance, discuss mechanisms, and provide 2026 -2035 roadmap.

II. ENERGY APPLICATIONS

A. Next-Gen Batteries and Supercapacitors

- Li-ion batteries suffer from low energy density and slow charging. Nanostructured anodes solve this.
- Silicon Nanowires: 10x theoretical capacity of graphite. 1D structure accommodates 300% volume expansion.
- MXene Ti_3C_2Tx: 2D conductivity >10,000 S/cm, used as anode and current collector. Achieved 380 mAh/g at 1C.
- Graphene-Sulfur Cathodes: Nanoconfinement prevents polysulfide shuttle. 1200 mAh/g over 500 cycles. [9][10][11]


Material	Capacity	Cycle Life	Charge Rate	TRL	Application
Graphite Anode	372 mAh/g	1000	1C	9	Commercial Li-ion
Si Nanowires	3500 mAh/g	300	0.5C	6	EV Batteries
MXene Ti_3C_2Tx	380 mAh/g	5000	10C	5	Fast Charging
Li-S Nanocomposite	1200 mAh/g	500	0.2C	5	Drones/UAV

©IJRASET: All Rights are Reserved

Table 1: Performance Comparison of Next-Gen Battery Materials

B. Solar Cells and Hydrogen

- Perovskite Nanocrystals: $CsPbI_3$ quantum dots achieved 25.8% PCE in tandem with Si. Stability improved via encapsulation to >1000h.
- Plasmonic Au Nanoparticles: Enhance light absorption in dye-sensitized solar cells by 22%.
- Nanocatalysts for H_2: Pt single atoms on graphene for HER: over potential 28 mV @10 mA/cm². MoS_2 nanosheets as cheap alternative: 150 mV. [6][12][13]



Graph 1: Solar Cell Efficiency Progression 2015-2025

III. ENVIRONMENTAL APPLICATIONS

A. Water Purification and Pollutant Removal

1.3 billion people lack clean water. Nanomaterials provide selective adsorption and photocatalysis.

- MOFs: are porous naomaterials used for selective gas adsorption and carbon capture applications. UiO-66-NH_2 has 1200 m²/g surface area. Removes 99.9% Pb^{2+} in 10 min.
- Graphene Oxide Membranes: 1 nm channels reject 99% NaCl and 100% dyes.
- TiO_2 Nanotubes: Under UV, degrade 95% of pharmaceutical waste in 2h.
- Magnetic Fe_3O_4@SiO_2: Easy recovery, removes microplastics >10 µm. [5][14][15][16]

B. Air Pollution and CO2 Capture

- ZIF-8 MOF: CO_2 uptake 2.1 mmol/g at 1 bar, 298K.
- Carbon Nanotube Filters: PM2.5 removal efficiency 99.97% with low pressure drop.
- Nano-photocatalysts: g-C_3N_4 nanosheets convert CO_2 to CH_4 with 12% quantum efficiency. [5][17][18]

Pollutant	Nanomaterial	Mechanism	Removal %	Cost $/kg
Heavy Metals Pb^{2+}	UiO-66-NH_2 MOF	Adsorption	99.9	45
Dyes	GO Membrane	Size Exclusion	99.0	60
CO_2	ZIF-8 MOF	Physisorption	2.1 mmol/g	30
PM2.5	CNT Filter	Mechanical + Electrostatic	99.97	25
Pesticides	TiO_2 Nanotubes	Photocatalysis	95.0	15

Table 2: Nanomaterials for Environmental Remediation


IV. HEALTHCARE APPLICATIONS

A. *Theranostics and Drug Delivery*

1) Next-gen nanomedicine combines diagnosis + therapy.
2) Gold Nanorods: NIR absorption for photothermal cancer therapy. Tumor reduction 80% in mice.
3) Lipid Nanoparticles: Used in mRNA COVID vaccines. Enables organ-specific delivery.
4) Quantum Dots: CdSe/ZnS QDs for tumor imaging with NIR-II emission, penetration 2 cm.
5) Nanorobots: DNA origami nanobots deliver thrombin to tumors, cutting blood supply. [19][20][4][21]

B. *Biosensors and Diagnostics*

1) Graphene FET Biosensors: Detect COVID antigen at 1 fg/mL in 10 min.
2) MXene Sensors: Wearable patch monitors glucose and lactate in sweat.
3) Nanozymes: Fe_3O_4 nanoparticles mimic peroxidase for colorimetric assays. [22][10][23]



Graph 2: Detection Limit Comparison of Biosensors

C. *Regenerative Medicine*

1) Hydroxyapatite *Nanoparticles*: Scaffold for bone regeneration, 90% cell viability.
2) Nanofiber Patches: PCL/Gelatin for wound healing, promotes angiogenesis. [7][24]

Nanomaterial	Application	Target	Clinical Phase	Key Advantage
LNP-mRNA	Vaccine	COVID, Cancer	Approved	Targeted delivery
Au Nanorods	Photothermal Therapy	Breast Cancer	Phase II	NIR activation
Iron Oxide NP	MRI Contrast	Liver Tumor	Approved	T2 contrast
Graphene Sensor	Point-of-care	COVID, Cancer	Phase I	10 min detection
HA Nanoparticles	Bone Scaffold	Orthopedics	Phase III	Osteoconductive

©IJRASET: All Rights are Reserved

Table 3: Clinical Status of Healthcare Nanomaterials

V. CHALLENGES AND 2026-2035 ROADMAPS

A. Challenges

Despite rapid progress in nanotechnology, several key challenges hinder its widespread adoption.

1) Toxicity: remains a major concern due to ROS generation and bioaccumulation of nanoparticles in living organisms, which poses risks to human health and ecosystems.

2) Scale-up: is difficult and expensive. For example, CVD graphene still costs around $100/m², making it unfeasible for mass production. Lab-scale synthesis methods often fail to maintain quality and reproducibility at industrial levels.

3) Regulation is lacking as there are no unified nano-safety guidelines globally, which creates uncertainty for industries and investors. Additionally, issues like material stability, high energy consumption during manufacturing, and public acceptance also slow down commercialization. Addressing these challenges requires interdisciplinary research, stricter safety protocols, and cost-effective green synthesis methods. [25][26]




Figure 1: Development Pipeline for Next-Gen Nanomaterials

B. Roadmap

Year	Milestone
2026-2028	AI predicts 10,000 new MOFs. Solid-state batteries with Si-NW reach market.
2029-2032	Perovskite tandems 30% efficient. MOF water filters in 1M homes.
2033-2035	Nanorobots in clinical trials. Satellite-based nanosensor network for pollution. Self - healing nanomaterials in construction.

Table 4: Technology Roadmap and key Milestones (2026-2035)
Source: Author's compilation based on literature review [25] [26]




Figure 2- Technology Roadmap for Next-Generation Nanomaterials (2026-2035)

If these challenges are solved, nanotechnology can transform energy, healthcare, and environment sectors by 2035.

VI. CONCLUSION

Next-generation nanomaterials are no longer lab curiosities. With efficiencies >25% in solar, 99.9% pollutant removal, and fg-level biosensing, they address energy, environment and healthcare simultaneously. Success depends on green synthesis, AI-driven design, and strict safety frameworks. By 2035, these materials will be central to net-zero and precision medicine goals. Interdisciplinary collaboration is essential to translate nano-innovation into global impact.


1) Conflict of Interest: The author's declare no conflict of interest.
2) Funding: No funding was received.
3) Acknowledgement: Author's thanks Brahmanand College, Kanpur for support.

REFERENCES

[1] Kroto, H. W. et al. C60: Buckminsterfullerene. Nature 318, 162-163 (1985).
[2] Iijima, S. Helical microtubules of graphitic carbon. Nature 354, 56-58 (1991).
[3] Novoselov, K. S. et al. Electric field effect in atomically thin carbon films. Science 306, 666-669 (2004).
[4] Chan, W. C. W. & Nie, S. Quantum dot bioconjugates for ultrasensitive nonisotopic detection. Science 281, 2016-2018 (1998).
[5] Furukawa, H. et al. The chemistry and applications of metal-organic frameworks. Science 341, 1230444 (2013).
[6] Kojima, A. et al. Organometal halide perovskites as visible-light sensitizers for photovoltaic cells. JACS 131, 6050-6051 (2009).
[7] Chen, Q. Z. et al. Bioactive nanocomposites for tissue engineering. Prog. Mater Sci. 54, 1-54 (2009).
[8] Grand View Research. Nanomaterials Market Size Report 2024-2030 (2024).

[9] Chan, C. K. et al. High-performance lithium battery anodes using silicon nanowires. Nat. Nanotechnol. 3, 31-35 (2008).
[10] Anasori, B. et al. Two-dimensional metal carbides and nitrides. Nat. Rev. Mater. 2, 16098 (2016).
[11] Ji, X. et al. Graphene-sulfur composite as cathode for Li-S batteries. Nano Lett. 9, 3843-3848 (2009).
[12] Atwater, H. A. & Polman, A. Plasmonics for improved photovoltaic devices. Nat. Mater. 9, 205-213 (2010).
[13] Deng, J. et al. Highly active and stable black phosphorus single-atom catalyst for HER. Nat. Commun. 11, 699 (2020).
[14] Nair, R. R. et al. Unimpeded permeation of water through graphene oxide membranes. Science 335, 442-444 (2012).
[15] Fujishima, A. & Honda, K. Electrochemical photolysis of water at a semiconductor electrode. Nature 238, 37-38 (1972).
[16] Zhang, W. et al. Magnetic nanoparticles for microplastic removal. Environ. Sci. Technol.54, 11832-11840 (2020).
[17] De Volder, M. F. L. et al. Carbon nanotubes: present and future commercial applications. Science 339, 535-539 (2013).
[18] Ong, W. J. et al. Graphitic carbon nitride for CO2 reduction. Chem. Rev. 118, 10451-10484 (2018).
[19] Huang, X. et al. Cancer cell imaging and photothermal therapy using Au nanorods. JACS 128, 2115-2120 (2006).
[20] Hou, X. et al. Lipid nanoparticles for mRNA delivery. Nat. Rev. Mater. 6, 1078-1094 (2021).
[21] Li, S. et al. A DNA nanorobot for tumor-targeted drug delivery. Nat. Biotechnol.36, 258-264 (2018).
[22] Seo, G. et al. Rapid detection of COVID-19 using graphene FET. ACS Nano14, 5135-5142 (2020).
[23] Gao, L. et al. Intrinsic peroxidase-like activity of ferromagnetic nanoparticles. Nat. Nanotechnol.2, 577-583 (2007).
[24] Li, W. J. et al. Electrospun nanofibrous scaffolds for tissue engineering. Biomaterials 23, 2467-2478 (2002).
[25] Nel, A. et al. Toxic potential of materials at the nanolevel. Science 311, 622-627 (2006).
[26] Klaessig, F. et al. Nanotechnology regulation and policy worldwide. Wiley Interdiscip. Rev. Nanomed. 13, e 1626 (2021).

©IJRASET: All Rights are Reserved | SJ Impact Factor 7.538 | ISRA Journal Impact Factor 7.894 |



10.22214/IJRASET

45.98

IMPACT FACTOR: 7.129

IMPACT FACTOR: 7.429

INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089 (24*7 Support on Whatsapp)