



IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 12 Issue: III Month of publication: March 2024
DOI: https://doi.org/10.22214/ijraset.2024.59116

www.ijraset.com

Call: 🕥 08813907089 🔰 E-mail ID: ijraset@gmail.com



Parameters Optimization on Abrasive Water Jet Machining of Zerconia Ceramics

Dr. B. Anjaneyulu¹, P. Bhuvaneswar², K. Amarnath³, A. Chennakesava Reddy⁴, Shaik Althaf⁵, V. Charan⁶ ¹Associate Professor, Dept. of Mechanical Engineering, Srinivasa Ramanujan Institute of Technology, Anantapur, Andhra Pradesh ^{2, 3, 4, 5, 6}Mechanical Students, Srinivasa Ramanujan Institute of Technology, Anantapur, Andhra Pradesh

Abstract: Ceramic materials play a vital role in industries for several reasons, owing to their unique combination of properties such as high temperature resistance, high wear and abrasion resistance and electrical insulation. Conducting experiments on an abrasive water jet machine involves manipulating three input parameters at three levels each. The parameters are water pressure (1.5 bar, 2.5 bar, and 3.5 bar), standoff distance (4 mm, 8 mm, and 12 mm), and abrasive flow rate (6 gm/sec, 12 gm/sec, and 18 gm/sec).

The responses measured are material removal rate (MRR) and surface roughness (Ra). To systematically study the impact of these parameters the Design of Experiments (DOE) methodology is employed utilizing the L_9 Orthogonal Array (OA) to streamline the experimental design.

The Taguchi technique is then applied to predict the optimal process parameters. For a comprehensive analysis of Variance (ANOVA) is employed to quantify the percentage contribution of each input parameter to the responses shedding light on their relative significance.

Additionally the regression coefficient (\mathbf{R}^2) is assessed to gauge the degree of agreement between the experimental and predicted values for the responses.

Keywords: ANOVA, DOE, ZrO₂, Water Jet Machine

I. INTRODUCTION

Zirconium oxide, commonly known as zirconium (ZrO_2) is a remarkable ceramic material that has garnered significant attention across industries due to its exceptional combination of properties. Formed from the chemical bonding of zirconium and oxygen atoms, zirconium exhibits a crystalline structure that can vary from cubic to tetragonal or monoclinic [1] each configuration offering distinct characteristics. With its high melting point [2], impressive mechanical strength, chemical inertness and biocompatibility, zirconium oxide has found myriad applications in fields as diverse as aerospace, biomedicine, electronics, and industrial manufacturing [3].

The abrasive water jet machine represents a cutting edge technology that revolutionizes the precision cutting and shaping of materials [4] across various industries. Harnessing the power of high pressure water streams infused with abrasive particles [5] this cutting system offers unparalleled versatility accuracy and efficiency in processing a wide range of materials, from metals and composites to stone and ceramics [6].

The Taguchi Method, developed by Dr. Genichi Taguchi is a powerful statistical approach to design optimization and quality improvement in manufacturing processes [7]. This methodology rooted in experimental design and robust engineering principles, aims to minimize variation and optimize performance by identifying and controlling key factors that influence product quality and performance [8].

ANOVA, or Analysis of Variance, is a statistical method used to analyze the differences among group means in a sample [9]. It is a powerful tool for comparing the means of three or more groups and determining whether there are statistically significant differences between them.

ANOVA is widely used in various fields such as psychology, biology, economics, and social sciences to compare the effects of different treatments or interventions on a dependent variable [10].

II. EXPERIMENTATION AND METHODOLOGY:

Size of the Specimen 50*50*5 mm

Experiment conducted on abrasive water jet machine on zerconia ceramic materials



International Journal for Research in Applied Science & Engineering Technology (IJRASET) ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 12 Issue III Mar 2024- Available at www.ijraset.com



Fig.1 ZrO₂ Specimens before machining

Fig.2 Abrasive water jet machine experimental setup



Fig.3 Specimens after machining



Fig.4 Digital Weighing Machine



Fig.5 Surface Roughness Tester

Table 1	: Input	Parameters	and	their	level	s
---------	---------	------------	-----	-------	-------	---

S. No.	Factors	Unit	Level 1	Level 2	Level 3
1.	Pressure	bar	1.5	2.5	3.5
2.	Standoff Distance	mm	4	8	12
3.	Abrasive flow rate	gm/Sec.	6	12	18



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538

Volume 12 Issue III Mar 2024- Available at www.ijraset.com

	/	6 ,				
	Process Parameters					
Exp. No.	Pressure (bar)	SOD (mm)	AFR (gm/Sec.)			
1	1.5	4	6			
2	1.5	8	12			
3	1.5	12	18			
4	2.5	4	12			
5	2.5	8	18			
6	2.5	12	6			
7	3.5	4	18			
8	3.5	8	6			
9	3.5	12	12			

Table: 2 L ₉ Orthogonal A	Array
--------------------------------------	-------

Table: 3 Weight of the specimen before and after machining

<i>61.33</i>		Parameters		Initial	Final	Time (Min)
SI. No.	Pressure (bar)	SOD (mm)	AFR (gm/Sec.)	(g)	Weight (g)	
1	1.5	4	6	48	47.493	3.16
2	1.5	8	12	47.493	46.76	3.01
3	1.5	12	18	46.76	46.02	3
4	2.5	4	12	48	47.24	3.3
5	2.5	8	18	47.24	46.51	3.18
6	2.5	12	6	46.51	45.83	3.13
7	3.5	4	18	48	47.16	3.3
8	3.5	8	6	47.16	46.55	3.05
9	3.5	12	12	46.55	45.71	2.98

III. RESULTS AND DISCUSSION

Table:	4 Material	Removing	Rate (MRR)	and S/N	Ratio of MRR
--------	------------	----------	------------	---------	--------------

SI No	Parameters			Measured MPP	Means	S/N Ratio
51. 110.	Pressure SOD (mm) AFR		(gm/Min.)			
	(bar)		(gm/Sec)	_		
1	1.5	4	6	0.160400	0.160400	-15.8959
2	1.5	8	12	0.243889	0.243889	-12.2562
3	1.5	12	18	0.245556	0.245556	-12.1970
4	2.5	4	12	0.228000	0.228000	-12.8413
5	2.5	8	18	0.228095	0.228095	-12.8377
6	2.5	12	6	0.217273	0.217273	-13.2599
7	3.5	4	18	0.252778	0.252778	-11.9452
8	3.5	8	6	0.199286	0.199286	-14.0105
9	3.5	12	12	0.280000	0.280000	-11.0568



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 12 Issue III Mar 2024- Available at www.ijraset.com

Level	Р	SOD	AFR
1	-13.45	-13.56	-14.39
2	-12.98	-13.03	-12.05
3	-12.34	-12.17	-12.33
Delta	1.11	1.39	2.34
Rank	3	2	1

Table 5: Response table for S/N Ratio of MRR

The material removal rate is influenced by various parameters as depicted in Table 7. Analyzing the Abrasive Flow Rate (AFR) parameter reveals that the maximum Signal-to-Noise (SN) ratio value occurs at the third level (-12.33 dB), while the minimum SN ratio value is observed at level 1 (-14.39 db). The resulting delta value, representing the difference between the maximum and minimum is 2.34 dB. Consequently AFR emerges as the most impactful parameter (Rank 1) when compared to the other two input parameters. Standoff distance, the second parameter, demonstrates a maximum SN ratio at level 3 (-12.17 db) and a minimum SN ratio at level 1 (-13.56 db), with a delta value of 1.39 dB (Rank 2). In contrast pressure is identified as the least impactful parameter on the material removal rate, with a delta value of 1.11 db highlighting its minimal influence.

Table 6: Response Table for Means						
Level	Р	SOD	AFR			
1	0.2166	0.2137	0.1923			
2	0.2245	0.2238	0.2506			
3	0.2440	0.2476	0.2421			
Delta	0.0274	0.0339	0.0583			
Rank	3	2	1			

T 11





ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 12 Issue III Mar 2024- Available at www.ijraset.com



Fig.7 Main Effects plots for S/N Ratio

Examining the connection between the means of Material Removal Rate (MRR) and the input parameters, as illustrated in Figure 16, reveals distinct patterns. When the pressure is elevated from 1.5 rpm to 3.5 bar there is a gradual increase in material removal. Similarly, as the standoff distance expands from 4 mm to 12 mm, the response value also exhibits a progressive rise. Finally as the abrasive flow rate (AFR) is increased from 6 mm to 12 mm, the response value experiences a sudden surge. However a further increase in AFR leads to a sudden decrease in the material removal rate.

The correlation between input parameters and the Signal-to-Noise (SN) ratio of the Material Removal Rate (MRR) is depicted in Figure 17. When the pressure is elevated from 1.5 bar to 3.5 bar there is a sudden increase in the SN ratio. Similarly, as the standoff distance expands from 4 mm to 12 mm, the SN ratio also experiences a sudden surge. Lastly, when the abrasive flow rate (AFR) is increased from 6 mm to 8 mm, the SN ratio rises abruptly. However, with a further increase in AFR, the SN ratio gradually declines

Sl. No	Input Parameters	Unit	Optimum level	Value		
1	1 Pressure (P) b		3	3.5		
2	Standoff distance (SOD)	mm	3	12		
3 Abrasive flow rate (AFR)		gm/min	2	12		
	Optimum SN Ratio: -11.0568 (0.280000db)					
Experimental SN ratio: -10.7156 (0.285532 db)						
Improvement SN Ratio:0.3412 (0.005532 db)						

Table. 7	Optimum	Parameters
----------	---------	------------

After selecting the optimum cutting parameters, the final step is checked and determines the improvement of MRR (g/sec.) to predict and verify the optimization by using the optimum level machining parameters the experimentation was once again performed at P_3 , SOD₃, AFR₂ The parametric combination for maximum MRR (g/sec) was observed at Pressure (P=3.5 bar), Standoff distance (SOD= 12 mm), and finally Abrasive flow rate (AFR = 12g/min) respectively.

	rable. 8 Analysis of Variance of Wixk						
Source	DF	Adj SS	Adj MS	F-Value	P-Value	% Contribution	
Р	2	0.001195	0.000598	2.85	0.260	12.7	
SOD	2	0.001818	0.000909	4.34	0.187	19.36	
AFR	2	0.005954	0.002977	14.20	0.066	63.42	
Error	2	0.000419	0.000210	-	-	4.4	
Total	8	0.009387	-				

 $R^2 = 95.53\% R^2 (adj) = 82.13$



International Journal for Research in Applied Science & Engineering Technology (IJRASET) ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 12 Issue III Mar 2024- Available at www.ijraset.com

At a 99% confidence level the analysis of variance (ANOVA) revealed the percentage contribution of each parameter and error to the material removal rate (MRR). The predominant influence on MRR was attributed to abrasive flow rate, accounting for 63.42%, followed by standoff distance with a contribution of 19.36%, and water pressure at 12.7%, respectively. The regression coefficient of MRR stands at 95.53%, indicating a strong agreement between the measured and predicted values. **Regression Equation**

 $MRR = 0.22836 - 0.01175 P_{1.5} - 0.00391 P_{2.5} + 0.01566 P_{3.5} - 0.01464 SOD_{4} - 0.00461 SOD_{8}$ + 0.01925 SOD_12 - 0.03604 AFR_6 + 0.02227 AFR_12 + 0.01378 AFR_18

Table 9. Surface Roughness Measurements						
		Parameters		Surface		
SI. No.	Pressure	SOD (mm)	AFR	Roughness		
	(bar)		(gm/Sec.)	(Ra)		
1	1.5	4	6	3.745		
2	1.5	8	12	3.695		
3	1.5	12	18	3.025		
4	2.5	4	12	4.145		
5	2.5	8	18	1.075		
6	2.5	12	6	1.085		
7	3.5	4	18	4.595		
8	3.5	8	6	3.135		
9	3.5	12	12	2.478		

Table.10 Response Table for Signal to Noise Ratios

Level	Р	SOD	AFR
1	-10.812	-12.355	-7.367
2	-4.562	-7.302	-10.695
3	-10.518	-6.235	-7.829
Delta	6.250	6.120	3.328
Rank	1	2	3

The surface roughness rate is influenced by various parameters as depicted in Table 7. Water pressure (P) parameter reveals that the maximum Signal-to-Noise (SN) ratio value occurs at the second level (-4.562 db), while the minimum SN ratio value is observed at level 1 (-10.812 dB). The resulting delta value representing the difference between the maximum and minimum is 6.250 dB. Consequently Pressure emerges as the most impactful parameter (Rank 1) when compared to the other two input parameters. Standoff distance the second parameter demonstrates a maximum SN ratio at level 3 (-6.235 db) and a minimum SN ratio at level 1 (-12.355 db) with a delta value of 6.120 db (Rank 2). In contrast abrasive flow rate is identified as the least impactful parameter on the material surface roughness with a delta value of 3.328 db highlighting its minimal influence.

Table.11 R	Response	Table for	Means of	Surface	Roughness
------------	----------	-----------	----------	---------	-----------

Level	Р	SOD	AFR
1	3.488	4.162	2.655
2	2.102	2.635	3.488
3	3.452	2.245	2.898
Delta	1.387	1.917	0.833
Rank	2	1	3



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 12 Issue III Mar 2024- Available at www.ijraset.com



Fig.8 Main effects plots for S/N Ratio



Fig.9 Main effects plot for Means

Analyzing the correlation between the Signal-to-Noise (S/N) ratio of Surface Roughness (Ra) and the input parameters as depicted in Figure 16, unveils distinctive trends. As the pressure ascended from 1.5 bar to 2.5 bar the S/N ratio exhibited a sudden increase however, with a subsequent rise in pressure from 2.5 bar to 3.5 bar, the S/N ratio experienced a sudden decrease. Regarding the relationship between the S/N ratio and standoff distance (SOD) an abrupt surge in the S/N ratio was observed when the SOD increased from 4 mm to 8 mm. With further increments in SOD the S/N ratio exhibited a gradual increase. Finally examining the connection between the Abrasive Flow Rate (AFR) and S/N ratio revealed that as AFR escalated from 6 gm/sec to 12 gm/sec the S/N ratio underwent a sudden decrease. Conversely, upon further elevation of the AFR value the S/N ratio exhibited a sudden increase.

The relationship between input parameters and the surface roughness means is illustrated in Figure 17. Upon increasing the pressure from 1.5 bar to 2.5 bar, there is a sudden decrease in the means. This trend continues with further increments in pressure showcasing a decline in the means of surface roughness. Similarly, as the standoff distance extends from 4 mm to 12 mm, the means experiences a gradual decrease, declining slowly. Finally, when the abrasive flow rate (AFR) is raised from 6 mm to 12 mm, the means shows an abrupt rise. However upon further increasing the AFR the means gradually declines.



International Journal for Research in Applied Science & Engineering Technology (IJRASET) ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538

Volume 12 Issue III Mar 2024- Available at www.ijraset.com

Table: 12 Optimum Parameters on Ra

Sl. No	Input Parameters	Unit	Optimum level	Value		
1	Pressure (P)	bar	2	2.5		
2	Standoff distance (SOD)	mm	3	12		
3	Abrasive flow rate (AFR)	gm/min	1	6		
Experimental SN ratio: -0.903745 db (0.97388µm)						
Optimum SN Ratio: -0.7086db (1.085µm)						
Improvement SN Ratio: 0.1951db (0.112µm)						

Table.13 Analysis of Variance of Ra

Source	DF	Adj SS	Adj MS	F-Value	P-	%
					Value	Contribution
Р	2	3.747	1.8733	2.64	0.275	30.15
SOD	2	6.156	3.0782	4.34	0.187	49.55
AFR	2	1.102	0.5509	0.78	0.563	8.86
Error	2	1.419	0.7094	-	-	11.42
Total	8	12.424	-	-		-

 $R^2 = 88.58\%$

Regression Equation of Ra

 $Ra = 3.014 + 0.474 P_{1.5} - 0.912 P_{2.5} + 0.438 P_{3.5} + 1.148 SOD_4 - 0.379 SOD_8 - 0.769 SOD_{12} - 0.359 AFR_6 + 0.474 AFR_{12} - 0.116 AFR_{18}$

IV. CONCLUSION

The study utilized an L_9 orthogonal array for experimentation. The results showed that all input parameters had probability values for responses that were less than 0.5, indicating their significance on the responses.

ANOVA analysis revealed the percentage contribution of each parameter to the outcomes. For the material removal rate, abrasive flow rate had the highest contribution at 63.42%, followed by standoff distance at 19.36%, and water pressure at 12.7%.

Regarding surface roughness, standoff distance had the most significant contribution at 49.55%, followed by water pressure at 30.15%, and abrasive flow rate at 8.86%.

The regression coefficients (R^2) for material removal rate and surface roughness were found to be 95.53% and 88.58%, respectively, at a 99% confidence level, as confirmed by further testing at the same confidence level. These findings underscore the substantial impact of the input parameters on the studied responses, highlighting the importance of optimizing these parameters for desired

REFERENCES

- Pecharromµn, B. C., Esteban-betegón, F., Bartolomø, J. F., López-esteban, S., and Moya, J. S., 2010, "New Percolative BaTiO 3 ± Ni Composites with A," (20), pp. 1541–1544.
- [2] Abden, M. J., Islam, M. K., and Afroze, J. D., 2014, "Microstructure and Mechanical Properties of 3YSZ Ceramics Rainforced with Al 2 O 3 Particles," 4(4), pp. 129–135.
- [3] Kim, S. W., and Khalil, K. A. R., 2006, "High-Frequency Induction Heat Sintering of Mechanically Alloyed Alumina-Yttria-Stabilized Zirconia Nano-Bioceramics," J. Am. Ceram. Soc., 89(4), pp. 1280–1285.
- [4] Daguano, J. K. M. F., Santos, C., and Souza, R. C., 2007, "Properties of ZrO 2 Al 2 O 3 Composite as a Function of Isothermal Holding Time," i, pp. 374– 379.
- [5] Chandra, B., 2011, "A Study of Effect of Process Parameters of Abrasive Jet Machining," Int. J. Eng. Sci., 3(1), pp. 504–513.
- [6] Jain, N. K., Jain, V. K., and Deb, K., 2007, "Optimization of Process Parameters of Mechanical Type Advanced Machining Processes Using Genetic Algorithms," Int. J. Mach. Tools Manuf., 47(6), pp. 900–919.



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 12 Issue III Mar 2024- Available at www.ijraset.com

- [7] Nagendra Prasad, K., John Basha, D., and Varaprasad, K. C., 2017, "Experimental Investigation and Analysis of Process Parameters in Abrasive Jet Machining of Ti-6Al-4V Alloy Using Taguchi Method," Mater. Today Proc., 4(10), pp. 10894–10903.
- [8] Srikanth, D. V, and Rao, D. M. S., 1987, "Review Article ABRASIVE JET MACHINING-RESEARCH REVIEW," Int. J. Adv. Eng. Technol.
- [9] Reddy, S. M., Hussain, S., and Rao, M. S., 2015, "Experimental Analysis and Optimization of Process Parameters in Machining of RCFRP by AJM," Int. J. Innov. Res. Sci. Eng. Technol., 4(8), pp. 7085–7092.
- [10] Neseli, S., 2014, "Optimization of Process Parameters with Minimum Thrust Force and Torque in Drilling Operation Using Taguchi Method," 2014.











45.98



IMPACT FACTOR: 7.129







INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089 🕓 (24*7 Support on Whatsapp)