



IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 9 Issue: XII Month of publication: December 2021 DOI: https://doi.org/10.22214/ijraset.2021.39388

www.ijraset.com

Call: 🕥 08813907089 🔰 E-mail ID: ijraset@gmail.com



## Production and Characterization of Commercial Aluminum Powders by a New Nozzle Design and Atomization Unit

Hakan GÖKMEŞE

Seydisehir Ahmet Cengiz Engineering of Faculty, Necmettin Erbakan University, Seydisehir-Konya, Turkey

Abstract: A large area cross section of the production of spherical metal powders by gas atomization in the manufacturing method. Powder metal characteristic improves with small powder size. This aim was realized by vertical gas atomization unit, a new a closely-matched nozzle system and manufacture. In the experimental studies, pure aluminium powders which has an important place in the automotive, air and defence industries were produced. In the studies carried out with the Vertical Gas Atomization unit, aluminium was superheated up to 900°C and atomized at different gas pressures (20-30 bar). Scanning electron microscope (SEM) and particle size measuring device were used for the characterization and size measurements of the produced powders, respectively. The average particle size of the finest powder produced with increasing atomization pressure was determined as d50=19.50µm. Aluminium powder shape and morphology was used as spherical and very little satellization was seen.

Keywords: Powder Metallurgy, Atomisation, Nozzle, Al powder, Characterisation

### I. INTRODUCTION

Powder metallurgy (P/M) is the production of metal or ceramic powders and the process of turning these powders into parts by combining them with mechanical and thermal effects. The production of parts by the powder metallurgy method is very widely used today, and this is increasingly becoming an alternative to the well-known classical production methods [1, 2].

The method is based on the principle of giving shape to metal or alloy particulates under pressure and keeping them at a temperature below melting temperatures [3].

The use of the powder metallurgy manufacturing technique is increasing in the production of engineering materials day by day. Advances in powder technology allow the production of complex-shaped machine parts at a high production speed, high quality, low dimensional tolerance, and economically by using different pressing techniques [4].

There are four basic mechanisms in the production of metal powders. These are mechanical methods, chemical methods, electrolysis method, and atomization methods. The fact that one method of powder production can be chosen over others depends on the economy of the method, whether it is understood, the characteristics of the powders obtained, and to what extent these characteristics can meet the needs of the place of use.

Depending on the production method, the geometric shape of a powder can be in many different shapes, from spherical to dendritic forms. Moreover, the surface condition of the powder (i.e. being smooth or porous) also varies based on the production method. Among these production methods, the gas atomization method is most commonly used to obtain fine and spherical powders [5].

Atomization is defined as the breaking down of molten metal into very small droplets by water, air, and gas pressure or mechanically and then the solidification of it.

Therefore, the atomization process is divided into four different parts: water atomization, gas atomization, centrifugal atomization, and vacuum atomization [6, 7]. Among them, gas atomization is the most common, and it is a low-cost method that allows the production of a variety of particle sizes from 1  $\mu$ m to several millimeters. Molten liquid metal is atomized with various gases such as air, argon and/or nitrogen [8]. In this system, it is possible to produce fine spherical powder particles by a closely-matched nozzle system or designs [9].

In this study, a pure aluminum material, which is widely used in automotive, aerospace, and defense industries, was produced in spherical powder shape morphology by using the vertical gas atomization method.



International Journal for Research in Applied Science & Engineering Technology (IJRASET)

ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 9 Issue XII Dec 2021- Available at www.ijraset.com

#### II. MATERIAL AND METHOD

The aluminum raw material used in pure aluminum (Al) powder metal productions was commercially supplied with a purity of 99.70% (Table 1). In the Al material, the remaining composition consists of trace amounts of other chemicals.

TABLE I							
Chemical composition of commercial Al material (%)							
Al	Si	Fe	Cu	Mg	Zn	Cr	Ni
99.7	0.0508	0.147	0.0013	0.005	0.0046	0.0054	< 0.0030

In the experimental studies, the vertical gas atomization method was used for the production of pure Al powders (Figure 1). The vertical gas atomization method used in the experimental studies includes stages such as the Melting system, Nozzle, Atomization tower and Cyclones, Powder collection sections, and Pressurized gas system. It can be said that one of the most important parameters in the production of metal powder is the design and manufacture of nozzles. In this study, a closely-matched nozzle system, which had been designed and manufactured, was used (Figure 2).



Fig 1. Vertical gas atomization unit designed and manufactured

In experimental studies focused on the production of metal powder, the liquid metal temperature was selected as 900°C and argon gas was used as a high-pressure fluid jet. In aluminum powder production experiments, gas pressures of 20-25-30 bar were studied. An optimum gas pressure providing a fine and spherical powder shape morphology in terms of these pressure values was investigated. Powder size analysis was performed with the Mastersizer 3000 model device. The XRD analyses of the powder material were also performed using the Mastersizer model device. In order to determine the effects of different gas pressure and temperature values on the shape and morphology of pure Al powder, microstructure imaging studies were carried out with an optical microscope and Scanning Electron Microscope (SEM).



Fig 2. Close-coupled nozzle design (a) and manufacture (b)



International Journal for Research in Applied Science & Engineering Technology (IJRASET) ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 9 Issue XII Dec 2021- Available at www.ijraset.com

#### III. RESULTS AND DISCUSSION

XRD analysis was applied to the commercial pure aluminum material supplied as the starting material for the production of aluminum powder by using the vertical gas atomization technique, which is one of the methods of powder metallurgy production (Figure 3). When the result of the obtained XRD analysis was examined, it was seen that all of the resulting peaks represented the pure aluminum material.



Fig 3. XRD analysis of commercial pure aluminum

The production of the material supplied as commercial pure aluminum was carried out at 900°C temperature and variable gas pressures (20-25-30 bar) by using the vertical gas atomization method. The powder shape and morphology of the pure aluminum material from which powder production was done are given in Figure 4. When the SEM images in Figure 4 were examined, it was determined that rod-like, teardrop, and spherical powder shapes and morphologies were formed. In particular, it was determined that the powders produced at an atomization pressure as low as 20 bar were mostly in the rod-like and teardrop powder shapes as well as the targeted spherical shape morphology (Figure 4a). On the other hand, it was observed that the powders were formed in the spherical powder shape and morphology in experiments performed with increased atomization pressures (25-30) (Figure 4b). In particular, when SEM images of aluminum powders obtained using an atomization pressure as high as 30 bar were examined (Figure 4c), it was determined that almost all of the powders were formed in spherical shapes. The powder shape that is likely to form in powder particles produced by the atomization method is known as spherical/near-spherical [10]. It was observed that the powder particles obtained in this way, especially with increasing atomization pressure, were in spherical forms (Figure 5).





International Journal for Research in Applied Science & Engineering Technology (IJRASET)

ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538 Volume 9 Issue XII Dec 2021- Available at www.ijraset.com



Fig 4 SEM images of pure Al powders; a) 20 bar, b) 25 bar, c) 30 bar

In particle size measurement processes performed after the production of metal powders, sieve analysis process is mostly applied conventionally. In addition, considering the imaging and microstructure studies that have been developing in recent years, size measurements are also performed during the imaging process by using electron microscopes. In this regard, particle size measurements were performed using SEM images of aluminum powders (Figure 5a). After particle size measurement procedures based on spherical powder shape and morphology, it was determined that the majority of powders were below  $20\mu$ m. In addition, when the SEM image was examined (Figure 5b), it was observed that there were powders in sizes of  $3\mu$ m,  $8.11\mu$ m, and  $2.54\mu$ m, respectively. In the literature, the holding/adhesion of fine powders that have just completed solidification to coarse powders that had completed solidification is defined as "satellization" [11]. This condition was detected in powders with a particle size of 3 or 5  $\mu$ m in the form of adhesion to large powder particles (satellization).



Fig 5 SEM images of pure Al powders produced at 30 bar

In commercial pure aluminum powder metal production processes, the atomization was tested by performing different experiments that had different gas pressures. The effect of this condition on the powder size was evaluated. It was found that as gas pressure increased, the size of the powder decreased.

The reason for this is the energy transferred to the molten liquid metal. Therefore, the more energy that can be transferred to liquid metal during the gas atomization, the smaller the produced powder particles can be [12]. In this context, it was found in experimental studies that the powder size decreased with increasing atomization gas pressure (Figure 6). As can be seen in Figure 6, the finest powder particle size was obtained at an atomization pressure of 30 bar as  $d_{50}=19.50\mu$ m. At low atomization pressures, that is, in experiments where 25 and 20 bars were applied, the particle sizes were measured as  $d_{50}=20.846\mu$ m and  $d_{50}=26.436\mu$ m, respectively.

Thus, it is believed that in addition to the increased atomization pressure, the designed and manufactured closely-matched nozzle system was also effective on the size of the powder examined.





Fig 6 Particle size variation at different atomization pressures

#### **IV. CONCLUSIONS**

In this study, the production and characterization of commercial pure aluminum powders were carried out by using the designed and manufactured vertical gas atomization unit and nozzle together. The obtained results are summarized below;

In the context of the production of commercial pure aluminum powders, the finest powder size was obtained under a molten metal temperature of 900°C and pressure of 30 bar. It was determined that especially at low pressures, the powders were in shapes and morphologies called rod-like and teardrop as well as the spherical powder form. With an atomization pressure of 30 bar, a completely spherical powder shape and morphology was produced. It was determined with SEM images that small-sized gas-atomized aluminum powders form a satellization over larger-sized powders. As a result of the particle size measurements, the smallest powder size was determined as  $d_{50}=19.50\mu m$  with an atomization pressure of 30 bar.

#### REFERENCES

- [1] Güven, Ş. Y., Powder Metallurgy and Metallic Foams, SDU Journal of Technical Sciences, 2011 1 (2) 22-28.
- [2] Gökmeşe, H., Effects on Pore Morphology and Microstructural Properties of Pressing and Sintering in AA 2014 Alloy, GU J Sci Part: C 1(1):1-8 (2013).
- [3] Gökçe, A., Powder Metallugy Processing of Magnesium and Its Alloys, Düzce University Journal of Science and Technology, 8 (2020) 522-534.
- [4] Çolak, N. Y., Turhan, H., The Investigation of Microstructure and Mechanical Properties of Al Si/B4C Composites Produced by Using Powder Metallurgy Method, Science and Eng. J of First Univ. 28 (2), 259-266, 2016.
- [5] Akkaş, M., Çetin, T., Boz, M., Am60 Magnesium Alloy Powder Production and Characterization by Gas Atomization Method, SDU International Journal of Technological Sciences Vol. 10, No 3, December 2018 pp. 1-9.
- [6] Akkaş, M., Akra, K.M., Çetin, T., Boz, M., Investigation of the Effect of Gas Pressure on AZ31 Mg Powder Production by Gas Atomization Method, GUFBED 9(2) (2019) 215-221.
- [7] Akkaş, M., Çetin, T., Boz, M., Production and characterization of All2Si powder by gas atomization method, DUMF Journal of Engineering 9:2 (2018): 795-804.
- [8] Tsirlis, M., Michailidis, N., The influence of gas pressure and temperature on the characteristics of aluminium powder produced by a novel low-pressure hot gas atomisation process, Powder Metallurgy DOI: 10.1080/00325899.2021.1963565, 2021.
- [9] Mullis, A.M., McCharty, I.N., Cochrane, R.F., High speed imaging of the flow during close-coupled gas atomisation: Effect of melt delivery nozzle geometry, Journal of Materials Processing Technology 211 (2011) 1471–1477
- [10] Mateusz, S , Marek, H., Ricardo, B, Gernot, P., Stefan, M. and Christof, S., Preparation Method of Spherical and Monocrystalline Aluminum Powder, Metals 2019, 9, 375.
- [11] Chao-feng GA, Zhi-yu X, Hai-ping, Z., Zhong-qiang, L., Jin, C., Shang-kui, L., Da-tong, Z., Characterization of spherical AlSi10Mg powder produced by double-nozzle gas atomization using different parameters, Trans. Nonferrous Met. Soc. China 29(2019) 374–384.
- [12] Bostan, B., "Production and Characterization of AA 2014 Alloy Powders by Gas Atomization Method", 5th National Powder Metallurgy Conference, TOBB, Ankara, 1-8, 2008.











45.98



IMPACT FACTOR: 7.129







# INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089 🕓 (24\*7 Support on Whatsapp)