iJRASET
International Journal For Research in Applied Science and Engineering Technology



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 14 **Issue:** XI **Month of publication:** November 2026

DOI: https://doi.org/10.22214/ijraset.2026.85606

www.ijraset.com

Call: 08813907089 | E-mail ID: ijraset@gmail.com

International Journal for Research in Applied Science & Engineering Technology (IJRASET)
ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538
Volume 14 Issue XI Nov 2026- Available at www.ijraset.com

Rice Husk Ash as a Partial Replacement of Cement in Concrete

K. Roshik[1], D. Prajwal[2], Ankit Dhakar[3], Farhan Rahman[4]
[1, 2, 3]*B.Tech (Civil), 2nd Year,* [4]*Assistant Professor, Department of Civil Engineering*

Abstract: ***Rice husk ash (RHA) is a silica-rich residue obtained from the combustion of rice husks. Its potential use as a supplementary cementitious material is of interest because Portland cement manufacture is carbon intensive and rice milling generates substantial agricultural residues. This paper critically reviews the mechanisms by which properly processed RHA affects concrete, identifies factors controlling performance, and proposes a laboratory program to compare ordinary concrete with mixtures incorporating 5%, 10%, 15%, and 20% RHA as a mass replacement for cement. The review considers ash production, amorphous silica, particle fineness, water demand, fresh properties, compressive and tensile strength, and durability. Existing studies support the feasibility of moderate cement replacement, but no single replacement percentage can be claimed optimal for all sources and mixture designs. A controlled experimental protocol and transparent results-reporting framework are developed for undergraduate research. Keywords Rice husk ash; supplementary cementitious material; pozzolanic reaction; sustainable concrete; compressive strength; workability; durability. Research questions How does replacement of cement with locally produced RHA affect workability and mechanical performance? Which processing and mix-design factors most strongly influence the result? Can the use of RHA reduce cement demand without compromising specified performance?***
Keywords: rice husk ash; cement replacement; pozzolanic reaction; concrete; sustainability; compressive strength.

I. INTRODUCTION

Concrete is fundamental to modern infrastructure, but its cement binder has substantial embodied environmental impacts. Partial replacement of Portland cement with supplementary cementitious materials is one route to reducing clinker consumption. Agricultural residues are attractive where they are available locally and can be processed consistently. Rice husk is the protective outer layer removed during rice milling. Controlled combustion produces an ash that can contain reactive, predominantly amorphous silica. When adequately fine and sufficiently reactive, this silica reacts with calcium hydroxide released during cement hydration to form additional calcium-silicate-hydrate (C-S-H), a major binding phase in hardened cement paste [1–4]. The behavior of RHA cannot be generalized from replacement percentage alone. Burning conditions, carbon content, silica structure, grinding, water-to-binder ratio, admixtures, and curing all matter. Consequently, studies reporting different optimum percentages are not necessarily contradictory.

A. Problem Statement

Uncontrolled rice husk disposal and cement-related emissions motivate investigation of alternative binders. Yet variable ash quality can reduce fresh workability and produce inconsistent strength. A systematic local study is needed before recommending RHA for structural applications.

B. Scope

This work is limited to partial replacement of cement by mass in conventional concrete. It does not establish structural design approval or certify an ash source for commercial use.

II. LITERATURE REVIEW

A. Early Research and pozzolanic behavior

Mehta [1] discussed the use of rice husk ash as a highly reactive pozzolan when produced under suitable conditions. Subsequent investigations established that the ash microstructure and the proportion of amorphous silica are important determinants of its behavior in cementitious mixtures [2,3].

©IJRASET: All Rights are Reserved

B. Processing effects

Ganesan, Rajagopal and Thangavel [4] evaluated rice husk ash blended cement concrete and reported that suitable RHA addition can improve performance. The benefits depend on ash properties and mix proportions; ash with high unburnt carbon or low reactivity may instead impair performance.

C. Fresh concrete

RHA often increases water demand because of its porous structure and high specific surface area. At fixed water-to-binder ratio, slump can decline with increasing RHA content. Workability adjustments using a compatible water-reducing admixture should be documented rather than silently adding water.

D. Hardened concrete

Fine reactive RHA can contribute both filler effects and secondary C-S-H formation, refining pore structure and sometimes improving later-age strength. However, excessive replacement may reduce early strength by diluting Portland cement and increasing the mixture's water demand [3–5].

III. MATERIAL SCIENCE OF RICE HUSK ASH

A. Production

Rice husks are collected, cleaned, dried and combusted under monitored conditions. Burning temperature and residence time should be recorded. Ash is then cooled, ground, sieved and stored in sealed containers to avoid moisture uptake and contamination. Open-air burning produces less consistent material than controlled combustion.

B. Chemical and physical characterization

Important measurements include loss on ignition (as an indicator of residual carbon), oxide composition by X-ray fluorescence, particle-size distribution, specific gravity, and evidence of amorphous silica by X-ray diffraction. Scanning electron microscopy can provide additional insight into particle morphology where facilities permit.

C. Reaction mechanism

Cement hydration produces calcium hydroxide and primary C-S-H. Reactive silica from RHA combines with calcium hydroxide in the presence of water, producing additional C-S-H. This simplified description does not represent a single balanced reaction because C-S-H composition varies.

D. Practical implications

A high total silica percentage alone does not prove pozzolanic reactivity. Crystalline silica, coarse particles, or ash with high carbon content may perform poorly. Laboratory characterization should therefore precede mixture optimization.

IV. AIM, OBJECTIVES AND HYPOTHESES

A. Aim

To assess the technical feasibility of using locally sourced rice husk ash as a partial replacement for cement in concrete, with emphasis on fresh and hardened properties.

B. Specific objectives

- Characterize the physical and, where feasible, chemical properties of the RHA.
- Prepare a control mix and four replacement mixtures at 5%, 10%, 15% and 20% RHA by binder mass.
- Measure slump under a consistent mixing and testing procedure.
- Compare 7-day and 28-day compressive strength using replicate specimens.
- Assess 28-day splitting tensile strength and selected durability indicators if facilities permit.
- Identify the best-performing replacement level under the tested materials and conditions.

C. Testable hypotheses

H1: At least one moderate RHA replacement mixture will achieve 28-day compressive strength comparable to the control.

©IJRASET: All Rights are Reserved

H2: At constant water-to-binder ratio and without additional admixture, slump will generally decrease as RHA dosage increases.
H3: Results will be sensitive to ash fineness and curing quality. These are hypotheses, not conclusions from an experiment conducted for this paper.

V. MATERIALS AND MIX DESIGN

Materials should be selected and tested in accordance with the applicable Indian Standards. Use a single cement source, consistent aggregate grading, potable mixing water and a single characterized RHA batch. Choose a target grade (for example, M25) and design the control mixture using IS 10262 and IS 456 as applicable [6,7].

A. Illustrative binder replacement schedule

The table assumes a control binder content of 400 kg/m³. It is an arithmetic example, not a validated concrete mix design. Water, aggregates and admixtures must be established by trial mixing.

Mix ID	RHA (% binder)	Cement (kg/m³)	RHA (kg/m³)
R0	0	400	0
R5	5	380	20
R10	10	360	40
R15	15	340	60
R20	20	320	80

B. Control of variables

Maintain a fixed water-to-binder ratio for the primary comparison; record actual added water and admixture dose. Keep aggregate source, mixing time, compaction method, specimen size, curing environment and test age constant. A second workability-matched series may be used to distinguish water-demand effects from binder chemistry.

VI. EXPERIMENTAL METHODOLOGY

A. Sample preparation

Dry and homogenize aggregates. Weigh cement, RHA, aggregates and water separately. Blend dry powders uniformly before adding water; use a standardized mixer and mixing duration. Record ambient temperature, mixing sequence, and visible segregation or bleeding.

B. Fresh concrete

Measure slump immediately after mixing using the relevant procedure in IS 1199 [8]. Record slump in millimetres, not qualitative terms alone. If slump is outside the planned range, report it; do not conceal water adjustments.

C. Casting and curing

Cast standard concrete cubes for compressive testing and cylinders for splitting tensile tests. Compact consistently and label every specimen with mix ID, casting date and intended test age. Demould and cure in accordance with the selected standard procedure.

D. Replication

At minimum, cast three cubes per mix per testing age. For five mixes and two ages this requires 30 cubes. Three cylinders per mix at 28 days would require 15 additional specimens. More replicates improve confidence if resources allow.

E. Quality assurance

Calibrate equipment, inspect mould dimensions, log curing temperatures and record specimen mass and dimensions. Note any deviations from the planned protocol before testing.

©IJRASET: All Rights are Reserved | SJ Impact Factor 7.538 | ISRA Journal Impact Factor 7.894 |

VII. TESTING AND CALCULATIONS

A. Compressive Strength

Test cubes at 7 and 28 days following IS 516 procedures [9]. For each specimen, calculate compressive strength as f = P/A, where P is maximum load in newtons and A is the loaded face area in mm²; the result is in N/mm² (MPa).

B. Splitting tensile strength

For cylindrical specimens, compute $f_t = 2P/(\pi LD)$, where P is load in newtons, L is specimen length and D is diameter in mm. Use the applicable standardized loading procedure and record failure mode.

C. Statistical reporting

For each mixture and age, report all individual readings, sample mean, sample standard deviation and percentage change relative to the control. Percentage change = 100 × (RHA mix mean − control mean) / control mean. Avoid conclusions based only on one specimen.

D. Optional durability testing

Water absorption, sorptivity and chloride penetration-related tests can supplement mechanical testing. Report the exact test standard and conditioning procedure; results from different methods should not be compared as though they were interchangeable.

VIII. ILLUSTRATIVE RESULTS TABLES

Values below are HYPOTHETICAL worked examples, not measured laboratory data or values extracted from a single published study. Replace them with tested results before submission.

A. Fresh concrete (illustrative)

Mix	Slump (mm)	Cohesion / bleeding
R0	87	Cohesive; no bleeding
R5	80	Cohesive; no bleeding
R10	68	Cohesive; no bleeding
R15	57	Stiffer; no bleeding
R20	41	Stiff; no bleeding

B. Compressive strength (illustrative)

Mix	7-day mean (MPa)	28-day mean (MPa)	28-day SD (MPa)
R0	22.0	31.0	1.1
R5	23.0	32.5	1.0
R10	24.0	34.0	1.2
R15	23.5	33.0	1.1
R20	21.0	29.5	1.3

C. Splitting tensile strength (illustrative)

Mix	28-day mean (MPa)	Specimens assumed
R0	2.65	3
R5	2.75	3
R10	2.90	3
R15	2.82	3
R20	2.55	3

SD = standard deviation; hypothetical SD values assume three test specimens per mix. Example pattern is for demonstration only; real optimum may differ with RHA and mix design.

IX. DISCUSSION OF PUBLISHED FINDINGS

Published studies indicate that finely processed RHA can act as an effective pozzolan, but results differ by ash source and experimental design [1–5]. Strength gains at moderate replacement levels are consistent with particle packing and secondary hydration products. Declining performance at higher levels may reflect cement dilution, incomplete reaction, and difficulties achieving adequate workability.

A. Interpreting workability

If slump decreases as RHA increases, discuss particle porosity, surface area, and water demand. If slump does not decrease, examine admixture dosage, grading and moisture corrections rather than assuming the trend is universal.

B. Interpreting strength

A strength increase relative to the control should be considered together with variability and the 7-to-28-day development pattern. A later-age gain with slower early strength is consistent with pozzolanic contribution, although microstructural tests would be needed to confirm the mechanism.

C. Defining optimum replacement

The optimum percentage is conditional: it depends on the chosen performance criteria, such as minimum strength, workability, durability, cost or embodied emissions. It should be reported as "optimum among the tested mixes under the stated conditions," not as a universal material constant.

X. SUSTAINABILITY, ECONOMICS AND LIMITATIONS

A. Environmental accounting

Replacing cement with RHA can reduce Portland cement demand, but net emissions depend on transport, drying, combustion, grinding, electricity use and any admixture changes. A meaningful comparison should define a functional unit, such as one cubic metre of concrete meeting a specified 28-day strength and durability requirement.

B. Cost considerations

Potential savings from lower cement consumption must be weighed against ash collection, controlled burning, grinding, testing and storage. Locally available husk is not necessarily low-cost RHA after quality control is included.

C. Constraints

The main limitations are ash-source variability, processing requirements, reduced workability, limited local laboratory characterization, and uncertainty in long-term field performance. The proposed experiment covers only a limited range of replacement percentages and test ages.

D. Safety

Use dust masks or appropriate respiratory protection, gloves and eye protection when handling fine ash. Controlled combustion must be undertaken only with approved equipment and supervision; do not burn husks in an unventilated laboratory.

XI. CONCLUSIONS AND FUTURE WORK

The literature supports rice husk ash as a potentially useful supplementary cementitious material when it is adequately processed and characterized. Its silica-rich composition can support pozzolanic reactions and pore refinement, but the quality of the ash is decisive.

Moderate cement replacement is a sensible starting point for a local investigation. The proposed 0–20% replacement series can establish trends in slump and strength, but it cannot determine an optimum until real tests are completed. It would be scientifically inappropriate to report laboratory results before testing.

The environmental case for RHA should be framed as a potential benefit rather than an automatic reduction in emissions, because processing and transport also carry impacts. A robust recommendation must consider strength, workability, durability, costs and life-cycle emissions together.

©IJRASET: All Rights are Reserved | SJ Impact Factor 7.538 | ISRA Journal Impact Factor 7.894 |

A. Future Research

Useful extensions include 56- and 90-day strength testing, sulfate and chloride exposure, sorptivity, X-ray diffraction and microscopy, optimization of ash grinding, comparisons between controlled and uncontrolled combustion, and life-cycle assessment of locally produced RHA.


B. Acknowledgement and disclosure

This document is a student-ready literature-based research draft and experimental plan. It does not include original data, author names, institutional affiliations, or claims of tests performed. These details should be added only when verified.

REFERENCES

[1] Mehta, P. K. (1977). Properties of blended cements made from rice husk ash. ACI Journal Proceedings, 74(9), 440–442.
[2] Zhang, M. H., & Malhotra, V. M. (1996). High-performance concrete incorporating rice husk ash as a supplementary cementing material. ACI Materials Journal, 93(6), 629–636.
[3] Bui, D. D., Hu, J., & Stroeven, P. (2005). Particle size effect on the strength of rice husk ash blended gap-graded Portland cement concrete. Cement and Concrete Composites, 27(3), 357–366.
[4] Ganesan, K., Rajagopal, K., & Thangavel, K. (2008). Rice husk ash blended cement: Assessment of optimal level of replacement for strength and permeability properties of concrete. Construction and Building Materials, 22(8), 1675–1683.
[5] Habeeb, G. A., & Mahmud, H. B. (2010). Study on properties of rice husk ash and its use as cement replacement material. Materials Research, 13(2), 185–190.
[6] Bureau of Indian Standards. IS 10262:2019. Concrete Mix Proportioning — Guidelines.
[7] Bureau of Indian Standards. IS 456:2000. Plain and Reinforced Concrete — Code of Practice.
[8] Bureau of Indian Standards. IS 1199 (relevant current parts). Methods of Sampling and Analysis of Concrete.
[9] Bureau of Indian Standards. IS 516 (relevant current parts). Methods of Tests for Strength of Concrete.

©IJRASET: All Rights are Reserved | SJ Impact Factor 7.538 | ISRA Journal Impact Factor 7.894 |



10.22214/IJRASET

45.98

IMPACT FACTOR: 7.129

IMPACT FACTOR: 7.429

INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089 (24*7 Support on Whatsapp)