



iJRASET

International Journal For Research in
Applied Science and Engineering Technology



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 10 Issue: VI Month of publication: June 2022

DOI: <https://doi.org/10.22214/ijraset.2022.44737>

www.ijraset.com

Call:  08813907089

E-mail ID: ijraset@gmail.com

Rubber Powder As a Partial Replacement To Fine Aggregate in Geopolymer Ferrocement

Mr. Ranjeet R. Karle¹, Dr. Sandip L. Hake²

M.E Civil (Structural Engineering), Department of Civil Engineering

¹Professor, ²P.G. Student, Department of Civil Engineering, D.V. Vikhe Patil College of engineering Ahmednagar

Abstract: Tyre manufacturing over the world has increased as the automobile industry has rapidly grown. The waste tyre disposal is very time-consuming and environmentally damaging process. Even though it is frequently disposed of in landfills, issues with supply and demand mean that the shortage and lack of available landfill space is very big concern. The fundamentals ferrocement is used in the construction of structures. Mix of sand and cement the manufacture of aggregates from stone Quarries are also a major source of environmental degradation. Thus, the goal of the project; the purpose of this research is to investigate the effects of varying the quantities of crumb rubber replacing sand content in ferrocement mixes. In order to enhance different percentages of glass fibre have a compressive strength included into the mix of cement. In this study, the primary objective is to discover replacing the old rubber with a new type of rubber Cement ferrocement aggregates are mixed with glass fibres. Finally, the product will have excellent engineering qualities.

Ferrocement is a flexible building material with unique structural features. It's a composite made of tightly wound wire mesh around skeletal steel and rich cement mortar.

It is made of welded mesh, mild steel angles or bars, and reinforced by chicken mesh, square mesh or expanded metal. 1:1.5 to 1:4 mortar mix by volume Ferrocement can be used to build foundations, wallpanels, floors, roofpanel, ornamental structures, shells, etc. They are thin-walled, durable, ductile, light-weight, strong, and impermeable. It combines the strength of steel with the mouldability of ferrocement, is lightweight and easy to work with, and has high tensile strength of pre-stressed ferrocement and crack control. Ferrocement requires no formwork or shuttering. Ferrocement has transformed RCC into a homogenous, ductile composite. This is because continuous meshes of fine steel wires replace steel bars. It has strengthened the link between wires and mortar such that wires break but are not pulled out of the matrix. Steel and mortar are bound together until steel yields, providing ductility to the composite. The structure may flex or deflect but will not fail.

Keywords: Waste tyre crumb rubber in Geopolymer ferrocement, , replacement

I. INTRODUCTION

The number of unusable waste tires from different kinds of vehicles is rapidly growing and is in fact turning out as one of the major ecological and environmental problems of the present day. Nearly one-billion waste tires are discarded each year and are predicted to be almost 1.3 billion per year by 2025.

Large amount of waste tyre rubber accumulate in the world every year, and the easy process to decompose the rubber is by burning but because of burning of rubber large amount of smoke and pollution is generated. Another method to dispose waste rubber is by landfill, but now days availability and capacity of land fill places decreases

A expanding global automobile industry and a growing preference for automobiles as a mode of transportation have resulted in a dramatic increase in tyre manufacturing over the last several decades. As a result, massive stockpiles of old tyres have been created. In the early 2010s, extensive research was conducted on the numerous applications of recycled tyres. At room temperature, scrap tyre is composed of non-biodegradable components. They almost always have a negative impact on the environment. One way to put these resources to use is to incorporate them into ferrocement and other building materials.

The following macroeconomic aspects should be contrasted and considered when evaluating the use of these materials in ferrocement. The cost of collecting, processing, and transporting scrap tyres reduced environmental expenses and increased landfill voids result in an increase in landfill voids.

By substituting tyre rubber for original materials in the manufacture of ferrocement; rubber waste is extremely durable and resistant to most natural environments. As a result, proper tyre recycling is critical, as improper disposal can have serious environmental and aesthetic consequences.

Fine wire mesh reinforcement is the most basic element of ferrocete, because it controls the specific surface, which is an important factor in design. The no. of steel mesh layer if meshes, decided the thickness of composite structure. Various types of meshes are in use:

- 1) Expanded wire mesh
- 2) Fine wire mesh in form of woven square mesh and interlocked diamond type or hexagonal mesh
- 3) Weld mesh
- 4) Crimped wire mesh

In Indigent countries, where this is especially true, used tyre management is primarily governed by environmental regulations. Following the implementation of numerous EU directives, reuse and material recovery are now regarded as the most environmentally sound waste management methods. The amount of waste glass has increased in recent years as a result of increased industrialization and a rapid rise in the standard of living. As a result, a significant amount of waste glass is discarded rather than recycled, resulting in environmental and natural resource loss and pollution. Ferrocete's brittle nature can be softened by adding fibres with short lengths and small diameters. Sustainability can be defined as the ability to use depleting nonrenewable resources indefinitely while also retaining depleting renewable resources. Sustainability is one of the most studied but least understood concepts on the planet. For the majority of countries, organizations, and individuals who consider its significance, sustainability entails the preservation of the Earth and critical issues related to development, such as stable economic growth, productive resource utilisation, poverty eradication, and consistent social advancement. In the coming years, sustainable construction expects to meet current prerequisites for a working situation, housing, and infrastructure without sacrificing people's capacity to address their issues. According to researcher's writing, the current state of the construction industry is unsustainable. In the industry, sustainable construction could be accomplished by substituting strong recycled products for normal crushed stone in ferrocete. However, the use of conventional coarse aggregates undermines sustainability by causing additional environmental issues. According to the India Farmer's Welfare and Horticulture Ministry, over 2390 billion were formed in India in 2016–2017, which will increase farming waste accumulation. Thus, the successful use of agricultural wastes as a substitute for traditional aggregates contributes to the preservation of non-renewable resources, reduces energy consumption, and lowers construction material costs. The authors used a variety of scrap materials in their ferrocete, including recycled aggregate, fly ash, silica fume waste elastic tyre, and GGBFS and waste and glass plastics. They also used tobacco wastes, coconut shell, rice husk ash, palm shell, pistachio shell, and oil palm shell. Aside from cement, aggregate is a major component of ferrocete. Fine aggregates are obtained from river beds or weathering of rocks into dust, whereas coarse aggregates are formed by crushing of stones. Waste tyres are currently a major problem all over the world. Because waste tyres decompose slowly and take over a century to disintegrate at ambient temperature, they can be reused in land filling. These tyres rubber are cut into small and large pieces for the reduction or reuse of waste tyres. Crumb rubber (C.R.) is made by cutting up old tyres. Large pieces are considered coarse crumb rubber, while small pieces are considered fine crumb rubber; in ferrocete, these are replaced with coarse aggregate and fine aggregate, respectively. Crumb rubber from tyre waste, reduced to a very fine size, was used as a fine aggregate in this research paper. The amount of crumb rubber is calculated as a percentage of the fine aggregate weight as 2.5 percent, 5.0 percent, 7.5 percent, and 10.0 percent replacement. ferrocete mixes are used to cast cubes, beams, and cylinders & Panels for various laboratory tests. Slump variation, compressive strength, compressive strength tests are performed in the laboratory According to research, increasing the percentage of crumb rubber & glass fiber reduces strength. One of the most concerning issues in the early stages of GRC development was the durability of the glass fibres, which became fragile over time due to the alkalinity of the cement mortar. Significant progress has been made since then, and the problem is now practically solved thanks to new types of alkali-resistant glass fibres and mortar additives that prevent the processes that cause GRC embrittlement. The lighter weight and higher tensile strength of GRC compared to ferrocete prompted a recent research programme to investigate its viability as a structural material. The study was conducted in collaboration with ferrocete precast companies, for whom the improved characteristics are particularly appealing because the precast elements' reduced weight is critical for transportation and installation. Reinforcement systems, such as carbon or glass strands and stainless steel bars, were also investigated in order to obtain a GRC with high durability, resulting in corrosion-free solutions. Although some of the average mechanical properties of GRC are known and are currently used for nonstructural elements, a much more thorough characterization is required when structural design is considered. The mechanical strength, Young's modulus, creep and shrinkage behaviour, and stress–strain diagrams of GRC specimens were then determined through experimental tests. The experimental tests had to consider cementitious matrix with various plain mortar productions, various types of glass fibres, and reinforced with carbon or glass strands or steel elements, as the material characteristics were highly dependent on the production procedures. These tests resulted in a characterization of the manufacturing conditions, allowing for the optimization of material properties.

A. Dispersion of Steel Wire

Ferrocete is formed by tying together a no. of layers of continuous wire meshes. Volume of steel Per cent is very large, may be upto 8%. Also the mortar cover over the meshes is upto 3-5 mm. Hence throughout the body of the composite, the wire reinforcement is fully dispersed. This leads ferrocete4 to become more homogeneous. It results in improving the properties of ferrocete in tension, flexure, impact resistance and crack resistance.

B. Crack Control

Closely spaced fine wires, very near to the surface of ferrocete, act as crack arrestors. In conventional reinforced ferrocete the bars are spaced some distance apart and the ferrocete in between them is prone to temperature expansion and contraction. This tendency is overcome by the tension taking member fully bonded to mortar and spaced very to the surface of ferrocete.

C. Equal Strength in Both Directions

The continuity and placement of equal mesh reinforcement in both directions make ferrocete to achieve equal strength in two direction and become strong in resisting diagonal tensions due to shear.

D. Containment off Mortar Matrix in Mesh Layers

In ferrocete, layers of wire meshes tightly tied together are impregnated with cement mortar. The matrix is held by the meshes in between and is contained by them. In RCC, steel bars are encased in ferrocete while in ferrocete layers of wire meshes encase the mortar and hold it bonded strongly. Thus there would not be sudden brittle failure of ferrocete element. In case of test upto failure or in the case of sudden shock loading like earthquake, the member will undergo large deflection with adequate warning.

E. Formless Construction

Tightly tied meshes in ferrocete can hold wet cement mortar when it is press filled in them. The consistency of cement mortar is very thick with very low water cement ratio. It won't out of the meshes. Thus casting of ferrocete does not need any formwork or shuttering. The other advantage of this aspect is that no honeycombing in press filling as the mortaring is done in front of your eyes.

F. Self-quality Conscious Material

If the steel wire mesh is tied loosely or water to cement ratio is not maintained to thick consistency, or over sanding is, the mortar will flow down and will not be held by the meshes. Thus the ferrocete may be characterized as a self-quality conscious material and will does not allow less cement, more sand or more water in the mortar mix.

G. Strength Through Shape

Ferrocete structure is thin walled and may be hardly 25 to 50mm in thickness. Hence to take care of slenderness and buckling, ferrocete is shaped in different forms to achieve its strength.

II. LITERATURE REVIEW

1) Camile B. George Saleem 2021

As waste accumulates and landfill capacity diminishes, agencies are expanding application and use of recycled resources such as crumb rubber from tyres in building. Ferrocete is made up of gravel and cement. Using recycled materials wisely may reduce costs and improve performance; however, not all recycled materials are suitable for ferrocete construction. The primary reasons for not using reused material are (1) performance loss and high cost. This study investigates the effectiveness of recycled crumb rubber as a 0–80% fine aggregate replacement for crushed sand in ferrocete mixtures. Using crumb rubber to replace up to 25% of fine aggregates improved compression strength.

2) Feng shi Guiuan Chen, Liuan Li Yoshugchan Guo 2018

Using chosen rubber particles of 0.175 mm, 1.15 mm, and 2 mm, and steel fibre of upto 25 mm in length and 0.5 percent volume percentage, he studied the impact resistance of rubber reinforced and rubber/steel fibre reinforced ferrocete. Ferrocete containing 5%, 10%, 15% and 20% rubber particles was tested dynamically under 0.2 MPa, 0.3 MPa, 0.4 MPa and 0.5 MPa impact loads. These curves were then utilised to depict the strain rate levels connected with the rubber reinforced ferrocete. Based on the findings, the impact resistance of rubber reinforced ferrocete was studied. The improved Holmquist–Johnson–Cook dynamic constitutive model was developed by finding the parameters of the improved Holmquist–Johnson–Cook constitutive model. The constitutive model of rubber reinforced ferrocete was created, with parameters given for various strain rates.

3) *F. Pacheco-Torgal, Yinning Ding 2018*

The volume of polymeric wastes like tyre rubber and PET bottles is rapidly growing. Every year, an estimated 1000 million tyres are wasted, with 5000 million more projected by 2030. Currently, only a small percentage gets recycled, while millions are dumped or buried. The yearly PET bottle use is above 300 million units. The majority is dumped. Research on ferrocrete including tyre rubber and PET wastes is reviewed. It also addresses the impact of waste treatments, waste particle size, and waste replacement volume on ferrocrete's fresh and hardened characteristics.

4) *Waung Her Yung a, Lin Chhin Yung 2020*

The mixing of regular sand with waste tyre rubber powder of varying fineness is described. The results revealed that adding 5% waste tyre rubber powder sieved #50 increased the 91-day compressive strength by 10% over the control group. The shrinkage increased with the amount of discarded rubber and peaked at 20%. The ultrasonic pulse velocity dropped as additional powder was added, and the 56-day electrical resistance rose from 20 kX-cm to over 30 kX-cm. Meanwhile, the ultrasonic pulse velocity and electrical resistance correlated well with compressive strength. The addition of 5% waste tyre rubber powder improved anti-sulfate corrosion. Leaky self-compacting rubber ferrocrete can benefit from waste tyre rubber powder.

such as sunscreens, secondary roofing slabs, water tanks, and repair material in the building industries.

5) *Hanif. Nafi (2019)*

The use of cementitious composites for infrastructure use is becoming most popular nowadays with the introduction of new high performance materials. Ferrocement laminates are introduced to increase the overall performance of structures, such as composite bridge deck, beams, bearing walls, etc. This paper presents lightweight truss roofing system. Earthquake resistance is ensured by analyzing the structure on design software for a seismic activity of zone The behavior of structure is found satisfactory under the earthquake loading. An estimate of cost is also presented which shows that it is an economical solution.

6) *Anwar (2018)*

Like many other countries in the world, significant developments in cementitious materials have been made in Singapore, spearheaded by the International Ferrocement of an Information Center (IFIS) located at Asian Institute of Technology (AIoT) Thailand, several other academic institutions, and the construction industry. This paper highlights some of these developments together with their applications. Special focus is given to ferrocement and laminated cementitious composites, and the use of indigenous materials such as vetiver grass, that silk, bamboo, etc. Different aspects such as materials, design, and construction are discussed together with the application of finite element analysis to structures made up of cementitious composites.

A. *Aim*

"This study's goal is to substitute sand in ferrocrete with crumb rubber in varying quantities. The Geopolymer in the cement is to be tried to increase flexural and impact strength".

B. *Objectives*

- 1) Study on its use in cement ferrocrete is limited. Rubberized Portland cement ferrocrete strength and hardness tests
- 2) To study goal is to substitute sand in ferrocrete with crumb rubber in varying quantities. The proportion of geopolymer in the ferrocrete is to be tried to increase flexure and impact strength.
- 3) To check flexure strength Up to 5%, 10%, 15%, 20% replacement of rubber aggregate to fine aggregate and

C. *Problem Statement*

"Study on Flexural strength Up to 5%, 10%, 15%, 20% replacement rubber aggregate to fine aggregate in Geopolymer Ferrocement

D. *Scope of the Study*

Rubberized ferrocrete has many applications in construction, further research is needed to determine its elastic constants and mechanical properties by varying the rubber volume proportions, water-cement ratios, aspect ratios, and rubber forms such as fibre chips, powder, etc. The study uses varied percentages of rubber waste in ferrocrete.

III. RESEARCH METHODOLOGY

A. Research Work

- 1) Study for literature review survey
- 2) To study the construction techniques of ferrocete, we have gone through various research papers, books, and some field works
- 3) To cast Panel for different configuration size Length - 1000mm, Width-.300mm, Thickness. 30mm and to study after 28 days curing
- 4) To check flexure strength Up to 5%, 10%, 15%, 20% replacement of sand to tire rubber aggregate and
- 5) Impact test
- 6) Compression Test
- 7) Analysis result
- 8) Result and discussion
- 9) Conclusion

IV. EXPERIMENTAL CONSIDERATION

A. Material Collection

- 1) **Cement:** Ordinary IS: 269 – 1976 Portland cement, 40 grade. All of the specimens were cast with ordinary Portland cement, grade 53. To produce pastes of uniform consistency, different types of cement require different amounts of water. Different types of cement will result in different rates of strength development in ferrocete. The most important factor in producing high-quality ferrocete is choosing the right brand and type of cement. Because the type of cement used affects the rate of hydration, the strength of the ferrocete at an early age can be significantly influenced. It's also crucial to make sure that the chemical and mineral admixtures are compatible with cement.
- 2) **Aggregate:** Local river sand conforming to IS: 383 –1970 Grading zone II. Local river sand will be used. All the specimens will be cast in IS 4.75mm sand.
- 3) **Rubber:** The crumb rubber particles ranging from 75 μ to 2.36mm
- 4) **Fly ash:** Fly ash used in this study is low calcium class F unprocessed fly ash from thermal power plant. Quantity and fineness of fly ash plays an important role in the activation process of geo- polymer. It was already pointed out that the strength of geo-polymer ferrocement increases with increase in quantity and fineness of fly ash
- 5) **GGBS:** Ground granulated blast furnace slag is a hydraulic binder, acquire by quenching molten iron slag from a blast furnace in water or steam to create a glazey, granular product that is then dried and ground into a fine powder.
- 6) **Alkaline Solution**
Sodium Hydroxide Solution (NaOH)
Sodium silicate solution (Na₂SiO₃)
- 7) **Steel Mesh:** Wire diameter of across 0.5mm to 5 mm should adopted. Size of mesh opening is between 7mm to 35 mm. Maximum utilization of upto 3 layers of work for various thickness. There should maximum 10% volume portion in both bearings Steel cover 1.5 to 5 millimeters.

Constituent Materials Used Materials that are used for making ferrocete for this study will be tested before casting the specimens. The preliminary tests will be conducted for the following materials.

- Cement
- Aggregate
- Water

B. Methodology and preparation

1) Cement

Cement used in construction is categorized as hydraulic or non-hydraulic. Hydraulic cement (e.g., Portland cement) harden because of heat of hydration, chemical reactions that occur independently of the mixture's water content; they can harden even underwater or when constantly exposed to wet weather. The chemical reaction that results when the anhydrous cement powder is mixed with water produces hydrates that are not water-soluble. Non-hydraulic cements (e.g., lime and gypsum plaster) must be kept dry in order to retain their strength. The most important use of cement is the production of mortar and ferrocete. The bonding of natural or artificial aggregates to form a strong building material that is durable in the face of normal environmental effects.

2) *Aggregates*

“Fine aggregate” is defined as material that will pass through 4.75mm sieve and will, for the most part, be retained on a 1.18mm sieve. For increased workability and for economy as reflected by use of less cement, the fine aggregate should have a rounded shape.

3) *Mix Proportion*

Ordinary portland cement and river sand passing through No. 8 (2.38 mm) sieve and having a fineness modulus of 2.72 were used for casting. In design mix proportion 40% cement replace with combination of fly ash and GGBS with different proportion. The geopolymer mortar used in this study is composed of low-calcium fly ash and alkaline solution composed of NaOH and sodium silicate combinations. NaOH is mixed with deionized water at a required concentration(12M) and kept for at least 24 h prior to casting. All geopolymer mortar specimens were made with sand-to-geopolymer ratio in equal proportion.

The cement, fly ash and fine aggregate were dry mixed together in a mixer machine for 5 min. W/c ratio is taken as 0.46 followed by the addition of activator solution containing hydroxide and silicate to the mixture, and mixed for another 10 min. The mixing was carried out at a room temperature of approximately 27–30°C

The crumb rubber is immersed in 1N NaOH solution for 30 minutes. After that the rubbers are water washed to remove the presence of NaOH residue. The moist rubber is free dried under sun light with ambient condition. 1lit of NaOH solution may require for treating up to 1kg of crumb rubber.

The Ferro cement panel is made by using expanded chicken mesh and geopolymer mortar. The panel mold is made of wooden base with the size of 1000mmX300mmX30mm with open top and bottom is rest on base plate & cubes of 150x150mm are prepared to check compressive strength of mixture.

4) *Flexure Test on Ferrocement*

Ferrocement specimens size (1000mmx300mmx30mm) have to tested in accordance with the applicable provision standard testing methods for flexural strength of ferrocement, using a fixed supported slab with uniformly distributed load. An experimental load-deflection curve of ferrocement with clearly defined transition point.

5) *Impact Testing*

After the 28 days of curing, slabs are taken out from the curing tank and white wash was applied to the slabs surface in order to get clear indication of cracks on repetitive drops. Impact test was conducted on the geopolymer ferrocement panel slabs after 28 days of curing by using a drop weight method and the test setup is consisted of a rigid welded steel frame square in plan and supported by short columns. The specimen was laid flat resting on four 75 mm diameter bars to provide line support along the four edges. The test setup consists of a cylindrical ball of 60mm diameter; 150mm height (the plunger) with hemispherical blunt tip to a height of 50mm. The plunger which loads the panel has a spherical tip enabling a point contact to be made. A rope and pulley arrangement with a pipe guide, which enables a central impact in the vertical direction, was used to manually raise the hammer to the required height for repeatedly dropping it on the specimen surface. Grease was applied on the rollers to reduce friction and to ensure smooth fall. The weight of the ball is 3.22kg and it is dropped from a height of 670mm. The mass was then dropped repeatedly and the number of blows required to cause first crack was recorded. Then the number of blows required for the failure is also recorded

V. CONCLUSION

- 1) The specimen of rubberized geopolymer ferrocement should have more impact energy absorption capacity than that of regular conventional specimen.
- 2) The specimen of rubberized geopolymer ferrocement should have flexural strength greater than that of conventional ferrocement
- 3) The crack resistance property of rubberized ferrocement must be slightly greater than regular one

REFERENCES

- [1] Ahanggar-Asr A, Faramarzi A & Javadi (2018) “An evolutionary numerical approach to modelling the mechanical properties of rubber ferrocement”, proceedings of the International Conference on Computing in Civil and Building Engineering, Nottingham University Press, iccbe 2018, 1 – 3.
- [2] Aiello M.F. F. (2010). “Waste tire rubberized ferrocement: Properties at fresh and fully hardened state”. Waste Management, 1697-1704.
- [3] Aazmi N. J., Mohammed B. S., Al- Mattarneh H. M. A., (2012) “Engineering Properties of Ferrocement Consist of Recycled Tire Rubber”, International Conference on Construction and Building Technology 2012, Malaysia ICCBT 2012 - C - (34), 373 – 382.
- [4] Bataynek Malek K., Marie Iqbal, Asi Ibrahim, (2008), “Promoting the use of crumb rubber ferrocement in developing countries”, Science Direct Elsevier Ltd, Waste Management 28 (2008) 2171–2176.



- [5] Bignozzi M.C., Sandrolini F. (2006) Tire rubber waste recycling in self-compacting ferrocete”, SCIENCE DIRECT Elsevier Ltd, Cement and Ferrocement Research 37 2006 7355–739.
- [6] Batayneh, M.K., I. Marie, and I. Asi, "Promoting the use of crumb rubber ferrocete in developing countries". Waste Management, 2008. 28(11)A. 2171-2176)
- [7] Elodin N.N. & Senoucci A.B. - "Rubber tire particles as ferrocete aggregates", ASCE Journal of materials in Civil Engineering, 1993, 5(4), 478-496.
- [8] Huang, B. et al., "Investigation into waste tire rubber-filled ferrocement." Journal of Materials in Civil Engineering, 2004. 16 p. 187- 194.
- [9] IS: 383-1970- "Specifications for coarse and fine aggregates from natural sources for ferrocete" (Second revision) BIS, New Delhi.
- [10] Lium W.G. 'Development of waste tire modified ferrocete'. Cement and Ferrocete Research, 2004. 34(12: C. 2283-2289



10.22214/IJRASET



45.98



IMPACT FACTOR:
7.129



IMPACT FACTOR:
7.429



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089  (24*7 Support on Whatsapp)