iJRASET
International Journal For Research in Applied Science and Engineering Technology



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 14 **Issue:** III **Month of publication:** March 2026

DOI: https://doi.org/10.22214/ijraset.2026.78481

www.ijraset.com

Call: 08813907089 | E-mail ID: ijraset@gmail.com

International Journal for Research in Applied Science & Engineering Technology (IJRASET)
ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.538
Volume 14 Issue III Mar 2026- Available at www.ijraset.com

Water Repellent Finishes in Textiles: Mechanisms, Materials, Applications, and Environmental Considerations

Haritha A G[1], Dr. K. M. Pachiyappan[2], Jothi Jerald[3]
[1]*PG Student*, [2]*Associate Professor & Dean, School of Applied Science*, [3]*P.hd Research Scholar Department of Costume Design and Fashion, PSG College of Arts and Science, Coimbatore*

Abstract: ***Water repellent finishes represent a significant advancement in functional textile engineering, designed to prevent water penetration while maintaining fabric breathability and comfort. These finishes operate by modifying the surface energy of fibers, enabling liquids to bead up and roll off instead of spreading and absorbing. Unlike waterproof coatings that block pores entirely, water repellent treatments preserve the air permeability and flexibility of fabrics, making them suitable for apparel, outdoor gear, medical textiles, and industrial applications. This paper provides a comprehensive overview of water repellent finishes, including their working principles, types of chemical treatments, application techniques, durability, performance evaluation, and environmental implications. Recent innovations such as fluorine-free alternatives and nano-based coatings are also critically examined. The study highlights the balance between performance efficiency and sustainability, emphasizing the need for eco-friendly solutions in modern textile processing.***

Keywords: sustainability, waterproof coatings, outdoor gear, medical textiles,roll off and industrial applications

I. INTRODUCTION

The textile industry has evolved from producing basic fabrics to engineering advanced functional materials with enhanced performance properties. Among these, water repellency has gained substantial importance due to its wide application in protective clothing, sportswear, and technical textiles. Water repellent finishes are surface treatments applied to fabrics to resist wetting without completely sealing the fabric pores. This allows moisture vapor to escape, ensuring wearer comfort while protecting against external water exposure.

Traditionally, untreated fabrics readily absorb water due to their hydrophilic nature and porous structure. However, through chemical modification of fiber surfaces, the wettability can be significantly reduced. The growing demand for multifunctional textiles has further accelerated research in this area, especially with the integration of nanotechnology and sustainable chemistry. This paper explores both conventional and emerging approaches to water repellent finishes.

II. PRINCIPLES OF WATER REPELLENCY

Water repellency in textiles is fundamentally governed by surface chemistry and fabric structure. The effectiveness of a water repellent finish is determined by the contact angle formed between a water droplet and the fabric surface. A higher contact angle indicates better repellency, as the liquid remains in a spherical form and does not spread.

Two key scientific models explain this behavior: the Young's equation, which describes ideal smooth surfaces, and the Cassie-Baxter model, which applies to rough and porous surfaces such as textiles. By introducing low surface energy materials, the adhesive forces between water molecules and the fiber surface are minimized. Simultaneously, micro- and nano-scale roughness enhances the hydrophobic effect, leading to improved water shedding behavior.

The combination of chemical treatment and surface morphology modification is essential for achieving durable water repellency in textiles.

III. TYPES OF WATER REPELLENT FINISHES

1) Fluorocarbon-Based Finishes

Fluorocarbon finishes are among the most effective water repellent treatments due to their extremely low surface energy. These compounds contain perfluorinated chains that repel both water and oil. They are widely used in high-performance textiles such as outdoor garments and protective clothing.

©IJRASET: All Rights are Reserved

However, concerns regarding environmental persistence and toxicity, particularly related to perfluorooctanoic acid (PFOA) and perfluoro octanesulfonic acid (PFOS), have led to regulatory restrictions and a shift toward safer alternatives.

2) Silicone-Based Finishes

Silicone finishes provide water repellency through the formation of a flexible hydrophobic film on the fabric surface. They are known for enhancing softness and maintaining fabric hand feel. While less effective than fluorocarbons in oil repellency, silicones are widely used due to their lower environmental impact.

3) Wax and Paraffin-Based Finishes

Wax-based finishes are among the oldest water repellent treatments. They work by filling the inter-fiber spaces and forming a hydrophobic barrier. Although cost-effective, these finishes may affect fabric breathability and durability.

4) Nano-Based Finishes

Nanotechnology has introduced advanced water repellent solutions by creating hierarchical surface structures. Nanoparticles such as silica, titanium dioxide, and zinc oxide are used to enhance surface roughness and improve hydrophobicity. These finishes often mimic the lotus leaf effect, resulting in self-cleaning properties.

IV. APPLICATION METHODS

The application of water repellent finishes is typically carried out using conventional textile finishing techniques. The most common method is the pad-dry-cure process, where the fabric is impregnated with the finishing solution, dried, and then cured at elevated temperatures to fix the chemicals onto the fiber surface.

Other methods include spray coating, foam finishing, and plasma treatment. Plasma technology, in particular, offers an eco-friendly alternative by modifying surface properties without the use of excessive chemicals or water. The choice of method depends on the type of fabric, finish, and desired performance characteristics.

V. PERFORMANCE EVALUATION

The effectiveness of water repellent finishes is assessed using standardized testing methods. Spray tests, such as AATCC 22, evaluate the resistance of fabrics to surface wetting. Hydrostatic pressure tests measure the fabric's ability to withstand water penetration under pressure.

Durability is another critical factor, often tested through repeated laundering cycles. High-quality finishes retain their repellency even after multiple washes. Additional parameters such as air permeability, fabric stiffness, and abrasion resistance are also evaluated to ensure overall performance is not compromised.

VI. APPLICATIONS OF WATER REPELLENT TEXTILES

Water repellent finishes are widely used across various sectors. In apparel, they are essential for rainwear, sportswear, and outdoor clothing. In medical textiles, they help prevent fluid penetration, reducing the risk of contamination.

Industrial applications include protective covers, tents, and upholstery fabrics. In automotive and aerospace industries, water repellent textiles contribute to durability and performance under harsh environmental conditions. The versatility of these finishes makes them indispensable in modern textile engineering.

VII. ENVIRONMENTAL AND SUSTAINABILITY ASPECTS

The environmental impact of water repellent finishes has become a major concern, particularly with the use of fluorinated compounds. These chemicals are persistent in the environment and can accumulate in living organisms, posing health risks.

As a result, there is a growing emphasis on developing fluorine-free alternatives, such as hydrocarbon-based and bio-based finishes. Researchers are also exploring biodegradable coatings and green chemistry approaches to reduce ecological impact. Sustainable finishing processes aim to minimize water consumption, energy use, and chemical waste.

VIII. DURABILITY AND LAUNDERING BEHAVIOR OF WATER REPELLENT FINISHES

Durability is a critical parameter in evaluating the long-term performance of water repellent finishes. In real-world applications, textiles are subjected to repeated washing, abrasion, and environmental exposure, which can degrade the hydrophobic layer.

©IJRASET: All Rights are Reserved

Studies show that fluorocarbon finishes retain high spray ratings even after multiple wash cycles due to their strong chemical bonding with fiber surfaces . However, performance degradation still occurs over time due to mechanical wear and detergent action.
The durability of water repellent finishes depends on factors such as curing temperature, chemical concentration, and binder compatibility. Research indicates that higher curing temperatures improve cross-linking, resulting in enhanced wash durability and water resistance Nano-based coatings, particularly those incorporating silica nanoparticles, demonstrate improved durability by forming hierarchical surface structures that resist mechanical damage.
Recent developments focus on improving durability using hybrid systems combining nanoparticles and polymer matrices. These systems create strong adhesion between coating and fiber, thereby maintaining performance after repeated laundering cycles.

IX. ROLE OF NANOTECHNOLOGY IN WATER REPELLENCY ENHANCEMENT

Nanotechnology has revolutionized textile finishing by enabling the creation of superhydrophobic surfaces that mimic natural phenomena such as the lotus leaf effect. The incorporation of nanoparticles increases surface roughness at micro- and nano-scale levels, which significantly enhances water repellency.
Silica nanoparticles are widely used due to their ability to create rough surface textures, leading to improved spray ratings and higher contact angles . Additionally, nanostructured coatings based on polymethylsilsesquioxane or similar compounds can maintain superhydrophobicity even under prolonged mechanical stress .
Recent research highlights the use of dual-layer nano coatings, where one layer provides roughness and the other reduces surface energy. Such coatings achieve contact angles above 150°, classifying them as superhydrophobic surfaces. These innovations not only improve water repellency but also introduce additional functionalities such as self-cleaning and anti-fouling properties.

X. FLUORINE-FREE AND SUSTAINABLE WATER REPELLENT TECHNOLOGIES

Environmental concerns surrounding perfluoroalkyl substances (PFAS) have driven the development of fluorine-free alternatives. These compounds, although highly effective, are persistent in the environment and pose risks to human health. Regulatory restrictions have accelerated research into safer alternatives.
Recent studies demonstrate that fluorine-free coatings based on polysiloxane, alkyl silanes, and plant-based materials can achieve comparable water repellency while reducing environmental impact. For instance, non-fluorinated finishes using silica nanoparticles and polydimethylsiloxane (PDMS) have shown excellent durability and comfort properties .
Bio-based materials such as beeswax, cellulose, and chitosan are also being explored for sustainable textile finishing. These materials provide hydrophobicity while being biodegradable and environmentally friendly. Water-based coating systems further reduce the use of hazardous solvents, aligning with green chemistry principles .

XI. ADVANCED FUNCTIONALITIES IN WATER REPELLENT TEXTILES

Modern water repellent finishes are no longer limited to hydrophobicity alone. Researchers are integrating multiple functionalities into a single coating system to enhance textile performance.
Multifunctional finishes may include:

- Antimicrobial properties (using silver nanoparticles or zinc oxide)
- UV protection (through titanium dioxide nanoparticles)
- Self-cleaning effects (lotus-inspired surfaces)
- Flame retardancy and anti-fouling properties

For example, advanced coatings have been developed that combine superhydrophobicity with flame retardancy and resistance to biological contamination, making them suitable for protective and military textiles . These multifunctional systems are particularly valuable in medical and industrial applications where hygiene and durability are critical.

XII. INDUSTRIAL CHALLENGES AND LIMITATIONS

Despite significant advancements, several challenges remain in the large-scale implementation of water repellent finishes. One major issue is the trade-off between water repellency and fabric comfort. High levels of hydrophobic coatings can reduce breathability and increase stiffness.

©IJRASET: All Rights are Reserved | SJ Impact Factor 7.538 | ISRA Journal Impact Factor 7.894 |

Another challenge is cost-effectiveness. Advanced nano-based and eco-friendly finishes often involve complex synthesis processes and expensive raw materials, limiting their commercial adoption. Additionally, achieving uniform coating distribution on fabric surfaces remains a technical challenge, especially for large-scale production.

Durability and reusability also require further improvement, particularly for fluorine-free alternatives, which may not yet match the performance of traditional fluorocarbon finishes.

XIII. FUTURE TRENDS AND INNOVATIONS

The future of water repellent finishes is focused on making them more sustainable and multifunctional. Modern textiles are being developed to adjust their water repellency based on environmental conditions like temperature and humidity. New technologies such as nanotechnology and biomimicry help create efficient and eco-friendly finishes by copying natural surfaces like lotus leaves. In addition to water resistance, these textiles are also being designed with extra features such as antimicrobial properties, UV protection, and self-cleaning ability. Researchers are also working on smart coatings that can respond to changes in the environment. The combination of water repellent finishes with smart textiles and wearable electronics is creating new possibilities for advanced fabrics. Overall, future developments aim to make these finishes affordable, scalable, and environmentally safe while meeting growing industry and consumer needs.

XIV. CONCLUSION

Water repellent finishes play a crucial role in enhancing the performance and functionality of textiles, evolving from traditional wax-based treatments to advanced nano-engineered and environmentally sustainable systems that reflect the dynamic progress of textile technology. While achieving high performance remains a primary objective, increasing environmental concerns have significantly influenced research and development, driving a shift from conventional fluorocarbon-based finishes—known for their superior repellency—toward safer, eco-friendly alternatives. The integration of nanotechnology, bio-based materials, and multifunctional properties has broadened the applications of water repellent textiles across diverse sectors, including apparel, medical, and industrial fields. At the same time, innovative application methods and green chemistry approaches highlight the industry's commitment to sustainable growth. Despite these advancements, challenges such as durability, cost-effectiveness, and large-scale scalability continue to limit widespread adoption. Future developments are therefore expected to focus on balancing performance with sustainability, ensuring minimal environmental impact while maintaining efficiency, and securing the continued relevance of water repellent finishes as a vital component of modern textile engineering.


REFERENCES

[1] Holme, I. (2007). Innovative technologies for high performance textiles. Coloration Technology, 123(2), 59–73.
[2] Schindler, W. D., & Hauser, P. J. (2004). Chemical finishing of textiles. Woodhead Publishing.
[3] Gao, L., & McCarthy, T. J. (2006). Artificial lotus leaf surfaces. Langmuir, 22(14), 5998–6000.
[4] Xue, C. H., & Jia, S. T. (2016). Fluorine-free water repellent finishes. Textile Research Journal, 86(3), 1–15.
[5] Bongiovanni, R., et al. (2013). UV-curable coatings for textile applications. Progress in Organic Coatings, 76(1), 1–6.
[6] Wang, S., Liu, H., & Yao, Y. (2015). Superhydrophobic surfaces for textiles. Advanced Materials Interfaces, 2(5), 1–10.
[7] Li, Y., & Zhu, Q. (2020). Eco-friendly water repellent finishes. Journal of Cleaner Production, 256, 120–145.
[8] Singh, A. V., et al. (2021). Nanotechnology in textile finishing. Materials Today Chemistry, 19, 100–120.
[9] Hossain, M. R., et al. (2025). Fluorine-free polysiloxane finishes. Journal of The Textile Institute
[10] Zhang, X., et al. (2018). Eco-friendly superhydrophobic fabrics. ACS Applied Materials & Interfaces
[11] Morrissette, J. M., et al. (2018). Green hydrophobic coatings. Green Chemistry
[12] Kim, J., et al. (2021). Non-fluorinated textile coatings. Progress in Organic Coatings
[13] Chen, T., et al. (2026). Fluorine-free repellent technologies review. Progress in Organic Coatings
[14] Patel, M., et al. (2024). Sustainable water repellent coatings. Polymers
[15] Rahman, M., et al. (2018). Performance evaluation of repellents. Textile Engineering Journal
[16] Kissa, E. (2001). Fluorinated surfactants and repellents. CRC Press.
[17] Ibrahim, N. A., et al. (2013). Functional finishes in textiles. Carbohydrate Polymers.
[18] Bhushan, B., & Jung, Y. C. (2011). Natural and biomimetic surfaces. Progress in Materials Science.
[19] Cassie, A. B. D., & Baxter, S. (1944). Wettability theory. Transactions of the Faraday Society.
[20] Young, T. (1805). Cohesion of fluids. Philosophical Transactions.
[21] Teli, M. D., & Sheikh, J. (2013). Silicone-based finishes. Journal of Textile Science.
[22] Mahltig, B., & Böttcher, H. (2003). Sol–gel coatings for textiles. Journal of Sol-Gel Science.
[23] Sun, G., et al. (2001). Durable press and repellency. Textile Research Journal.
[24] Pakdel, E., et al. (2020). Nanotechnology in textiles. Nanomaterials.
[25] Periyasamy, A. P., & Militky, J. (2017). Functional textiles review. Journal of Industrial Textiles.

©IJRASET: All Rights are Reserved | SJ Impact Factor 7.538 | ISRA Journal Impact Factor 7.894 |

[26] Vigneshwaran, N., et al. (2006). Nano-finished textiles. Carbohydrate Polymers.
[27] Verma, S., et al. (2012). Hydrophobic textile modification using nanoparticles
[28] Sharma, S., & Goel, A. (2025). Green repellent chemistry review

©IJRASET: All Rights are Reserved | SJ Impact Factor 7.538 | ISRA Journal Impact Factor 7.894 |



10.22214/IJRASET

45.98

IMPACT FACTOR: 7.129

IMPACT FACTOR: 7.429

INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089 (24*7 Support on Whatsapp)