



IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 6 Issue: I Month of publication: January 2018 DOI: http://doi.org/10.22214/ijraset.2018.1115

www.ijraset.com

Call: 🛇 08813907089 🕴 E-mail ID: ijraset@gmail.com



# Optimization of Drilling Process Parameters during the Drilling of Ti-6Al-4V Alloy Using Carbide Drill bit

P Prasanna<sup>1</sup>, V Y Manu Sharma<sup>2</sup>

<sup>1,2</sup>Department of Mechanical Engineering, JNTUH College of Engineering, Hyderabad

Abstract: The optimization of process parameters is of prime importance for the industry to be able to control and optimise the material cost and time effectively. In this paper the average thrust force on the tool, tool wear and average temperature of the work-piece are obtained from the simulation model developed using DEFORM software. The work-piece used was Ti-6Al-4V and tool used is carbide type drill. Optimisation of the values is done using Integrated PCA-Taguchi method. Keywords: Drilling, Thrust Force, Tool Temperature, Tool Wear, DEFORM Software, Integrated PCA-Taguchi Method

## I. INTRODUCTION

Drilling is a popular and widely used machining process in industries. The main considerations during the drilling are hole quality, surface finish and tool life. Industries are constantly striving for lower cost solutions to get the higher quality. Since, machining is largely an operator's skill dependant job, various methods were used in the past to quantify the impact of machining variables on the final quality of the product. Now, the CNC machinery has replaced the conventional machinery and many computer aided design based modelling tools are being used efficiently by the industries.

During the drilling, a considerable heat is generated due to the deformation and the friction at the interface. The heat generation raises the levels of temperature and this temperature generated greatly affects the material behaviour and the mechanics of chip formation. Many parameters like tool life, cutting forces, surface quality, mechanics of chip formation, etc., are also dependent on the machining temperature. In the present work, Ti-6Al-4V is considered as the work piece material because of its widespread applications in aerospace, medical, marine, and chemical processing. The main advantages of the alloy are high strength to low weight ratio and its outstanding corrosion resistance. Machining of these alloys can be treated as "hard to machine materials" because of their lower thermal conductivity and higher chemical reactivity [Zhang et al., (2010)]. The present work simulates the drilling of the chosen material for temperature and tool wear using a commercial finite element code called DEFORM-3D. The simulated results are subsequently considered to obtain optimal values of process parameters using Taguchi Integrated PCA Analysis

### II. FEA SIMULATION

In this investigation, cutting speed, feed rate and drill depth are considered as the process control variables. The geometric parameters of the drill are: drill diameter 10 mm, web thickness 2 mm, helix angle 280°, point angle 180°, margin 0.4 mm, and clearance 0.2 mm. Uncoated carbide twist drill bit of 24 per cent cobalt is used to machine Ti-6Al-4V work piece at 2700°C and the convection heat transfer coefficient at the work piece – cutting insert interface is chosen as 45 N/sec/mm/°C. The model is simulated for thermal analysis by assuming the work piece as a plastic material with a diameter of 30 mm and the cutting insert is assumed as a rigid body. Geometrically identical meshes for the thermal equations are used for the computation of cutting temperature and the Usui model (1978) is used to calculate the tool wear. This model is a widely used one for estimating tool wear which was derived considering sliding velocity between chip and cutting tool, tool temperature and normal pressure on tool face.

Since, the accuracy of any FEA model is directly dependent on the number of assumptions made, as well as the effort involved in correlating the computer model and the real application, some assumptions are made to define the problem and to apply the boundary conditions such as: the work piece is a homogeneous, isotropic, and incompressible solid; the work piece is set at room temperature as reference temperature of  $25^{\circ}$ C at the beginning of simulation, the machine tool is perfectly rigid and no influence of machine tool dynamics on machining is considered; and constant friction at tool-chip interaction and tool-work piece interaction.

Experiments are planned based on Design of Experiments (DOE). A rotatable central composite full factorial design with two center points is chosen.



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor :6.887

Volume 6 Issue I, January 2018- Available at www.ijraset.com

Table i				
Parameters and their levels				
Factors		Levels		
Pactors	1	2	3	
Speed (S) (rpm)	500	750	1000	
Feed(F) (mm/rev)	0.1	0.15	0.2	
Depth of cut(D) (mm)	1	3	5	

	Tab	le 2	
	Design of e	experiments	
Trial No	S	F	D
1	1	1	1
2	1	1	2
3	1	1	3
4	1	2	1
5	1	2	2
6	1	2	3
7	1	3	1
8	1	3	2
9	1	3	3
10	2	1	1
11	2	1	2
12	2	1	3
13	2	2	1
14	2	2	2
15	2	2	3
16	2	3	1
17	2	3	2
18	2	3	3
19	3	1	1
20	3	1	2
21	3	1	3
22	3	2	1
23	3	2	2
24	3	2	3
25	3	3	1
26	3	3	2
27	3	3	3

The simulation runs were conducted for the design of experiments table and the temperatures were tabulated. The interface of simulation software after loading the tool and the work-piece from its library is given in the Fig.1 below



International Journal for Research in Applied Science & Engineering Technology (IJRASET) ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor :6.887

Volume 6 Issue I, January 2018- Available at www.ijraset.com



FIG 1: Deform Interface

The experimental results of Thrust force, tool wear and simulation temperature for all the trails are tabulated in Table 3 as shown below.

		Resp		Tompor	Tool	Thrust
Eve No	c	Б	Б	atura	Ween	Forma
Exp No	3	Г	D		wear	rorce
				(°C)	(mm)	(N)
1	500	0.1	1	246	0.0024	2280
-	000	011	-	1.0	4	
2	500	0.1	3	400	0.0036	2572
2	500	0.1	5	477	4	2312
3	500	0.1	5	695	0.0044	2818
4	500	0.15	1	170	0.0047	2111
4	500	0.15	1	1/8	3	5111
_			_		0.0059	
5	500	0.15	3	437	9	3369
6	500	0.15	5	615	0.0068	3707
-			-		0.0064	
7	500	0.2	1	156	2	3987
					0.0077	
8	500	0.2	3	390	0.0077	4360
					3	
9	500	0.2	5	561	0.0085	4682
					9	
10	750	0.1	1	259	0.0078	5001
10	750	0.1	-	207	9	2001
11	750	0.1	3	524	0.0090	5370
11	750	0.1	5	524	6	5519
10	750	0.1	5	(00	0.0097	5707
12	750	0.1	Э	099	8	5727
10	750	0.15	1	016	0.0101	(000
13	/50	0.15	1	216	3	6099
		0.15		4.64	0.0113	
14	750	0.15	3	461	5	6511
					0.0121	
15	750	0.15	5	618	2	6953
	1	1			-	

#### Table 3 Responses for trials



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor :6.887 Volume 6 Issue I, January 2018- Available at www.ijraset.com

16	750	0.2	1	211	0.0117 6	7348
17	750	0.2	3	424	0.0130 3	7814
18	750	0.2	5	588	0.0138 6	8299
19	1000	0.1	1	309	0.0133 1	8803
20	1000	0.1	3	539	0.0144 5	9292
21	1000	0.1	5	710	0.0151 4	9748
22	1000	0.15	1	243	0.0154 9	10227
23	1000	0.15	3	492	0.0166 8	10734
24	1000	0.15	5	666	0.0174 2	11266
25	1000	0.2	1	220	0.0170 7	11848
26	1000	0.2	3	441	0.0183	12427
27	1000	0.2	5	606	0.0191 1	12962

## III. RESULTS AND DISCUSSION

### A. Analysis of Variance (ANOVA)

Analysis of Variance is carried out on the obtained experimental data to check the significance of the model.

Table 4					
	Anova- temperature				
Source	Sum of	df	Mean	E Value	n-value
Source	Squares	ui	Squares	i value	p-value
Model	833260.5278	9	92584.503	981.1722	< 0.0001
A-s	11200.05556	1	11200.055	118.6935	< 0.0001
B-f	43316.05556	1	43316.055	459.0456	< 0.0001
C-d	768800.000	1	768800.00	8147.424	< 0.0001
AB	147.000000	1	147.0000	1.557845	0.22890
AC	546.750000	1	546.7500	5.794230	0.02772
BC	1240.333333	1	1240.3333	13.14453	0.00209
A^2	0.166666667	1	0.166666	0.001766	0.96697
B^2	937.5000000	1	937.5000	9.935236	0.00582
C^2	7072.666667	1	7072.666	74.95319	< 0.0001
Residual	1604.138889	17	94.36111		
Cor	83/86/ 6667	26			
Total	054004.0007	20			



## International Journal for Research in Applied Science & Engineering Technology (IJRASET) ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor :6.887 Volume 6 Issue I, January 2018- Available at www.ijraset.com

From the above analysis it was found that feed and depth of cut are the most significant terms affecting the Tool Temperature as their p-values are <0.0001. R2=0.9450 which is 94.5%. The desirable value is close to 1 which indicates that the model has a variance of 5.5% and hence is within the acceptable limits.

Source	Sum of Squares	d f	Mean Squares	F Value	p- value
Model	2.79E+0 8	9	3.10E+0 7	7.74E+0 4	<0.000 1
A-s	2.45E+0 8	1	2.45E+0 8	6.12E+0 5	<0.000 1
B-f	2.72E+0 7	1	2.72E+0 7	6.78E+0 4	<0.000 1
C-d	3.09E+0 6	1	3.09E+0 6	7.72E+0 3	<0.000 1
AB	1.36E+0 6	1	1.36E+0 6	3.39E+0 3	<0.000 1
AC	1.34E+0 5	1	1.34E+0 5	3.35E+0 2	<0.000 1
BC	2.53E+0 4	1	2.53E+0 4	6.32E+0 1	<0.000 1
A^2	1.83E+0 6	1	1.83E+0 6	4.56E+0 3	<0.000
B^2	3.59E+0 4	1	3.59E+0 4	8.98E+0 1	<0.000 1
C^2	4.63E+0 1	1	4.63E+0 1	1.16E- 01	0.7379 6
Residu	6.80E+0	1	4.00E+0		
ai Cor	2 70E+0	2	2		
Cor Total	2.79E+0	6			
Total	δ	0			

Table 5Anova- thrust force

From the above analysis it was found that speed and feed are the most significant terms affecting the Tool Temperature as their p-values are <0.0001. R2=0.9546 which is 95.46%. The desirable value is close to 1 which indicates that the model has a variance of 4.54% and hence is within the acceptable limits

#### B. Principal Component Analysis (PCA) Integrated Taguchi Analysis

PCA is an optimisation tool which converts several multiple correlated responses into several uncorrelated quality indices. It maximises the variability of the data while minimizing the dimensionality of the data. The following steps are involved in the process.

1) Normalisation of data: The normalized values are calculated using the formula given below.

$$x_t(k) = \frac{\max y_t(k) - y_t(k)}{\max y_t(k) - \min y_t(K)}$$



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor :6.887

Volume 6 Issue I, January 2018- Available at www.ijraset.com

Table 6

	Normalised data			
Trial	Temperature	Tool	Thrust	
No	Temperature	Wear	Force	
1	0.837545	1	1	
2	0.380866	0.928014	0.972664	
3	0.027076	0.882424	0.949635	
4	0.960289	0.862627	0.922206	
5	0.49278	0.787043	0.898053	
6	0.17148	0.738452	0.866411	
7	1	0.761248	0.840198	
8	0.577617	0.682663	0.80528	
9	0.268953	0.631074	0.775136	
10	0.814079	0.673065	0.745272	
11	0.33574	0.602879	0.709886	
12	0.019856	0.559688	0.677308	
13	0.891697	0.538692	0.642483	
14	0.449458	0.465507	0.603913	
15	0.166065	0.419316	0.562535	
16	0.900722	0.440912	0.525557	
17	0.516245	0.364727	0.481932	
18	0.220217	0.314937	0.436529	
19	0.723827	0.34793	0.389347	
20	0.308664	0.279544	0.343569	
21	0	0.238152	0.30088	
22	0.84296	0.217157	0.256038	
23	0.393502	0.145771	0.208575	
24	0.079422	0.10138	0.158772	
25	0.884477	0.122376	0.104288	
26	0.48556	0.04799	0.050084	
27	0.187726	0	0	

Table 7
---------

	$PC_1$	$PC_2$	PC <sub>3</sub>
Eigen Value	2.0428	0.9482	0.0091
Accountability Proportion (AP)	0.681	0.316	0.003
Cumulative AP	0.681	0.997	1



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor :6.887 Volume 6 Issue I, January 2018- Available at www.ijraset.com

#### TABLE 7 FIGEN VECTORS

LIGEN VECTORS					
0.221	0.974	0.041			
0.693	-0.127	-0.71			
0.687	-0.185	0.703			

2) Calculating Principal Components (PC), Composite Principal Components (CPC) and S/N values: The principal components, Composite Principal components and S/N values are calculated from the following formulae.

$$\begin{split} &PC_1{=}(0.221^*T){+}(0.693^*T_w){+}(0.687^*T_f) \\ &PC_2{=}(0.974^*T){+}({-}0.127^*T_w){+}({-}0.185^*T_f) \\ &PC_3{=}(0.041^*T){+}({-}0.71^*T_w){+}(0.703^*T_f) \\ &CPC = (PC_1^2{+}PC_2^2{+}PC_3^2)^{1/3} \end{split}$$

$$= -10 \log_{10} \frac{1}{2} \sum_{n=1}^{\infty} \frac{1}{2}$$

Where is S/N Value and y is CPC Value

TABLE 8PRINCIPLE COMPONENTS TABLE

Trial	DC	DC	DC
No	$\mathbf{r}\mathbf{C}_1$	$rC_2$	$\Gamma C_3$
1	1.565097	0.503769	0.027339
2	1.395506	0.073163	0.040508
3	1.269902	-0.26138	0.042183
4	1.44358	0.65516	0.075217
5	1.271287	0.213873	0.092735
6	1.144869	-0.08705	0.091816
7	1.325761	0.721885	0.091174
8	1.153967	0.326924	0.105103
9	1.029291	0.038414	0.107885
10	1.158348	0.569559	0.079427
11	0.979686	0.119116	0.084771
12	0.857562	-0.17704	0.079583
13	1.011764	0.681239	0.105753
14	0.836815	0.266929	0.112469
15	0.713748	0.004425	0.104556
16	0.865669	0.724079	0.093349
17	0.697934	0.367345	0.101008
18	0.566814	0.093736	0.092303
19	0.668563	0.588791	0.056357
20	0.49797	0.201577	0.055708
21	0.371744	-0.08591	0.04243
22	0.512682	0.746097	0.060375
23	0.331274	0.326171	0.059265
C24	0.196885	0.035109	0.042893
25	0.351921	0.826645	0.022691
26	0.174974	0.457575	0.021044
27	0.041487	0.182845	0.007697



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor :6.887

Volume 6 Issue I, January 2018- Available at www.ijraset.com

Table 9				
C	Cpc and s/n v	alues		
Trial	CPC	S/N		
No	CrC	Value		
1	1.393174	-2.88011		
2	1.250278	-1.94013		
3	1.189433	-1.5068		
4	1.360605	-2.67464		
5	1.186542	-1.48566		
6	1.098823	-0.81855		
7	1.317528	-2.3952		
8	1.131738	-1.07492		
9	1.023623	-0.2028		
10	1.187007	-1.48907		
11	0.99368	0.055072		
12	0.91779	0.745131		
13	1.144444	-1.17189		
14	0.92215	0.70397		
15	0.804345	1.891152		
16	1.086442	-0.72013		
17	0.858284	1.327378		
18	0.696984	3.135549		
19	0.927089	0.657574		
20	0.66321	3.56698		
21	0.528211	5.543856		
22	0.937187	0.563476		
23	0.603354	4.388554		
24	0.34715	9.18966		
25	0.931289	0.618312		
26	0.62182	4.126703		
27	0.327768	9.688675		

From the above analysis the mean of S/N values plot was obtained



## Fig 2: ean of S/N plots

#### IV. CONCLUSION

The optimal values of Temperature, Tool wear and Thrust Force 666°C, 0.01742mm and 11266N respectively were obtained at a cutting speed of 1000 rpm, feed rate of 0.15 mm/rev, Drill depth of 5 mm.



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor :6.887

Volume 6 Issue I, January 2018- Available at www.ijraset.com

#### REFERENCES

- [1] SFTC Deform 3D, V.6.1, Scientific Forming Technologies Corporation
- [2] A.V. Mitrfanov, V.I. Babitsky, V.V. Silbersschmidt (2005), Finite element analysis of ultrasonicallyassisted turning of Inconel 718, journal of Materials Processing Technology, vol. 153–154, pp. 233–239.
- [3] C.Z. Duan, T. Dou, Y.J. Cai, Y.Y. Li (2005), Finite Element Simulation and Experiment of Chipformation Process during High Speed Machining of AISI 1045 Hardened Steel, International Journal of Recent Trends in Engineering, Vol. 5, pp. 46–50
- [4] Design Expert Software, version 8, Users Guide, Technical Manual, Stat-Ease Inc.
- [5] H.K. Kansal, Sehijpal Sing, P. Kumar (2005), Parametric optimization of powder mixed electricaldischarge machining by response surface methodology, Journal of Materials Processing Technology, vol.169, pp. 427–436.
- [6] I.A. Choudary, M.A. El-Baradie (1999), Machinability assessment of Inconel 718 by factorial design of experiment coupled with response surface methodology, Journal of Material processing Technology vol.95, pp. 30–39.
- [7] K. Kadirgama, M.M. Noor, M.M. Rahman, W.S.W. Harun, C.H.C. Haron (2009), Finite ElementAnalysis and Statistical Method to Determine Temperature Distribution on Cutting Tool in End-Milling, European Journal of Scientific Research, Vol. 30, No. 3, pp. 415–463.
- [8] L. Filice, D. Umbrello, S. Beccari, F. Micari (2006), On the FE codes capability for tool temperaturecalculation in machining processes, Journal of Materials Processing Technology, vol. 174, pp. 286–292.
- [9] RavirajShetty, Laxmikant K, R. Pai and S.S. Rao (2008), Finite element modeling of stress distributionin the cutting path in machining of discontinuously reinforced aluminium composites, ARPN Journal ofEngineering and Applied Sciences, Vol. 3, pp. 25–31.
- [10] Rui Li, Albert J.Shih (2006), Finite element modeling of 3D turning of titanium, International Journal of Advanced Manufacturing Technology, vol. 29, pp. 253–261.
- [11] A. Karabulut (2010), Determination of diametral error using finite element and experimental method, METABK, vol. 49(1), pp. 57-60
- [12] Usui, E., Shirakashi, T. and Kitagawa, T. (1978), Analytical prediction of three dimensional cuttingprocess, part 3: cutting temperature and crater wear of carbide tool, Journal of Engineering for Industry, vol. 100 (5), pp. 236–243.
- [13] Yancheng Zhang et al. (2010), FE-model for Titanium alloy (Ti-6Al-4V) cutting based on theidentification of limiting shear stress at tool-chip interface, international journal of Material Forming,DOI 10.1007/s12289-010-0986-7











45.98



IMPACT FACTOR: 7.129







INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089 🕓 (24\*7 Support on Whatsapp)