



IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 6 Issue: III Month of publication: March 2018 DOI: http://doi.org/10.22214/ijraset.2018.3341

www.ijraset.com

Call: 🕥 08813907089 🔰 E-mail ID: ijraset@gmail.com

The Effect of Laterally Substituted Methoxy Group on Mesomorphicity

Jwalant j. Travadi¹

¹ Kamani Sc. and Prataprai Arts College, Amreli, Gujarat, (India).

Abstract: To understand structure-activity relationship, comparative A study of newly synthesised homologous series with structurally similar known homologous series is carried out. Newly synthesised homologous series 1 to $7^{[6-12]}$ and selected other series-X and $-Y^{[13-23]}$ for comparative study, resemble to each other in all respect i.e. two phenyl rings, central bridge -COO-, right handed tail -CH=CH-COOR, left n-alkoxy end-group for the same homologue, but differs with respect to laterally substituted -OCH₃ group. Especially this study is focused to understand the effect of laterally substituted methoxy group on mesomorphicity. Different liquid crystalline properties (viz. type of mesophase, mesophaselength, and relative thermal stabilities, upper transition temperatures etc are mutually compared. 1) Presence and/or absence, 2) Size 3) Position and 4) Polarity of laterally substitution of methoxy group affect the mesomorphic characteristics of similar type compounds. A phenomenon of mesomorphism is very sensitive and susceptible to molecular structure of a substance. Present comparative study supports the views and conclusions drawn earlier.


Keywords: Smectogenic, nematogenic, mesophaselength, structure-activity relationship, polarity, steric effect

I. INTRODUCTION

Some substances possess ability to flow as liquid and optical properties as crystal since they are recognize as mesomorphic state^[1] known as a special state of matter. Liquid crystalline (LC) state of a substance is well known for its importance in various fields of applications^[2, 3, 4, 5]. Liquid crystalline properties are strictly depends on molecular geometry of mesomorphs and they vary by varying molecular aromaticity, central groups, terminal groups, positions of same or different functional groups on phenyl ring or rings, geometrical shape, size, polarity and polarizability etc. This is because of factors (like length to breadth ratio, net polarity and polarizability of molecules, intermolecular hydrogen bonding, effect of size and polarity of lateral substituent as well as terminal end groups etc) affecting predominantly to liquid crystalanity of material (e.g. type of mesophase, thermal stability, mesophase length, early and late commencement of mesophase in series). Present study is focused to understand structure-activity relationship with respect to study of the effect of laterally substituted methoxy group on mesomorphicity. Here comparative study among different homologous series with similar type of geometry and structural features has been carrying out.

II. MATERIALS AND METHODS

A. General Formula Of Newly Synthesised Compounds



B. Comparative study


Comparative study of newly synthesised homologous series with structurally similar known homologous series is carried out. Newly synthesised homologous series 1 to $7^{[6-12]}$ and selected other series-X and $-Y^{[13-23]}$ for comparative study, resemble to each other in all respect i.e. two phenyl rings, central bridge -COO-, right handed tail -CH=CH-COOR, left n-alkoxy end-group for the same homologue, but differs with respect to laterally substituted -OCH₃ group, which are reflected in "Flow Chart-1.

A source of the source of the

International Journal for Research in Applied Science & Engineering Technology (IJRASET)

ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 6.887

Volume 6 Issue III, March 2018- Available at www.ijraset.com



III. RESULTS AND DISCUSSION

A novel homologous series ($R_2 = C_1$ to C_4) of esters with two phenyl rings and lateral substitution are partly smectogenic and partly nematogenic, while novel homologous series ($R_2 = C_5$ to C_7) are totally smectogenic without exhibition of nematic property.

All novel homologous series are middle ordered melting type with considerable mesophaselength temperature range.

Comparison of presently investigated series with other structurally similar known series is carry out with respect to structural geometry and liquid crystalline properties (viz. type of mesophase, mesophaselength, relative thermal stabilities, upper transition temperatures etc) to understand structure-activity relationship (especially to understand the effect of laterally substituted methoxy group on mesomorphicity).

High smectic phase stability is largely attributed to; (i) efficient filling of space by bulky $-OCH_3$ group, which enhances intermolecular attractions. (ii) favourable lamellar packing afforded by the polarity of the lateral $-OCH_3$ group. (iii) large size of laterally substituted $-OCH_3$ group hinders parallel arrangement of molecules which reduce end-to-end intermolecular attractions favourable to exhibit nematic properties. (iv) lateral group at ortho position with respect to -COO- central bridge, {a} increases molecular breadth, reduces the strength of the lateral intermolecular attraction. {b} increases in molecular breadth which decreases the thermal stability of the nematic mesophase. (v) Polarity of $-OCH_3$ group affect π -electron conjugation, electron density on phenyl rings etc which might major effect on mesomorphic characteristics of compound.

The polarity of laterally substituted functional group in combination with the ratio of polarity to polarisability of lateral substituent affect directly net intermolecular attractions and therefore, the nature of lateral functional group, might alter, induce or diminished liquid crystalline properties.

Steric effect of the bulky substituent prevents a close molecular packing, and thus the liquid crystalline order may more easily destroyed by thermal fluctuations.

IV. CONCLUSION

- A. Present investigation may be useful for the study of binary systems to operate LC devices at desired temperature between 60° C to 100° C and agricultural production.
- B. Ester derivatives containing -CH=CH- unit may be useful in agricultural production.
- *C*. Some of the transition temperatures varies between 36° C to 96° C for mesomorphic homologues. Such mesomorphs are useful for the study of binary systems for the devices workable at room temperatures.



International Journal for Research in Applied Science & Engineering Technology (IJRASET)

ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 6.887

Volume 6 Issue III, March 2018- Available at www.ijraset.com

- *D.* Suitable magnitudes of anisotropic forces of intermolecular attractions as a consequence of molecular rigidity and/or flexibility can induce mesomorphic behaviours in a substance.
- E. Favourable molecular rigidity and flexibility are governing mesomorphism depending on molecular structure.
- F. Phenomena of mesomorphism is very sensitive and susceptible to molecular structure of a substance.
- G. Present comparative study supports the views and conclusions drawn earlier.
- *H.* Present comparative study might be useful to the groups of researchers to design new liquid crystals with desired liquid crystalline properties (viz. mesophase, mesophaselength, and relative thermal stabilities, upper transition temperatures etc).

V. ACKNOWLEDGEMENTS

The authors are especially thankful to management, principal and HOD (chemistry Dept.) of Shree M. & N. Virani Sc. College (Autonomous), Rajkot and Kamani Sc. College & Prataprai Arts College, Amreli for their valuable cooperation to facilitate for present research work.

REFERENCES

- [1] Reinitzer, F. (1888). Monatsch, 9, 421.
- [2] Naemura, S. (2001). Advance LCD technologies, Displays: 22(1) p.1.
- [3] Kim, W. S., Elston, S. J., and Raynes, F. P. (2008). Displays: 29, pp. 458-463.
- [4] Calliste, C. A., Le Bail, J. C., Trouilas, P., Pouget, C., Chulia, A. J., Duroux, L. J. (2001). Anticancer research,
- 21, 3949-3956.
 [5] Jahng, Y., Zhao, L., Moon, Y., Basnet, A., Kim, E., Chang, H. W., Ju, H. K., Jeong, T. C. & Lee, E. S., (2004). Bioorg. Med. Chem. Lett., 14, 2559-2562.
- [6] Vadodaria, M. S., Ladva, K. D., Doshi, A. V. and Travadi J. J., (2016), "Synthesis of novel ester series and study of itsmesomorphism dependence on terminal end group with lateral –OCH₃ group", Mole. Cryst. Liq. Cryst., Vol. 624, No. 1, 59-68.
- [7] Travadi J. J., Vadodaria, M. S., Ladva, K. D. and Doshi, A. V., (2016), "Mesomorphism dependence on molecular flexibility", Mole. Cryst. Liq. Cryst., Vol. 630, 69-78.
- [8] Travadi J. J., Vadodaria, M. S., Ladva, K. D. and Doshi, A. V., (2016), "Dependence of Mesomorphism on Molecular Rigidity with Reference to Lateral Substitution and Central Bridge", Mole. Cryst. Liq. Cryst., Vol. 626, 58-67.
- [9] Travadi J. J., Vadodaria, M. S., Ladva, K. D. and Doshi, A. V., (2016), "Study of the Effect of Lateral Substitution on Mesogenic Behavior with Reference to -CH=CH- Unit", Mole. Cryst. Liq. Cryst., Vol. 626, 90-99.
- [10] Travadi J. J., Vadodaria, M. S., Ladva, K. D. and Doshi, A. V., (2016), "Mesomorphism Dependence on Molecular Structure", Mole. Cryst. Liq. Cryst., Vol. 626, 21-30.
- [11] Vadodaria, M. S., Ladva, K. D., Doshi, A. V. and Travadi J. J., (2016), "Mesomorphism dependence on lateral substitution and central bridge", Mole. Cryst. Liq. Cryst., Vol. 624, Vol.1, 103-111.
- [12] Travadi J. J., Vadodaria, M. S., Ladva, K. D. and Doshi, A. V., (2016), "Dependence of mesomorphism on tail group in combination with a lateral methoxy group", Mole. Cryst. Liq. Cryst., Vol. 625, 63-71.
- [13] Chauhan, M. L. and Doshi, A. V., Mol. Cryst. Liq. Cryst. Vol. 548, pp. 228-234, (2011).
- [14] Lohar, J. M., and Doshi, A. V., Acta Ciencia Indica, vol. XVIII C(3), pp. 245-250, (1992).
- [15] Chauhan, M. L. and Doshi A. V. Mole. Cryst. Liq. Cryst. Vol. 623, Issue-1, pp. 157-165, (2015).
- [16] Patel, R. B. and Doshi, A. V., "Synthesis and Study of a New Homologous Series of Cis n-Propyl-p-(p'-n-alkoxy Cinnamoyloxy) Cinnamates", Der Pharma Chemica, 3(1): 538-548, (2011).
- [17] Doshi, A. V. and Chauhan, M. L., Acta Ciencia Indica Vol.XXXIV C, No. 1, pp. 79-84, (2008).
- [18] Doshi, A. V. and Lohar, J. M., Acta Ciencia Indica Vol.XVIII C, No. 3, pp. 245 248, (1992).
- [19] Chauhan, M. L. and Doshi A. V. Mole. Cryst. Liq. Cryst. Vol. 623, Issue-1, pp. 166-175, (2015).
- [20] Patel R. B., Chauhan M. L., and Doshi A. V., Der Pharma Chemica, Vol.-2 (6), p.p. 157-164, (2010).
- [21] Chauhan, M. L., Ph.D. Thesis entitled "Synthesis and study of mesogenic material" submitted to the Saurastra University. Rajkot, Gujarat, (Nov.2006).
- [22] Doshi, A. V. and Patel, R. B., Synthesis and study of a new homologous series of cis cinnamate ester of mesogens: n-Hexyl-p-(p'-n-alkoxy cinnamouloxy) cinnamates, Derpharma chemica, 3(1): 338-348, (2011).
- [23] Patel, Brijesh, H., and Doshi, A. V., "Synthesis and study of a novel Ester homologous series and evaluation of its Liquid Crystal behaviour in Relation with Molecular Structure" Mol. Cryst. Liq. Cryst., Volume 605, p. 43-51 (2015).











45.98



IMPACT FACTOR: 7.129







INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089 🕓 (24*7 Support on Whatsapp)