



IJRASET

International Journal For Research in
Applied Science and Engineering Technology



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 6 Issue: VIII Month of publication: August 2018

DOI:

www.ijraset.com

Call:  08813907089

E-mail ID: ijraset@gmail.com

Synthesis of CuO Nanoparticles using Coffea Powder by Simple Chemical Precipitation Method

Amita Mathew

Department of Physics, Christ College of Science and Management, Karnataka-563130

Abstract: Copper oxides nanoparticles is emerging in our research field and can be synthesised by many methods. In this work, CuO nanoparticles were synthesised by Coffea powder extract. The synthesised CuO nanoparticle was characterized by XRD. The results indicate that CuO nanoparticles synthesised by Coffea powder extract has an average particle size of 28.80 nm-11.27 nm.

Keywords: Synthesis, Coffea powder extract, XRD, CuO Nanoparticles.

I. INTRODUCTION

Copper(II) oxide is a p-type semiconductor, having a energy gap of 1.2eV with a work function value of 5.3eV. They belong to monoclinic crystal system [1]. CuO has wide range of applications, antibacterial, anti-biotic, catalysis, sensors, dry cell batteries and so on [2]-[4]. In this work, CuO nanoparticles are synthesised using Coffea commonly known as coffee powder extract. The particle size, crystal and amorphous nature of materials of particles were studied using XRD characterization.

II. MATERIALS AND METHODS

The Coffea (or coffee) beans were purchased from the market, for the synthesis it was grinded into fine powder. Cupric Nitrate and distilled water was purchased from Merck, India, and was used as purchased without any modification.

A. Chemical Precipitation Method

20g fine grounded Coffea powder was dissolved in 250 ml of distilled water and boiled for 4 hours in medium flame and cooled down to the room temperature. The extract obtained was then kept overnight. Copper Nitrate solution and Coffea extract was taken in 1:2 ratio and was slowly added to the extract under vigorous constant stirring at 270°C for 3 hours which gives the brown precipitate. After cooling at room temperature, the extract was filtered using Whatman filter paper and was thoroughly washed with distilled water three times to remove any impurities present in it. The collected precipitate was dried in Hot Air Oven for 8 hours at 80°C and then transferred to silica crucibles and kept in Muffle Furnace for 3-3.5 hours at 500°C. The powder obtained was grinded into fine powder using mortar pestal.

B. Characterization

The CuO nanoparticles were send to SAIF, Kochi, for the XRD characterization. XRD was carried out with Bruker AXS D8 Advance model and Cu Wavelength 1.5406 Å was used with the temperature range of -170 °C to +450 °C.

III. RESULTS AND DISCUSSION

The XRD spectra of synthesised CuO nanoparticles was carried out and resulted 2Theta values ranging from 20° to 80°. The 2Theta values at 28.3, 32.5, 38.7, 48.8, 62.1 and 66.2 were observed as shown in Fig.1. The average crystalline size was found to be 27nm and 32nm. The peaks obtained with this method was matching with the JCPDS No.80-1268 data, which confirms the CuO nanoparticles presence.




Fig. 1 XRD of CuO nanoparticles

TABLE I Particle size measurements

Peak Position (degree)	FWHM	Particle size (nm)
28.3	0.297	28.80
32.5	0.348	24.83
38.7	0.459	19.16
48.8	0.452	20.15
62.1	0.447	21.61
66.2	0.879	11.27

IV. CONCLUSIONS

CuO nanoparticles were synthesized by the chemical precipitation method using Coffea powder extract. Its simple and low cost. The prepared CuO nanoparticles were characterized using XRD. The intensity counts and 2Theta graph was plotted, the peaks obtained from the experiment clearly matches with the JCPDS No.80-1268 data. CuO nanoparticles presence were confirmed. The average CuO nanoparticle size was found to be 28.0 nm – 11.27 nm.

V. ACKNOWLEDGMENT

My heartfelt thanks to Department of Physics, Christ College of Science and Management for providing me the opportunity to complete the work successfully.

REFERENCES

- [1] R.K Swarnkar, S.C Singh and R. Gopal, Synthesis of Copper/Copper-oxide Nanoparticles: Optical and Structural Characterizations. AIP.Conf.Proc.1147.2009,205-210.
- [2] L.Zhang, F.X Gu, J.M Chan, A.Z Wang, R.S Langer, O.C Farokhza, Nanoparticles in Medicine: Therapeutic Applications and Developments, nature, 83(5),2008,761-769.
- [3] M.Yhi, C.Wu, Y. Lou, C. Burda, J.T.Koberstein, Y.Zhu and Stephen O'Brien. Copper Oxide Nanocrystals. J.Am. Chem. Soc.,127(26), 2005,9506-9511.
- [4] P.Chand, A.Gaur and A Kumar, Structural and Optical Studies of CuO nanostructures. AIP.Conf.Proc.1591,2014,262-264.
- [5] N.Sanvicens and M.P Macro, Multifunctional nanoparticles- Properties and prospects for their use in human medicine. Trends Biotechnol.,26(8),2008,425-433.



10.22214/IJRASET



45.98



IMPACT FACTOR:
7.129



IMPACT FACTOR:
7.429



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089  (24*7 Support on Whatsapp)