



IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 7 Issue: IV Month of publication: April 2019

DOI: https://doi.org/10.22214/ijraset.2019.4091

www.ijraset.com

Call: 🕥 08813907089 🔰 E-mail ID: ijraset@gmail.com



Design and Analysis of Pressure Vessel used in Gasoline Industries

K. Arun Kumar Reddy¹, M. Surya Prakash Reddy², K. Lokesh Kumar³

^{1,2} IV B.Tech Students, ³Assistant Professor, Mechanical Engineering, Vignana Bharathi Institute of Technology, Proddatur, YSR Kadapa Dist. JNTU Ananthapur

Abstract: Pressure vessels are closed containers used for handling and storing of fluids. It passes the sequence of hydrostatic test. The process industry designers have recognized the limitations for confining large volumes of high internal pressures in single wall vessel. The increment in thickness beyond certain value will posses only fabrication difficulties. Multilayer pressure vessels are reliable equipment useful in wide range of operating conditions. So for this purpose we are adding the material called carbon fibre to steel. We are using hydrogen as a fluid in both single wall pressure vessel and multilayer pressure vessel at the pressure of 21 N/mm². Single wall pressure vessel and multilayer pressure vessel are designed in "Solidworks". The stresses, strains, displacements, frequencies developed in solid wall pressure vessel and multilayer pressure vessel are analyzed by using "COSMOS".

Keywords: Design, Analysis, Solid and multilayer pressure vessel, Solidworks, COSMOS.

I. INTRODUCTION

The pressure vessels are used to store fluids under pressure. The fluid being stored may undergo a change of state inside the pressure vessels as in case of steam boilers or it may combine with other reagents as in chemical plants. Pressure vessels find wide applications in thermal and nuclear power plants process, and chemical industries, in space and ocean depths, and in water, steam, gas and air supply systems in industries. The material of a pressure vessel may be brittle such as cast iron or ductile such as mild steel. High pressure vessels are used as reactors, separators and heat exchangers. They are vessel with an integral bottom and a removable top head and are generally provided with an inlet, heating and cooling systems and also an agitator system. High pressure vessels are used for a pressure range of 15 N/mm² to a maximum of 300 N/mm². These are essentially thick walled cylindrical vessels ranging in size from small tubes to several meters diameter. Both the size of the vessel and the pressure involved with dictate the type of construction used.

II. DIMENSIONS AND PROPERTIES

- A. For Solid Wall Pressure Vessel
- 1) Analysis type = Static and Modal
- 2) Material = Steel (Iron-85%, Chromium-13%, Carbon-2%)
- 3) Design pressure = 21 N/mm^2
- 4) Inside radius of vessel =1143 mm
- 5) Thickness = 219 mm
- 6) Length = 3352 mm

Description	Material	Young's Modulus	Density (kg/m ³)	Poisson's ratio	Yield strength
		(G Pa)			(M Pa)
Vessel	Steel S235	190	8050	0.26	215
Dished ends	Steel S235	190	8050	0.26	215

B. For Multilayer Pressure Vessel


- 1) Analysis type = Static and Modal
- 2) Material type = 1. Steel (Iron-85%, Chromium-13%, Carbon-2%)
 - 2. Carbon fibre (Polyacrylonitrile-90%, Resin-10%)
- 3) Design pressure = 21 N/mm^2
- 4) Inside radius of vessel = 1143 mm



- 5) Thickness = 219 mm
- 6) Length = 3352 mm
- 7) Number of layers = 5
- 8) Thickness of each layer = 12 mm

Description	Material	Young's Modulus	Density (kg/m ³)	Poisson's ratio	Yield strength
		(G Pa)			(M Pa)
Vessel	Steel S235	190	8050	0.26	215
Dished ends	Steel S235	190	8050	0.26	215
Vessel	Carbon fibre	70	1600	0.10	600
Dished ends	Carbon fibre	70	1600	0.10	600


III. MODEL-PRESSURE VESSEL



IV. ANALYSIS

- A. For Solid Wall Pressure Vessel
- 1) Static Analysis:
- a) Stress:


Name	Туре	Minimum	Maximum
Stress	VON: von Mises stress	4.293e+000N/mm^2 (MPa)	3.782e+002N/mm^2 (MPa)
		Node: 39720	Node: 21613






b) Displacement:

Name	Туре	Minimum	Maximum
Displacement	URES: Resultant	0.000e+000mm	0.000e+000mm
	Displacement	Node: 1743	Node: 1743



c) Strain:


Name	Туре	Minimum	Maximum
Strain	ESTRN: Equivalent Strain	4.477e-003	1.381e-001
		Element: 701	Element: 24188




2) Modal Analysis:

Name	Туре	Minimum	Maximum
Amplitude 1	AMPRES: Resultant	0.000e+000	6.628e-003
	Amplitude Plot for Mode Shape: 1(Value = 26.8921 Hz)	Node: 1743	Node: 244






Name	Туре	Minimum	Maximum
Amplitude 2	AMPRES: Resultant	0.000e+000	6.521e-003
	Amplitude Plot for Mode	Node: 1743	Node: 337
	Shape: $2(Value = 27.11 Hz)$		




Name	Туре	Minimum	Maximum
Amplitude 3	AMPRES: Resultant	0.000e+000	7.532e-003
	Amplitude Plot for Mode	Node: 1743	Node: 20851
	Shape: 3(Value = 29.3825		
	Hz)		






Name	Туре	Minimum	Maximum
Amplitude 4	AMPRES: Resultant	0.000e+000	7.579e-003
	Amplitude Plot for Mode	Node: 1743	Node: 4949
	Shape: $4(Value = 29.5239)$		
	Hz)		




Name	Туре	Minimum	Maximum
Amplitude 5	AMPRES: Resultant	0.000e+000	9.729e-003
	Amplitude Plot for Mode	Node: 1743	Node: 6
	Shape: $5(Value = 31.9516)$		
	Hz)		



- B. For Multilayer Pressure Vessel
- 1) Static Analysis:
- a) Stress:


Name	Туре	Minimum	Maximum
Stress	VON: von Mises Stress	5.988e+000N/mm^2 (MPa)	2.061e+003N/mm^2 (MPa)
		Node: 212755	Node: 152260






b) Displacement:

Name	Туре		Minimum	Maximum
Displacement	URES:	Resultant	0.000e+000mm	2.208e+002mm
	Displacement		Node: 183056	Node: 66458




c) Strain:

Name	Туре	Minimum	Maximum
Strain	ESTRN: Equivalent Strain	1.840e-004	6.386e-002
		Element: 111603	Element: 136275




2) Modal Analysis:

Name	Туре	Minimum	Maximum
Amplitude 1	AMPRES: Resultant	0.000e+000	1.756e-002
	Amplitude Plot for Mode	Node: 135677	Node: 16848
	Shape: $1(Value = 37.9109)$		
	Hz)		







Name	Туре	Minimum	Maximum
Amplitude 2	AMPRES: Resultant	0.000e+000	1.027e-002
	Amplitude Plot for Mode Shape: 2(Value = 46.6183	Node: 135677	Node: 2
	Shape: $2(v \text{ and } = 40.0183 \text{ Hz})$		



Name	Туре	Minimum	Maximum
Amplitude 3	AMPRES: Resulta	nt 0.000e+000	6.783e-003
	Amplitude Plot for Mo	de Node: 135677	Node: 5578
	Shape: 3(Value = 50.2801 H	Iz	




Name	Туре	Minimum	Maximum
Amplitude 4	AMPRES: Resultant	0.000e+000	6.798e-003
	Amplitude Plot for Mode	Node: 135677	Node: 358
	Shape: 4(Value = 50.297 Hz)		





Name	Туре	Minimum	Maximum
Amplitude 5	AMPRES: Resultant	0.000e+000	9.309e-003
	Amplitude Plot for Mode Shape: 5(Value = 50.7976 Hz)		Node: 451



V. RESULTS

A. Static Analysis

Single wall pressure vessel		Multilayer pressure vessel			
Material	Displacement (mm)	Stress (N/mm ²)	Material	Displacement (mm)	Stress (N/mm ²)
Steel	5.699e2	3.78e2	Steel and Carbon fibre	2.208e2	2.061e3

B. Modal Analysis

Material	Amplitude 1 (Hz)	Amplitude 2 (Hz)	Amplitude 3 (Hz)	Amplitude 4 (Hz)	Amplitude 5 (Hz)
Steel	26.892	27.11	29.382	29.524	31.952
Steel and Carbon	37.911	46.618	50.28	50.297	50.798
fibre					

C. Weight Comparison

Single wall pressure vessel		Multilayer pressure vessel	
Steel	197703 kg	Steel and Carbon fibre	181159.29 kg

VI. CONCLUSION

- *A.* At present solid wall pressure vessels are used extensively. But buy using multilayered vessels, there is a huge difference in weight. The weight is almost decreased by 16543.71kg when multilayered vessels are used in place of solid vessels.
- *B.* This decreases not only the overall weight of the component but also the cost of the material required to manufactured the pressure vessels. This is one of the main aspects of designer to keep the weight and cost as low as possible.
- *C.* Owing to the advantages of the multi layered pressure vessels over the conventional single walls pressure vessels, it is concluded that multi layered pressure vessels are superior for high pressures and high temperature operating conditions.
- *D*. By analysis it is proved that using carbon fibre is also safe since the analyzed stress value is less than yield stress value 600 M Pa and also less than that by using carbon fibre. The factor of safety obtained is also more than 2.



REFERENCES

- [1] BHPV manual on Multilayer pressure vessels
- [2] Brownell and Young, "Process Equipment Design" Seely, F.B., and Smith.
- [3] John F.Henvey "Pressure Vessel Design Nuclear and chemical Applications" an East West Edition, Newyork
- [4] Henry H.Bednar "Pressure Vessel Code Book"
- [5] Fratcher, G.E : New alloys for Multilayer Vessels" Vol 33
- [6] Harold.H.Wait e, "Pressure vessel and piping Design Analysis"
- [7] Mc Cabe, J.S and Rothrock, E.W., Multilayer Vessels for high Pressure," ASME Mechanical Engineering PP 34-39.











45.98



IMPACT FACTOR: 7.129







INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089 🕓 (24*7 Support on Whatsapp)