



IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 7 Issue: IV Month of publication: April 2019 DOI: https://doi.org/10.22214/ijraset.2019.4201

www.ijraset.com

Call: 🕥 08813907089 🔰 E-mail ID: ijraset@gmail.com



Optimization of Process Parameters of Plastic Injection Molding Machine by using Taguchi Method

Parvinder Singh Brar¹, Abdul Samad²

¹Mtech Mechanical Engineering (production), Marudhar Engineering College, Bikaner, Rajasthan ²Assistant Professor Mechanical Engineering, Marudhar Engineering College, Bikaner, Rajasthan

Abstract: The present study is application of taguchi method to optimize the process parameters of injection molding machine to minimize the shrinkage of product to enhance the quality of product. The predicted optimal setting ensures minimum shrinkage of product. Five process parameters of plastic injection molding machine were taken as melt temperature, mold temperature, injection pressure, holding pressure and cooling time. By ANOVA analysis it is found that melt temperature is most significant and cooling time is least significant factor affecting the dimensional shrinkage of manufactured plastic product. Keywords: Plastic injection molding, Dimensional shrinkage, Taguchi method, ANOVA Analysis, process parameter

I.INTRODUCTION AND LITERATURE REVIEW

Plastic injection molding is a technique which is used to produce plastic products. In this technique raw thermo plastic material is used to make the plastic products. Thermo plastic material is having property of easy melting and regaining shape when temperature is lowered. Raw material in form of pallets is fed into hopper. From hopper the raw material is transferred to machine by piston and cylinder mechanism. Raw material is heated to melting temperature with the help of heating elements during movement of raw material to injection chamber. The raw material which is in molten phase is transferred to mold cavity with the help of injection nozzle. The required injection pressure and holding pressure is applied with the help of control panel of plastic injection molding machine. It has the mechanism of product cooling so that product gets solidify. The product is holded for some time for proper cooling of product is removed from mold cavity. Like metal casting, in PIM also various types of defects are present due to process and design parameters maintained during plastic product during PIM process. In small and medium scale industries most of the workers set the process parameter data by their experience so that product dimensional shrinkage can be minimized, they do not have guidance in technical way for proper selection and tuning of process parameters and constants. Proper selection of process parameters in PIM Machine lead to minimize the defects from product and maintain best quality component in first attempt for the specific material [1].

Akbarzadeh, et al. [2] used Polypropylene as raw material and process parameters which were selected for optimization are injection pressure, melt temperature, packing pressure, packing time. Response surface methodology (RSM) is used to optimize the process parameters and response was in the terms of product shrinkage. Different type of regression equations are used to interpolate the data of experiments and to get optimum value of parameters for minimum dimensional shrinkage. Andrisano, et al. [3] used Polyphenylsulfone (ppsu) as raw material and process parameters which were selected for optimization are mold temperature, melt temperature, holding pressure, packing time. Response surface methodology (RSM) and Design of Simulation Experiments (DOSE) is used to optimize the process parameters and response was warpage. Warpage was less affected by mold temperature and more affected by melt temperature & holding pressure. Barghash, et al. [4] used seven process parameters with three levels to reduce shrinkage and warpage of plastic product made of Polypropylene (PP). Taguchi and ANOVA analysis is used to optimize the process parameters to reduce the cycle time of plastic injection molding process. Lixia, et al. [6] Artificial Neural network (ANN) and Genetic Algorithm (GA) optimization technique is used by researchers for five process parameters to reduce shrinkage defect from plastic cover. Xuan-Phuong Dang, et al., [7] optimized directional shrinkage and war page by using RSM, GA and ANN by taking five factors.



International Journal for Research in Applied Science & Engineering Technology (IJRASET)

ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 6.887 Volume 7 Issue IV, Apr 2019- Available at www.ijraset.com

II.EXPERIMENTAL SET-UP

The analysis was done on a plastic injection molding machine with fixed column and moving table as shown in figure 1 named as Electron-155 PIM. The raw material which is used in this research is thermoplastic which will be used to make top cover of food packaging box. This examination was conducted by using design of experiment (DOE) strategy named as Taguchi Method [8]. The essential execution measure in PIM is dimensional shrinkage which demonstrates the quality aspect of plastic product. [9].



Figure 1: PIM machine used for experimentation

| Table 1: Process Parameters a | and their Levels |
|-------------------------------|------------------|
|-------------------------------|------------------|

| Factor | Parameter Name | Levels | | | | |
|--------|--------------------|--------|-----|-----|-----|--|
| Pactor | | Ι | II | III | IV | |
| А | Mold Temperature | 50 | 55 | 60 | 65 | |
| В | Melt Temperature | 205 | 210 | 215 | 220 | |
| С | Injection Pressure | 60 | 65 | 70 | 75 | |
| D | Holding-Pressure | 70 | 80 | 90 | 100 | |
| E | Cooling time | 20 | 25 | 30 | 35 | |

Table 1 shows the process parameters and their levels. Total five process parameters and four levels are taken and accordingly orthogonal array has been made.

III.RESULTS AND DISCUSSION

Experiments are carried out by using taguchi L-16 orthogonal array. There is combination of 16 different sets of melt temperature, mold temperature, injection pressure, holding pressure and cooling time which is prepared by taguchi design requirement of five factors and their four levels. The dimensional shrinkage is measured with the help of vernier caliper.



| Sr No | Mold-T | Melt-T | Inj-P | Hold-P | Cool-T | Dim. Sh. (mm) | S/N |
|--------|--------|--------|-------|--------|--------|---------------|-------|
| 51 110 | А | В | С | D | Е | sh | Ratio |
| 1 | 50 | 205 | 60 | 70 | 20 | 1.4 | -2.9 |
| 2 | 50 | 210 | 65 | 80 | 25 | 1.5 | -3.5 |
| 3 | 50 | 215 | 70 | 90 | 30 | 1.7 | -4.6 |
| 4 | 50 | 220 | 75 | 100 | 35 | 1.9 | -5.5 |
| 5 | 55 | 205 | 65 | 90 | 35 | 1.5 | -3.5 |
| 6 | 55 | 210 | 60 | 100 | 30 | 1.6 | -4.0 |
| 7 | 55 | 215 | 75 | 70 | 25 | 2.0 | -6.0 |
| 8 | 55 | 220 | 70 | 80 | 20 | 2.1 | -6.4 |
| 9 | 60 | 205 | 70 | 100 | 25 | 1.7 | -4.6 |
| 10 | 60 | 210 | 75 | 90 | 20 | 1.9 | -5.5 |
| 11 | 60 | 215 | 60 | 80 | 35 | 2.1 | -6.4 |
| 12 | 60 | 220 | 65 | 70 | 30 | 2.3 | -7.2 |
| 13 | 65 | 205 | 75 | 80 | 30 | 1.8 | -5.1 |
| 14 | 65 | 210 | 70 | 70 | 35 | 2.0 | -6.0 |
| 15 | 65 | 215 | 65 | 100 | 20 | 2.2 | -6.8 |
| 16 | 65 | 220 | 60 | 90 | 25 | 2.3 | -7.2 |

Table 2: Experimental result of Dimensional shrinkage

In order to know the significance of process parameters on dimensional shrinkage on product, ANOVA analysis [10] was performed and it was observed that melt temperature was most significant factor and cooling time is least significant factor. The rank is assigned to the factors based on delta statistics. The value with highest delta is ranked highest and lowest delta with least rank.

| Table 5. Response table for DB (Raw data) | | | | | | |
|---|--------|--------|--------|--------|--------|--|
| Level | А | В | С | D | E | |
| 1 | -4.157 | -4.040 | -5.171 | -5.550 | -5.448 | |
| 2 | -5.017 | -4.800 | -5.282 | -5.379 | -5.346 | |
| 3 | -5.966 | -5.981 | -5.421 | -5.235 | -5.258 | |
| 4 | -6.302 | -6.622 | -5.569 | -5.279 | -5.390 | |
| Delta | 2.145 | 2.582 | 0.398 | 0.314 | 0.190 | |
| Rank | 2 | 1 | 3 | 4 | 5 | |

Table 3: Response table for DS (Raw data)

In figure 2 it is clear that factors which are ranked higher are having peak profile and factors which are having lower ranks are having low profiles. Our objective is to always have higher value of S/N ratio which can be achieved by the peak point of the factors in figure 2 which will give the optimal case for DS response as shown in table 4.

| Table 4. Optimal case for DS response | | | | | |
|---------------------------------------|-----|----|----|----|--|
| Δ | B | C | D | F | |
| 1 1 | Ъ | C | D | Ľ | |
| | | | | | |
| 50 | 205 | 60 | 90 | 30 | |
| 50 | 203 | 00 | 90 | 30 | |





Figure 2: S/N ratio analysis for DS

| Source | DF | Adj SS | Adj MS | F- | P- |
|------------|----|---------|----------|--------|-------|
| | | | | Value | Value |
| Regression | 5 | 1.22150 | 0.244300 | 85.72 | 0.000 |
| А | 1 | 0.48050 | 0.480500 | 168.60 | 0.000 |
| В | 1 | 0.72200 | 0.722000 | 253.33 | 0.000 |
| C | 1 | 0.00450 | 0.004500 | 1.58 | 0.237 |
| D | 1 | 0.01250 | 0.012500 | 4.39 | 0.063 |
| E | 1 | 0.00200 | 0.002000 | 0.70 | 0.422 |
| Error | 10 | 0.02850 | 0.002850 | | |
| Total | | 1.25000 | | - | |
| | 15 | | | | |

Table 5: Analysis of variance for dimensional shrinkage





Figure 3 shows the residual plots for dimensional shrinkage. In normal probability plot, residuals follow the straight line. Histogram is also symmetric in nature which indicates normal distribution of residuals. In residual versus fitted value, residuals are scattered randomly around zero which shows that they posses constant variance. There is no error due to time or data collection order as no clear pattern is exhibited by residuals.

A. Optimum Value of Dimensional Shrinkage

The optimum value of process parameters have been found as A1, B1, C1, D3, E3 to minimize the dimensional shrinkage which is given by equation —

μ ds =A1+ B1+C1+D3+E3-4 T

Where, T = overall mean of dimensional shrinkage = $(\sum Ri)/16 = 1.875$ mm Where, values of R1 to R16 has been taken from the Table 2, and the values of A1,B1,C1,D3 &E3 has been taken from taguchi experimental data.

A1 =average value of dimensional shrinkage at first level of mold temperature = 1.625 mm

B1= average value of dimensional shrinkage at first level of melt temperature= 1.6 mm

C1= average value of dimensional shrinkage at first level of Injection pressure = 1.85mm

D3= average value of dimensional shrinkage at third level of holding pressure = 1.85 mm

E3= average value of dimensional shrinkage at third level of cooling time = 1.85 mm

Substituting the values of various terms in the above equation,

 $\mu ds = 1.625 + 1.6 + 1.85 + 1.85 + 1.85 - 4*1.875 = 1.275$

The 95 % confidence intervals of confirmation experiments (CI_{CE}) and population (CI_{POP}) are calculated as below:

$$\operatorname{CI}_{CE} = \sqrt{F_{\alpha}(1, f_{e}) \operatorname{V}_{e}\left[\frac{1}{n_{eff}} + \frac{1}{R}\right]}$$
 and

$$CI_{POP} = \sqrt{\frac{F_{\alpha}(1, f_{e}) V_{e}}{n_{eff}}}$$

Where, $F_{\alpha}(1, f_e)$ = The F ratio at the confidence level of (1- α) against DOF 1 and error degree of freedom f_e .

$$n_{\text{eff}} = \frac{\text{N}}{1 + [\text{DOF associated in the estimate of mean response]}}$$

= 16 / (1+3) = 4

$$\begin{split} N &= \text{Total number of results} = 16, \\ R &= \text{Sample size for confirmation experiments} = 1 \\ V_e &= \text{Error variance} = 0.0028; \ f_e = \text{error DOF} = 10 \\ & (\text{Table 5}) \\ F_{0.05} (1, 10) &= 4.97 \text{ (Tabulated F value ; Roy,1990)} \end{split}$$

 $CI_{CE}~=\pm0.1318,$ and $CI_{POP}~=\pm~0.059$

© IJRASET: All Rights are Reserved

(Tabulated



Therefore, the predicted confidence interval for confirmation experiments is: Mean μ_{ds} - CI_{CE} < μ_{ds} < Mean μ_{ds} + CI_{CE} i.e. 1.1432 < μ_{ds} < 1.14068

The 95% confidence interval of the population is: Mean μ_{ds} – CI_{POP} < μ_{ds} < Mean μ_{ds} + CI_{POP} i.e. 1.1216 < μ_{ds} < 1.334

B. Confirmation Test

Confirmation test is very important in research which is designed by taguchi method. The objective of confirmation experiment is to know that how close theoretical value which is suggested by matrix experiment is to real data.

| Response Parameter | Optimal Set of Parameters | Predicted Optimal Value | Predicted Confidence Intervals at 95% Confidence Level | Experiment al Value |
|--------------------------|---------------------------------|-------------------------------|--|------------------------|
| Dimensional Shrinkage | $A_1B_1C_1D_3E_3$ | 1.275 | CI _{POP} : 1.1216<µds<1.334 CI _{CE} : 1.1432<µds<1.4068 | 1.2 |

| Table 6. | Predicted o | ntimal valu | e and result | t of confirm | ation experiment |
|----------|-------------|-------------|--------------|--------------|------------------|
| | FIGUICIEU U | pumai valu | e and result | | |

As the result is tabulated in table 6. It is clear that optimal value predicted by matrix experiment using taguchi method is very close to experimental value.

IV.CONCLUSION

Influence of plastic injection molding machine process parameters on dimensional shrinkage was studied in this research. The process parameters included in this study are mold temperature, melt temperature, injection pressure, holding pressure and cooling time. Significant variables affecting the dimensional shrinkage were identified by ANOVA analysis. Result shows that most significant variable affecting dimensional shrinkage is melt temperature and least significant variable is cooling time. A₁ = 50, B₁ = 205, C₁ = 60, D₃ = 90 and E₃ = 30 is the optimized value of machine process parameters for the present study.

REFERENCES

- Behrooz Farshi, Siavash Gheshmi and Elyar Miandoabchi, "Optimization of injection molding process parameters using sequential simplex algorithm", Materials and Design 32, 414–423, 2011.
- [2] Alireza Akbarzadeh and Mohammad Sadeghi, "Parameter Study in Plastic Injection Molding Process using Statistical Methods and IWO Algorithm", International Journal of Modeling and Optimization, Vol. 1, No. 2, June 2011.
- [3] A.O.Andrisano, F.Gherardini, F.Leali, M.Pellicciari and A.Vergnano, "Design of Simulation Experiments method for Injection Molding process optimization", International conference on Innovative Methods in Product Design, Venice, Italy, June 2011.
- [4] Mahmoud A. Barghash and Faisal Alkhannan Alkaabneh, "Shrinkage and Warpage Detailed Analysis and Optimization for the Injection Molding Process Using Multistage Experimental Design", Quality Engineering, 26:319–334, 2014.
- [5] E. Bociga and T. Jaruga, "Experimental investigation of polymer flow in injection mold", Archives of Materials Science and Engineering, Volume 28 Issue 3 Pages 165-172, March 2007.
- [6] Shen Changyu, Wang Lixia and Li Qian, "Optimization of injection molding process parameters using combination of artificial neural network and genetic algorithm method", Journal of Materials Processing Technology 183, 412–418, 2007.
- [7] Xuan-Phuong Dang, "General frameworks for optimization of plastic injection molding process parameters", Simulation Modelling Practice and Theory 41, 15–27, 2014.
- [8] Radhwan Hussin, Rozaimi Mohd Saad, Razaidi Hussin and Mohd Syedi Imran Mohd Dawi, "An Optimization of Plastic Injection Molding Parameters Using Taguchi Optimization Method", Asian Transactions on Engineering (ATE ISSN: 2221-4267) Volume 02, Issue 05, 2014.
- M.C. Song, Z. Liu, M.J. Wang, T.M. Yu and D.Y. Zhao, "Research on effects of injection process parameters on the molding process for ultra-thin wall plastic parts", Journal of Materials Processing Technology, 187–188, 668–671, 2007.
- [10] Yi-qi Wang, Jae-gyu Kim and Jung-il Song, "Optimization of plastic injection molding process parameters for manufacturing a brake booster valve body", Materials and Design 56, 313–317, 2014.











45.98



IMPACT FACTOR: 7.129







INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089 🕓 (24*7 Support on Whatsapp)