



iJRASET

International Journal For Research in
Applied Science and Engineering Technology



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 7 Issue: IV Month of publication: April 2019

DOI: <https://doi.org/10.22214/ijraset.2019.4411>

www.ijraset.com

Call:  08813907089

E-mail ID: ijraset@gmail.com

Study of Natural Aggregates and Testing of EPS based Concrete

P. Punitha

Department of Civil and Structural Engineering, SCSVMV University, Kanchipuram-631561

Abstract: Recent technology has also improved the recycling process. This study aims to Testing of coarse aggregate by using concrete. In this research concrete With the increase in demand for construction materials, there is a strong need to utilize alternative materials for sustainable development. The main objective of this investigation is to study the properties, such as compressive strength and tensile strengths of lightweight concrete containing Expanded Polystyrene (EPS) beads. Its properties are compared with those of the normal concrete i.e., without EPS beads. EPS beads are used as partial replacement to coarse aggregates. Water absorption test, specific gravity test, sieve analysis test, mix design, slump test, compressive strength test for all The major test are computed .

Keywords: sources of aggregate, coarse aggregate, testing of materials, EPS beads.

I. INTRODUCTION

A. General

In this chapter, the brief of description of the methodology and the sequence of the work to be carried out in this complete duration of project are presented.

II. SOURCES OF NATURAL AGGREGATE

Igneous rock these rocks are primarily crystalline and are formed by the cooling of molten rock material beneath the earth's crust (magma). Sedimentary rocks, these rocks are formed from depositing insoluble material (e.g., the remains of existing rock deposited on the bottom of an ocean or lake). This material is transformed to rock by heat and pressure. Sedimentary rocks are layered in appearance and are further classified based on their predominant mineral as calcareous (limestone, chalk). Aggregates can come from either natural or manufactured sources. Natural aggregates come from rock, of which there are three broad geological classifications. Siliceous (sandstone) or argillaceous (shale) metamorphic rock, These are igneous or sedimentary rocks that have been subjected to heat and/or pressure great enough to change their mineral structure so as to be different from the original rock.

Aggregates are produced in a quarry or mine whose basic function is to convert in situ rock into aggregate with specified characteristics. Usually the rock is blasted or dug from the quarry walls, then reduced in size using a series of screens and crushers. Some quarries are also capable of washing the finished aggregate.

III. METHODOLOGY OF THE PROJECT

EPS is used for the project is available in packing factories. The percentage replacements of coarse aggregate by EPS have been replacement at 10%, 20% and 25% respectively. The W/C ratio for the various replacement of PPC has been investigated.

The casting specimen as tested as after 3days, 7days, 14days and 28days curing. The compressive test, split test and flexural strength of the specimens at various ages have been found out.

IV. EXPERIMENTAL INVESTIGATION:

A. Tests Carried Out For Physical Properties

- 1) **Setting Time Test:** Take 500 gm of cement sample and gauge it with 0.85 times the water required to produce cement past of standard consistency (0.85 mm). the paste shall be gauged and filled into the vicat mould is specified manner with 3-5minutes. Start the stop watch the moment water is added to the cement. The temperature of water and that of the test room, at the time of gauging shall be within 27⁰ C.
- 2) **Initial Setting Time:** In the vicat apparatus Lower the needle gently and bring it in contact with the surface of the test block and quickly release. Allow it to penetrate into the test block. In the beginning, the needle will completely pierce through the test block. But after some time when the paste starts losing its plasticity, the needle may penetrate only to the depth of 33-35 mm from the top. The period elapsing between the time when water is added to the cement and the time at which the needle penetrates the test block to the depth equal to 33-35 mm from the top is taken as initial setting time.

- 3) **Final Setting Time:** Replace the needle of the vicat apparatus by a circular attachment. The cement shall be considered as finally set when, upon, lowering the attachment gently cover the surface of the test block, the center needle makes an impression, while the circular cutting edge of the attachment fails to do so. In other word the paste has attained such hardness that the center needle does not pierce through the paste more than 0.5mm.

V. SPECIFIC GRAVITY TEST

A. Specific Gravity Of Cement Test

Table 1 Specific gravity values of cement

S.No	Description	Trail 1	Trail 2	Trail 3	Mean
1	Weight Of Empty Bottle (w_1)	675	675	675	3.129
2	Weight Of Bottle + Cement (w_2)	1303	1309	1311	
3	Weight Of Bottle + Kerosene + Cement (w_3)	1775	1780	1783	
4	Weight Of Bottle + Kerosene (w_4)	1401	1401	1401	
5	Specific Gravity Of Cement	3.129	3.147	3.169	

- 1) **Calculation:** Specific gravity of cement = $w_2 - w_1 / (w_4 - w_1) - (w_3 - w_2) \times 0.79$
 $= 1303 - 675 / (1303 - 675) - (1775 - 1401) \times 0.79$
 $= 3.129$

B. Specific Gravity Of Fine Aggregate Test

Table 2 Specific gravity values of fine aggregate

S.No	Description	Trail 1	Trail 2	Trail 3	Mean
1	Weight Of Empty Pycnometer(w_1)	609	609	609	2.24
2	Weight Of Bottle + Pycnometer Aggregate(w_2)	1109	1113	1116	
3	Weight Of Bottle + Pycnometer Aggregate + Water(w_3)	1758	1764	1769	
4	Weight Of Pycnometer + Water(w_4)	1478	1478	1478	
5	Specific Gravity Of FA	2.24	2.23	2.25	

- 1) **Calculation:** Specific gravity of fine aggregate = $(w_2 - w_1) / (w_4 - w_1) - (w_3 - w_2)$
 $= (1109 - 609) / ((1174 - 906) - (1758 - 1109))$
 $= 2.24$

C. Specific Gravity Of Coarse Aggregate

Table 3 Specific gravity values of coarse aggregate

S.no	Description	Trail 1	Trail 2	Trail 3	Mean
1	Weight Of Empty Bottle(w_1)	609	609	609	2.74
2	Weight Of Bottle + Coarse Aggregate(w_2)	990	1053	1026	
3	Weight Of Bottle + Coarse Aggregate + Water(w_3)	1724	1765	1726	
4	Weight Of Bottle + Water(w_4)	1482	1482	1482	
5	Specific Gravity Of Coarse Aggregate	2.74	2.75	2.74	

- 1) Calculation: Specific gravity of coarse aggregate = $(w_2 - w_1) / (w_4 - w_1) - (w_3 - w_2)$
 $= (990 - 609) / ((1482 - 609) - (1724 - 990))$
 $= 2.74$

VI. WATER ABSORPTION TEST

Water absorption test is used to determine the absorption content of water by fine aggregate and coarse aggregate

A. Water Absorption of Fine Aggregate

Table 4 Water absorption values of fine aggregate

S.No	Description	Trial
1	Weight of oven dry sample w_1	1000
2	Weight of oven dry sample w_2	990.83
3	Water absorption	0.917%

- 1) Calculation: Water absorption = $w_2 - w_1 / w_1 \times 100$
 $= 1000 - 990.83 / 1000 \times 100 = 0.917\%$

B. Water Absorption Of Coarse Aggregate

Table 5 Water absorption values of coarse aggregate

S.No	Description	Trial
1	Weight of oven dry sample w_1	1000
2	Weight of oven dry sample w_2	1004
3	Water absorption	0.4

Calculation:

$$\text{Water absorption} = w_2 - w_1 / w_1 \times 100$$

$$= 1004 - 1000 / 1000 \times 100 = 0.4\%$$

C. The Test Results Obtained Are

- 1) Water Absorption for Fine Aggregate : 0.917%
- 2) Water Absorption for Coarse Aggregate : 0.4%

VII. SIEVE ANALYSIS TEST

Table 6 Sieve analysis test values of fine aggregate

S.no	Sieve opening size	Weight of F.A retained (g)	Cumulative Weight of F.A retained (g)	Cumulative percentage of F.A retained(g)	Cumulative percentage of F.A passing
1	4.75 mm	1039	10	1.0	99.0
2	2.36 mm	39	49	4.9	95.1
3	1.18 mm	235	284	28.4	71.6
4	600 μ	304	588	58.8	41.2
5	300 μ	290	878	87.8	12.2
6	150 μ	95	973	97.3	2.7
7	75 μ	25	998	-	0.2
8	Pan	0	0	-	-
		990		Total = 278.2	

- 1) Calculation: Fineness modulus = Total cumulative % weight retained / 100

$$= 278.2 / 100$$

$$= 2.78\%$$

A. Sieve Analysis Of Coarse Aggregate

Table 7 Sieve analysis test values of coarse aggregate

S.no	Sieve size (mm)	Weight of coarse aggregate (g)	percentage retained(g)	Cumulative percentage retained(g)	Cumulative percentage Passing
1	40 mm	-	-	-	100
2	37.5mm	-	-	-	100
3	22.4mm	-	-	-	100
4	20mm	1030	51.5	51.50	48.5
5	10mm	966	48.3	99.80	0.2
6	4.75mm	3	0.15	99.95	0.05
7	2.36mm	-	-	100	-
8	1.18mm	-	-	100	-
9	600μ	-	-	100	-
10	300μ	-	-	100	-
11	150μ	-	-	100	-
12	Pan	-	-	100	-
Cumulative percentage retained = 751.25					

- 1) Calculation: Fineness modulus = Total cumulative % weight retained / 100

$$= 751.25 / 100$$

$$= 7.5\%$$

VIII. IMPACT TEST

The aggregate impact test is carried out to evaluate the resistance to impact of aggregates. Aggregates passing 20 mm sieve and retained on 12.5 mm sieve is filled in a cylindrical steel cup of internal dia 10.2 mm and depth 5 cm which is attached to a metal base of impact testing machine. The material is filled in 3 layers where each layer is tamped for 25 numbers of blows. Metal hammer of weight 13.5 to 14 Kg is arranged to drop with a free fall of 38.0 cm by vertical guides and the test specimen is subjected to 15 numbers of blows. The crushed aggregate is allowed to pass through 2.36 mm IS sieve. And the impact value is measured as percentage of aggregates passing sieve (w_2) to the total weight of the sample (w_1).

A. Formula For Impact Test

Aggregate impact value = $W_2/W_1 \times 100\%$

= $95/600 \times 100$

= 15.833

W_1 = weight of the sample

W_2 = weight of the fraction passing 2.36 mm sieve.

Aggregate Impact Value	Classification
<20%	Exceptionally Strong
10 – 20%	Strong
20-30%	Satisfactory for road surfacing
>35%	Weak for road surfacing

B. Impact Testing



Fig. 1 impact testing

IX. SLUMP CONE TEST

Concrete slump cone test is to determine the workability or consistency of concrete mix prepared at the laboratory or the construction site during the progress of the work. Concrete slump cone test is carried out from batch to batch to check the uniform quality of concrete during construction. The slump cone test is the most simple workability test for concrete, involves low cost and provides immediate results. Due to this fact, it has been widely used for workability tests since 1922.



Fig.2 slump cone test

A. Slump Value Observation

The slump (Vertical settlement) measured shall be recorded in terms of millimeters of subsidence of the specimen during the test. The mix was confirmed to be a mix with a medium workability having slump value between 60 -100mm. 70mm or 7cm.



Fig. 3 slump cone result

Mix Proportions For One Cum Of Concrete					
Cement Kg	Fine aggregate Kg	Coarse aggregate Kg	Water Lit	Water cement ratio	Mix proportion ratio
419	746	924	189	0.45	1:1.78:2.24

X. TESTING OF EPS BASED CONCRETE

A. Compressive Strength

Specimens are casted in concrete cube of size (150mmx150xmm150mm) and cured the tested under compressive strength under compression testing Machine (CTM).



Fig. 4 compressive strength test

B. After Compression Of Concrete Cube



Fig. 5 failure concrete cube

Specimens are casted in concrete cylinder of size (150mm X 300mm) and cured and then tested. Below graph shows split tensile strength of concrete using polystyrene at 28 days for 0.45 W/C



Fig.7 failure of eps cylinder

E. Flexural Strength

Flexural strength, also known as modulus of rupture, or bend strength, or transverse rupture strength is a material property, defined as the stress in a material just before it yields in a flexure test. The transverse bending test is most frequently employed, in which a specimen having either a circular or rectangular cross-section is bent until fracture or yielding using a three point flexural test technique. The flexural strength represents the highest stress experienced within the material at its moment of yield. It is measured in terms of stress, here given the symbol



Fig.8 flexural strength testing

F. Flexural Failure



Fig.9 failure of flexural strength test



XI. RESULT AND DISCUSSION

Water absorption test, specific gravity test, sieve analysis test on fine aggregate, sieve analysis test on coarse aggregate, slump cone test, compressive strength test are computed. Testing values are coming in within limits.

XII. CONCLUSION

From the experimental results, it can be concluded that, The workability (slump test) of EPS Concrete is same for Normal concrete because the rate absorption of EPS Concrete is equal to Normal concrete. The general properties of EPS Concrete and Normal concrete are same in the specific gravity, water absorption, and Aggregate impact value. The sieve Analysis test of coarse Aggregate and Fine Aggregate are compared with EPS Concrete. The 28-day target compressive strength for all mixes was achieved to 30MPa even though the EPS Concrete strength is lower than Normal concrete. All the EPS concrete without any special bonding agent show good Workability and could easily be compacted and finished.

REFERENCES

- [1] Lightweight Concrete Using EPS, Int. Jour. of Sci and Re, Abhijit Mandlik, Tarun Sarthak Sood, Shekhar Karade, Sangran Naik, Amruta Kulkarni.- Volume 4(3) (2015) pp2007-2010.
- [2] Properties of Modified, Polystyrene lightweight Aggregate in Concrete, Environ. Eng. Dept. University Malaysia Perli, PetraVenny R, KhairulNizar I, Mohd Mustafa Al Bakri A. -volume 1(2010) pp 2180-3811.
- [3] Partial Replacement of Coarse Aggregates by Expanded Polystyrene Beads in Concrete. Int. Jour. of Res. in Engg and Tech, Thomas Tamut, Prabhu Rajendra, Katta Venkataramana, Yaragal Subhash.-volume 3(2) (2014) pp 238-246.
- [4] Thermal and Mechanical Properties of Concretes with Styropor. Department of Chemical Engineering, Thermal and Mechanical Properties of Concretes with Styropor Firat University, Elazing, Turkey. volume 2 pp310-315.
- [5] Strength Properties of Expanded Polystyrene Beads in Concrete. Jour of Environ. . Chowdary P L. Sci., Comp.Sci. and Eng. & Tech.- volume 4(3) (2015) pp734-742.
- [6] Particle size effect on EPS lightweight concrete compressive strength, Experimental investigation and modeling, Mechanics of Materials Miled K, Sab K, LeRoy R.- volume 39(2006) pp222 – 240.
- [7] A novel material for lightweight concrete production, Cement & Concrete Composites Abdulkadir Kan, Ramazan Demirboga.-volume 31(2009) pp 489 – 495.
- [8] Thermal Behaviour and Admissible Compressive Strength of Expanded Polystyrene Wall Panelsof Varying Thickness, Current Trends in Technology and Science , Anthony Nkem Ede.-volume 3 (2)(2014) pp 110-117.



10.22214/IJRASET



45.98



IMPACT FACTOR:
7.129



IMPACT FACTOR:
7.429



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089  (24*7 Support on Whatsapp)