



iJRASET

International Journal For Research in
Applied Science and Engineering Technology



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 7 Issue: V Month of publication: May 2019

DOI: <https://doi.org/10.22214/ijraset.2019.5286>

www.ijraset.com

Call:  08813907089

E-mail ID: ijraset@gmail.com



Invitro Assessment of Antibacterial, Antioxidant and Drug Release Property of Extracellularly Bio-Fabricated Gold Nanoparticles using *Pimpinella Anisum*

Mohanapriya. P¹, Murugeswari. S²

¹PG Research Student, ²Professor HOD, Department of Nanoscience and Technology, GKM College of Engineering and Technology, Perungalathur, Chennai 600 063.

Abstract: Biosynthesis of nanoparticles is gaining more importance nowadays in research field. Especially using plant extracts, according to WHO about 80% of world population is belongs to plant/ herbal based medicine. Gold nanoparticles has wide range of biomedical applications such as drug delivery, cancer treatment, radiation therapy etc,. In the present investigation, the gold nanoparticles were synthesized using aqueous extract of *Pimpinella anisum*. The synthesised gold nanoparticles were characterized using UV- Visible spectrometer, SEM analysis, XRD analysis and FT-IR analysis. Further, the antibacterial activity, antioxidant property and in vitro drug release assessment for the synthesised gold nanoparticles were performed.

Keywords: Gold Nanoparticles, Biosynthesis, *Pimpinella anisum*, Biomedical applications

I. INTRODUCTION

Nanotechnology is the day-to-day growing technology in modern research field [1]. Nanoparticles are 1000 times smaller than the human cells. Due to its small size and large surface area to volume ratio [2], it was utilized in drug delivery, bio- imaging, gene therapy, cancer therapy and bio molecules carrier etc [5]. Though the nanoparticles can be synthesized by an array of physical and chemical methods which cause disturbance in ecological balance because of toxic gas exhaust and requirement of high temperature, pressure etc [3]. Biosynthesis of nanoparticles is attaining a broad mind of research to synthesis metal nanoparticles using herbs/ medicinal plants. It is alternate to overcome the limitations of conventional method with low cost, simple, less time consumption and relatively reproducible method [6]. Gold nanoparticles are gaining a importance due to its biocompatibility and non- toxicity, which is used by human history since last 50 years [7]. A gold nanoparticle produces wide range of applications due to its optical property of SPR band formation from UV- Visible to IR region [4]. From the literature survey, it is novel to synthesise gold nanoparticles using *Pimpinella anisum*. *Pimpinella anisum* belongs to *Apiaceae* family, flowering plant commonly known as anise seed, one of the spices [8]. In ancient days, it is utilized for stomach disorders and commonly named as Shombu in Tamil. It is used as folklore medicine in human history as medicinal appliances.

II. EXPERIMENTAL SECTION

A. Chemicals

The 99.9% pure Chloroauric acid was purchased from Loba Chem Pvt Ltd, Chennai. The Deionised water, Ascorbic acid and Muller Hinton Agar medium were purchased and chemicals prepared were standard and merck.

B. Collection Of Plant

The anise seeds were purchased from shop in Kanchipuram and sowed in the agriculture field after 30 days, the plant were grown and matured after 65 days. The leaf of the plant were collected and washed with tap water to remove sand particles and dust, followed by distilled water.

C. Extract preparation

5g of fresh leaves were chopped into small pieces using sterile knife and taken in a 250mL flask containing 50mL of deionised water. The flask was kept onto the heating mantel for boiling at 80°C for 20 minutes. After boiling, the flask were taken and allowed to cool. After cooling, the extracts were filtered using Whatmann filter paper No: 1. The collected filtrate were stored at frozen condition for further research.

D. Biosynthesis Of Gold Nanoparticles

1mM concentration of Chloroauric acid solution was prepared using deionised water. 5mL of plant extract was added to 95 mL of 1mM of Chloroauric acid solution and kept undisturbed condition at room temperature. After 1 hour, the color of the solution mixture was changed into ruby red was observed and the color change indicates the reduction of gold ions to gold nanoparticles formation. Further it was confirmed through characterization of colloidal solution using UV- Visible spectrophotometer, in the range of 400- 800nm.

E. Purification And Characterization Of Gold Nanoparticles

The colloidal solution was centrifuged at 10000 rpm and the supernatant were discarded. The pellets were dried at 60°C in hot air oven and powder form of gold nanoparticles was collected. The powder forms of gold nanoparticles were subjected to SEM, XRD and FT-IR analysis.

F. Antioxidant Study

Hydrogen peroxide scavenging assay is used to study the antioxidant property of the synthesised gold nanoparticles. Different concentrations of synthesized gold nanoparticles were added to PBS buffer of pH 7.4 containing 40mM of H₂O₂ solution mixture. The solution mixture is kept for incubation at room temperature for 10 minutes and analysed at 560nm using UV- Visible spectrophotometer. The PBS buffer without H₂O₂ is used as blank. The ascorbic acid is used as standard. The percentage of inhibition was calculated from the absorbance values using the formula as follow as:

$$\% \text{ Inhibition} = \frac{\text{Absorbance Sample} - \text{Absorbance Control}}{\text{Absorbance Control}} \times 100$$

G. Antibacterial Study

To analyse the antibacterial activity of the synthesized gold nanoparticles against One day culture of *E. coli* and *B. subtilis* by Muller Hinton Agar Well Diffusion method. The media was prepared under aseptic condition and poured onto the sterile petriplate and allowed to get solidify and the wells were punched using sterile cork borer. The wells were loaded with synthesized colloidal gold nanoparticle solution and plant extract.

H. In Vitro Drug Release Assessment

The synthesized gold nanoparticles were assessed for in vitro drug release by sample and separation method. The 20 µL of human insulin drug was incubated with 50 µL of synthesized colloidal gold nanoparticle solution under continuous stirring by centrifugation for 72 hours. The drug loading into the nanoparticles was monitored by taking the sample 6 hrs intervals and analyzed using UV- Visible spectrophotometer [10, 11]. And the drug loading efficiency was calculated from the formula given below:

$$\% \text{ Entrapment efficiency} = \frac{\text{Total amount of drug} - \text{Amount of drug in Supernatant}}{\text{Total amount of the drug}} \times 100$$

The drug loaded- gold nanoparticles were incubated with PBS buffer (pH 7.4) in micro centrifuge tube and stirred at 10000 rpm. The samples were collected at selected time interval and replaced with fresh buffer. The drug content was analyzed by using UV- Visible spectrophotometer. A similar work was reported by Ghosh et al. [9].

III. RESULT AND DISCUSSION

Biosynthesis of gold nanoparticles is simple, low cost and eco-friendly method. In the present study, the gold nanoparticles were synthesized using aqueous extract of *Pimpinella anisum* and the presence of bioactive compounds in the plant extract were analyzed (Figure 1). Biomolecules present in the plant extract is given in the table (1) as follows:




Table 1: Presence Of Bioactive Compounds in Aqueous Extract of *Pimpinella anisum*

S. NO	PHYTOCHEMICAL	AQUEOUS EXTRACT OF FRESH LEAVES
		<i>Pimpinella anisum</i>
1	Carbohydrates	+
2	Tannins	+
3	Saponins	+
4	Flavonoids	+
5	Alkaloids	-
6	Quinones	+
7	Glycosides	-
8	Cardiac glycosides	+
9	Terpenoids	+
10	Phenols	-
11	Coumarins	+
12	Proteins	+
13	Steroids	+
14	Phylobatannins	-
15	Anthraquinones	-

A. Biosynthesis of Gold Nanoparticles

The gold nanoparticles were extracellularly synthesized by using aqueous extract of *Pimpinella anisum*. The color of the solution mixture changed into ruby red indicates the formation of gold nanoparticles was visually observed. The presence of bioactive compounds in the extract act to reduces Au^+ ions to Au^0 . It represents that the bio molecules in the extract are acting as reducing and capping agents.




Figure 2 Biosynthesized Gold Nanoparticles using *Pimpinella anisum*

B. Characterization

- 1) *UV- Visible Spectrophotometer Analysis:* The biosynthesized colloidal gold nanoparticles solution was analysed using UV-Visible spectrophotometer. The SPR band was formed at 534.9 nm.




Figure 3 UV- Visible Spectra of *Pimpinella anisum* biosynthesized gold nanoparticles

- 2) *Scanning Electron Microscope Analysis*: The powder form of biosynthesized gold nanoparticles was analysed using scanning electron microscope. It was found that the gold nanoparticles were spherical in shape and 80-90 nm in size.




Figure 4 SEM images of *Pimpinella anisum* biosynthesized gold nanoparticles

- 3) *X- Ray Diffraction Spectroscopy Analysis*: The powder form of gold nanoparticles were analysed using XRD. The strong peaks were observed at 2θ values of 37.88° , 46.24° and 64.52° correspond to (111), (200) and (220) set of planes and it found to be FCC crystal structure. Thus, the XRD spectrum show that the biosynthesised gold nanoparticles were crystalline in nature. And also the particle size were determined using Scherrer formula and found to be 87.76 nm, 90.26nm and 98.17 nm in size.




Figure 5 XRD spectra of *Pimpinella anisum* biosynthesized gold nanoparticles

- 4) **Fourier Transform – Infra Red Spectroscopy Analysis:** The powder form of gold nanoparticles was made into pellets by ground with KBr disc. The pellets were analysed using FT- IR spectroscopy. The functional groups associated with biosynthesized gold nanoparticles were found (Figure 7), the peak at 3251.98 cm^{-1} indicates the Phenol group (-OH) stretch, the peak at 2922.16 cm^{-1} indicates Alkyl C-H stretch, the peak at 2854.65 cm^{-1} indicates Carboxylic acid -OH stretch, the peak at 1631.73 cm^{-1} indicates Alkanyl C=C stretch, peak at 1546.91 cm^{-1} indicates Aromatic C=C bending, peak at 1375.25 cm^{-1} indicates Nitro compound -NO_2 , peak at 1236.37 cm^{-1} indicates ASlcohol group and the peak at 1020.34 cm^{-1} indicates Ether (C-O).




Figure 6 FT- IR spectra of *Pimpinella anisum* biosynthesized gold nanoparticles

C. Antioxidant Study

Hydrogen peroxide scavenging assay was used to study the antioxidant property of *Pimpinella anisum* biosynthesized gold nanoparticles. The antioxidant potential of the *Pimpinella anisum* biosynthesized gold nanoparticles registered increase in scavenging activity in according to the concentration increase. The result obtained with *Pimpinella anisum* biosynthesized gold nanoparticles was compared with plant extract and standard ascorbic acid. (Figure 7)




Figure 7 Hydrogen Peroxide Scavenging Assay for *Pimpinella anisum* Biosynthesized Gold Nanoparticles

D. Antibacterial Study

Agar well diffusion method was used to study the antibacterial property of the synthesized gold nanoparticles against *E. coli* and *B. subtilis* using Nalidixic acid as control at centre. The synthesised gold nanoparticles showed high resistance against the growth of microbes and zone of inhibition was measured in mm diameter (Table2).




Figure 8 Antibacterial activities of *Pimpinella anisum* synthesized gold nanoparticles against *E. coli* Figure 9 Antibacterial activities of *Pimpinella anisum* synthesized gold nanoparticles against *B. subtilis*

Table 2 : Antibacterial Activity Of Synthesised Gold Nanoparticles Using *Pimpinella anisum* – Zone Of Inhibition In mm Diameter

S. No	Microorganism	Zone Of Inhibition Measurement In mm Diameter	
		Aqueous extract of <i>Pimpinella anisum</i>	<i>Pimpinella anisum</i> mediated synthesized gold nanoparticles
1.	<i>Escherichia coli</i>	8	12
2.	<i>Bacillus subtilis</i>	13	14
Control: Nalidixic acid= 20mm			

E. In Vitro Drug Release Assessment

The *Pimpinella anisum* synthesised gold nanoparticles were assessed for in vitro drug release of human insulin drug by using sample and separation method. The 89% of drug molecules were loaded onto the synthesised gold nanoparticles were attained. And the release of drug molecules from the drug loaded – gold nanoparticles were analysed using PBS buffer as releasing media under centrifugation and samples were taken at selected interval of time and analysed with UV- Visible spectrophotometer. The 83% of drug release achieved by this method was calculated from the absorbance value.




Figure 10 Collection of Supernatant from Drug Loaded Gold Nanoparticles colloidal solution for UV- Visible spectrophotometer analysis



IV. CONCLUSION

Biological synthesis of nanoparticles has upsurge in the field of nano-biotechnology to create novel materials that are eco-friendly, cost effective, stable nanoparticles with a great importance for wider application in various fields such as electronics, medicine and agriculture. Hence the present investigation deals with extracellular biosynthesis of gold nanoparticles using *Pimpinella anisum* based aqueous extract as reducing and capping agent was demonstrated. The reducing potential of the plant extract is due to the presence of bioactive compounds which act to reduce the gold ions to gold nanoparticles. The color change of the chloro auric acid and extract solution mixture from light green to ruby red was visually observed and confirmed with UV- Visible spectrometer analysis. The SEM image of the synthesised gold nanoparticles showed the spherical shape of the nanoparticles was formed. The XRD analysis was done to know the crystalline nature of the gold nanoparticles and the particle size was calculated using Scherrer formula. It was found to be 87.76nm, 90.26 nm and 98.17nm in size. The FT-IR analysis was performed to know the functional groups associated with the gold nanoparticles. The antioxidant property of the gold nanoparticles is increased with scavenging potential as concentration increases. The antibacterial activity study of the gold nanoparticles showed high sensitivity against the pathogenic microbes. The invitro drug release assessment of the gold nanoparticles was performed using sample and separation method. And the drug loading efficiency of the gold nanoparticles was found to be 89% and the drug release efficiency of the gold nanoparticles was found to be 83%. From the investigation in future, the young nano- biotechnologists can light their research into the biosynthesised gold nanoparticle for drug delivery vehicles.

REFERENCES

- [1] A.Lalitha, R.Subbaiya and P.Ponmurugan, 'Green synthesis of silver nanoparticles from leaf extract *Azadirachta indica* and to study its anti-bacterial and antioxidant property', *Int.J.Curr.Microbiol.App.Sci* (2013) 2(6): 228-235.
- [2] Arangasamy Leela and Munusamy Vivekanandan, 2008. Tapping the unexploited plant resources for the synthesis of silver nanoparticles. *African. J. Biotechnol.* 7 (17): 3162-3165.
- [3] Balagurunathan, R., M. Radhakrishnan, R. Babu Rajendran and Velmurugan, D. 2011. Biosynthesis of gold nanoparticles by actinomycete *Streptomyces viridogens* strain HM10, *Indian. J. Biochem. Biophys.* 48:331-335.
- [4] Muralikrishna, T, Monalisa Pattanayak and Nayal. P. L, (2014), 'Green synthesis of Gold Nanoparticles using Aloe Vera aqueous extract', *World Journal of Nano Science & Technology* 3(2): 45-51.
- [5] Salam H.A., Rajiv P., Kamaraj M., Jagadeeswaran P. Gunalan S. and Sivaraj R., Plants: Green Route for Nanoparticle Synthesis. *I. Res. J. Biological Sci.*, 1,85-90 (2012).
- [6] Shakeel Ahmed, Saifullah, Mudasir Ahmad, Babu Lal Swami, Saiqa Ikram, 'Green synthesis of silver nanoparticles using *Azadirachta indica* aqueous leaf extract', *Journal of Radiation Research and Applied Sciences* 9 (2016) 1- 7.
- [7] Avnika Tomar and Garima Garg, 'Short Review on Application of Gold Nanoparticles', *Global Journal of Pharmacology* 7 (1): 34-38, 2013.
- [8] B. Shiney ramya and P. Ganesh, 'Phytochemical Analysis and Comparative Effect of *Cinnamomum zeylanicum*, *Piper nigrum* and *Pimpinella anisum* with Selected Antibiotics and Its Antibacterial Activity against Enterobacteriaceae Family', *International Journal of Pharmaceutical & Biological Archives* 2012; 3(4):914-917.
- [9] Ghosh P, Han G, De M, Kim KC, Rotello MV. 'Gold nanoparticles in delivery applications', *Advanced Drug Delivery Reviews*. 2008; 60: 1307- 1315.
- [10] Deva Prasad V, 'Nanoparticulate Drug Delivery Systems, In Vitro drug Release Test Methods', *Int J Pharm Bio Sci* 2017 July ; 8(3): (P) 103 – 119.
- [11] Susan D Souza, 'A Review of In Vitro Drug Release Test Methods for Nano-Sized Dosage Forms', *Advances in Pharmaceutics* Volume 2014, Article ID 304757, 12 pages.



10.22214/IJRASET



45.98



IMPACT FACTOR:
7.129



IMPACT FACTOR:
7.429



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089  (24*7 Support on Whatsapp)