



IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 8 Issue: VI Month of publication: June 2020

DOI: http://doi.org/10.22214/ijraset.2020.6083

www.ijraset.com

Call: 🕥 08813907089 🔰 E-mail ID: ijraset@gmail.com

Effect of Hygrothermal Aging & Artificially Introduced Delamination on Mode-I Interlaminar Fracture Toughness of E-Glass Epoxy Matrix Composites

Ch Divya¹, P. Madhavi², K. Uday Kumar³, K. Rohith⁴ ^{1, 2, 3, 4}Vignan Instutute Of Technology & Science, India

Abstract: Various types of polymer matrix composites are being considered for use in high temperature applications such as for supersonic aircraft and naval applications. An attempt to find Fracture toughness of hygrothermally aged delaminated E-Glass epoxy matrix composites is done as fracture toughness is important material property to consider in any design applications. Delamination is one of the major failure modes seen in the laminated polymeric matrix composite (PMC). Hydrophilic nature of epoxy polymers can lead to both reversible and irreversible/permanent changes in epoxy upon moisture absorption. The present work deals with the experimental investigation of hygrothermal aging of delaminated E-glass-fibre-reinforced polymer composite and its effect on the fracture toughness due to the exposure to elevated temperatures and wet conditions which resulted in decrease of maximum load required for fracture with increase of temperature toughness (G_I) decreased with increase of temperature.

Keywords: Delamination. Fracture Toughness. Hygrothermal aging. E- Glass. Epoxy.

I. INTRODUCTION

As composite have stunning physical and mechanical property of high strength to weight ratio they are widely used in aircraft construction industries and in naval base, where they are likely to be harmed by the environment. It is generally stated that mechanical properties of composite materials are affected by material ageing, which is often accompanied by moisture absorption [8-12]. However, composite laminates are known to be susceptible to delamination failure due to their poor interlaminar strength. The delaminations usually occur through manufacturing defects or low velocity impact damages during service, and they propagate predominantly under mode I, mode II and mixed mode I/II loadings. The growth of the delamination progressively reduces the inplane strength, stiffness; durability of composite structures and may finally lead to catastrophic failure. Therefore, delamination is one of the major limiting factors in composite structure design, and various techniques have been developed to toughen the inter laminar strength. In most applications it is unavoidable to react with water at different temperature which will influence the mechanical properties of the material. As there will be different service temperatures the properties of the material changes accordingly. Therefore it is important to understand the effect of environment and estimate the durability of composites when subjected to such hard environments. Many studies reported that hygrothermal ageing will definitely influence the fracture toughness of composite laminates. The duration and temperature of the exposure affect the fracture toughness .The hygrothermal effects are generally more noticeable For the specimens immersed in fluid than exposed in humid air. The present study investigated the effects of water immersion at different temperatures on the fracture load and fracture toughness of E-Glass Epoxy matrix composite. The failure criterion of mode-I delamination under the influence of hygrothermal environment was studied.

II. LITERATURE REVIEW

Yian Zhao *et. al* [2] have conducted different delamination tests which include mode-I, mode-II and mixed mode I & II for woven E-glass/Bismaleimide (BMI) composite to find the resistance curve & fracture toughness before ageing and after ageing in seawater at varying temperatures and reported that except in mode-II, fracture toughness decreased with increase of immersion temperature and resistance increased with growth of delamination which is because of more ductility of composite after immersion and plasticization. S. larbi *et.al*[3]studied the effect of time period of ageing in sea water at room temperature of GFRP composites and reported that at the starting of the process the absorption kinetics is fickian and in case of ageing it is non fickian. Reduce in weight



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.429 Volume 8 Issue VI June 2020- Available at www.ijraset.com

of the specimens after ageing is due to effect of high pH value of sea water which causes matrix degradation. Three-point bending test conducted for specimens after oven drying resulted that tensile strength of the specimens reduced due to ageing. B.C ray et.al [4] reported that at higher temperatures the hygrothermal ageing is faster which resulted in more moisture absorption for both woven and unidirectional carbon fiber composites. Large effect on fiber matrix interface, increase in thermal stress due to ageing at higher temperatures and more duration. Shivakumar et.al [5] worked on GFRP composites, by ageing for 200 days in water at different temperatures .The moisture absorption rate is largely dependent on temperature, which results in debonding of fiber and matrix due to swelling and voids created will act as pool for moisture. The hygrothermal ageing for 200 days at 70°C resulted in decrease of flexural strength of the GFRP composite specimen by 30% when compared to specimen which did not undergo any ageing. Masaki Hojo *et.al* [6] studied the delamination fatigue crack growth and fracture toughness of carbon fiber/epoxy laminate with epoxy interleaf. Mode-I and mode-II tests were done for finding the interlaminar fracture toughness and delamination fatigue and reported that in mode-I the results are same for specimens with and without interleaf because toughness of interleaf played a major role. Interlaminar fracture toughness and delamination fatigue crack growth are more for epoxy interleafed composites compared to without interleaf under mode-II tests because interleaf thickness played a major role. Alessi et.al [12] reported a fixed fracture toughness tendency for carbon/epoxy composites, when subjected to ageing at 30°C for 4 week & 8 week immersion of composite specimens in distilled water, but at the same time a decrease in fracture toughness is found when the temperature is increased to 70° С.

III. EXPERIMENTAL PROCEDURE:

A. Material & Specimens

The versatility of glass as a fibre makes it unique industrial textile material. Due to the dimensional stability, moisture Resistance, high Strength, fire Resistance, chemical resistance, electrical Properties & thermal conductivity E-Glass fiber is selected. The resin LAPOX L-12 is mixed with hardner K-6 in ratio of 70:10 gm. The E-Glass fiber which is passed through the resin bath mixed with corresponding hardner on the drum is covered with a thin polythene sheet is opened and laid on the table for 24hrs to dry up.



Fig 1. Composite laminate with delamination



To prepare a laminate the following procedure is used

- 1) Smoothing of surface of mould.
- 2) Cleaning of mould (MS Plate).
- *3)* Applying waxpol to plate.
- 4) Marking of lamina.
- 5) Inserting artificial de-lamination.
- 6) Layup on the MS plate.
- 7) Curing for 24hours.
- 8) Extraction of laminate.





Fig 2. Specimens with delamination



International Journal for Research in Applied Science & Engineering Technology (IJRASET) ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.429

Volume 8 Issue VI June 2020- Available at www.ijraset.com

The laminas are cut according to the dimensions of the mould. Mould dimensions are 400x400mm so as the laminate dimensions and no of layers of pre-preg is 10. Insertion of de-lamination strip that is a thin polymer layer strip is placed in the middle layer of the laminate that is after the fifth layer. The laminate is left for 24hrs in the room temp for curing and then laminate is extracted carefully. The specimen dimensions are marked on the laminate and the specimens are cut using the cutting machine setup where width of specimen is 25mm &length of the specimens is 114mm. The end of the specimen with delamination (interlayer) is attached with hinges to support the specimen on UTM for conducting double cantilever beam test.

C. Hygrothermal Aging and Observations

Using a heating element, the water was initially heated to a temperature of 100° C to accelerate the ageing process and the specimens were subsequently aged for periods of 6 hours. Further different specimens are heated to temperatures 80° C, 60° C, 40° C respectively for 6 hours duration.



Fig 3. Hygrothermal ageing of composite Specimens

Hydrothermal ageing is expected to affect the fibre-matrix interface, lead to chemical reaction and leaching, thus the compressive response of composite[7]. This was investigated by comparing the virgin specimens and the specimens conditioned with accelerated ageing. Water absorption causes the fibre-matrix interface to weaken, which results in fibre-matrix debonding. The primary role of the matrix in the composites is for it to transfer stresses between the fibers to provide a barrier against an adverse environment.

Table 1: Data of specimens subjected to aging.	
--	--

Temperature (subjected to aging)	Specimen numbers
25°(Virgin)	1,2,3,4,5
40°	6,7,8,9,10
60°	11,12,13,14,15
80°	16,17,18,19,20
100°	21,22,23,24,25

IV. TESTING

A. Mode 1 double cantilever beam (DCB) test for Fracture Toughness



Fig 4. Testing of Specimen.



International Journal for Research in Applied Science & Engineering Technology (IJRASET) ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.429 Volume 8 Issue VI June 2020- Available at www.ijraset.com

The mode I delamination toughness is usually measured using the double cantilever beam (DCB) test, which was standardized for fiber reinforced composites by ASTM D-5228 (1994). A schematic of the DCB test is shown in Figure 4, where the specimen thickness is given by t, the crack length is given by a, and the applied load is given by P. The single point loading condition of the DCB provides the ability to use a compliance calibration based data reduction procedure, which is preferred because the only assumptions that must be made are of linear elastic behaviour and of self-similar crack advance. Stable crack advance occurs under displacement-controlled loading (Broek, 1986), which makes continuous measurement of fracture toughness with crack growth feasible.

In this mode 1 fracture test the hinges attached to the specimen are securely inserted into the Universal Testing Machine as shown in the figure above, and subjected to the tensile load. Due to the load the specimen fractures exactly at the delamination layer. The load and displacement are noted at regular intervals to find out the mode 1 fracture behaviour. The same procedure is repeated for all the specimens and results are tabulated.

V. RESULTS& DISCUSSIONS

A. Interlaminar Fracture Toughness

It became a common practise to characterize the resistance to delamination using fracture mechanics. There is competing terminology in literature, such as fracture toughness, average fracture energy, J integral, WOF and critical strain energy release rate. The critical fracture toughness or critical strain energy release rate is the value at the onset of crack propagation. Crack propagation under pure mode-I (opening mode), pure mode-II (shearing or sliding mode) loading has been extensively studied in the literature. Mode-I fracture toughness is given by

$$G_I = \frac{3P\delta}{2Wa}$$

Where G_{I} fracture toughness, P - Ultimate load Width of specimen i.e. W = 25mm Thickness of specimen i.e. T=5mm ' a ' is crack propagation length = 57mm

'δ' is crack displacement

S.no	Specimen	Temperature	Fracture	Displacement	Fracture
	no.	(T °C)	load (P KN)	(δ)	toughness
					(G _i)
1	1	virgin	0.99	7.3	0.00761
2	3	virgin	0.89	9.2	0.00862
3	7	40	0.77	6.7	0.00543
4	8	40	0.71	6.3	0.00471
5	11	60	0.59	4.8	0.00298
6	12	60	0.65	3.7	0.00253
7	16	80	0.59	4.4	0.00298
8	17	80	0.44	5.4	0.00239
9	21	100	0.49	3.5	0.00181
10	22	100	0.47	2.8	0.00139

Table 2: Calculation of fracture toughness (G_I)



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.429 Volume 8 Issue VI June 2020- Available at www.ijraset.com

Before and after subjecting to Hygrothermal aging, the specimens are weighed and the values are noted.

It is observed that after Hygrothermal aging the weight of the specimens increased, it is due to the fact that the salt particles get clogged between the space of matrix and fibre. During ageing, diffusion is caused by hydrolysis and plasticisation of the immediate neighbouring molecules in the resin matrix, and swelling was caused by moisture absorption. The rate of diffusion depends on the nature of the resin matrix, fibre orientation, fibre volume fraction, porosity and voids.

The presence of fibres slowed the movement of the molecules, and hence, lowered the diffusivity factors after the initial stage. Moisture intake caused swelling of the specimens, creating internal stress on the matrix bonding, in turn, leading to the formation of matrix cracks. Moisture absorption caused osmotic cracking inside the matrix and the mechanical properties of the composites deteriorated. Glass fibres showed higher resistance to water absorption, slowing the deterioration.

The following curves represent the load Vs displacement for the specimens





C. Results of specimen 7& 8 at $40^{\circ}C$





International Journal for Research in Applied Science & Engineering Technology (IJRASET) ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.429 Volume 8 Issue VI June 2020- Available at www.ijraset.com

D. Results of specimens 11& 12 at $60^{\circ}C$



Graph 5. Load Vs Displacement for specimen 11



E. Results of specimens 16 & 17 at $80^{\circ}C$





International Journal for Research in Applied Science & Engineering Technology (IJRASET) ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.429

Volume 8 Issue VI June 2020- Available at www.ijraset.com

F. Results of specimens 21&22 at $100^{\circ}C$



Graph 9. Load Vs Displacement for specimen 21

Graph 10. Load Vs Displacement for specimen 22

rubie.s. variation of attimate four Due for riging at anterent temperatures

Temperature (°C)	Ultimate load	% decrease in Ultimate load
Virgin (25°C)	0.89	-
40°C	0.77	13.48
60°C	0.65	26.97
80°C	0.59	33.71
100°C	0.47	47.19



Graph 11. Temperature Vs Ultimate load

Due to hygrothermal aging the ultimate load of the specimens decreased, this is due to degradation of matrix strength because of salt particles.

Table.4. Variation Of Fracture Toughness Due To Aging at different temperatures

Temperature (°C)	Fracture toughness	% decrease in toughness
Virgin (25)	0.00862	-
40	0.00543	37.00
60	0.00298	65.43
80	0.00239	72.27
100	0.00139	83.88



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.429 Volume 8 Issue VI June 2020- Available at www.ijraset.com



Graph 12. Temperature Vs Fracture Toughness

Due to hygrothermal aging the fracture toughness of the specimens decreased, this is due to degradation of matrix strength because of salt particles.

VI. CONCLUSION

The following conclusions and observations are made from the test results: As the temperature increases the maximum load required for fracture is decreased.

- A. The average ultimate load of virgin specimen is 0.94kN.
- B. The average ultimate load of specimens at 40° C is 0.74kN
- C. The average ultimate load of specimens at 60°C is 0.62kN
- D. The average ultimate load of specimens at 80°C is 0.51kN
- E. The average ultimate load of specimens at 100°C is 0.48kN

As the temperature increases the fracture toughness (G_I) is decreased.

- 1) The average toughness for virgin specimen is 0.0081.
- 2) The average toughness for specimen at 40° C is 0.0050.
- 3) The average toughness for specimen at 60° C is 0.0028.
- 4) The average toughness for specimen at 80° C is 0.0025.
- 5) The average toughness for specimen at 100° C is 0.0016.

The results revealed that hygrothermal aging conditions at higher temperature had negative impact on mechanical properties of GFRP composites.

REFERENCES

- Standard test methods for Mode-I Interlaminar Fracture toughness of unidirectional fiber reinforced polymer matrix composites ASTM standard D 5528 94a. ASTM annual book of standards, vol. 15.30, 1994. Pp. 272-281.
- [2] Zhao, Y., Liu, W., Seah, L.K. and Chai, G.B., 2016. Delamination growth behaviour of a woven E-glass/Bismaleimide composite in seawater environment. Composites Part B: Engineering, 106, pp.332-343."
- [3] Larbi, S., Bensaada, R., Bilek, A. and Djebali, S., 2015, March. Hygrothermal ageing effect on mechanical properties of FRP laminates. In AIP Conference Proceedings (Vol. 1653, No. 1, p. 020066). AIP Publishing.)
- [4] Shivakumar, S., 2010. Shivarudraiah,—Effect of Temperature on the Hygrothermal and Mechanical Behaviour of Glass-Epoxy laminates. Int. J. Adv. Eng. Technol, 1(3), pp.225-231.
- [5] Hojo, M., Ando, T., Tanaka, M., Adachi, T., Ochiai, S. and Endo, Y., 2006. Modes I and II interlaminar fracture toughness and fatigue delamination of CF/epoxy laminate with self-same epoxy interleaf. International journal of fatigue, 28(10), pp.1154-1165.
- [6] Vauthier, E., Chateauminois, A. and Bailliez, T., 1995. Hygrothermal aging and durability of unidirectional glass-epoxy composites. In Tenth International Conference on Composite Materials. VI. Microstructure, Degradation, and Design (pp. 185-192).
- [7] Vlot, A. and Gunnink, J.W. eds., 2011. Fibre metal laminates: an introduction. Springer Science & Business Media.
- [8] Hojo, M., Ando, T., Tanaka, M., Adachi, T., Ochiai, S. and Endo, Y., 2006. Modes I and II interlaminar fracture toughness and fatigue delamination of CF/epoxy laminate with self-same epoxy interleaf. International journal of fatigue, 28(10), pp.1154-1165.



ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.429

Volume 8 Issue VI June 2020- Available at www.ijraset.com

- [9] Botelho, E.C., Costa, M.L., Pardini, L.C. and Rezende, M.C., 2005. Processing and hygrothermal effects on viscoelastic behaviour of glass fiber/epoxy composites. Journal of Materials Science, 40(14), pp.3615-3623.
- [10] Subhani, M., Al-Ameri, R. and Al-Tamimi, A., 2016. Assessment of bond strength in CFRP retrofitted beams under marine environment. Composite Structures, 140, pp.463-472.
- [11] Mouritz, A.P., Gellert, E., Burchill, P. and Challis, K., 2001. Review of advanced composite structures for naval ships and submarines. Composite structures, 53(1), pp.21-42.
- [12] Alessi, S., Pitarresi, G. and Spadaro, G., 2014. Effect of hydrothermal ageing on the thermal and delamination fracture behaviour of CFRP composites. Composites Part B: Engineering, 67, pp.145-153.
- [13] Tamin, M.N. ed., 2012. Damage and fracture of composite materials and structures (Vol. 17). Heidelberg, Germany: Springer.
- [14] Nash, N.H., Young, T.M. and Stanley, W.F., 2016. The reversibility of Mode-I and-II interlaminar fracture toughness after hydrothermal aging of Carbon/Benzoxazine composites with a thermoplastic toughening interlayer. Composite Structures, 152, pp.558-56
- [15] Davidson, B.D., Kumar, M. and Soffa, M.A., 2009. Influence of mode ratio and hygrothermal condition on the delamination toughness of a thermoplastic particulate interlayered carbon/epoxy composite. Composites Part A: Applied Science and Manufacturing, 40(1), pp.67-79.
- [16] Zhong, Y. and Joshi, S.C., 2015. Impact behaviour and damage characteristics of hygrothermally conditioned carbon epoxy composite laminates. Materials & Design (1980-2015), 65, pp.254-264.
- [17] Nash, N.H., Ray, D., Young, T.M. and Stanley, W.F., 2015. The influence of hydrothermal conditioning on the Mode-I, thermal and flexural properties of Carbon/Benzoxazine composites with a thermoplastic toughening interlayer. Composites Part A: Applied Science and Manufacturing, 76, pp.135-144.











45.98



IMPACT FACTOR: 7.129







INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089 🕓 (24*7 Support on Whatsapp)