



IJRASET

International Journal For Research in
Applied Science and Engineering Technology



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 9 Issue: III Month of publication: March 2021

DOI: <https://doi.org/10.22214/ijraset.2021.33335>

www.ijraset.com

Call:  08813907089

E-mail ID: ijraset@gmail.com

Study of Structural, Morphological and Compositional Characteristics of Vacuum Deposited $Zn_{0.75}Cd_{0.25}Se$ Thin Films

Premjeet G. Jadhav¹, D. K. Sawant², K. D. Girase³, K. B. Mahajan⁴, V. R. Khadse⁵, R. R. Attarde⁶, D. S. Bhavsar⁷

^{1, 4, 5, 6}Moolji Jaitha College, Jalgaon, MS

²J.E.S.'S Arts, Comm & Sci. Coll. Nandurbar, MS

³Dadasaheb Rawal College, Dondaicha, MS

⁷Pratap College, Amalner, MS

Abstract: In this study, $Zn_{0.75}Cd_{0.25}Se$ ternary semiconductor thin films of thickness 1000 \AA and 2500 \AA belong to II-VI group were deposited onto glass substrates by the vacuum deposition method under the pressure of 10^{-5} mbar. The effect of Zinc content on different physics and chemical properties in $Zn_{0.75}Cd_{0.25}Se$ thin films has been investigated. Systematic characterizations of structural, morphological and compositional, properties have been carried out by XRD, SEM and EDAX.

Keywords: Ternary, cadmium selenide, zinc selenium, thin films, vacuum deposited

I. INTRODUCTION

The research on Zn doped CdSe nanostructures i.e. $Zn_{0.75}Cd_{0.25}Se$, a ternary semiconductor alloy from group II-VI material, is getting attention due to its application in a photo sensor [1] and other optoelectronic devices. Ternary alloy is a type of alloy which is made up of three different chemical elements; usually two cations and an anion and their band gap is a continuous function of composition of elements [2]. The band gap of $Zn_xCd_{1-x}Se$ material can be tuned from 1.70 to 2.70 eV. Zn doped CdSe ($Zn_{0.75}Cd_{0.25}Se$) is an efficient absorber in the visible region of solar spectrum [3]. Recent developments in science and technology related to nano engineered materials have demonstrated that, nanostructure semiconductors have greater flexibility and control in designing various nano scale structures and devices. Zinc doped cadmium selenide thin film is one of the important materials used in photo luminescent, photoconductive and photovoltaic device applications [4], etc. have shown its prominence and ability. Numbers of researchers have prepared $Zn_{0.75}Cd_{0.25}Se$ thin films by various deposition techniques like vacuum evaporation, molecular beam epitaxy, electron beam pumping [5], chemical bath deposition etc [6]. In present investigation we have prepared Zinc doped Cadmium Selenide ($Zn_{0.75}Cd_{0.25}Se$) thin films having thickness of 1000 \AA and 2500 \AA and investigate the effect of thickness on their structural, morphological and compositional properties by controlling the stoichiometric ratio of Zn and Cd in [7] $Zn_{0.75}Cd_{0.25}Se$ thin films.

II. EXPERIMENTAL

A. Thin Film Deposition

In deposition of $Zn_xCd_{1-x}Se$ ($x = 0.75$) the zinc and cadmium material used was in core granular form and selenium material was in core powder form of purity 99.999 from Sigma Aldrich Company [2]. Initially ampoule of CdSe were formed, then mixed Zinc core material in given proportion and fused to very high temperature in quartz tube for uniform mixing of Zn, and CdSe to form ternary $Zn_{0.75}Cd_{0.25}Se$ compound.

Thin films of $Zn_xCd_{1-x}Se$ were prepared by vacuum evaporation technique on glass substrate [8]. Then $Zn_{0.75}Cd_{0.25}Se$ compound was grinded to get fine powder and placed in molybdenum boat for evaporation. The evaporation was performed in a vacuum environment (10^{-6} mbar) with the help of HINDHIVAC: 15F6D coating unit [3, 9]. The low tension (LT) supply for evaporation source is obtained from a 230V input transformer by means of parallel connections in the secondary side of the transformer [10]. The $Zn_{0.75}Cd_{0.25}Se$ samples of different thicknesses (1000 \AA and 2500 \AA) were deposited under almost same environment [8,11]. The thickness monitor model no. DTM - 101 provided by Hind-High Vac. machine to determine the thickness of deposited thin films [12]. The deposition rate was maintained constant throughout the sample preparations [3, 9]. The substrate temperature was kept at lower temperature as compare to source temperature with the continuous supply of chilled water [13]

B. Characteristics

1) **X-Ray Diffraction (XRD):** The structural investigation of Zn_{0.75}Cd_{0.25}Se thin films of thickness 1000 Å and 2500 Å has been carried out by The X-ray diffraction (XRD). The particle size (D) is calculated by using The Scherer’s formula [1,2] $D = \frac{0.94\lambda}{\beta \cos \theta}$, The lattice parameter (a) for the thin film is determined by using the following expression [6,14]. $\frac{1}{d^2} = \frac{h^2+k^2+l^2}{a^2}$, The interplanar spacing ‘d’ has been obtained by using Bragg’s law [15] ie $n\lambda = 2d \sin \theta$, Dislocation density is calculated by using formula $\delta = 1/D^2$, Micro strain of given thin film is also obtain by formula $\epsilon_s = \beta \cos \theta / 4$ [11]




Fig. 1 & 2: XRD of Zn_{0.75}Cd_{0.25}Se films of thickness 1000 Å and 2500 Å

[hkl] values from JCPDS data	d(Å) values from JCPDS data of cdse	Observed values of d(Å) Zn _{0.75} Cd _{0.25} Se 1000 Å	Observed (2θ)° values of peaks	intensity	Lattice parameter a (Å)	Particle size D (Å)	Dislocation density δ (×10 ¹⁵ lines/m ²)	Micro strain (ε _s)
100	3.720	3.720	23.900	536	3.720	2.895	0.1193	0.1250
002	3.510	3.509	25.370	626	7.016	2.930	0.1164	0.1235
101	3.290	3.290	27.080	904	4.652	2.973	0.1131	0.1217
102	2.554	2.555	35.090	276	5.713	3.235	0.0955	0.1118
110	2.151	2.151	41.960	215	3.041	3.560	0.0789	0.1016

Table 1. XRD JCPDS hexagonal data for Zn_{0.75}Cd_{0.25}Se sample of thickness 1000 Å⁰

[hkl] values from JCPDS data	d(Å) values from JCPDS data of znse	Observed values of d(Å) Zn _{0.75} Cd _{0.25} Se 1000 Å	Observed (2θ)° values of peaks	intensity	Lattice parameter a (Å)	Particle size D (Å)	Dislocation density δ (×10 ¹⁵ lines/m ²)	Micro strain (ε _s)
111	3.273	3.273	27.230	747	5.669	2.977	0.1128	0.1215
200	2.835	2.836	31.520	363	5.671	3.105	0.1037	0.1165
220	2.004	2.005	45.200	245	5.670	3.757	0.0708	0.0963
311	1.707	1.708	53.600	171	5.661	4.461	0.0502	0.0811
222	1.635	1.635	56.150	160	5.663	4.752	0.0442	0.0761

Table 2. XRD JCPDS cubic data for Zn_{0.75}Cd_{0.25}Se sample of thickness 1000 Å⁰

[hkl] values from JCPDS data	d(Å) values from JCPDS data of cdse	Observed values of d(Å) Zn _{0.75} Cd _{0.25} Se 2500	Observed (2θ) ^o values of peaks	intensity	Lattice parameter a(Å)	Particle size D (Å)	Dislocation density δ (×10 ¹⁵ lines/m ²)	Micro strain (ε _s)
100	3.720	3.720	23.900	359	3.720	2.4673	0.1642	0.1467
002	3.510	3.509	25.370	464	7.016	2.4965	0.1604	0.1450
101	3.290	3.290	27.080	567	4.652	2.5335	0.1557	0.1428
102	2.554	2.555	35.090	265	5.713	2.7567	0.1315	0.1313
110	2.151	2.151	41.960	176	3.041	3.0333	0.1086	0.1193

Table 3. XRD JCPDS hexagonal data for Zn_{0.75}Cd_{0.25}Se sample of thickness 2500 Å⁰

[hkl] values from JCPDS data	d(Å) values from JCPDS data of znse	Observed values of d(Å) Zn _{0.75} Cd _{0.25} Se 2500	Observed (2θ) ^o values of peaks	intensity	Lattice parameter a(Å)	Particle size D (Å)	Dislocation density δ (×10 ¹⁵ lines/m ²)	Micro strain (ε _s)
111	3.273	3.273	27.230	578	5.669	2.536	0.1554	0.1427
200	2.835	2.836	31.520	294	5.670	2.646	0.1428	0.1368
220	2.004	2.005	45.200	227	5.670	3.201	0.0975	0.1130
311	1.707	1.708	53.600	144	5.661	3.801	0.0692	0.0952
222	1.635	1.635	56.150	156	5.663	4.049	0.0609	0.0893

Table 4. XRD JCPDS cubic data for Zn_{0.75}Cd_{0.25}Se sample of thickness 2500 Å⁰

2) *Scanning Electron Microscope (SEM)*: In order to study the microstructures of Zn_{0.75}Cd_{0.25}Se thin films, scanning electron microscopy (SEM) was used [9] as it provides valuable information regarding the growth mechanism, shape and size of the particles and/or grains. Fig. 3 shows the SEM images of vacuum deposited thin films of thickness 1000 Å⁰ and 2500 Å⁰ respectively. Surface morphology by SEM studies shows very small, fine and hardly distinguishable grains smeared all over the film surface. These are the characteristic features of zinc-rich surfaces. No crack was observed on the surface of the Zn_{0.75}Cd_{0.25}Se thin film. The sharp cleavage edge indicates the well adhesive nature of the films onto the glass substrates [16]




Fig 3: SEM pictures for Zn_{0.75}Cd_{0.25}Se films 1000 Å⁰ (a) 400 nm, x = 120k (b) 500 nm, x = 60k (c) 1.0 μm, x = 30k (d) 2.0 μm, x = 20k




Fig 4: SEM pictures for Zn_{0.75}Cd_{0.25}Se films 2500 Å⁰ (a) 400 nm, x = 120k (b) 500 nm, x = 60k (c) 1.0 μm, x = 30k (d) 5.0 μm, x = 20k

3) *Energy-dispersive X-ray spectroscopy (EDAX)*: The presence of elemental constituents in Zn doped CdSe ($Zn_{0.75}Cd_{0.25}Se$) thin film is confirmed from Energy-dispersive X-ray spectroscopy analysis [10]. The selenium content is always present in stoichiometric percentage which nearly equal to starting material [17]. These results show the *n*-type nature of these $Zn_{0.75}Cd_{0.25}Se$ thin films as Selenium is present in a more proportion compare to Zn and Cd.




Fig 5 and 6:- EDAX spectra of $Zn_{0.75}Cd_{0.25}Se$ of thickness 1000 Å and 2500 Å

Element	CdSe 1000Å		CdSe 2500Å	
	Mass %	Atomic %	Mass %	Atomic %
Se 34	53.09	57.80	48.14	51.88
Cd 48	35.43	27.10	35.59	26.94
Zn 30	11.49	15.10	16.27	21.18

Table 5 - EDAX mass and atomic Percentages of Zn, Se and Cd

III. CONCLUSION

From **XRD** It is found that the deposited films i.e. $Zn_{0.75}Cd_{0.25}Se$ of thickness 1000 Å and 2500 Å show wurtzite structure along crystallographic planes (100), (002), (101),(102),(110) and (103) (JCPDS 08-0459) and for cubic structure the preferred crystal orientation is along (111), (200), (220),(311) and (222) planes (JCPDS 19 - 0191). The XRD analysis shows that the films are polycrystalline in nature. The lattice parameters are almost matching with the JCPDS data of CdSe and ZnSe. The values of interplanar spacing's (d) are 2.867 Å and 2.291 Å and lattice constant (a) are 5.067 Å and 5.668 Å for thickness 1000 Å and 2500 Å respectively. While the average particle size (D) is 3.231 Å and 3.810 Å, Dislocation density (δ) 0.0987 and 0.0763 and Micro strain (ϵ_s) 0.113 and 0.098 for wuritz and cubic structure respectively of thickness 1000 Å and the average particle size (D) is 2.7535 Å and 3.2466 Å, Dislocation density (δ) 0.1360 and 0.1051 and Micro strain (ϵ_s) 0.1328 and 0.1154 for wuritz and cubic structure respectively of thickness 2500 Å. The **SEM** shows uniform growth of $Zn_{0.75}Cd_{0.25}Se$ thin films on a glass substrate. The results of SEM show that the sizes of grain were 99 nm to 169 nm for film of thickness 1000 Å and 154 nm to 228 nm for $Zn_{0.75}Cd_{0.25}Se$ thin films of thickness 2500 Å.

The presence of elemental constituents is confirmed from **EDAX** analysis strong peaks for Zn and Se were found in the spectrum of $Zn_{0.75}Cd_{0.25}Se$ thin film.

REFERENCES

- [1] Premjeet G. Jadhav and Deelip Bhavsar Characterization of Zinc Doped Cadmium Selenide [$Cd_{1-x}Zn_xSe$] Thin Films Prepared by Vacuum Deposition Technique journal of Emerging Technologies and Innovative Research (JETIR) April 2019, Volume 6, Issue 4 www.jetir.org (ISSN-2349-5162) page 276 – 280
- [2] Premjeet Jadhav and Deelip Bhavsar Comparative Study of Characterization of CdSe, ZnSe and $Cd_{0.5}Zn_{0.5}Se$ Thin Films Prepared by Vacuum Deposition Technique Journal of Emerging Technologies and Innovative Research (JETIR) May 2019, Volume 6, Issue 5 www.jetir.org (ISSN-2349-5162) Page 529 – 534
- [3] D. Soundararajan, J. K. Yoon, Y. I. Kim, J. S. Kwon, C. W. Park, S. H. Kim, J. M. Ko, Vertically Aligned CdSe and Zn doped CdSe Nano rod Arrays Grown Directly on FTO Coated Glass: Synthesis and Characterization, International Journal of Electrochemical Science **4** (2009) 1628 – 1637.
- [4] Jamal. F. Mohammad and Hamed. S. Al-jumaili, Structural and optical properties of nano crystalline $Zn_xCd_{1-x}S$ thin films deposited by chemical bath technique, International Journal of Application or Innovation in Engineering & Management (IJAIEM) **Vol. 3 Issue 5** (2014) 204.
- [5] T. Mahalingam, V. Dhanasekaran, S. Rajendran, R. Chandramohan, Luis Ixtlilco and P. J. Sebastian, Electrochem. Systems electro synthesis and Studies on CdZnSe Thin Films, Journal of New Materials for Electrochemical Systems **15** (2012) 37-42.

- [6] J. R. Heine, J. Rodriguez-Viejo, M.G. Bawendi, K. F. Jensen, Synthesis of CdSe quantum dot ZnS matrix thin films via electrospray organometallic chemical vapor deposition, *Journal of Crystal Growth* **195** (1998) 564 – 568.
- [7] J. Suthagar, S. Rajesh, K. Perumal, T. Balasubramaniam and N. J. Suthan Kissinger, Growth and Characterization of Wide Gap Cd_{1-x}Zn_xSe Ternary Alloys by using Electron Beam Evaporation Technique, *Acta Physica Polonica A* **Vol. 117 No. 3** (2010) 506 – 511.
- [8] S. D. Chavhan, S. Senthilarasu, J. Lee and Soo-Hyoung Lee, Effect of annealing on the structural and optical properties of indium-diffused Cd_{0.7}Zn_{0.3}Se thin films, *Journal of Physics D: Applied Physics* **41** (2008) 165502 (6pp) [doi:10.1088/0022-3727/41/16/165502](https://doi.org/10.1088/0022-3727/41/16/165502)
- [9] Ijaz Ali, Amjid Iqbal, Arshad Mahmood, A. Shah, M. Zakria, Asad Ali, Optical spectroscopic analysis of annealed Cd_{1-x}Zn_xSe thin films deposited by close space sublimation technique, *Materials Science-Poland*, **34(4)** (2016) 828-833.
- [10] N. J. Suthan Kissinger, G. Gnana Kumar, K. Perumal, Properties of Cd_{1-x}Zn_xSe Composite thin films Prepared by Electron Beam Evaporation Technique, *Scientia Acta Xaveriana, An International Science Journal* **Vol. 1 No. 2** (2010) 11–22.
- [11] R. Chandramohan, C Sanjeeviraja, S Rajendra, T Mah Lingam, M Jayachandran and Mary Julian Chockalingam, Electro synthesis and Characterization of Zn_{1-x}Cd_xSe Thin Films, *Bull. of Electrochemistry* **14 (11)** (Nov 1998) 402-406.
- [12] Shu-Ru Chung, Kuan-Wen Wang, Hong-Shuo Chen, Hong-Hong Chen, Novel red emission of ternary ZnCdSe semiconductor nano crystals, *J. Nanopart. Res* **17** (2015) 101 [DOI 10.1007/s11051-015-2906-8](https://doi.org/10.1007/s11051-015-2906-8)
- [13] Soumya R. Deo, Ajaya K. Singh, Lata Deshmukh, L. J. Paliwal, R. S. Singh, Rameshwar Adhikari, Structural, Morphological and Optical Studies on Chemically Deposited Nano crystalline CdZnSe Thin Films, *Journal of Saudi Chemical Society* (2014),
- [14] N. J. Suthan Kissinger, K. Perumal, J. Suthagar, Preparation and Properties of Zinc Doped Cadmium Selenide Compounds by E-Beam Evaporation, *J. Nano-Electron. Phys.* **3 No. 3** (2011) 5-14.
- [15] N. Thirugnanam and D. Govindarajan, Structural, optical and morphological studies of undoped and Zn doped CdSe QDs via aqueous route synthesis, *Bull. Mater. Sci.* **Vol. 39 No. 7** (Dec 2016) 1775–1781.
- [16] Usama A.A. Al- Mustansiriya, Electrical, Thermal, and Optical Properties Study for CdSe Thin Film, *J. Sci.* **Vol. 20 No 1** (2009) 55 – 61.
- [17] U. Pal, M. Herrera Zaldivar, R. Sathyamoorthy, V. Manjuladevi, P. Sudhagar, S. Chandra Mohan, and S. Senthilarasu, Nano crystalline CdSe Thin Films of Different Morphologies in Thermal Evaporation Process, *Journal of Nano Science and Nanotechnology* **Vol.8** (2008)1–7



10.22214/IJRASET



45.98



IMPACT FACTOR:
7.129



IMPACT FACTOR:
7.429



INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089  (24*7 Support on Whatsapp)