



IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 9 Issue: VI Month of publication: June 2021

DOI: https://doi.org/10.22214/ijraset.2021.34942

www.ijraset.com

Call: 🕥 08813907089 🔰 E-mail ID: ijraset@gmail.com



Vasundhara Singh¹, Mahesh Ram Patel²

¹MTech Scholar (Structural Engineering), SSTC, SSGI, BHILAI, C.G., India ²Assitant Professor, Department of Civil Engineering, SSTC, SSGI, BHILAI, C.G., India

Abstract: Solid waste management is one of the major environmental concerns in our country now a day. The present study covers the use or recycled plastics as replacement of coarse aggregates in concrete. The main aim of the study is to investigate the change in mechanical properties of concrete with the addition of plastics in concrete. Along with the mechanical properties, thermal characteristics of the resultant concrete are also studied.

It is found that the use of plastic aggregates results in the formation of lightweight concrete. The compressive, as well as tensile strength of concrete reduces with the introduction of plastics. The most important change brought about by the use of plastics is that the thermal conductivity of concrete is reduced by using plastics in concrete. Therefore, it can be said that recycled plastics can be used for thermal insulation of buildings.

Keywords: Plastic aggregate, self compacting concrete, Compressive strength, Tensile Strength.

I. INTRODUCTION

The main source for recycled aggregates is construction and demolition waste. Most of the waste materials produced by demolishing structures are disposed by dumping them as landfill or for reclaiming land. But with the demand for land increasing day by day, the locations, capacity and width of the land that can receive waste materials are becoming limited. Added to it, the cost of transportation makes disposal a major problem. Hence, reuse of demolition waste appears to be an effective solution and the most appropriate and large-scale use would be to use it as aggregates to produce concrete for new construction. Recycled aggregate concrete utilizes demolition material from concrete and burnt clay brick masonry construction as aggregate.

It is necessary to work out a project proposal to carry out further studies on various aspects such as collection, processing and effective utilization of this waste material. To start with, such a study could be initiated with the following components:

- A. Estimation of the types, quantity and useful components present in the waste plastic materials in the city and surrounding areas.
- *B.* Methodology for collection and sorting out the useful components of the plastic waste.
- *C.* Methodology for processing the plastic bags as required for use in the preparation of modified bitumen, including cleaning, shredding and further processing of the plastic waste materials
- D. Carrying out further laboratory investigations, construction of some test tracks and field studies on the performance of concrete using the modified concrete.
- *E.* Working out relative economics of using the modified concrete mixes in road construction works, considering the improved performance and increased service life of the pavement.

II. LITERATURE REVIEW

In this research work concerning to the various application and methods used for testing of the concrete made by recycled aggregate and recycled plastics aggregates are discussed. This chapter gives a comprehensive review of the work carried out by various researchers in the field of using recycled plastics in concrete as full or partial replacement of aggregates.

The most important property of concrete in fresh state is its workability. It is defined as the ease with which concrete can be mixed, transported, placed and finished easily without segregation. From many research papers we investigated the effect of ground plastic on the slump of concrete. The Concrete mixes with partial replacement of plastic aggregate up to 20% are proportioned to the fine aggregates is gives the best results. Hence we consider the Partial replacement of plastic aggregate up to 20% (Taken 5%, 10%, 15% % 20%) for different mix proportions. Details of mixture proportions are decided for further is based on the research papers listed in reference sections.



A. Basic Materials

International Journal for Research in Applied Science & Engineering Technology (IJRASET) ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.429

Volume 9 Issue VI Jun 2021 - Available at www.ijraset.com

It is also observed that the change in water cement ration may also effect the strength and workability of concrete, hence different water cement ratios (0.40, 0.44, 0.48 & 0.52) are also taken in account in this research.

(*Siddique*, 2007). It was concluded that 19 mm fibrillated polypropylene fibers had no obvious effect on the compressive strength of concrete. However, 19 mm fibrillated polypropylene fibers enhanced the energy absorption and toughness characteristics of concrete under compression, as evidenced by increase in compressive toughness index of concrete with fiber addition.

III.EXPERIMENTAL PROGRAM

1) Cement: 53 Grade Ultra Tech cement was used for casting cubes and cylinders for all concrete mixes. The cement was of uniform colour and before use the compressive strength and tensile strength of cement is determined and for w/c ratio consistency of cement is also determined by using vicat apparatus. The initial and final setting time, fines of cement also determined. All the details are show in table below:-

S.No.	Characteristics	Values obtained	Standard values		
1.	Normal	Normal 33%			
	Consistency				
2	Initial Setting time	18 min	Not be less than		
2.	Initial Setting time	40 11111	30 minutes		
	Final Setting time		Not be		
3.		240 min	greater		
			then 600 minutes		
4.	Fineness 4.8 %		<10		
5.	Specific gravity	3.09	-		
Compressive strength: - Cement : Sand (1:3)					
1.	3 days	24.5 N/mm ²	27 N/mm ²		
2.	7 days	35 N/mm ²	41 N/mm ²		
3.	28 days	53.5 N/mm ²	53 N/mm ²		

- 2) Coarse Aggregates: The coarse aggregate used were a mixture of two locally available crushed stone of 20 mm and 10 mm size in 70:30 proportion. Coarse aggregate of maximum size 20mm and minimum 10 mm is used throughout the concrete. The specific gravity of coarse aggregate is 2.825.
- *3) Fine Aggregates:* Fine aggregate which is used in this experimental study for concrete is taken from local river sand conforming to zone- II. The specific gravity of fine aggregates 2.68.
- 4) Plastics Aggregates: Recycled plastic was used to replace coarse aggregates for making concrete specimens. These aggregates were available in three different sizes (Bigger size plastic aggregate PB, Medium sized plastics aggregates PM & Smaller sized plastics aggregates PS) as shown in Figure below:



Figure.3.2. Three types of plastic aggregates (smaller, medium and coarser size)

Fineness Modulus of bigger sized plastic aggregate, Medium sized plastics aggregates & Smaller sized plastics aggregates is 7.59, 9.99 and 9.18 respectively. Specific gravity of the plastics aggregates =1.1



IV.METHODOLOGY

A. Mix Prapotioning

In this work the water cement ratio is ranges between 0.40 to 0.52 and the Partial Replacement of plastic aggregate per cube of various water cement ratios is done. The mix proportioning is listed in table below:

S. No.	% of Plastic Agg.	W/C Ratio
MR1	5	0.40
MR2	10	0.40
MR3	15	0.40
MR4	5	0.44
MR5	10	0.44
MR6	15	0.44
MR7	5	0.48
MR8	10	0.48
MR9	15	0.48
MR10	5	0.52
MR11	10	0.52
MR12	15	0.52

B. Moulds

To determine the compression strength of the self-compacting concrete, cubes of 150mm×150mm×150mm size were used. Cylindrical moulds are used to determine split tensile strength, having the dimension 150mm diameter and 300mm length. For flexural strength test, Prisms of 100mm×100mm×500mm size were used.



Figure: Casting of Concrete



V. RESULTS

In this chapter, the experimental results are presented and discussed. The effects of various important parameters on the slump test, compressive strength, split tensile strength of control concrete, plastic concrete and partially replaced concrete are studied for percentage reduction of compressive and split tensile strength and there results are shown below. Tests were performed after 7 and 28 days of proper curing of concrete.

A. Compressive Strength

Table: Percentage reduction in 7 Days Compressive strength of Control concrete and Plastic concrete

W/C Datio	7 Days Compressi	ive strength (MPa)	Percentage reduction in
W/C Katio	control concrete plastic concrete		Compressive strength (%)
0.40	25.84	8.55	66.91
0.44	25.16	7.51	70.15
0.48	23.10	6.84	70.39
0.52	18.21	6.60	63.76





W/C Patio	28 Days Compress	ive strength (MPa)	Percentage reduction in
W/C Katio	control concrete plastic concrete		Compressive strength (%)
0.40	39.67	13.09	67.00
0.44	38.47	11.39	70.39
0.48	35.37	10.65	69.89
0.52	27.67	10.21	63.10





International Journal for Research in Applied Science & Engineering Technology (IJRASET) ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.429 Volume 9 Issue VI Jun 2021- Available at www.ijraset.com

	% Replacement of plastic Agg.	W/C Ratio	7 Days Compress	Percentage reduction	
S. No.					in
			control concrete	Partially Replaced	Compressive strength
					(%)
MR1	5	0.40	25.84	21.65	16.23
MR2	10	0.40	25.84	20.99	18.78
MR3	15	0.40	25.84	17.77	31.22
MR4	5	0.44	25.16	20.66	17.88
MR5	10	0.44	25.16	20.53	18.39
MR6	15	0.44	25.16	18.19	27.72
MR7	5	0.48	23.1	21.74	5.87
MR8	10	0.48	23.1	18.62	19.38
MR9	15	0.48	23.1	16.15	30.08
MR10	5	0.52	18.21	15.53	14.74
MR11	10	0.52	18.21	14.94	17.98
MR12	15	0.52	18.21	11.82	35.11

Table: Percentage reduction in 7 Days Compressive strength of Control concrete and partially Replaced Plastic aggregate concrete



Table: Percentage reduction in 28 Days Compressive strength of Control concrete and partially Replaced Plastic aggregate concrete

	% Replacement of plastic Agg.	W/C Ratio	28 Days Compres	Percentage reduction	
S. No.			control concrete	Partially Replaced	in Compressive strength (%)
MR1	5	0.40	39.67	33.08	16.61
MR2	10	0.40	39.67	32.08	19.13
MR3	15	0.40	39.67	27.76	30.03
MR4	5	0.44	38.47	32.80	14.75
MR5	10	0.44	38.47	31.53	18.04
MR6	15	0.44	38.47	27.45	28.64
MR7	5	0.48	35.37	33.12	6.37
MR8	10	0.48	35.37	28.17	20.37
MR9	15	0.48	35.37	25.01	29.28
MR10	5	0.52	27.67	23.47	15.17
MR11	10	0.52	27.67	22.51	18.65
MR12	15	0.52	27.67	18.05	34.78





B. Split Tensile Strength

Table: Percentage reduction in 28 Days Split tensile strength of Control concrete and Plastic concrete

W/C Ratio	28 Days Split tens	sile strength (MPa)	Percentage reduction in Split	
	control concrete	plastic concrete	Tensile strength (%)	
0.40	3.98	1.13	71.6	
0.44	3.92	0.8	79.6	
0.48	3.67	0.76	79.3	
0.52	3.04	0.74	75.7	





International Journal for Research in Applied Science & Engineering Technology (IJRASET)

ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.429 Volume 9 Issue VI Jun 2021- Available at www.ijraset.com

Fable: Percentage red	uction in 28 Days Spl	t tensile strength of Cor	trol concrete and partially	Replaced Plastic aggregate concrete
-----------------------	-----------------------	---------------------------	-----------------------------	-------------------------------------

		28 Days Split te	(%) Reduction on	
S. No.	W/C Ratio	control concrete	Partially Replaced	split tensile strength
MR1	0.40	3.98	4.4	- 10.55
MR2	0.40	3.98	4.13	-3.76
MR3	0.40	3.98	3.86	3.01
MR4	0.44	3.92	4.23	-7.9
MR5	0.44	3.92	4.1	-4.6
MR6	0.44	3.92	3.73	4.85
MR7	0.48	3.67	3.95	-7.63
MR8	0.48	3.67	3.8	3.54
MR9	0.48	3.67	3.58	2.45
MR10	0.52	3.04	3.46	-13.82
MR11	0.52	3.04	3.35	-10.2
MR12	0.52	3.04	3.01	0.98



VI.CONCLUSIONS

- *A*. The Plastics can be used to replace some of the aggregates in a concrete mixture. This contributes to reducing the unit weight of the concrete. This is useful in applications requiring non bearing lightweight concrete, such as concrete panels used in facades.
- B. Partial replacement of plastic aggregate shows less reduction in compressive strength as compared to complete replacement.
- *C.* The split tensile strength of partially replaced plastic aggregate is more for less water cement ratio, so it can be used where split tensile strength are required and compressive strength may sacrificed.

REFERENCES

- [1] Al-Manaseer, A.A., T.R., Dalal., 1997. "Concrete containing plastic aggregates", Concrete International, 47-52.
- [2] Ashraf, M., Ghaly, F., 2004. ASCE, 1 and Michael S. Gill, A.M.ASCE2 "Journals of materials in civil engineering" © ASCE , 289-296.
- [3] Balaguru, P.N., Shah, S.P., 1992., "Fiber Reinforced Cement Composites". McGraw- Hill, Inc., 530 p.
- [4] Batayneh, M., Marie, I., Asi I., 2006. "Use of selected waste materials in concrete mixes". Waste Management (27) 1870–1876
- [5] Bayasi, Z., Zeng, J., 1993." Properties of polypropylene fiber reinforced concrete". ACI Materials Journal 90 (6), 605–610.



International Journal for Research in Applied Science & Engineering Technology (IJRASET)

ISSN: 2321-9653; IC Value: 45.98; SJ Impact Factor: 7.429

Volume 9 Issue VI Jun 2021- Available at www.ijraset.com

- [6] Benazzouk, A., Queneudec, M., 2002. "Durability of cement-rubber composites under freeze thaw cycles". Proceedings of the International Conference on Sustainable Concrete Construction, University of Dundee, Scotland, UK, pp. 356–362
- [7] Boutemeur, R., Taibi, M., Ouhib, N., Bali, A., 2004. "Investigation of the use of waste plastic as aggregate for concrete" In: International Conference, Sustainable Waste Management and Recycling: Challenges and Opportunities, 14–15. Thomas Telford Publishing, Thomas Telford Ltd., London, ISBN 0727732854.
- [8] Cheong, K. H. and Lee, S. C., 1993. "Strength of Retempered Concrete", ACI Materials J. 90 (3), 203-206
- [9] Choi, Y.W., Moon, D.J., Chung, J.S., Cho, S.K., 2005. "Effects of waste PET bottles aggregate on properties of concrete". Cement and Concrete Research 35, 776–781.
- [10] Eldin, N. N., 1993 Member, ASCE, and Ahmed B. Senouci, 2 Associate Member, ASCE., "Rubber-tire particles as concrete aggregates". Journal of Materials in Civil Engineering, Vol. 5, No. 4
- [11] Fattuhi, N.I., Clark, N.A., 1996. "Cement-based materials containing tire rubber". Journal of Construction and Building Materials 10 (4), 229–236.
- [12] Goulias, D.G., Ali, A.H., 1997. "Non-destructive evaluation of rubber modified concrete". In: Proceedings of a Special Conference, ASCE, New York, pp. 111–120.
- [13] Hernandez-Olivares, F., Barluenga, G., Bollati, M., Witoszek, B., 2002. "Static and dynamic behavior of recycled tire rubber-filled concrete". Cement and Concrete Research 32 (10), 1587–1596.
- [14] Jain, R. K., Singh, Y., Rai, Mohan., 1977.," Recent Trends of Research in Plastic Building materials in India". Building and Environment, Vol. 12, pp. 277-280
- [15] Jo,B.W., Park, S.K., Park, J.C., 2007. "Mechanical properties of polymer concrete made with recycled PET and recycled concrete aggregates". Construction and Building Materials
- [16] Karim, S., Rebeiz, D., Fowler, W., Fellow, and Donald R. P., 1993. "Recycling plastics in polymer concrete for construction applications". Journal of Materials in Civil Engineering, Vol. 5, 237-248.
- [17] Khatib, Z.K., Bayomy, F.M., 1999."Rubberized portland cement concrete" ASCE Journal of Materials in Civil Engineering 11 (3), 206–213.
- [18] Kline, C. (1989). "Plastics recycling take off in the USA." Chem. & Industry, 4(July), 440-442.
- [19] Mehta, P.K., Monteiro, P.M., 1993. Concrete: Structure, Properties, and Materials. Prentice Hall, 549
- [20] Naik, T.R., Singh, S.S., Brodersen, B.S., 1996. "Use of post-consumer waste plastics in cement-based composites". Cement and Concrete Research 26, 1489– 1492.
- [21] Marzouk, O. Y., Dheilly R.M., Queneudec, M., 2007. "Valorization of post-consumer waste plastic in cementitious concrete composites". Waste Management (27) 310–318
- [22] Marzouk, Y.O., 2005. "Valorisation of plastic bottle waste in cementitious concrete". Doctoral dissertation, University of Picardie Jules Verne, Laboratory of Innovative Technologies, EA 3899, Amiens, France.
- [23] Panyakapo.P., Panyakapo.M., 2007. "Reuse of thermosetting plastic waste for lightweight concrete." Waste Management.
- [24] Raghvan, D., Huynh, H., Ferraris, C.F., 1998. "Workability, mechanical properties and chemical stability of a recycled tire rubber-filled cementitious composite". Journal of Materials Science 33 (7), 1745–1752.
- [25] Saradhi Babua, D. T, Ganesh Babub, K. T.H. Wee., 2005. "Properties of lightweight expanded polystyrene aggregate concretes containing fly ash". Cement and Concrete Research (35) 1218–1223.
- [26] Siddique, R., Naik, T. R., 2004. "Properties of concrete containing scrap-tire rubber an overview". Waste Management (24) 563-569.











45.98



IMPACT FACTOR: 7.129







INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089 🕓 (24*7 Support on Whatsapp)