



IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Volume: 2 Issue: VI Month of publication: June 2014 DOI:

www.ijraset.com

Call: 🛇 08813907089 🕴 E-mail ID: ijraset@gmail.com

### INTERNATIONAL JOURNAL FOR RESEARCH IN APPLIED SCIENCE AN D ENGINEERING TECHNOLOGY (IJRASET)

# An Experimental Study on Partial Replacement of Natural Coarse Aggregate With Fly Ash Coarse Aggregate (FACA)

V.R.Prasath Kumar<sup>1</sup>, K.S.Anandh<sup>2</sup>, Midhun Kumar. V<sup>3</sup>

1,2- Asst Professor, 3- student Department of Civil Engineering, SRM University, Chennai

Abstract: A construction industry plays vital role in India which leads into the economic developments. The materials like a cement, fine aggregate & natural coarse aggregate which is used to prepare concrete where once easily available in our country, but now there is high demand in materials which has gone to a high scenario. In this project an experimental investigation is done on the partial replacement of coarse aggregate with fly ash aggregate. The quantity of fly ash produced from thermal power plants in India is approximately 80 million tons each year, and its percentage utilization is less than 10%. Majority of fly ash produced is of Class F type. During the last few years, some cement companies have started using fly ash in manufacturing cement, known as 'pozzolana Portland cement, but the overall percentage utilization remains very low, and most of the fly ash is dumped at landfills. Many researchers have been carried out in the area of fly ash utilization in the past. It mainly concentrated on replacement of cement with fly ash but production of artificial aggregates with fly ash helps in utilizing large volume of ash in concrete. The world is much interested in this part recently due to this large scale utilization which also reduces environmental pollution and dwindling of natural resources. This paper mainly focuses on manufacturing process of light weight aggregates. The production of fly ash aggregate is produced in ratio of 10:90, 15:85 and 20:80.Based upon the above mix ratio, fly ash aggregates are produced and used for casting the concrete cubes and cylinder for comparing the strength with conventional aggregate concrete at 7 and 28 days curing period.

#### Keywords: FACA, compressive strength, *fl*

### 1. INTRODUCTION

In conventional concrete, weight of concrete is one of the parameters to compare with weight of fly ash aggregate concrete. Normally density of concrete is in the order of 2200 to 2600 kg/m3. This heavy self weight makes an uneconomical structural material compared to low self weight of fly ash aggregate concrete. In order to produce concrete of desired density to suit the required application, the self weight of structural and non-structural members are to be reduced. Hence economy is achieved in the design of supporting structural elements which lead to the development of light weight concrete. Lightweight concrete is defined as a concrete that has been made lighter than the conventional concrete by changing material composition or production method. Lightweight aggregate concrete is the concrete made by replacing the usual material aggregate by lightweight aggregates. Though lightweight concrete can't always substitute normal concrete for its strength potential, it has its own advantages like reduced dead load, and thus economic structures and enhanced seismic resistance, high sound

absorption and good fire resistance. Because of the above reasons the study on fly ash aggregate concrete is taken in this project work. A mix design was done for M30 grade of concrete by IS method. Ordinary Portland cement of 43 grade was selected and fly ash aggregates were prepared by mixing fly ash with cement and water. The properties of fly ash coarse aggregates were studied. The aggregate crushing value, abrasion value and aggregate impact value of fly ash coarse aggregates were also studied. The concrete cubes, cylinders and beams were cast with the fly ash aggregates obtained from the above six cement fly ash proportions. Then the compressive strength, split tensile strength and flexural strength were tested and compared with control concrete.

#### 2. PREVIOUS STUDY

Selection of mortar for light weight aggregate concrete made with fly ash based aggregate

*N.P.Rajamani* and *P.S. Ambily*, scientist, SERC, Chennai carried out the research work on They concluded that conversion of fly ash with aggregate is technically feasible

### INTERNATIONAL JOURNAL FOR RESEARCH IN APPLIED SCIENCE AN D ENGINEERING TECHNOLOGY (IJRASET)

and are found to be light weight in nature. They found fly ash aggregate concrete up to 20Mpa can be used for production of concrete blocks for masonry construction in structures. They also suggested selecting mortar which can produce fly ash aggregate concrete of strength up to40Mpa. However concrete strengths more than 40Mpa can also be produced using less content of fly ash aggregates.

### Light weight concrete with sintered fly ash aggregates

*Dr.J.P.Behera*, *Dr.H.S.Ray*, *Dr.B.D.Nayak and Dr. B. Sarangi.*(2004) Examined the use of sintered fly ash aggregate in concrete as a partial replacement of granite aggregate. A study on partial replacement to normal granite aggregate. Institution of Engineers, India (IE(I)) Journal – CV Vol 85 August'2004, PP 84 to 87. They concluded that in addition to light weight characteristics, the sintered fly ash concrete possesses strength and deformation characteristics similar to concrete with natural granite aggregate.

# Effect of fine aggregate replacement with class F fly ash on the mechanical properties of concrete

RafatSiddique Cement and Concrete Research 33 (2003) 539–547 Department of Civil Engineering, Thapar Institute of Engineering and Technology, Deemed University, Patiala 147004, India. Experimental investigation carried out to evaluate the mechanical properties of concrete mixtures in which fine aggregate (sand) was partially replaced with Class F fly ash. Fine aggregate (sand) was replaced with five percentages (10%, 20%, 30%, 40%, and 50%) of Class F fly ash by weight. Tests were performed for properties of fresh concrete. Compressive strength, splitting tensile strength, flexural strength, and modulus of elasticity were determined at 7, 14, 28, 56, 91, and 365 days. Test results indicate significant improvement in the strength properties of plain concrete by the inclusion of fly ash as partial replacement of fine aggregate (sand), and can be effectively used in structural concrete.

### 3. PROPERTIÉS OF FLY ASH PHYSICAL PROPERTIES

Fly ash consists of fine, powdery particles that are predominantly spherical in shape, either solid or hollow, and mostly glassy (amorphous) in nature. The carbonaceous material in fly ash is composed of angular particles. The particle size distribution of most bituminous coal fly ashes is generally similar to that of silt (less than a 0.075 mm or No. 200 sieve). Although sub bituminous coal fly ashes are also silt-sized, they are generally slightly coarser than bituminous coal fly ashes. The specific gravity of fly ash usually ranges from 2.1 to 3.0, while its specific surface area (measured by the Blaine air permeability method) may range from 170 to  $1000 \text{ m}^2/\text{kg}$ .

The colour of fly ash can vary from tan to gray to black, depending on the amount of unburned carbon in the ash. The lighter the colour, the lower the carbon content. Lignite or sub bituminous fly ashes are usually light tan to buff in colour, indicating relatively low amounts of carbon as well as the presence of some lime or calcium. Bituminous fly ashes are usually some shade of gray, with the lighter shades of gray generally indicating a higher quality of ash.

The burning of harder, older anthracite and bituminous coal typically produces Class F fly ash. This fly ash is pozzolanic in nature, and contains less than 10% lime (CaO). Possessing pozzolanic properties, the glassy silica and alumina of Class F fly ash requires a cementing agent, such as Portland cement, quicklime, or hydrated lime, with the presence of water in order to react and produce cementitious compounds. Table 1 Physical requirements for fly ash (IS 3812-2003)

Characteristics	Siliceous PFA (Class F)	Calcareous PFA (Class C)			
Fineness, specific surface area in m <sup>2</sup> /kg determined by the Blaine apparatus, min	320	320			
Particles retained on 45µm IS sieve (wet sieving), % max	34	34			
Lime reactivity, average compressive strength in N/mm <sup>2</sup> , min	4.5	4.5			
Compressive strength at 28 days, N/mm <sup>2</sup> , min	80% of the strength of corresponding plain cement mortar works	80% of the strength of corresponding plain cement mortar works			
Soundness, autoclave expansion or contraction, % max	0.8	0.8			

# INTERNATIONAL JOURNAL FOR RESEARCH IN APPLIED SCIENCE AN D ENGINEERING TECHNOLOGY (IJRASET)

### CHEMICAL PROPERTIES

Fly ash material solidifies while suspended in the exhaust gases and is collected by electrostatic precipitators or filter bags. Since the particles solidify while suspended in the exhaust gases, fly ash particles are generally spherical in shape and range in size from 0.5  $\mu$ m to 100  $\mu$ m. They consist mostly of silicon dioxide (SiO<sub>2</sub>), which is present in two forms: amorphous, which is rounded and smooth, and crystalline, which is sharp, pointed and hazardous; aluminium oxide (Al<sub>2</sub>O<sub>3</sub>) and iron oxide (Fe<sub>2</sub>O<sub>3</sub>). Fly ashes are generally highly heterogeneous, consisting of a mixture of glassy particles with various identifiable crystalline phases such as quartz, mullite, and various iron oxides.

Two classes of fly ash are defined by ASTM C618: Class F fly ash and Class C fly ash. The chief difference between these classes is the amount of calcium, silica, alumina, and iron content in the ash. The chemical properties of the fly ash are largely influenced by the chemical content of the coal burned (i.e., anthracite, bituminous, and lignite).Not all fly ashes meet ASTM C618 requirements, although depending on the application, this may not be necessary. Ash used as a cement replacement must meet strict construction standards, but no standard environmental standards have been established in the United States. 75% of the ash must have a fineness of 45 µm or less, and have a carbon content, measured by the loss on ignition (LOI), of less than 4%. In the U.S., LOI needs to be under 6%. The particle size distribution of raw fly ash is very often fluctuating constantly, due to changing performance of the coal mills and the boiler performance. Especially important is the ongoing quality verification. This is mainly expressed by quality control seals like the Indian ISI mark or the DCL mark of the Dubai Municipality

Table 2 Chemical re	quiren	nents for	fly ash (IS	3812-2003)

characteristics	Siliceous PFA	Calcareous PFA			
	(~ ASTM Class F)	(~ ASTM Class C)			
SiO <sub>2</sub> + Al <sub>2</sub> O <sub>3</sub> + Fe <sub>2</sub> O <sub>3</sub> , % by mass, min	70	50			

SiO <sub>2</sub> , % by mass, min	35	25
Total sulphur as SO <sub>3</sub> , % by mass, max	3.0	3.0
MgO, % by mass, max	5.0	5.0
Loss on ignition (LOI), % by mass, max	5.0	5.0
Available alkalis (Na <sub>2</sub> Oeq), % by mass, max	1.5	1.5
Total chlorides, % by mass, max	0.05	0.05

Table 3 AASHTO M 295 (ASTM C 618) - Class F and C

Chemical Components	Range %	Class F	Class C
$SiO_2 + Al_2O_3 + Fe_2O_3$	min	70 <sup>1</sup>	50
SiO <sub>3</sub>	Max	5	5
Moisture Content	Max	3	3
Loss on ignition (LOI)	Max	5 <sup>1</sup>	5 <sup>1</sup>
Optional Chemical Requirements	Range%	Class F	Class C
Available alkalies	Max	1.5	1.5

# INTERNATIONAL JOURNAL FOR RESEARCH IN APPLIED SCIENCE AN D ENGINEERING TECHNOLOGY (IJRASET)

Physical Requirements	Range%	Class F	Class C		
Fineness (+325 Mesh)	Max	34	34		
Pozzolanic activity/cement (7 days)	Min	75	75		
Pozzolanic activity/cement (28 days)	Min	75	75		
Water requirement	Max	105	105		
Autoclave expansion	Max	0.8	0.8		
Uniform requirements <sup>2</sup> : density	Max	5	5		
Uniform requirements <sup>2</sup> : Fineness	max	5	5		

Properties	Class C fly ash	Class F fly ash		
Early strengths (< 28 days)	Very effective; Can replace cement 1:1	Effective; May replace cement as high as 1:2		
Reduce Permeability	Effective	Very effective		
Resistance to ASR	Effective but may require higher amounts	Very effective even at lower amounts		
Resistance to sulphate attack	Less effective	Very effective		

Table 4 Influence of type of fly ash on its properties

### 4. CLASSIFICATION OF FLY ASH ASTM C618 Defines two classes of fly ash:

- Class C
- ➢ Class F

Primary difference between Class C and Class F fly ash is the amount of the amount of calcium, silica, alumina, and iron content in the ash.

Class F fly ash

> Produced from burning harder, older anthracite and bituminous coal.

➤ Contains less than 20% lime

➤ Requires cementing agent like PC, quick lime, hydrated lime

- Used in high sulfate exposure conditions
- Addition of air entrained needed

> Used for structural concretes, HP concretes, high sulfate exposure concretes.

> Useful in high fly ash content concrete mixes.

Class C fly ash

- Produced from burning younger lignite and sub bituminous coal
- Higher concentration of alkali and sulfate
- ➢ Contains more than 20% lime
- Self-cementing properties
- Does not require activator
- Not for use in high sulfate conditions
- Primarily residential construction
- Limited to low fly ash content concrete mixes 5. CURRENT MANAGEMENT OPTIONS

The quantity of fly ash produced from thermal power plants in India is approximately 80 million tons each year, and its percentage utilization is less than 10%. Majority of fly ash produced is of Class F type

Recycling and disposal

In 1996, approximately 14.6 million metric tons (16.2 million tons) of fly ash were used. Of this total, 11.85 million metric tons (13.3 million tons), or approximately 22 percent of the total quantity of fly ash produced, were used in construction-related applications. Table lists the leading construction applications in which fly ash were used during 1996. Approximately 70 to 75 percent of fly ash generated is still disposed of in landfills or storage lagoons.

 Table 5 Fly ash construction-related applications (2011)

Vol. 2 Issue VI, June 2014

ISSN: 2321-9653

## INTERNATIONAL JOURNAL FOR RESEARCH IN APPLIED SCIENCE AN D ENGINEERING TECHNOLOGY (IJRASET)

	Quantity Used						
Applications	Million Metric Tons	Million Tons	Percentage of Total used				
Cement production and/or concrete products	7.2	8.0	60				
Structural fills or embankments	1.9	2.2	17				
Stabilization of waste materials	1.7	1.9	14				
Road base or sub base materials	0.63	0.7	5				
Flow able fill and grouting mixes	0.27	0.3	2				
Mineral filler in asphalt paving	0.15	0.2	2				
Approximate Total	11.85	13.3	100				

# 6. PRODUCTION OF FLY ASH AGGREGATE

Proportion of fly ash aggregates

The constituents like cement, fly ash and water produce the fly ash aggregates. Water is the binding material that paves way for the formation of the aggregate with good bond property. The production of FAA is the theme of this project. It is detailed below.

Table 6 Proportions for cement and fly ash

Ratio	Cement (%)	Fly Ash (%)
R1	10	90
R2	15	85
R3	20	80

Preparation of FAA

Cement and fly ash were mixed in above six proportions in a concrete mixer. Water was added to the mix by adopting the water cement ratio of 0.3. The contents were thoroughly mixed in the drum until the complete formation of fly ash aggregates. This method of formation of fly ash aggregates is called pelletisation.

#### Pelletisation

It is a process of agglomeration of moisturized fines in a rotating drum or disc, to produce 'fresh pellet' having strength enough for further handling. Formation of pellets is based on the mechanism involved in balling phenomenon of powdery materials. When a fine-grained material is moisturized, a thin liquid film develops on the surface of each grain and bridges are formed at points where the moisturized particles contact each other. The particles are rotated into balls bonding forces develop gradually. The initial bonding between particles is due to a water bridge or meniscus. When more liquid is added, the liquid film on the particle surface began to coalesce, but closed and air-filled cavities remain between the grains. The ball grows as more moisturized particles are coated onto the nucleus. Mechanical forces, produced by the balls bumping against each other and against the walls of the rotating device, expel the air enveloped in the balls. At this capillary stage, the liquid fills the free space between the particles. The filled pores become bridged over, and the capillary forces affect the particle coherence throughout the whole ball. The concave membrane on the surface of the liquid seals surface pores. Under uneven or excessive moisturizing, particle clusters are enveloped in the droplets that tend to produce large, irregular entities. Grain size distribution and surface texture of the material influence the efficiency of pelletisation process. In the present study green pellets were produced from a mixture of fly ash, ordinary Portland cement and water as binder in the concrete mixer, which performed as a pelletiser.

#### Processing and curing of fly ash aggregate

The prepared 'Green Pellets' is allowed to dry for a day. Fly ash aggregates are then put for 28 days curing. The fly ash aggregates were weighed before and after curing process. It was found that no change was observed.

## INTERNATIONAL JOURNAL FOR RESEARCH IN APPLIED SCIENCE AN D ENGINEERING TECHNOLOGY (IJRASET)



Figure 1 Formations of fly ash aggregates



Figure 2 Prepared sample of FAA



Figure 3 Curing of FAA

Segregation of fly ash aggregates

The cured aggregates are allowed to dry completely for segregating fine and coarse aggregates based on particle size. Sieving is adopted for the separation of aggregates.

Fly ash coarse aggregates have a size above 4.75mm to 20mm and fly ash fine aggregates have a size of less than 4.75mm. Fly ash aggregates of size 20mm are separated and used as coarse aggregate.

7. TESTING THE STRENGTH OF CONCRETE Sieve analysis of fly ash aggregate



The blow graph shown the sieve analysis of fly ash aggregate

Figure 4 Sieve analysis of fly ash aggregate

20mm

specific gravity of fly ash aggregate

25mm

The specific gravity of fly ash aggregate can be obtain by using the formula given below

Sieve

Coarser..

10mm

Dry weight of aggregate

4.75mm

Specific gravity =\_

Weight of equal volume of water

-- Finer

Table 7 Specific gravity of FAA

Ratio	Specific gravity	Limits	Water absorption	Limits %
10:90	1.72	2.5 to 3.0	22.47%	0.1 to 2.0
15:85	1.83	2.5 to 3.0	20.41%	0.1 to 2.0
20:80	1.97	2.5 to 3.0	19.90%	0.1 to 2.0

Impact value of fly ash aggregate

The impact value of fly ash aggregate can be obtain by using the formula given below

# INTERNATIONAL JOURNAL FOR RESEARCH IN APPLIED SCIENCE AN D ENGINEERING TECHNOLOGY (IJRASET)

Aggregate Impa	Weight of passin act value =	g through 2.36mm sieve x 100	10:90	52.43%	vary f	rom 30.0
	Weig	ht of sample			to 50.0	0 percent
Table 8 Impact	value of FAA				vary f	rom 30.0
Ratio	Impact value	Limits	15:85	49.76%	to 50.0	0 percent
10:90	53.6%	Not more than 45%	20.80	18 3404	vary f	rom 30.0
15:85	47.9%	Not more than 45%	20.80	48.34%	to 50.0	0 percent
20:80	45%	Not more than 45%	CONCRETE MIZ IS metho Table 11 Concret	X DESIGN od of mix design e Mix Design	is based on I	S 10262-1982
Crushing value	of fly ash aggregate	ly ash aggregate can be	Grade / Type o Mix	M30 Grade	M30 Grade	M30 Grade
obtain by using	the formula given belo Weight of passing t	w hrough 2 36mm sieve	Trial Mi Reference no.	x FAAC 1	FAAC 2	FAAC 3
Aggregate crus	hing value = We	x100 x100	Material Design		Design	Design
Table 9 Crushir	ng value of FAA		OPC	350	250	350
Ratio	Crushing value	Limits	010	550	350	550
10:90	28.5%	Not exceed 30%	20mm Coars Aggregates	<sup>e</sup> 548	548	548
15:85	25.6%	Not exceed 30%	Fly As	h 385 (15:85)	385	385 (20:80)
20:80	24.9%	Not exceed 30%	Tigglegates		(10.90)	
Abrasion value	of fly ash aggregates		River Sand	736	736	736
T obtain by using	The abrasion value of find the formula given belo	ly ash aggregate can be w	Water	183	180	178
	Weight passi	ng 1.7mm IS sieve	Conplast SP430	0.52	0.51	0.48
Abrasion Value	e = Weight of ag	x 100 ggregate sample	Total	2202	2199	2197
Table 10 Abras	ion value of FAA		Water to Cemer Ratio	<sup>nt</sup> 0.54	0.51	0.50
Ratio	Abrasion value	Limits	Workability – Slu	Imp Test Value i	n mm	1
			Initial	130	130	170

# INTERNATIONAL JOURNAL FOR RESEARCH IN APPLIED SCIENCE AN D ENGINEERING TECHNOLOGY (IJRASET)

@ 4	5min		80		110	70				M30		7	8.08	590	26.1	25.2
										IVI JU		/	8.10	545	24.3	23.2
CON	IPRESSIV	E STRE	ENGT	H OF C	CONCRET	E (CUB	ES)		4	FAAC(R	M30					
teste	d as ner	15cm	x 15 5-1950	cm x 1	5cm concr	ete cube	es were			atio		28	8.13	770	34.2	25.1
1207	compressi	on testi	ng ma	chine.	The load	was app	plied at			20.80)		20	8.17	810	36.0	55.1
the r	ate approx	imately	140kg	g/cm2/r	nin until th	e failure	e of the									
spec:	men. The	maxim	ım lo	ad app	lied to the	specime	en until			Ag	ge of con	crete	e in da	ys	-	
Stree	igth Result		and	I CCAG	5										Figu	re 5
	Т		essi	ve stre	ngth of con	ncrete g	ives an			40 -		<u> </u>			8**	
idea	about the c	ngth	lity	of a co	oncrete.					35					-	
Tabl	e 12 Comp	stre	eng	th of F.	AAC and C	CAC				30					-	
S1.	Structure	ive	Age	Actua	Dial	Comp.	Avera			25 -		7-	_	F/	AC (Rat	io
No.	Concrete	ress	n	1	Reading/	Strengt	ge			20		H	_	<mark>10</mark>	<del>):</del> 90) `	
	d	ldu	lays	weigh	max load	h Ni	Comp.					H			CAC	
		C		t kg	(KIN)	$^{(1N/mm)}$	Streng						_		_	
						/	(N/m								_	
							$m^2$ )			5						
										0 -7""""		ŗ	• •	-		
			7	8.26	590	26.1	26.3				7 days	5	28	days	Com	pressive
	conventio		ŕ	8.30	595	26.5	20.5	г	7 A A	C (Datio 1	(0,00) on				strength	of
1	nal	M30						Г	'AA'	C (Kallo I	0.90) and	ucc	AC			
	concrete		20	8.38	850	37.9	20.2									
			28	8 34	860	38 5	38.2			10 🧹						
				0.51		50.5			_	35				1-		
				7.97	500	22.2			lgth	30 -						
	M30		7	0.05	520	22.2	22.7		trer	25		1		□ FAAC	2(	
2	FAAC	M30		0.05	520	23.2			S ·	20				Ratio	20:80)	
	(Ratio			8.10	750	33.2			1002	15					~	
	10:90)		28	0.01	775	22.6	33.4	th	r.d m	10						
				8.21	/55	33.6		gnə	3							
	1			7.95	520	23.0		str		U I	7 davs		28 dav	S		
	M30		7				24	sive			Age of	cone	rete in	davs		
2	FAAC(R	M30		7.98	560	25.0		pres	7117	e 6 compr	essive st	renot	$h \text{ of } F^{\perp}$	AC(Ratio	o 20·80) (	CAC
5	atio	10130		8.13	815	36.2		om	,u1	e o compi	C351 VC 50	ingt			5 20.00) <b>(</b>	
	15:85)		28		-		37.3	U								
				8.10	860	38.4										

# INTERNATIONAL JOURNAL FOR RESEARCH IN APPLIED SCIENCE AN D ENGINEERING TECHNOLOGY (IJRASET)



Figure 7 Compressive strength of FAAC

Inference: The compressive strength of FAAC is found to be 24 N/mm  $^2$  at 7<sup>th</sup> day for 15:85 ratio same at 7<sup>th</sup> day compressive strength in CCA concrete 26.37N/mm  $^2$  .This shows the FAAC strength at 7<sup>th</sup> almost equal to CCA.An end of 28<sup>th</sup> day compressive strength for FAAC and CCA is almost equal.

### CONCRETE SPLIT TENSILE STRENGTH

Concrete cylinders of 15cm diameter and 30 cm height were tested for Split tensile strength as per IS 5816-1976.The specimen was placed horizontally between the loading surfaces of the compression testing machine and the load was applied without shock until the failure of the specimen. The maximum load at failure was recorded.

				rete Spiit	Tensne	Suengui	
S1.	Structure	Grade	Age	Actual	Dial	Comp.	Avera
No.	Concreted	of	in	weight	Readin	Strength	ge
		Concre	days	kg	g/max	$(N/mm^2)$	Comp
		te			load		
				<b>y</b>	(kN)		Stren
							gth
							(N/m
							$m^2$ )
	conventio		7	13.528	340	4.8	10
1	nal	M30		13.523	355	5.0	4.9
	concrete		28	13.485	400	5.6	57
				13.541	420	5.9	5.7
	M30			13.170	280	4.0	
2		M30	7				4.1
	FAAC			13.187	300	4.2	

	(Ratio			13.220	360	5.1	
	10:90)		28				4.9
	,			13.234	330	4.7	
3	M30	M30	7	13.197	310	4.3	
							4.3
	FAAC			13.205	310	4.3	
				1			
	(Ratio 15:85)			13.254	350	4.9	5.0
			28	13.235	360	5.1	
4	M30	M30		13.215	310	4.3	
			7				4.2
	FAAC			13.205	290	4.1	
			28	13.255	370	5.2	
							5.1
	20:80)			13.240	360	5.0	





Figure 8 Split tensile strength of FAAC (Ratio 15:85) and CCAC  $% \left( {{\rm{CCAC}}} \right) = \left( {{\rm{TCAC}}} \right) =$ 

# INTERNATIONAL JOURNAL FOR RESEARCH IN APPLIED SCIENCE AN D ENGINEERING TECHNOLOGY (IJRASET)



Inference: The split tensile strength of FAAC is found to be 4.3 N/mm<sup>2</sup> at7<sup>th</sup> day for 15:85 ratio same at 7<sup>th</sup> day split tensile strength in CCA concrete 4.9N/mm<sup>2</sup>. This shows the FAAC strength at 7<sup>th</sup> almost equal to CCA. An end of 28<sup>th</sup> day split tensile strength for FAAC and CCA is almost equal.

14 days

### FLEXURAL STRENGTH

7 days

 Age of concrete in days

 Figure 10 Spin conore succession of the

The concrete beams of size 10cm x 10cm x 50cm were tested as per IS 516-1959. The load was applied through two similar rollers mounted at one third points of the supporting span. The load was applied without shock until the failure occurs. The maximum load at failure was recorded. Table 13 Flexural strength of FAAC &CCAC

Sl. No.	Structure	Grade	ofAge	inAverage
				Flexural

	Concreted	Concrete	days	strength (N/mm <sup>2</sup> )
1	conventional concrete	M30	7	4.8
			28	6.3
2	M30	M30	7	3.5
<b>~</b>	10:90)		28	4.2
3	M30 FAAC (Ratic 15:85)	M30	7	3.9
			28	4.7
4	M30	DM30	7	3.9
	20:80)		28	4.5

### INTERNATIONAL JOURNAL FOR RESEARCH IN APPLIED SCIENCE AN D ENGINEERING TECHNOLOGY (IJRASET)



### 7. CONCLUSION

Based upon the test carried out on compressive strength, Flexural strength and Split tensile strength test for conventional aggregate concrete and fly ash aggregate concrete.

On comparing the test result for CCAC & FAAC it is founded that the value is almost same for both concretes. This shows fly ash aggregate concrete has an equal strength while comparing to CCAC.

Figure 12 Flexural strength of FAAC (Ratio 15:85) and CCAC

334-965-

## INTERNATIONAL JOURNAL FOR RESEARCH IN APPLIED SCIENCE AN D ENGINEERING TECHNOLOGY (IJRASET)

Therefore FAA can be recommended as coarse aggregate for preparing of concrete which will reduce the usage of natural aggregate.

### REFERENCES

[1]. The Indian Concrete Journel, November 2004, Vol.78..

[2]. RafatSiddique Cement and Concrete Research 33 (2003) 539–547 Effect of fine aggregate replacement with Class F fly ash on the mechanical properties of concrete. Department of Civil Engineering, Thapar Institute of Engineering and Technology, Deemed University, Patiala 147004, India.

[3]. ACI committee 211.2 (1991) standard practices for selecting proportions for structural light weight concrete.ACI Material Journel,87,638-651.

[4]. N.P.Rajamani and P.S. Ambily, scientist, SERC, Chennai carried out the research work on "Selection of mortar for light weight aggregate concrete made with fly ash based aggregate".

[5]. www.sustainabledevelopment.in

[6]. <u>www.sciencedirect.com</u>

[7]. www.flyash.com

[8]. <u>www.FACprojectindia.com</u>

[9]. www.cement.org

[10]. M.S.Shetty,Concrete Technology Theory and practical Reprint-2005 Publishers S.Chand and Company Ltd., New Delhi

[11]. Neville, A.M and Brooks J.J "concrete technology", ELBS, 1987

[12]. IS 10262-1982 recommended guidelines for concrete "Mix Design", BIS,New Delhi.

[13]. Hand Book on Concrete Mixes:, SP.23:1982, BIS, New Delhi.











45.98



IMPACT FACTOR: 7.129







# INTERNATIONAL JOURNAL FOR RESEARCH

IN APPLIED SCIENCE & ENGINEERING TECHNOLOGY

Call : 08813907089 🕓 (24\*7 Support on Whatsapp)